

New Cyclic Peptide Assemblies with Hydrophobic Cavities: The Structural and Thermodynamic Basis of a New Class of Peptide Nanotubes

Manuel Amorín, Luis Castedo, and Juan R. Granja*

Departamento de Química Orgánica e Unidade Asociada ó C.S.I.C., Facultade de Química, Universidade de Santiago, 15782 Santiago de Compostela, Spain

Received December 7, 2002 ; E-mail: qojuangg@usc.es

In recent years, considerable effort has been devoted to the synthesis of organic and inorganic nanotubes.¹ Self-assembling peptide nanotubes (SPN) made from cyclic D,L- α -peptides² or from cyclic β -peptides³ have structural and functional properties that may be suitable for various applications in biology and materials science.^{1b,4–6} Here we describe a new member of self-assembling peptides with novel structural and internal cavity, validating the possibility of expanding the SPN class to other hybrid systems. The present structures are based on a hybrid of α - γ -cyclic peptides⁷ subunits and have been characterized by NMR, FT-IR, and X-ray crystallography.

Cyclic peptides in which (1R,3S)-3-aminocyclohexanecarboxylic acid (γ -Acc-OH) alternates with a D- α -amino acid, such as **1a**, can adopt a conformation in which the peptide backbone is essentially flat and the C=O and N-H groups lie roughly perpendicular to the plane of this cyclic backbone (Figure 1). This flat ring-shaped conformation may facilitate antiparallel β -sheetlike hydrogen bonding between oppositely oriented rings and the formation of hydrogen-bonded nanotubes composed of rings of alternating orientation, in which one face of each ring is hydrogen-bonded via γ -Acc C=O and N-H groups to the similar face of the neighbor (Figure 1, frame A), while the other face is hydrogen-bonded via C=O and N-H groups of the α -amino acid to the similar face of the other neighbor (Figure 1, frame B). In such structures, the β -methylene moiety of each cyclohexane is projected into the lumen of the cylinder, creating a partial hydrophobic cavity.

To establish and evaluate the feasibility and the thermodynamic properties of such nanotubes, we prepared dimers featuring each of the two hydrogen-bonding patterns described above, using cyclic peptides in which hydrogen bond donation from one face of the ring structure was blocked by *N*-methylation (Figure 2).⁸ Specifi-

cally, cyclopeptide **1b**, in which the α -amino acids are *N*-methylated, was used to prepare dimer **2b**, which features A-type hydrogen-bonding (Figure 1), and cyclopeptide **1c**, in which all γ -Acc are *N*-methylated (^{Me}N- γ -Acc), was used to prepare stacked dimeric ensemble **2c**, which features Figure 1B-type hydrogen bonding.

The cyclopeptides *cyclo*-[(1R,3S)- γ -Acc-D-^{Me}NAla]₃ (**1b**, R = Me) and *cyclo*-[D-Phe-(1R,3S)-^{Me}N- γ -Acc]₃ (**1c**, R = Bn) were synthesized by standard procedures and characterized by NMR and MS. The ¹H NMR spectra of the peptide **1b**, in both polar and nonpolar solvents (CCl₄, CDCl₃, MeOH, or DMSO), are well defined, highly symmetrical, and show a *J*_{NH,γH} coupling constant of 7.5–8.2 Hz, indications that the peptide exists in an all-trans conformation with a flat-ring-shaped backbone. In nonpolar solvents, the formation of dimers is reflected by the downfield shift upon increasing the concentration of the N-H resonance of γ -Acc from δ 6.6 to 7.8 ppm;⁹ the corresponding association constant, determined at 298 K by dilution experiments, is 230 M⁻¹ in CDCl₃ and 2.5×10^4 M⁻¹ in 2:3 CDCl₃/CCl₄. Van't Hoff plots for the range 273–313 K afford values of –34.1 KJ mol⁻¹ for ΔH°_{298} and –69.8 J/K·mol for ΔS°_{298} that, like the fall in *K*_a with increasing solvent polarity, are consistent with dimerization being essentially an enthalpy-driven¹⁰ hydrogen-bonding process.^{8a,c} The β -sheet nature of the hydrogen bonding is also supported by the chemical shift of ^{Me}N-Ala C α undergoing a concentration-dependent downfield shift of > 0.1 ppm¹¹ and by FT-IR spectra recorded in CHCl₃, which show amide I and amide II_{ij} bands at 1626 and 1538 cm⁻¹, respectively (positions that are typical of β -sheets and similar to those found for nanotubes and dimers composed of cyclic D,L-peptides). Hydrogen bonding by N-H is further supported by amide A bands near 3325 cm⁻¹, while a band that appears at 3400 cm⁻¹




Figure 1. Design for self-assembling peptide nanotubes composed of *cyclo*-[(1R,3S)- γ -Acc-D-Aa]₃ units (for clarity, amino acid side chains have been omitted in the representation of the nanotube and dimers). The two different H-bonding patterns (A and B) are shown in different colors. Dimers used to study the basic parameters of the proposed self-assembling nanotube are shown at the right.




Figure 2. Crystal structures of dimeric assemblies **2c** with five molecules of chloroform, one of which occupies the central cavity of the dimer: (left) top view; (right) side view.

in more dilute (0.5 M) solutions may correspond to the N–H band of the monomer.^{8e}

A flat, all-trans conformation is also indicated by the ¹H NMR spectra of **1c** in polar and nonpolar solvents ($J_{\text{NH}-\alpha\text{H}} = 9.0\text{--}9.5$ Hz). However, the chemical shift of Phe NH in nonpolar solvents is a constant 8.7 ppm at concentrations down to 2×10^{-4} M and with heating or addition of up to 20% of methanol, showing that if dimers are formed the association constant for dimerization must be at least 10^5 M^{-1} (larger than for any peptide nanotube reported hitherto). Solution (CHCl_3) FT-IR studies showed the characteristic features of β -sheet structure of peptide nanotubes and dimers: amide I (1625 cm^{-1}), amide II_i (1523 cm^{-1}), and amide A (3309 cm^{-1}) bands. Dimer formation was also supported by FAB-MS, showing a signal arising from single charged species corresponding to proton dimer **2c** (1718).

Colorless prismatic crystals suitable for X-ray were obtained from the solutions of peptide **1c** in chloroform by vapor-phase equilibration with hexane. The crystal structure characterized by X-ray crystallography shows an unsymmetrical dimeric ensemble that corroborates the nanotube structure. The two peptide subunits are closely stacked in an antiparallel orientation with the β -sheetlike cyclindrical ensemble stabilized by six intersubunit hydrogen-bonding interactions with an intersubunit N–O distance ranging between 2.78 and 2.94 Å and distorted by the presence of five chloroform molecules hydrogen-bonded to the peptide backbone. The cyclindrical dimer has an approximate van der Waals internal diameter of 5.4 Å and a volume of 165 Å^3 , which is filled with one molecule of chloroform, showing the partial hydrophobic character of the inner face of the nanotube which is distinct from previously reported hydrophilic nanotubes.^{2,8,12}

In conclusion, NMR, FT-IR, MS, and X-ray diffraction data show conclusively that the cyclic peptides **1b** and **1c** form dimers in which antiparallel peptide rings are linked by a β -sheetlike set of six hydrogen bonds. These dimers (one of which, **2c**, is extremely stable in nonpolar solvents) may be considered as essentially the basic units of a new class of peptide nanotubes, in which the inner-cavity properties are due in part to the cyclohexane C2. Cyclic peptides containing C2-modified γ -Acc should endow SPN with a functionalized inner surface, something that is precluded in the α - or β -nanotubes because all amino acid side chains lie on the exterior of the ensemble and additional modification in C_α or C_β would disrupt the assembling.² Appropriate functionalization should lead

to nanotubes with greater selectivity as ion channels, catalysts, receptors, or molecule containers. Work is in progress to this end.

Acknowledgment. This work was supported by Ministerios de Educación y Ciencia and Ciencia y Tecnología and the Xunta de Galicia under Projects PB97-0524, SAF2001-3120, and PGIDT00PXI20912PR, respectively, and through a research grant to M.A.

Supporting Information Available: Detailed descriptions of the synthesis and characterization of key compounds and crystal data, atomic coordinates, bond lengths and angles, and anisotropic displacement coefficients of **1c**. This material is available free of charge via the Internet at <http://pubs.acs.org>.

References

- (1) (a) Patzke, G. R.; Krumeich, F.; Nesper, R. *Angew. Chem., Int. Ed.* **2002**, *41*, 2446–2461. (b) Bong, D. T.; Clark, T. D.; Granja, J. R.; Ghadiri, M. R. *Angew. Chem., Int. Ed.* **2001**, *40*, 988–1011. (c) Ajayan, P. M.; Zhou, O. Z. *Top. Appl. Phys.* **2001**, *80*, 391–425.
- (2) Ghadiri, M. R.; Granja, J. R.; Milligan, R. A.; McRee, D. E.; Khazanovich, N. *Nature* **1993**, *366*, 324–327. Khazanovich, N.; Granja, J. R.; McRee, D. E.; Milligan, R. A.; Ghadiri, M. R. *J. Am. Chem. Soc.* **1994**, *116*, 6011–6012. Ghadiri, M. R.; Granja, J. R.; Buehler, L. K. *Nature* **1994**, *369*, 301–304. Hartgerink, J. D.; Granja, J. R.; Milligan, R. A.; Ghadiri, M. R. *J. Am. Chem. Soc.* **1996**, *118*, 43–50.
- (3) Seebach, D.; Matthews, J. L.; Meden, A.; Wessels, T.; Baerlocher, C.; McCusker, L. B. *Helv. Chim. Acta* **1997**, *80*, 173–182. Clark, T. D.; Buehler, L. K.; Ghadiri, M. R. *J. Am. Chem. Soc.* **1998**, *120*, 651–656.
- (4) Steinem, C.; Janshoff, A.; Vollmer, M. S.; Ghadiri, M. R. *Langmuir* **1999**, *15*, 3956–3964. Fernández-López, S.; Kim, H.-S.; Choi, E. C.; Delgado, M.; Granja, J. R.; Khasanov, A.; Kraehenbuehl, K.; Long, G.; Weinberger, D. A.; Wilcoxon, K.; Ghadiri, M. R. *Nature* **2001**, *412*, 452–455.
- (5) For a recent example of nanotubes made of δ -amino acids, see: Gauthier, D.; Baillargeon, P.; Drouin, M.; Dory, Y. L. *Angew. Chem., Int. Ed.* **2001**, *40*, 4635–4638.
- (6) For a recent review on supramolecular chemistry and self-assembly, see: *Science* **2002**, *295*, 2395–2421 (special issue).
- (7) For some studies with peptides made of alternating α -amino acid and 3-aminobenzoic acid derivatives, see: (a) as cation receptors, Kubik, S.; Goddard, R. J. *Org. Chem.* **1999**, *64*, 9475–9486. Kubik, S. *J. Am. Chem. Soc.* **1999**, *121*, 5846–5855. Pohl, S.; Goddard, R. Kubik, S. *Tetrahedron Lett.* **2001**, *42*, 7555–7558. (b) As ion channels: Ishida, H.; Qi, Z.; Sokabe, M.; Donowaki, K.; Inoue, Y. *J. Org. Chem.* **2001**, *66*, 2978–2989.
- (8) (a) Ghadiri, M. R.; Kobayashi, K.; Granja, J. R.; Chadha, R. K.; McRee, D. E. *Angew. Chem., Int. Ed. Engl.* **1995**, *34*, 93–95. (b) Kobayashi, K.; Granja, J. R.; Ghadiri, M. R. *Angew. Chem., Int. Ed. Engl.* **1995**, *34*, 95–98. (c) Clark, T. D.; Buriak, J. M.; Kobayashi, K.; Isler, M. P.; McRee, D. E.; Ghadiri, M. R. *J. Am. Chem. Soc.* **1998**, *120*, 8949–8962. (d) Bong, D. T.; Ghadiri, M. R. *Angew. Chem., Int. Ed.* **2001**, *40*, 2163–2166. (e) Saviano, M.; Zaccaro, L.; Lombardi, A.; Pedone, C.; Di Blasio, B.; Sun, X.; Lorenzi, G. P. *J. Incl. Phenom.* **1994**, *18*, 27–36. (f) Sun, X.; Lorenzi, G. P. *Helv. Chim. Acta* **1994**, *77*, 1520–1526.
- (9) Slow monomer–dimer equilibration was observed in NMR spectra of **1b** (0.5 mM in CH_2Cl_2) obtained at 189 K, which showed NH signals for both the dimer (at 7.84 ppm) and the monomer (at 6.54 ppm). ¹H NMR spectrum is available in the Supporting Information.
- (10) (a) Searle, M. S.; Westwell, M. S.; Williams, D. H. *J. Chem. Soc., Perkin Trans. 2* **1995**, 141–151. (b) Dunitz, J. D. *Chem. Biol.* **1995**, *2*, 709–712.
- (11) Downfield shifts of C_αH signals with respect to random coil values are reliable indicators of β -sheet structure (for recent examples concerning β hairpin models in aqueous solution, see: (a) Maynard, A. J.; Sharman, G. J.; Searle, M. S. *J. Am. Chem. Soc.* **1998**, *120*, 1996–2007. (b) Haque, T. S.; Gellman, S. H. *J. Am. Chem. Soc.* **1997**, *119*, 2303–2304; also ref 8c. The ¹H NMR spectrum of **1b** recorded in CH_2Cl_2 at 189 K, showing the C_αH signals of both the monomer and the dimer (at 4.85 and 5.36 ppm, respectively), is available in the Supporting Information, as are room-temperature spectra showing the C_αH signal shifting with increasing concentration.
- (12) Engels, M.; Bashford, D.; Ghadiri, M. R. *J. Am. Chem. Soc.* **1995**, *117*, 9151–9158.

JA0296273