## ChemComm

## COMMUNICATION

Cite this: DOI: 10.1039/c3cc48618d

Received 12th November 2013, Accepted 27th November 2013 Hui-Qing Peng,<sup>ab</sup> Jiang-Fei Xu,<sup>ab</sup> Yu-Zhe Chen,<sup>a</sup> Li-Zhu Wu,<sup>a</sup> Chen-Ho Tung<sup>a</sup> and Qing-Zheng Yang\*<sup>a</sup>

mimicking light-harvesting systems\*

Water-dispersible nanospheres of hydrogen-bonded supramolecular polymers and their application for

DOI: 10.1039/c3cc48618d

www.rsc.org/chemcomm

Water-dispersible nanospheres of hydrogen-bonded supramolecular polymers have been prepared for the first time by using the miniemulsion method. Nanospheres containing chromophores with high fluorescence quantum yields were fabricated to mimic the natural light-harvesting system.

Supramolecular polymers are arrays of small molecular-weight monomers connected through reversible non-covalent linkages, such as hydrogen bonds, hydrophobic interactions or other weak interactions.<sup>1</sup> The highly directional quadruple hydrogen bonding units of ureidopyrimidinone (UPy) are among the most used building blocks in supramolecular polymer construction due to their high association constant and synthetic accessibility.<sup>2</sup> Impressive progress has been achieved with these supramolecular polymers in the fabrication of functional materials.<sup>3</sup> UPy-based monomers are typically polymerized in apolar organic solvents, because polar solvents, such as water, weaken or eliminate the hydrogen bonding pairing.<sup>4</sup> As a result, applications of UPy-based supramolecular polymers in life science or eco-friendly materials have been less explored. Nanospheres are one of the most widely used shapes in nano materials due to their good dispersibility and low surface energy. Nanospheres of UPy-based supramolecular polymers generated in the aqueous phase may find wide-ranging applications in areas such as biomaterials and luminescent nanomaterials.

Supramolecular polymers share many properties with traditional polymers but are also capable of rapid and reversible polymerization–depolymerization.<sup>5</sup> The methods for preparation of polymer nano-particles with a desired architecture may also be suitable for supramolecular polymers.<sup>6</sup> Traditional polymers are fabricated as nanospheres by the miniemulsion method.<sup>7</sup> Homogeneous miniemulsions are easily formed by ultrasonication of a mixture of water

and organic phase in the presence of a surfactant. The polymers aggregate into nanospheres upon evaporation of the organic solvent. Inspired by such a method, we envisioned that miniemulsions could be utilized to prepare nanoparticles of hydrogen-bonded supramolecular polymers. Stable emulsified organic droplets may provide a hydrophobic environment to stabilize hydrogen-bonded supramolecular polymers, which could aggregate into nanospheres. Here we report a highly efficient preparation of nanospheres of hydrogen-bonded supramolecular polymers in water based on miniemulsions (Scheme 1). We prepared nanospheres of four types of UPy-based supramolecular polymers. The supramolecular polymers containing chromophores with high fluorescence quantum yields form nanospheres for efficient light harvesting. To the best of our knowledge, this work is the first example of water-dispersible nanospheres of hydrogen-bonded supramolecular polymers.

We synthesized monomers **1–4** containing two UPy moieties (ESI<sup>†</sup>). The formation of high-molecular-weight supramolecular polymers in chloroform from the monomers was confirmed by NMR spectroscopy and viscometry.<sup>8</sup> The <sup>1</sup>H NMR spectra of **1–4** in CDCl<sub>3</sub> clearly indicated dimerization of the UPy units, as the UPy N–H signals showed a large downfield shift (10.0–13.5 ppm) (Fig. S1, ESI<sup>†</sup>). The viscosity measurements of CHCl<sub>3</sub> solutions of **1–4** were



Scheme 1 Chemical structures of monomer **1–4** and graphical representation for preparation of water-dispersible nanospheres of hydrogenbonded supramolecular polymers.



**View Article Online** 

<sup>&</sup>lt;sup>a</sup> Key Laboratory of Photochemical Conversion and Optoelectronic Materials, Technical Institute of Physics and Chemistry, Chinese Academy of Sciences, Beijing 100190, China. E-mail: qzyang@mail.ipc.ac.cn; Fax: +86 10-62554670

<sup>&</sup>lt;sup>b</sup> University of the Chinese Academy of Sciences, Beijing 100049, China

<sup>†</sup> Electronic supplementary information (ESI) available: Experimental details, <sup>1</sup>H NMR, specific viscosity, SEM, TEM, DLS, FT-IR, absorption and fluorescence measurements. See DOI: 10.1039/c3cc48618d

consistent with the results of the NMR studies (Fig. S3, ESI<sup>†</sup>). The double logarithmic plots of specific viscosity *vs.* concentration of **2** was linear with a slope of 1.08 at a concentration of <33 mM, indicating the presence of solutes with concentration-independent size (*e.g.*, oligomers). A slope of 3.11 was observed at >33 mM indicating an increase in the degree of polymerization of **2** with concentration. Similar to **2**, a critical polymerization concentration was also observed at 100 mM for **3**.<sup>3b</sup> In contrast to **2** and **3**, the slope of the graph for **1** and **4** was constant at 1.67 and 2.11, respectively, over the whole concentration range, indicating the propensity of **1** and **4** to polymerize even at low concentrations.

We prepared nanospheres of hydrogen-bonded supramolecular polymers in water by the miniemulsion method. A 200 µL stock solution of 1-4 in CHCl<sub>3</sub> (25 mg mL<sup>-1</sup>) was quickly added to an aqueous solution of the cetyl trimethyl ammonium bromide (CTAB) surfactant (10 mL,  $c_{\text{CTAB}}$  = 0.9 mM). We sonicated the resulting solution for 25 minutes to emulsify the organic phase. After three cycles of centrifuge-wash with water, we obtained stable waterdispersible nanospheres as confirmed by electron microscopy and dynamic light scattering (DLS). As illustrated in Fig. 1, scanning electron microscopy (SEM) and transmission electron microscopy (TEM) images indicated regular shape and uniform size of the welldispersed nanospheres of 1 with an average diameter of  $\sim 60$  nm. The average hydrodynamic diameter estimated from DLS was  $\sim$ 109 nm (Fig. S4, ESI<sup>+</sup>). The size of nanospheres formed from 3 and 4 were similar to that from 1, and 2 formed slightly larger nanospheres than 1 (Fig. S5, Table S1, ESI<sup>†</sup>).

Because water lowers the dimerization constant of UPy considerably by competing with hydrogen-bond donor and acceptor sites of these units, the importance of hydrogen bonding in the formation of nanospheres from 1-4 is not obvious. The presence of peaks at 3212 and 3147  $\text{cm}^{-1}$  (Fig. S6, ESI<sup> $\dagger$ </sup>) in the FT-IR spectra of the nanospheres suggests the formation of the self-complementary hydrogen bonds.<sup>2a</sup> To further establish the importance of such self-complementary hydrogen bonding for the formation of the nanospheres, we synthesized derivatives of 2 and 4 (benzyl 2 and benzyl 4, Scheme 2 and Scheme S1, ESI<sup>+</sup>) in which one of the hydrogen-bonding acceptor sites was blocked.9 The formation of our supramolecular polymers is based on the UPy dimerization. The absence of the UPy N-H signals between 10.0 and 13.5 ppm in the <sup>1</sup>H NMR spectrum suggests that the UPy dimers are not formed (Fig. S2, ESI<sup>+</sup>). As a result, these derivatives did not assemble into supramolecular polymers. The aggregates formed from benzyl 2 and benzyl 4 under identical conditions were disorderly (Fig. S7, ESI<sup>†</sup>). Such results prove that supramolecular polymerization by



Fig. 1 (a) SEM and (b) TEM images of nanospheres prepared from supramolecular polymers of  ${\bf 1}$ .



Scheme 2 Synthesis of compound benzyl 2

dimerization of UPy moieties through the quadruple hydrogen bonding is the prerequisite for the formation of the nanospheres.

We speculated that the hydrogen bonding of the supramolecular polymers was protected by a hydrophobic microenvironment provided by emulsified organic droplets during preparation in water. As a result, the random-coil supramolecular polymers aggregate into nanospheres under the influence of hydrophobic interactions. It should be noted that our nanospheres made from supramolecular polymers have smaller size and better defined structures than most of those obtained from common covalent polymers by using the miniemulsion method,<sup>7</sup> which may reflect the dynamic character of supramolecular polymers. The dynamic formation and breaking of hydrogen bonds adjust the length and configuration of the polymers, which may lower the energy of the system especially the surface energy. Finally the polymers aggregate into the stable nanospheres with desired shape and size.

We studied the influence of surfactants and the concentration of monomers on properties of such nanospheres. Both anionic (*e.g.*, sodium dodecyl sulfate) and nonionic surfactants (*e.g.*, Pluronic F-127) yielded nanospheres whose shape and size distribution were similar to those of the nanospheres prepared with CTAB as the emulsifier, indicating that the method is not restricted to a particular surfactant type (Fig. S8, ESI<sup>†</sup>). On the other hand, the average size of the nanospheres was sensitive to the initial monomer concentration. As the monomer concentration increased from 5 to 100 mg mL<sup>-1</sup>, the hydrodynamic diameters measured by DLS increased from 49 nm to 237 nm (Fig. S9, ESI<sup>†</sup>). This correlation enables us to fabricate nanospheres of different sizes by adjusting the monomer concentration.

To illustrate the utility of the described method we fabricated nanospheres to mimic the natural light-harvesting systems. Construction of artificial light-harvesting systems is important due to their potential applications in solar cells, photocatalysts and optical sensors.<sup>10</sup> Although impressive progress has been made using directed synthesis, the multiple steps needed to prepare complex architectures limit the reach of such approaches. Preparation of a highly efficient antenna system by self-assembly from readily available building blocks can avoid such complex synthesis and separation.<sup>11</sup> We chose green emissive chromophore 9-(4-methoxyphenylethynyl)-10-(4-UPyphenylethynyl) anthracene (5) derivatized with a UPy moiety (Fig. 2) as the energy acceptor since its absorption has a significant overlap with the emission of energy donor 4 (Fig. S10, ESI<sup>†</sup>). We constructed a light-harvesting system from the copolymer of 4 and 5 (Fig. 3). Because 5 contains a single UPy moiety, it terminates a supramolecular macrochain of chromophores 4. The presence of 5 did not affect the shape and size distribution of the nanospheres within molar ratios of 4 to 5 from 352:1 to 44:1 (Fig. 4).

The energy transfer from the donor to the acceptor was confirmed by steady state and time-resolved fluorescence spectroscopy.



**Fig. 2** Fluorescence spectra of nanospheres dispersed in water with different molar ratios between donor (D) and acceptor (A). [D] = 49.7  $\mu$ M. [D] to [A] molar ratio is 352:1, 176:1, 88:1, 58:1, 44:1 from bottom to top.  $\lambda_{ex} = 375$  nm. Inset: chemical structure of **5**.



Fig. 3 Schematic illustrations of the energy transfer among chromophores densely organized in the nanospheres. Left: nanospheres prepared from supramolecular polymers of **4**. Right: nanospheres prepared from supramolecular copolymers of 88:1 of **4** to **5**. Inset: photographs of nanospheres in water under UV light ( $\lambda_{ex}$  = 365 nm).

As shown in Fig. 2, an increase of the acceptor-to-donor molar ratio from 1/352 to 1/44 lowered the intensity of the donor emission at 430 nm while enhancing that of the acceptor at 496 nm when the donor was selectively excited at 375 nm. The excitation spectrum of the acceptor was nearly identical to the absorption spectrum of 4, indicating that the donor contributed directly to the acceptor emission (Fig. S11, ESI<sup>†</sup>). Time-resolved fluorescence measurements clearly show that the fluorescence decay of chromophore 4 accelerates after the co-assembly of acceptor 5, indicating an efficient energy transfer (Fig. S12, ESI<sup>†</sup>).

The change of fluorescence was easily visualized by a variation in the emission color from the bright blue emission of the donor to the bright green emission of the acceptor (Fig. 3), indicating that the unique optical properties of the nanosphere generated from small monomers could be tuned *via* convenient backbone copolymerization. Such fluorescent nanospheres may have potential applications for *in vitro* and *in vivo* fluorescence imaging.



Fig. 4 (a) SEM and (b) TEM images of nanospheres prepared from supramolecular copolymers of 88:1 molar ratio of 4 to 5.

To evaluate the light-harvesting ability of the system, we studied the "antenna effect", a widely used empirical parameter, which is defined to determine the degree of the amplified acceptor emission assisted by the donor excitation.<sup>11*a*,*b*</sup> In our system, the antenna effect was calculated according to eqn (1):

Antenna effect = 
$$I_A(\lambda_{ex} = 375 \text{ nm})/I_A(\lambda_{ex} = 445 \text{ nm})$$
 (1)

where  $I_A(\lambda_{ex} = 375 \text{ nm})$  and  $I_A(\lambda_{ex} = 445 \text{ nm})$  are the fluorescence intensities of 5 upon excitation of the donor at 375 nm and direct excitation of the acceptor at 445 nm, respectively. With different molar ratios between the donor and acceptor, the acceptor emission amplified significantly as the ratio of the donor increased (Fig. S13, Table S2, ESI†). A value of 11 fold emission enhancement was obtained for nanospheres of copolymers containing 44:1 molar ratio of donor to acceptor. With donor to acceptor ratios of 58:1, 88:1, and 176:1, the antenna effects resulted in 13, 20, and 29 fold enhancement of acceptor fluorescence, respectively. Eventually, the energy transfer was saturated at one acceptor per 352 donors, when the maximum acceptor emission amplification reached a factor of 35, which is much higher than that of other artificial light harvesting systems.<sup>11a,b</sup>

In summary, we have described a highly efficient method to prepare water dispersible nanospheres of hydrogen-bonded supramolecular polymers with well-defined shape and size by the miniemulsion method. This method is not restricted to a particular surfactant type. The size of the nanospheres was controlled by adjusting the monomer concentration in the precursor solution. We used this new method to construct brightly fluorescent lightharvesting nanospheres, from supramolecular copolymers containing an energy donor and acceptor. In contrast to their covalent counterparts, nanospheres of supramolecular polymers are formed from low-molecular-weight molecules and their composition and functions are easily tunable. These features may offer great opportunities in bioapplications. Such an efficient fabrication of nanospheres of hydrogen-bonded supramolecular polymers also opens up new opportunities for wide applications of UPy based supramolecular polymers in areas such as biomaterials and optoelectronic materials.

We are grateful for the financial support from the 973 Program (2013CB933800, 2013CB834505), the National Natural Science Foundation of China (21072202, 21222210, 91027041) and the Chinese Academy of Sciences (100 Talents Program).

## Notes and references

- 1 L. Brunsveld, B. J. B. Folmer, E. W. Meijer and R. P. Sijbesma, *Chem. Rev.*, 2001, **101**, 4071..
- (a) F. H. Beijer, R. P. Sijbesma, H. Kooijman, A. L. Spek and E. W. Meijer, J. Am. Chem. Soc., 1998, **120**, 6761; (b) Z.-M. Shi, C.-F. Wu, T.-Y. Zhou, D.-W. Zhang, X. Zhao and Z.-T. Li, Chem. Commun., 2013, **49**, 2673; (c) T. Xiao, X. Feng, Q. Wang, C. Lin, L. Wang and Y. Pan, Chem. Commun., 2013, **49**, 8329.
- (a) R. Abbel, C. Grenier, M. J. Pouderoijen, J. W. Stouwdam, P. E. L. G. Leclère, R. P. Sijbesma, E. W. Meijer and A. P. H. J. Schenning, *J. Am. Chem. Soc.*, 2009, **131**, 833; (b) J.-F. Xu, Y.-Z. Chen, D. Wu, L.-Z. Wu, C.-H. Tung and Q.-Z. Yang, *Angew. Chem., Int. Ed.*, 2013, **52**, 9738; (c) X. Yan, S. Li, J. B. Pollock, T. R. Cook, J. Chen, Y. Zhang, X. Ji, Y. Yu, F. Huang and P. J. Stang, *Proc. Natl. Acad. Sci. U. S. A.*, 2013, **110**, 15585.
- 4 T. H. Rehm and C. Schmuck, Chem. Soc. Rev., 2010, 39, 3597.

- 5 X. Ji, Y. Yao, J. Li, X. Yan and F. Huang, J. Am. Chem. Soc., 2013, 135, 74.
  6 R. Tong and J. Cheng, J. Am. Chem. Soc., 2009, 131, 4744.
  7 L. Feng, C. Zhu, H. Yuan, L. Liu, F. Lv and S. Wang, Chem. Soc. Rev., 2013, 42, 6620.
- Y. Liu, Z. Wang and X. Zhang, *Chem. Soc. Rev.*, 2012, **41**, 5922.
   B. J. B. Folmer, E. Cavini, R. P. Sijbesma and E. W. Meijer, *Chem. Commun.*, 1998, 1847.
- 10 D. T. McQuade, A. H. Hegedus and T. M. Swager, J. Am. Chem. Soc., 2000, 122, 12389.
- 11 (a) R. A. Miller, A. D. Presley and M. B. Francis, J. Am. Chem. Soc., 2007, 129, 3104; (b) P. K. Dutta, R. Varghese, J. Nangreave, S. Lin, H. Yan and Y. Liu, J. Am. Chem. Soc., 2011, 133, 11985; (c) H.-Q. Peng, Y.-Z. Chen, Y. Zhao, Q.-Z. Yang, L.-Z. Wu, C.-H. Tung, L.-P. Zhang and Q.-X. Tong, *Angew. Chem., Int. Ed.*, 2012, **51**, 2088.