Bithiophene-Fused Benzo[c]phospholes: Novel P,S-Containing Hybrid π -Conjugated Systems with Small HOMO–LUMO Energy Gaps

Tooru Miyajima,^[a] Yoshihiro Matano,^{*[a]} and Hiroshi Imahori^[a,b]

Keywords: Phospholes / Thiophenes / Fused-ring systems / Conjugation / Pi interactions

Bithiophene-fused benzo[c]phospholes were successfully prepared by a Ti^{II}-mediated cyclization of dialkynylated bithiophene derivatives. It was revealed that the optical and electrochemical properties of the bithiophene-fused benzo-[c]phospholes are deeply related to the π -conjugation modes at the fused bithiophene subunits. Both experimental and theoretical results demonstrate that the appropriately ring-

Introduction

Phosphole is known as a poorly aromatic heterocyclopentadiene having a low-lying LUMO and a narrow HOMO-LUMO energy gap due to the effective $\sigma^* - \pi^*$ conjugation.^[1,2] The optical and electrochemical properties of phospholes, which are derived from the phosphane-linked cis-1,3-diene functionality, can be varied widely by chemical modifications at the dienic backbone and at the phosphorus center. In this context, the phosphole-based π -conjugated systems^[3-5] are promising candidates for use in optoelectronic applications.^[6,7] In particular, the ring-annulated polycyclic π -conjugated systems such as dibenzo[b,d]phospholes and dithieno[b.d]phospholes have attracted growing interest, as they possess rigid and elongated π networks that are beneficial for designing efficient light-emitting and electron-conducting materials.^[8,9] A recent theoretical study on the electronic structures and reactivities of a series of benzo[c]heteroles predicted that benzo[c]phosphole would also be an attractive skeleton for developing novel phosphole-based π -conjugated systems with relatively small HOMO-LUMO energy gaps.^[10] However, the chemistry of benzo[c]phospholes still remains unveiled due to the lack of a general method for the synthesis of thermally stable derivatives. Namely, the highly reactive o-quinonoid character of unsubstituted benzo[c]phosphole has precluded its isolation under ambient conditions.^[11] With this in mind,

- [a] Department of Molecular Engineering, Graduate School of Engineering, Kyoto University, Nishikyo-ku, Kyoto 615-8510, Japan Fax: +81-75-383-2571
 - E-mail: matano@scl.kyoto-u.ac.jp
- [b] Institute for Integrated Cell-Material Sciences, Kyoto University Nishikyo-ku, Kyoto 615-8510, Japan
- Supporting information for this article is available on the WWW under http://www.eurjoc.org or from the author.

annulated systems are potential emitters with small HOMO-LUMO energy gaps covering the orange-to-red region due to the efficient π -electron delocalization over the three conjugated heterole rings.

(© Wiley-VCH Verlag GmbH & Co. KGaA, 69451 Weinheim, Germany, 2008)

we designed a new class of ring-annulated benzo[c]phospholes that would possess a small o-quinonoid character. Herein, we report the first systematic study of the synthesis, structure, and optical and electrochemical properties of three types of bithiophene-fused benzo[c]phospholes. We experimentally demonstrated that changing the bithiophene skeleton dramatically affects the HOMO and LUMO energies as well as the intrinsic emitting properties of the hybrid phosphole–bithiophene-fused π systems.

Results and Discussion

Bithiophene-fused benzo[c]phospholes 4–9 were successfully prepared by the Ti^{II}-mediated cyclization^[12] of dialkynylated bithiophene derivatives 1-3 (Scheme 1). Reaction of $1a^{[13]}$ with (η^2 -propene)Ti(O*i*Pr)₂ generated in situ from Ti(OiPr)4 and 2 equiv. of iPrMgCl,^[14] followed by treatment with dichloro(phenyl)phosphane, gave a mixture containing target compound 4a and unreacted 1a, which were not separable by column chromatography. Therefore, the mixture was subsequently treated with AuCl(SMe₂) to afford Au^I-phosphole complex 7a, which could be easily isolated as a red solid in 57% yield. Treatment of 7a with an excess amount of P(NMe₂)₃ in toluene, followed by reprecipitation from MeOH reproduced σ^3 -phosphole 4a in 91% yield in high purity. The 2-thienyl-substituted derivatives (4b and 7b) and the other types of bithiophene-fused benzo[c]phospholes (5, 6, 8, and 9) were prepared from the corresponding bithiophene derivatives (1b, 2, and 3) according to a similar procedure.

Compounds **4–9** are air- and thermally stable solids soluble in common organic solvents such as CHCl₃, CH₂Cl₂, THF, and toluene, and they were fully characterized by standard spectroscopic techniques. The ³¹P NMR peaks of

SHORT COMMUNICATION



Scheme 1. Synthesis of bithiophene-fused benzo[c]phospholes 4-9.

 $σ^3$ -derivatives **4–6** appeared at δ = 24.2–29.6 ppm, whereas those of Au complexes **7–9** appeared at δ = 46.5–51.4 ppm. The observed downfield shifts (Δδ = 19.0–23.9 ppm for **7**, **8**, **9** vs. **4**, **5**, **6**) clearly support that the gold is coordinated to the phosphorus center. The downfield appearances of the ³¹P NMR peaks of **4–6** relative to those (δ = 12.7–13.6 ppm) of Réau's 3,4-C₄-bridged $σ^3$ -phospholes **10a,b** (Figure 1)^[3c] are presumably due to π conjugation along the benzo[*c*]-backbone of the present fused π system.



Figure 1. 2,5-Diarylphospholes **10** and **11**, dithieno[*b*,*d*]phosphole **12**, and bithiophene-fused benzo[*c*]phosphole models **4m–6m**.

The structures of **4a** and **7a** were further elucidated by X-ray crystallography.^[15] As shown in Figure 2, the π -conjugated phosphole and bithiophene rings in **4a** are nearly coplanar with moderate C–C/C=C bond length alternations ($\Delta d = 0.04-0.13$ Å).^[16] The phosphorus atom is pyramidalized with the sum of the C–P–C bond angles of 303.2°. The planar, fused π structure was also observed for **7a** (Supporting Information, Figure S1), in which the phosphorus atom adopts a distorted tetrahedral geometry ($\Sigma_{C-P-C} = 310.9^\circ$). The C_a–C_b and C_b–C_b bond lengths of the

phosphole ring in **7a** [1.353(6)–1.374(5) Å and 1.502(7) Å] are close to those in **11a** [1.346(9)–1.350(9) Å and 1.484(9) Å],^[6b] and the Au–P bond length [2.2283(10) Å] and the P–Au–Cl bond angle [177.27(4)°] are within the range of typical values reported for Au^I–phosphole complexes.^[17] In both **4a** and **7a**, the two α -phenyl groups are twisted from the phosphole ring with dihedral angles of 53.1–54.7° and 51.8–88.0°, respectively.



Figure 2. ORTEP diagram of **4a** (50% probability ellipsoids). Hydrogen atoms are omitted for clarity. Selected bond lengths [Å] and angles [°]: P1–C1 1.7934(14), P1–C4 1.7958(16), P1–C13 1.8272(15), C1–C2 1.374(2), C2–C3 1.486(2), C3–C4 1.374(2); C1–P1–C4 92.22(7), C1–P1–C13 104.97(6), C4–P1–C13 106.00(7).

To disclose the optical and electrochemical properties of the bithiophene-fused benzo[c]phospholes, we measured UV/Vis absorption and fluorescence spectra and redox potentials of **4–9**, and the results are summarized in Table 1. The UV/Vis absorption spectra of **4a** and **5a** display broad absorption bands attributable to the π - π * transition in the visible region (Figure 3). In the fluorescence spectra, **4a** and **5a** show single emission bands in the orange region with relatively high quantum yields (**4a**, $\Phi_{\rm F} = 17.6\%$; **5a**, $\Phi_{\rm F} = 9.7\%$). The absorption and fluorescence maxima of **4a** (462 nm; 600 nm) and **5a** (472 nm; 609 nm) are remarkably

Table 1. Optical and electrochemical data for 4-9.

Compd.	Absorption ^[a]		Fluorescence ^[a]		Redox potentials[b]	
	$\lambda_{\rm abs}$ / nm ^[c]	$\log \varepsilon$	$\lambda_{\rm em}$ / nm ^[d]	$\Phi_{\mathrm{F}}/\%^{\mathrm{[e]}}$	$E_{\rm ox}$ / V ^[f]	$E_{\rm red}$ / V ^[f]
4a	462	3.89	600	17.6	0.45	-2.14
4b	483	3.94	646	2.9	0.36	-2.00
5a	472	3.66	609	9.7	0.47	-2.09
5b	491	3.69	656	2.6	0.39	-1.97
6a	395 (sh)	3.36	548	0.64	0.66	-2.35
6b	409 (sh)	3.51	582	1.10	0.56	-2.18
7a	502	3.73	661	0.30	0.83	-1.63
7b	535	3.79	710	0.05	0.66	-1.55
8a	503	3.46	675	0.10	0.86	-1.62
8b	539	3.67	720	0.02	0.70	-1.50
9a	420 (sh)	3.15	596	0.47	1.12	-1.86
9b	435 (sh)	3.45	606	0.67	0.88	-1.76

[a] Measured in CH₂Cl₂. [b] Determined by DPV in CH₂Cl₂ with 0.1 M *n*Bu₄NPF₆. [c] The longest absorption maxima. [d] Excited at 440 nm for **4**, **5**, **7**, and **8** and at 420 nm for **6** and **9**. [e] Fluorescence quantum yields relative to **11b** ($\Phi_{\rm F} = 12.9\%$; ref.^[6b]). [f] Redox potentials vs. Fc/Fc⁺ couple.





Figure 3. UV/Vis absorption (solid line) and fluorescence (dashed line) spectra of 4a, 5a, and 6a in CH₂Cl₂.

It is well known that the chemical functionalizations at the α -carbon atoms and the phosphorus atom affect optical and electrochemical properties of the phosphole ring.^[2] The α -2-thienyl-substituted derivatives **4b**, **5b**, and **6b** exhibit absorption and emission maxima at longer wavelengths than do the corresponding α -phenyl derivatives, although the bathochromic shifts ($\Delta \lambda_{abs} = 14-21 \text{ nm}; \Delta \lambda_{em} = 34-47 \text{ nm}: 2$ thienyl vs. phenyl) are smaller than those reported for 10b versus 10a (Supporting Information, Figure S2a).^[3c] The P coordination to the AuCl salt induces more pronounced effects on the optical properties, that is, the larger bathochromic shifts in absorption and emission spectra ($\Delta \lambda_{abs} =$ 25–52 nm; $\Delta \lambda_{em} = 24$ –66 nm) and the considerable decrease in emission efficiency (Supporting Information, Figure S2b). Note that the fluorescence of chromophores 4 and 5 covers the orange-to-red region ($\lambda_{em} = 600-656$ nm).

The electrochemical redox processes of **4–9** were found to be irreversible, and the redox potentials listed in Table 1 were determined by means of differential pulse voltammetry (DPV). The first oxidation potentials (E_{ox}) and the first reduction potentials (E_{red}) of **4a** are 0.45 and -2.14 V (vs. ferrocene/ferrocenium), respectively, both of which are comparable to the respective potentials of **5a** ($E_{ox} = 0.47$ V; E_{red} = -2.09 V). By contrast, **6a** showed more positive E_{ox}



(0.66 V) and more negative $E_{\rm red}$ (-2.35 V) relative to those of 4a and 5a, showing that the HOMO–LUMO energy gaps of 4a and 5a ($\Delta E = 2.56-2.59$ V) are much smaller than that of 6a ($\Delta E = 3.01$ V). This is in good agreement with the results obtained from the absorption and fluorescence spectra (vide supra).

The complexation at the phosphorus center shifted the redox potentials to the positive direction (7, 8, 9 vs. 4, 5, 6). Noticeably, the shifts of the reduction potentials ($\Delta E_{red} = 0.42-0.51$ V) are somewhat larger than those of the oxidation potentials ($\Delta E_{ox} = 0.30-0.46$ V), indicating that the LUMO is lowered more largely than the HOMO by the complexation. On the other hand, the replacement of the *a*-substituents at the phosphole ring from phenyl to 2-thienyl shifted the oxidation and reduction potentials to the negative and positive directions, respectively, thereby narrowing the HOMO–LUMO energy gaps by 0.20–0.34 V.

To gain more insight into the electronic structures of bithiophene-fused benzo[c]phospholes, we carried out DFT calculations at the B3LYP/6-31G* level on α-unsubstituted model compounds 4m, 5m, and 6m.^[18] As visualized in Figure 4, the frontier orbitals of 4m and 5m are derived from the typical frontier orbitals of both the phosphole and bithiophene moieties, and they are spread over the entire π conjugated plane. The HOMOs hold antibonding characters between the adjacent heterole subunits, whereas the LUMOs represent interring bonding interactions. On the other hand, the frontier orbitals of 6m differ from those of 4m and 5m. For instance, the LUMO of 6m represents almost no bonding interactions among the three heterole rings. As a consequence, the calculated HOMO-LUMO separations of 4m (3.21 eV) and 5m (3.20 eV) are much smaller than that of 6m (3.95 eV).^[19] This agrees well with the experimentally observed results. As illustrated in Figure 4, the $\sigma^*(P-C_{Ph})$ orbital contributes to the LUMO to some degree, which explains the more pronounced effects of the complexation on the LUMOs relative to their HOMOs.



Figure 4. HOMO (lower) and LUMO (upper) of 4m (a), 5m (b), and 6m (c).

Conclusions

We successfully applied the Ti^{II}-mediated cyclization protocol to the preparation of three types of bithiophene-fused

SHORT COMMUNICATION

benzo[*c*]phospholes, which are the first examples of thermally and chemically stable benzo[*c*]phospholes. It was revealed that the optical and electrochemical properties of the bithiophene-fused benzo[*c*]phospholes strongly depend on the π -conjugation modes of the fused rings. Both experimental and theoretical results demonstrate that the appropriately fused π systems are potential emitters with small HOMO–LUMO energy gaps reaching into the near-infrared region. The chemical functionalization at the annulated bithiophene moieties will allow us to further extend the two-dimensional π networks. In this regard, the bithiophene-fused benzo[*c*]phospholes are highly promising building blocks for tailoring P,S-containing hybrid π -conjugated materials toward optoelectronic applications.

Experimental Section

7a: To a mixture of 1a (110 mg, 0.30 mmol), Ti(OiPr)₄ (0.088 mL, 0.30 mmol), and Et₂O (9 mL) was added a solution of *i*PrMgCl (2.0 M in ether, 0.30 mL, 0.60 mmol) at -60 °C. The resulting mixture was stirred for 3 h at -40 °C, followed by the addition of PhPCl₂ (0.041 mL, 0.30 mmol) at this temperature. The resulting suspension was warmed to 0 °C and stirred for 1 h. After stirring for an additional 3 h at room temperature, the mixture was subjected to short silica gel column chromatography (CH₂Cl₂). The orange fraction was then collected and treated with AuCl(SMe₂) (90 mg, 0.30 mmol). The color of the solution turned to red in a few seconds, and the mixture was concentrated under reduced pressure. The solid residue was subjected to silica gel column chromatography (CH₂Cl₂/hexane). The red fraction was collected, evaporated, and washed with MeOH to give 7a as a red solid (120 mg, 57%). M.p. 215 °C (dec). ¹H NMR (400 MHz, CD₂Cl₂): $\delta = 6.56$ (d, J = 5.2 Hz, 2 H), 7.01 (d, J = 5.2 Hz, 2 H), 7.05 (br., 2 H), 7.27 (br., 2 H), 7.32–7.42 (m, 4 H), 7.42–7.60 (m, 5 H), 7.79 (br., 2 H) ppm. ³¹P{¹H} NMR (162 MHz, CD₂Cl₂): δ = +46.5 ppm. MS (MALDI-TOF): $m/z = 707 \text{ [M]}^+$. HRMS (FAB): calcd. for C₃₀H₁₉AuClPS₂ [M]⁺ 706.0020; found 706.0016.

4a: P(NMe₂)₃ (32 µL, 0.18 mmol) was added to a toluene solution (5 mL) containing **7a** (42 mg, 0.060 mmol). After stirring at room temperature for 10 min, the mixture was concentrated under reduced pressure. The residue was washed with MeOH to give **4a** as an orange solid (26 mg, 91%). M.p. 175 °C (dec). ¹H NMR (400 MHz, CD₂Cl₂): $\delta = 6.85$ (d, J = 5.2 Hz, 2 H), 7.02 (d, J = 5.2 Hz, 2 H), 7.10–7.24 (m, 5 H), 7.25–7.40 (m, 10 H) ppm. ¹³C{¹H} NMR (100 MHz, CD₂Cl₂): $\delta = 122.8$, 126.3, 127.4, 128.5 (d, $J_{P,C} = 9.9$ Hz), 128.8, 128.9 (d, $J_{P,C} = 9.1$ Hz), 129.9 (d, $J_{P,C} = 7.4$ Hz), 130.3 (d, $J_{P,C} = 1.7$ Hz), 132.6 (d, $J_{P,C} = 3.3$ Hz), 134.7 (d, $J_{P,C} = 1.6$ Hz), 134.9 (d, $J_{P,C} = 1.9$ Hz), 136.2 (J = 14.9 Hz), 138.0 (d, $J_{P,C} = 14.9$ Hz), 146.1 (d, $J_{P,C} = 3.3$ Hz) ppm. ³¹P{¹H} NMR (162 MHz, CD₂Cl₂): $\delta = +24.6$ ppm. MS (MALDI-TOF): m/z = 474 [M]⁺. HRMS (FAB): calcd. for C₃₀H₁₉PS₂ [M]⁺ 474.0666; found 474.0672.

Supporting Information (see footnote on the first page of this article): Experimental details, characterization data, and DFT computational results.

Acknowledgments

This work was partly supported by Japan Science and Technology Agency in Research for Promoting Technological Seeds (No. 10-034).

- For reviews, see: a) L. D. Quin, The Heterocyclic Chemistry of Phosphorus, Wiley, New York, 1981; b) F. Mathey, Chem. Rev. 1988, 88, 429; c) L. D. Quin in Comprehensive Heterocyclic Chemistry (Eds.: A. R. Katritzky, C. W. Rees, E. F. V. Scriven), Elsevier, Oxford, 1996, vol. 2; d) F. Mathey, Phosphorus–Carbon Heterocyclic Chemistry: The Rise of a New Domain, Elsevier, Oxford, 2001; e) F. Mathey, Angew. Chem. 2003, 115, 1616; Angew. Chem. Int. Ed. 2003, 42, 1578.
- [2] For reviews, see: a) M. Hissler, P. W. Dyer, R. Réau, *Coord. Chem. Rev.* 2003, 244, 1; b) T. Baumgartner, R. Réau, *Chem. Rev.* 2006, 106, 4681 (*Correction:* 2007, 107, 303); c) P. W. Dyer, R. Réau in *Functional Organic Materials* (Eds.: T. J. J. Müller, U. H. F. Bunz), Wiley-VCH, Weinheim, 2007, pp. 119–177; d) M. G. Hobbs, T. Baumgartner, *Eur. J. Inorg. Chem.* 2007, 3611.
- [3] a) C. Hay, D. L. Vilain, V. Deborde, L. Toupet, R. Réau, Chem. Commun. 1999, 345; b) C. Hay, C. Fischmeister, M. Hissler, L. Toupet, R. Réau, Angew. Chem. 2000, 112, 1882; Angew. Chem. Int. Ed. 2000, 39, 1812; c) C. Hay, M. Hissler, C. Fischmeister, J. Rault-Berthelot, L. Toupet, L. Nyulászi, R. Réau, Chem. Eur. J. 2001, 7, 4222; d) C. Hay, C. Fave, M. Hissler, J. Rault-Berthelot, R. Réau, Org. Lett. 2003, 5, 3467; e) C. Fave, M. Hissler, T. Kárpáti, J. Rault-Berthelot, V. Deborde, L. Toupet, L. Nyulászi, R. Réau, J. Am. Chem. Soc. 2004, 126, 6058.
- [4] a) E. Deschamps, L. Ricard, F. Mathey, Angew. Chem. 1994, 106, 1214; Angew. Chem. Int. Ed. Engl. 1994, 33, 1158; b)
 S. S. H. Mao, T. D. Tilley, Macromolecules 1997, 30, 5566; c)
 Y. Morisaki, Y. Aiki, Y. Chujo, Macromolecules 2003, 36, 2594; d) T. Sanji, K. Shiraishi, M. Tanaka, Org. Lett. 2007, 9, 3611.
- [5] a) D. Delaere, M. T. Nguyen, L. G. Vanquickenborne, *Phys. Chem. Chem. Phys.* 2002, *4*, 1522; b) D. Delaere, M. T. Nguyen, L. G. Vanquickenborne, *J. Phys. Chem. A* 2003, *107*, 838; c) Y.-L. Liu, J.-K. Feng, A.-M. Ren, *J. Comput. Chem.* 2007, *28*, 2500.
- [6] a) C. Fave, T.-Y. Cho, M. Hissler, C.-W. Chen, T.-Y. Luh, C.-C. Wu, R. Réau, J. Am. Chem. Soc. 2003, 125, 9254; b) H.-C. Su, O. Fedhel, C.-J. Yang, T.-Y. Cho, C. Fave, M. Hissler, C.-C. Wu, R. Réau, J. Am. Chem. Soc. 2006, 128, 983.
- [7] a) C. Fave, M. Hissler, K. Sénéchal, I. Ledoux, J. Zyss, R. Réau, *Chem. Commun.* 2002, 1674; b) Y. Matano, T. Miyajima, H. Imahori, Y. Kimura, *J. Org. Chem.* 2007, *72*, 6200.
- [8] a) S. Kobayashi, M. Noguchi, Y. Tsubata, M. Kitano, H. Doi, T. Kamioka, A. Nakazono, *Jpn. Pat.* 2003231741, 2003; b) Y. Makioka, T. Hayashi, M. Tanaka, *Chem. Lett.* 2004, 33, 44. See also ref.^[6b]
- [9] a) T. Baumgartner, T. Neumann, B. Wirges, Angew. Chem.
 2004, 116, 6323; Angew. Chem. Int. Ed. 2004, 43, 6197; b) T. Baumgartner, W. Bergmans, T. Kárpáti, T. Neumann, M. Nieger, L. Nyulázi, Chem. Eur. J. 2005, 11, 4687; c) Y. Dienes, S. Durben, T. Kárpáti, T. Neumann, U. Englert, L. Nyulázi, T. Baumgartner, Chem. Eur. J. 2007, 13, 7487; d) A. Acharya, Y. Koizumi, S. Seki, A. Saeki, S. Tagawa, Y. Ie, Y. Aso, J. Photochem. Photobiol. A 2005, 173, 161.
- [10] T. C. Dinadayalane, G. N. Sastry, J. Chem. Soc. Perkin Trans. 2 2002, 1902.
- [11] Most of the benzo[c]phospholes reported have no substituent at the benzo backbone and readily undergo Diels-Alder reactions. The isolated benzo[c]phospholes bearing phosphonio groups at the a-positions were reported to be highly moisturesensitive solids. See: a) J. M. Holland, D. W. Jones, J. Chem. Soc., C 1970, 122; b) J. M. Holland, D. W. Jones, J. Chem. Soc., C 1970, 122; b) J. M. Holland, D. W. Jones, J. Chem. Soc. Perkin Trans. 1 1973, 927; c) T. H. Chan, K. T. Nwe, Tetrahedron Lett. 1973, 48, 4815; d) T. H. Chan, K. T. Nwe, Tetrahedron 1975, 31, 2537; e) A. Schmidpeter, M. Thiele, Angew. Chem. 1991, 103, 333; Angew. Chem. Int. Ed. Engl. 1991, 30, 308; f) A. Decken, F. Bottomley, B. E. Wilkins, E. D. Gill, Organometallics 2004, 23, 3683; g) R. A. Aitken in Science of Synthesis (Eds.: D. Bellus, S. V. Ley, R. Noyori, M. Regitz, P. J. Reider, E. Schaumann, I. Shinkai, E. J. Thomas, B. M. Trost), Thieme, New York, 2000, vol. 10, pp. 809–815.

- [12] For the syntheses of phospholes by titanacyclopentadienes, see:
 a) I. Tomita, M. Ueda, *Macromol. Symp.* 2004, 209, 217; b) I. Tomita, *Polym. Prepr.* 2004, 45, 415; c) Y. Matano, T. Miya-jima, T. Nakabuchi, Y. Matsutani, H. Imahori, *J. Org. Chem.* 2006, 71, 5792. See also refs.^[4d,7b]
- [13] U. Dahlmann, R. Neidlein, Helv. Chim. Acta 1996, 79, 755.
- [14] a) H. Urabe, T. Hata, F. Sato, *Tetrahedron Lett.* 1995, 36, 4261;
 b) H. Urabe, F. Sato, J. Org. Chem. 1996, 61, 6756; c) F. Sato,
 H. Urabe, S. Okamoto, Chem. Rev. 2000, 100, 2835 and references cited therein.
- [15] Crystal data for **4a**: formula $C_{30}H_{19}PS_2$, monoclinic, crystal size $0.45 \times 0.20 \times 0.15$ mm, space group $P2_1/n$ (#14), a = 6.2062(2) Å, b = 21.4229(9) Å, c = 17.4039(8) Å, $\beta = 97.372(3)^\circ$, V = 2294.80(16) Å³, Z = 4, $\rho_{calcd.} = 1.374$ g cm⁻³, $\mu = 3.19$ cm⁻¹, collected 18067, independent 5203, parameters 299, $R_w = 0.0728$, R = 0.0383 [$I > 2.00\sigma(I$)], GOF = 1.015. Crystal data for **7a**: formula $C_{31}H_{21}PAuCl_3PS_2$, triclinic, crystal size $0.20 \times 0.15 \times 0.05$ mm, space group P1, a = 9.888(3) Å, b = 12.243(4) Å, c = 12.481(4) Å, $a = 100.709(4)^\circ$, $\beta = 102.781(4)^\circ$, $\gamma = 95.077(4)^\circ$, V = 1434.5(8) Å³, Z = 2, $\rho_{calcd.} = 1.833$ g cm⁻³, $\mu = 26.29$ cm⁻¹, collected 11613, independent 6302, parameters 344, $R_w = 0.0648$, R = 0.0329 [$I > 2.00\sigma(I$]], GOF = 1.012. CCDC-660029 (for **4a**) and -660028 (for **7a**) contain the supplementary crystallographic data for this paper.



These data can be obtained free of charge from The Cambridge Crystallographic Data Centre via www.ccdc.cam.ac.uk/ data_request/cif.

- [16] The dihedral angles between the phosphole ring and the two thiophene rings are 6.0–8.8° for 4a and 3.3–7.7° for 7a. The phosphorus atom is slightly deviated from the mean plane of the benzo[c]phosphole skeleton by 0.14 Å for 4a and 0.06 Å for 7a.
- [17] a) S. Attar, W. H. Bearden, N. W. Alcock, E. C. Alyea, J. H. Nelson, *Inorg. Chem.* **1990**, *29*, 425. Au–P, 2.220(9)–2.227(2) Å; P–Au–Cl, 172.4(1)–178.8(1)°; b) see ref.^[6b] Au–P, 2.2290(16)–2.2300(16) Å; P–Au–Cl, 171.64(7)–174.63(8)°; c) Y. Dienes, M. Eggenstein, T. Neumann, U. Englert, T. Baumgartner, *Dalton Trans.* **2006**, 1424. Au–P, 2.2249(12) Å; P–Au–Cl, 177.
- [18] The calculated structural parameters of 4m are in good accordance with the experimentally determined parameters of 4a, suggesting that 4m is a good model for discussing the electronic structure of 4a. The structural parameters of 4m, 5m, and 6m are summarized in Figure S4 in the Supporting Information.
- [19] The HOMO and LUMO energies (in eV) are as follows: 4m (-5.10, -1.89), 5m (-5.16, -1.96), 6m (-5.55, -1.60).

Received: October 24, 2007 Published Online: November 27, 2007