The preparation and some properties of substituted phenyleneethynylene and phenylenebuta-1,3-diynylene polymers

Andrew Pelter * and D. Elfyn Jones

Department of Chemistry, University of Wales Swansea, Singleton Park, Swansea, UK SA2 8PP

Received (in Cambridge, UK) 29th October 1999, Accepted 23rd May 2000 Published on the Web 3rd July 2000

Syntheses are described for the preparation of a variety of diynes which are converted to high molecular weight substituted arylenebuta-1,3-diynylene polymers by oxidative coupling and to high molecular weight substituted arylene-ethynylene polymers by Pd(II) catalysed cross coupling reactions. The products tend to be insoluble in normal organic solvents. Doping with ferric chloride produces significant changes in conductivity but these are less than those produced on equivalently substituted thienylene-phenylene polymers.

Introduction

Since the discovery that films of polyacetylene can be made electrically conducting^{1,2} much effort has been directed to the design, synthesis and application of novel organic materials which combine the desirable material properties of conventional synthetic polymers with the electrical properties of metals. This active interest is reflected in the hundreds of research reports that appear annually as well as in a variety of review articles^{3,4} and books.^{5,6}

Our interest in this area began^{7,8} with the realisation that the then available methods for the chemical and electrochemical preparation of conjugated polymers resulted in some degree of randomisation in the unit linkages.⁹⁻¹¹ Thus methodology was required that would allow complete control of regiochemistry and be versatile enough to allow synthesis of a large number of structures so that structure–property relationships could be defined. We introduced such a methodology based on transition metal catalysed cross coupling of arylene dihalides with variously metallated heteroaryls^{7,8} and recently reported our results on the synthesis of substituted phenylene–thiophenylene oligomers and polymers.¹²

Despite the success of this methodology for the control of regiochemistry and the introduction of substituents, only low molecular weights of *ca.* 3000–10000 were obtained.^{12,13} It is generally agreed ¹⁴ that oligomers/polymers of this kind of molecular weight cannot achieve the mechanical strength required to make films and fibres. Indeed as a single cross-coupling reaction proceeds in only 70–90% yield Caruther's equation ¹⁵ indicates that this methodology *cannot* yield high molecular weight polymers.

A new approach was required and we chose to examine the synthesis and properties of poly(arylylenebuta-1,3-diynylene)s **1**. This decision was based on the known cyclisations of buta-1,3-diynes to yield heteroaromatics.^{16–21} The extension of this methodology to the preparation of poly(heteroarylenephenylene)s **2** can be readily envisaged (Scheme 1) as long as the necessary precursor polymers **1** are available.



Thus if high molecular weight polymers 1 could be prepared in a regiospecific fashion not only might they yield the polymers 2 but their own electrical properties would also be of great interest.

Acetylenic polymers

Only wholly organic systems and not metal containing acetylenic polymers²²⁻³⁰ will be considered here. 1,4- and 1,3-Diethynylbenzenes have been polymerized to give phenylenebuta-1,3-diynylene polymers with average molecular weights of between 8700 to 30000.³¹⁻³³ Thienylenebuta-1,3-dienylene polymers have recently been synthesised in an analogous fashion.³⁴

Palladium catalysed cross coupling reactions have been used to build phenylene-ethynylene polymers³⁵⁻³⁸ but molecular weights were only in the region of 1500–5000.

Results and discussion

1. General considerations

We realised that high molecular weight, substituted poly-(arylenebuta-1,3-diynylene) **1** and poly(arylene-ethynylene) type polymers **4** could both be produced from the appropriate arylenediynes and that they could be utilised in a variety of ways (Scheme 2).

Scheme 2 outlines some potential polymers derived from diyne precursors 3. Not only should 3 yield 1 and then 2, but also 4 by cross-coupling reactions which would allow for the incorporation, in a controlled fashion, of a variety of aryl groups. Hydrogenation of 4 would yield poly(phenylene-vinylene)s³⁹ 5, whilst reaction of 4 with 1,3-dipolar compounds⁴⁰ would yield a set of heteroaromatic polymers 6 of a quite different constitution from 2. Reaction of 3 with metal halides should yield polymers 7 incorporating the metal.⁴¹

A conceptually similar approach to 2 which involved the cyclisation of poly(arylene-1,4-diketones) using ammonium acetate and Lawesson's reagent has been described.⁴²

The nearest analogy⁴³ for the conversion of 3 to 1 to 2 involves the reactions of a mixed 'polyethynylbenzene' with H_2S and anilines. The product poly(thienylene-phenylene) were completely insoluble, possibly due to extensive cross linking.

The copper catalysed reactions with anilines were extremely sensitive to oxidants, the presence of which rapidly gave Aniline Black. The product *N*-arylpyrrolylene-phenylene polymers however were soluble but were determined by analysis to be high

J. Chem. Soc., Perkin Trans. 1, 2000, 2289–2294 2289

This journal is © The Royal Society of Chemistry 2000



in nitrogen as a result of 1,3-additions. The polymer from 4-methylaniline had a molecular weight of 86000.

2. Preparation of substituted 1,4-diethynylbenzene monomers

Two routes to give the required 1,4-diethynylbenzenes are shown in Scheme 3. The substituents were chosen based on our



Scheme 3 Reagents and conditions: (i) $Pd(PPh_3)_2Cl_2$ (cat.), CuI (cat.), HC=CSiMe₃, **28**, piperidine, 70 °C, 30 h; (ii) K₂CO₃, MeOH, 20 °C; (iii) $Pd(PPh_3)_2Cl_2$ (cat.), CuI (cat.), HC=CC(OH)Me₂, **29**, Pr_2^i NH, 75 °C, 24 h; (iv) NaH, toluene, reflux, 18 h; (v) CuCl, TMEDA, O₂, pyridine, 30 °C, ultrasound.

experience that two *n*-butyl or *n*-butyloxy groups/benzene unit greatly enhanced the solubility of oligomers 2^{12} As compared with products with R = H the substitution of two 1,4-related *n*-butyl groups should not lead to great perturbations in the electronics of the polymers, but when R = OMe or R = OBuⁿ then interesting electronic as well as solubility effects were expected.

1,4-Dibromobenzene 8 is commercially available and 9, 10 and 11 were prepared by our previous method.¹² For 8 and 10 the process^{44,45} leading to 12 and 14 and then to 20 and 22 proceeded in acceptable overall yields of 77 and 62% respectively. However when two equivalents of 28 (see Scheme 3) were

reacted with 9 then 13 was obtained in 7% yield only. A large amount of mono-coupled product was isolated together with some starting material. As 28 is expensive it was not desirable to force the reactions by using it in large excess therefore the much cheaper reagent 29 (see Scheme 3) was substituted for 28 for the coupling reactions.^{35–37,46,47}

Reaction of 4.8 equivalents of 29 with 9 gave 17 in 73% yield and deprotection to 21 with sodium hydride 46,47 proceeded in 51% yield. A similar procedure led from 11 to 19 in 88% yield and from 19 to 23 in 64% yield. Thus the required diethynylbenzenes, 20, 21, 22 and 23 were readily available in good quantities and it was unnecessary to make 15, 16 and 18.

3. Oxidative polymerisations of diynes 20-23

The conditions introduced by Hay³⁰⁻³² were tested on phenylethyne and gave 1,4-diphenylbuta-1,3-diyne in 85% yield. Using the same conditions diyne 20 gave a powder which was finely ground and suspended in methanol-1 M HCl aq. The mixture was sonicated for 5 h so as to remove residual CuCl, pyridine and low molecular weight oligomers, and the remaining solid was collected and dried. All polymeric products were treated in this way. Polymer 24 was obtained as a pale yellow solid which was completely insoluble in petroleum ether, dichloromethane, chloroform, THF and methanol at 50 °C. Polymer 25 was obtained as a bright yellow solid which became black but did not melt below 360 °C. The polymer had a limited solubility in organic solvents, e.g. 10 mg dissolved in 30 ml of THF at 50 °C, and was four times more soluble in hot nitrobenzene or anisole. The dimethoxypolymer 26 was obtained as an orange solid with similar solubility to 25 in THF. It did not melt up to 270 °C. Polymer 27 was a yellow-orange solid which also showed limited solubility in organic solvents, e.g. 10 mg dissolved in 50 ml THF, 18 ml PhNO₂ or 15 ml of hot anisole.

For all the above polymers unsatisfactory elemental analyses were obtained which may partly be explained by the presence of low molecular weight oligomers giving rise to lower C: H ratios, in a fashion similar to that recorded recently for binaphthylene-ethynylene polymers.⁴⁸

4. Polymerisations by cross-coupling reactions

Scheme 2 outlined a possible synthesis of polymers **4** by cross coupling reactions of **3** with dibromoarenes. We decided to test this, but keeping $Ar^1 = Ar^2$ (Scheme 2) as shown in Scheme 4. The same coupling conditions were used as for the preparation of the starting diynes.⁴¹



Scheme 4 Reagents and conditions: (i) $Pd(PPh_3)_2Cl_2$ (3–4 mol%), CuI (3–4 mol%), Pr_2^i NH, 70 °C.

All of polymers 30-33 were treated in the same way as polymers 24-27 in an effort to get rid of inorganic and organic impurities. However elemental analysis in each case deviated greatly from that expected. The greatest cause of impurity is Pr₂ⁱNH·HCl which was not completely removed even after sonication for 5 h in an aqueous medium. Thus 32 gave 0.4%nitrogen even after repeated washings with organic solvents, water and methanol. Similar problems of purification have been experienced by others who employed similar polymerisation methods. Thus Corriu et al.²⁸ removed Et₂NH·HCl from silicon containing polymers by repeated precipitation from THF-pentane. Marvel and Trumbo³⁶ removed the salt from their acetylenic polymers by repeated washing with 10% HCl, water and methanol followed by repeated precipitation from chloroformmethanol. Bochmann and Kelly³⁸ found as much as 6.7% of residual bromine. The very limited solubilities of our polymers makes purification by the dissolution-precipitation method impractical and purification remains a major problem as with other arylene-ethynylene polymers.48 Possibly the use of longer alkyl chains on the benzene rings would enhance solubility and this could be the most promising approach.

5. Molecular weight analyses of polymers 24-27 and 30-33

Molecular weight analyses were carried out by gel permeation chromatography using a polystyrene standard, a method that may overestimate the molecular weight of conjugated polymers by a factor between 1 and 2.^{49,50} For polymers **24** and **30**, total insolubility precluded molecular weight determination. The limited solubility of **26** and **27** meant that only some low molecular weight oligomers were observed. Polymer **32** was sufficiently soluble so that oligomers with M_w of 10000 were observed in the soluble fraction. The same was true of **33** which gave M_w 10380 and M_n 3207 for the soluble fraction. Polymer **25** was somewhat more soluble and M_w 46000 and M_n 11539 were obtained for the soluble fraction.

In general for molecular weight determinations we have used a 2% w/v solution^{12,51} but we were forced in these cases to use significantly lower concentrations. Even then only the lower molecular weight 'polymers' were observed and the results obtained are not a true reflection of the molecular weight of the bulk polymer. However, even the soluble fractions showed peaks ranging from a few thousand up to several hundred thousand.⁵¹ The results show that polymers can be obtained that are of much higher molecular weight than those made by the cross coupling reactions we previously employed. This is as true of the ethynyl cross-coupled polymers **30–33** as of polymers **24–27** obtained by the Hay–Glaser oxidation procedure.

6. Electrical conductivity measurements

The electrical conductivity of both the undoped polymers and the polymers doped with ferric chloride (see Experimental section) was examined and gave the results shown in Table 1.

All the undoped polymers have conductivities, as expected, in the insulator range. Doping has far less effect on the conductivities of these polymers than on polymers $2.^{12}$ Polymer 24 has been previously prepared 30,52 and solid state 13 C NMR suggested that it was defect free and of high molecular weight.

Table 1Electrical conductivities of polymers 24–27 and 30–33

Polymer	Conductivity S/cm ⁻¹	
	Undoped	Doped with FeCl ₃
24	3.434×10^{-12}	7.326×10^{-9}
25	1.330×10^{-11}	а
26	5.570×10^{-12}	6.044×10^{-11}
27	2.236×10^{-12}	4.463×10^{-8}
30	1.654×10^{-11}	2.399×10^{-10}
31	a	2.037×10^{-8}
32	1.889×10^{-12}	5.701×10^{-10}
33	4.112×10^{-11}	3.061×10^{-8}

Iodine doping was reported to increase the conductivity threefold ⁵² as compared with our increase using ferric chloride doping of 2.13×10^3 . The range of increase in conductivity of our diynyl polymers was from 2.0×10^4 for 27 to 10.9 for polymer 26, the effect of the methoxy substituents being very marked. The increases in the phenylenevinylene polymers 30, 32, 33 ranged from 14 to 1.34×10^3 . In both sets the changes were greatest with butyloxy substituents.

Conclusions

The approach adopted has resulted in high molecular weight polymers which however are very difficult to purify. Ongoing work concerns the production of polymers 1 and 4 with more lipophilic substituents, such as R = n-hexyl, *n*-octyl, *O*-*n*-hex, *O*-*n*-oct, in order to enhance the solubility of the polymers and thus greatly assist their purification and characterisation.

Experimental

General conditions

Trimethylsilylethyne, 2-methylbut-3-yn-2-ol, (Ph₃P)₂PdCl₂, CuI, CuCl, K₂CO₃, NaOH and reagent grade oxygen were commercially available and were used as bought. Sodium hydride (80% dispersion) was stirred with hexane and the hexane removed by a double ended needle. This was repeated at least three times and then the hexane was removed under vacuum. Phenylethyne and piperidine were refluxed over and distilled from CaH₂. Pyridine, TMEDA and diisopropylamine were refluxed over NaOH followed by distillation. Diethyl ether was passed through activated alumina then refluxed over and distilled from CaH2. THF was passed through activated alumina then refluxed over and distilled from CaH₂. Toluene was shaken with aliquots of ice-cooled conc. H₂SO₄, H₂O, 10% aqueous K_2CO_3 , H_2O then dried over $CaCl_2$ and distilled. Ferric chloride was used from a freshly purchased bottle taking care only to use lustrous, dark green needles.

All procedures, including polymer doping, that involved air sensitive reagents were performed in oven dried glassware that was assembled whilst hot and cooled in a slow stream of dry nitrogen. Transfer of air sensitive chemicals was achieved by using double ended needles under nitrogen or argon pressure or by graduated syringes. Doped polymers were stored over P_2O_5 in a vacuum desiccator. Chromatographic purifications were performed on either silica gel (230–400 mesh) or alumina under medium pressure using mixtures of pentane and chloroform.

Melting points were recorded on a Gallenkamp hot stage apparatus and are uncorrected. ¹H and ¹³C NMR spectra were recorded on a WM 250 Bruker instrument at 250.1 and 62.9 MHz respectively. DEPT/135 spectra were also obtained on this instrument. NMR spectra were recorded in CDCl₃ unless otherwise stated and are reported relative to tetramethylsilane ($\delta = 0$). J values are quoted in Hz. Infrared spectra were recorded on a Perkin-Elmer 1420 ratio recording spectrometer and a UNICAM SP 1050 spectrometer as KBr discs unless otherwise stated. UV-visible spectra were recorded on a Phillips PV 8720 UV-vis scanning spectrophotometer with absorption maxima reported in nm along with $(\log_{10} \varepsilon)$. Mass spectra were obtained using a VG MASSLAB 12-250 quadrupole instrument using alternating chemical/electron impact ionisation (ACE) conditions. Accurate masses were recorded on a ZAB-E VG analytical reverse geometry magnetic instrument. Elemental analyses were provided by the Microanalytical Service at the University of Wales Cardiff. Molecular weight determinations were carried out at the RARDE (MoD) establishment, Waltham Abbey using a Waters GPC system equipped with Waters Expert Version 4.0 analytical software, and are in polystyrene equivalents. The ultrasonic probe used was a 100 W Ultrasonic Amplifier, type L665. Electrical conductivities were determined by converting the dried powders to discs of 1 cm diameter and 0.5 mm thickness. Slabs of these discs, of known dimensions were cut and the ends coated with colloidal silver. Two platinum wires were attached to the silver and to a 10 point plug. The resistance was measured using a Keithley 602 programmable electrometer.

Preparation of aryldiyne monomers

1,4-Bis(trimethylsilylethynyl)benzene, 12. Trimethylsilylethyne **28** (7.7 g, 38.6 mmol) was added by syringe to a 500 ml round-bottomed flask containing a well stirred mixture of 1,4-dibromobenzene (9.1 g, 38.6 mmol), Pd(PPh₃)₂Cl₂ (0.3 g, 0.43 mmol, 1.1 mol%), CuI (0.14 g, 0.74 mmol) and diisopropylamine (150 ml). The resultant mixture was stirred at 70 °C for 3.5 h. The solvent was removed and the grey–black residue was placed on alumina (100 g) and eluted with petroleum spirit (40–60 °C). Compound **12** (10 g, 96%) was obtained as white crystals, mp 122 °C (lit.⁵² 122 °C). δ_H 7.39 (4H, s), 0.24 (18H, s). δ_C 104.5, 96.2 (*C*≡*C*H), 131 (d, (Ar)*C*H), 123.1 ((Ar)*C*-*C*≡*C*), -0.21 (Si-*C*H₃). λ_{max} (CHCl₃) 279.6 (3.59), 287.8 (3.44), 294.1 (3.67). v_{max}/cm^{-1} 2150 (-*C*≡*C* stretch). *m*/*z* 270, 255, 240, 225, 210, 195, 180. Found, M⁺, 270.1260. C₁₆H₂₂Si₂ requires 270.1259.

2,5-Bis(trimethylsilylethynyl)-1,4-dimethoxybenzene, 14. mixture of 1,4-dimethoxy-2,5-dibromobenzene¹² (15 g, 50.7 mmol), Pd(PPh₃)₂Cl₂ (0.38 g, 0.54 mmol, 1.1 mol%), CuI (0.1 g, 0.53 mmol) and piperidine (150 ml) was well stirred in a 500 ml round-bottomed flask. Trimethylsilylethyne 28 (10 g, 102 mmol) was added by syringe and the reaction mixture stirred at 70 °C for 6 h. The solvent was evaporated and 14 (12 g, 71%) was obtained as pale yellow crystals, mp 162-163 °C, by elution with light petroleum from alumina. $\delta_{\rm H}$ 6.29 (2H, s, Ar-H), 3.83 (6H, s, OCH₃), 0.27 (18H, s, Si(CH₃)₃). δ_C 0.12 (Si-CH₃), 56.55 (OCH₃), 100.5, 101.0 (C≡C), 113.7 ((Ar)C-C≡C), 116.4 (Ar-CH), 154.35 (Ar, C-OCH₃). λ_{max} (CHCl₃) 241.3 (3.19), 271.1 (3.40), 287.2 (3.67), 355.2 (3.17). v_{max}/cm^{-1} 2140 (C=C stretch). m/z 330, 315, 300, 285, 270, 255, 240, 225. Found, C 65.46; H, 7.87%, M⁺, 330.1471. C₁₈H₂₆O₂Si₂ requires C, 65.5; H, 7.9%, M⁺, 330.14698.

1,4-Bis(trimethylsilylethynyl)-2,5-di-*n*-butylbenzene, 13.

Piperidine (50 ml), 1,4-dibromo-2,5-di-*n*-butylbenzene **9** (3.1 g, 8.1 mmol), Pd(PPh₃)₂Cl₂ (0.167 g, 0.24 mmol, 2.9 mol%) and CuI (0.056 g, 0.29 mmol) were stirred in a 250 ml round-bottomed flask. Trimethylsilylethyne **28** (1.8 g, 18.4 mmol) was added and the reaction mixture was stirred at 70 °C for 30 h. The solvent was removed and the residue was chromatographed twice through alumina (2 × 200 g) using light petroleum (40–60 °C) as eluent. Compound **13** was obtained as light brown crystals which on crystallisation from ethanol–water gave **13** (0.19 g, 7%) as cream coloured needles, mp 53–55 °C. $\delta_{\rm H}$ 7.24 (2H, s, Ar-*H*), 2.69 (4H, t, Ar-CH₂-), 1.58 (4H, m, (Ar) CH₂CH₂-), 1.37 (4H, m, CH₂-CH₃), 0.93 (6H, *t*, CH₃-CH₂-),

0.25 (18H, s, Si-CH₃). $\delta_{\rm C}$ 0.44 (Si-CH₃), 14.41 (CH₃CH₂), 23.11 (CH₂CH₃), 33.17 (Ar-CH₂CH₂-), 34.25 (Ar-CH₂-CH₂), 99.39 (-C=*C*-SiMe₃), 104.48 (Ar-*C*=*C*-), 123.1 (C-1), 132.98 (C-3), 143.09 (C-2). *m*/*z* 382, 367, 351, 339, 310, 295, 280. Found, C, 75.25; H, 9.99%, M⁺, 382.2512. C₂₄H₃₈Si₂ requires C, 75.4; H, 9.9%, M⁺, 382.2510.

1,4-Bis(3-hydroxy-3-methylbut-1-ynyl)-2,5-di-n-butylbenzene, 17. A mixture of 1,4-dibromo-2,5-di-n-butylbenzene 9 (9.0 g, 25.8 mmol), Pd(PPh₃)₂Cl₂ (0.51 g, 0.73 mmol, 2.8 mol%), CuI (0.15 g, 0.79 mmol), and 2-methylbut-3-yn-2-ol, 29 in Pr₂ⁱNH (200 ml) was stirred at 75 °C for 24 h. Removal of the solvent was followed by chromatography on silica gel (500 g) using petroleum ether (40-60 °C) and chloroform mixtures. The product (6.7 g, 73%) was obtained as pale yellow needles, mp 130–132 °C. $\delta_{\rm H}$ 7.19 (2H, s, H-3), 2.65 (4H, t, Ar-CH₂), 2.35 (2H, s, OH), 1.62 (12H, s, CH₃-C(OH)), 1.54 (4H, m, Ar-CH₂-CH₂), 1.36 (4H, m, CH₂-CH₃), 0.93 (6H, t, CH₂-CH₃). δ_C 142.21 (C-2), 132.44 (C-3), 122.15 (C-1), 98.35 (Ar-C=C), 81.1 (Ar C≡C-), 65.87 (CMe₂), 33.81 (ArCH₂), 32.82 (Ar CH₂CH₂), 22.7 (CH₂CH₃), 14.11 (CH₃CH₂). λ_{max} 272 (4.45), 280.5 (4.48). m/z, 354, 339, 297. Found, C, 81.42; H, 9.76%; M⁺, 354.2559. C₂₄H₃₄O₂ requires C, 81.4; H, 9.6%; M⁺, 354.2557.

1,4-Bis(3-hydroxy-3-methylbut-1-ynyl)-2,5-di-n-butoxy-

benzene, 19. A 500 ml round-bottomed flask was charged with 1,4-dibromo-2,5-di-n-butoxybenzene, 11 (15 g, 39.5 mmol), Pd(PPh₃)₂Cl₂ (0.4 g, 0.37 mmol, 1.4 mol%), CuI (0.19 g, 1 mmol), **29** (15 g, 179 mmol, 4.5 equiv.) and Prⁱ₂NH (250 ml). The reaction mixture was stirred at 70 °C for 18 h, the solvent was evaporated and the residue was purified on silica (500 g) using CHCl₃ as eluent. Brown needles (15 g) were obtained and on crystallisation from acetone-water, and the *product* **19** (13.2 g, 88%) was isolated as fine white needles, mp 139–141 °C. $\delta_{\rm H}$ 6.82 (2H, s, H-3), 3.92 (4H, t, OCH₂), 2.90 (2H, s, HO-), 1.76 (4H, m, OCH₂CH₂), 1.61 (12H, s, C(OH)-CH₃), 1.51 (4H, m, CH₂CH₃), 0.97 (6H, t, CH₃CH₂). δ_C 153.56 (C-2), 117.13 (C-3), 113.48 (C-1), 99.28 (C-4'), 78.37 (C-3'), 31.4 (O-CH₂CH₂ and C-2'), 19.20 (CH₂CH₃), 13.85 (CH₃-CH₂). λ_{max} 269.9 (4.73), 278 (4.87), 338 (4.11). *m*/*z* 386, 328. Found, C, 74.78; H, 9.08%; M⁺, 386.2457. C₂₄H₃₄O₄ requires C, 74.6; H, 8.8%; M⁺, 386.2455.

1,4-Diethynylbenzene, **20.**⁵² Potassium carbonate (0.25 g, 1.85 mmol) was added to a 250 ml round-bottomed flask charged with **12** (0.5 g, 1.85 mmol) and methanol (100 ml). The mixture was stirred at room temperature for 16 h during which time the K₂CO₃ dissolved. Water (200 ml) was added and the precipitate was filtered and dried under reduced pressure at room temperature. *Product* **20** was obtained as white crystals mp 95–96 °C (lit.⁴⁴ 95–96 °C). $\delta_{\rm H}$ 3.17 (2H, s, *H*-C=C), 7.44 (4H, s, Ar-H). $\delta_{\rm C}$ 132.18 (C-2), 127.77 (C-1), 83.22 (Ar C=C), 79.21 (C=CH). $\lambda_{\rm max}$ (CHCl₃) 262.3 (4.39), 275 (4.45). $v_{\rm max}/{\rm cm}^{-1}$ 3270 (C=C-H).

2,5-Diethynyl-1,4-dimethoxybenzene, 22.⁵³ Compound **14** (4.5 g, 13.6 mmol) dissolved in MeOH (150 ml) was stirred with K₂CO₃, (4 g, 29 mmol) for 12 h at room temperature. Water (200 ml) was added and the *product* (2.2 g, 87%) was collected as white crystals, mp 163–166 °C (lit.⁵³ 153–154 °C). $\delta_{\rm H}$ 6.97 (2H, s, C-1), 3.85 (6H, s, OCH₃), 3.39 (2H, s, C=C-H). $\delta_{\rm C}$ 154.47 (C-1), 116.27 (C-2), 112.75 (C-3), 82.12 (Ar*C*=CH), 79.7 (-C=*C*H). $\lambda_{\rm max}$ 243.1 (3.89), 263.7 (4.18), 272.5 (4.22), 347.3 (3.95). $v_{\rm max}/{\rm cm}^{-1}$ 3260 (C=C-H stretch).

1,4-Diethynyl-2,5-di-*n***-butylbenzene, 21.** Sodium hydride (2.5 g, 104 mmol) was added to a solution of **17** (10.5 g, 29.6 mmol) in toluene (150 ml). The mixture was heated under reflux for 16 h then cooled and the supernatant liquid was decanted from the solid in the bottom of the flask. The solvent was evaporated leaving a viscous blood-red liquid which was placed on silica (250 g) and eluted with petroleum spirit (30–40 °C). *Product* **21**

(3.5 g, 50%) was obtained as a pale yellow liquid which turned to orange even on standing in the dark under nitrogen. The material solidified to a blood-red gel-like substance when reduced pressure distillation was attempted. $\delta_{\rm H}$ 7.27 (2H, s, H-3), 3.2 (2H, s, C=C-H), 2.7 (4H, t, Ar CH₂CH₂), 1.58 (4H, m, Ar CH₂CH₂), 1.34 (4H, m, CH₂CH₃), 0.9 (6H, t, CH₂CH₃). δ_c 142.62 (*C*(Ar)-Bu), 133.04 (C-3), 122.16 (Ar(*C*)-C=CH), 82.36 (Ar-C≡CH), 81.66 (Ar-C≡CH), 33.66 (Ar-CH₂), 32.82 (Ar-CH₂CH₂-), 22.63 (CH₂CH₃), 14.0 (CH₂CH₃). Found, C, 89.65; H, 9.89%. C₁₈H₂₂ requires C, 90.8; H, 9.2%.

1,4-Di-n-butoxy-2,5-diethynylbenzene, 23. A 250 ml roundbottomed flask was charged with a solution of 19 (18 g, 46.6 mmol) in toluene (175 ml). Sodium hydride (5.5 g, 229 mmol) was added and the mixture heated under reflux for 12 h. The liquid was decanted from the solid residue, evaporated and the red residue chromatographed on silica (500 g) using as eluent a mixture of light petroleum and chloroform (1:1). Product 23 was obtained as pale green needles, mp 102-104 °C (8 g, 64%). δ_H 6.96 (H-3), 3.97 (4H, t, CH₂-O), 3.34 (2H, s, C≡CH), 1.77 (4H, m, OCH₂CH₂), 1.49 (4H, m, CH₂CH₃), 0.95 (6H, t, CH₃).

Preparation of aryldiyne polymers

Poly(1,4-phenylenebuta-1,3-diynylene), 24. Oxygen was bubbled into a sonicated 250 ml round-bottomed flask containing CuCl (0.2 g, 2 mmol), TMEDA (0.5 g, 4.3 mmol) and pyridine (50 ml) at 32 °C. A solution of 1,4-diethynylbenzene, 20 (0.7 g, 5.6 mmol) in pyridine (30 ml), also at 32 °C, was added rapidly and the mixture left at 32 °C for 16 h. Evaporation of the solvent gave a green solid which was suspended in a mixture of methanol (50 ml) and aqueous 1 M HCl (50 ml) and sonicated for 3 h. The very fine yellow powder that resulted was filtered, washed with water and dried at 40 °C/0.1 mmHg for 2 h and then for 16 h at room temperature. This process gave 24 (0.6 g, 86%). λ_{max} 331.9, 341.5, 355.3. Found, C, 91.57; H, 4.05%. (C₁₀H₄)_n requires C, 96.8; H, 3.2%.

Poly[(2,5-di-n-butyl-1,4-phenylene)buta-1,3-diynylene], 25. A solution of 21 (4.9 g, 18.1 mmol) in pyridine (50 ml) was added to a sonicated 3-necked 250 ml round-bottomed flask charged with CuCl (0.7 g, 7.1 mmol), TMEDA (0.8 g, 6.9 mmol) and pyridine (150 ml) at 52 °C through which oxygen was bubbled. During the addition the temperature rose to 65 °C. The reaction was continued at 55 °C for 19 h, solvent was evaporated and the product obtained as for 24. The product was reprecipitated from chloroform-acetone and dried at room temperature under reduced pressure to give product 25 (2.8 g, 82%) as a yellow powder. $\delta_{\rm H}$ 7.35 (2H, br s, Ar-H), 2.76 (4H, br t, Ar-CH_2), 1.6 (4H, br m, Ar-CH₂CH₂), 0.97 (6H, t, CH₃). λ_{max} 247.6, 280.8, 369.0, 395.7. Found C, 88.77; H, 8.76%. (C18H20)n requires C, 91.5; H, 8.5%.

Poly[(2,5-dimethoxy-1,4-phenylene)buta-1,3-diynylene], 26. The same procedure as for 25 was used, the quantities being 22 (2.4 g, 12.9 mmol), CuCl (0.3 g, 3 mmol), TMEDA (0.5 g, 4.3 mmol) and pyridine (160 ml). The reaction temperature was 45 °C and the reaction time was 14.5 h. Work-up as before gave 26 (2.8 g) as an orange solid which had very low solubility in most organic solvents. λ_{max} (CHCl₃) 409. Found, C, 74.0; H, 4.7%. $(C_{12}H_8O_2)_n$ requires C, 78.2; H, 4.3%.

Poly[(2,5-di-*n*-butyloxy-1,4-phenylene)buta-1,3-diynylene],

27. The same procedure as for 24 and 25 was followed. Monomer 23 (4.9 g, 18.1 mmol) in pyridine was added to a mixture of CuCl (0.54 g, 5.5 mmol), TMEDA (1.05 g, 9 mmol) and pyridine (120 ml) at 53 °C. The temperature rose to 83 °C during the 13 h reaction time. Solvent was removed and the usual work-up gave product 27 (2.2 g, 45%) as an orange solid.

 λ_{max} (CHCl_3) 243.0, 349.6, 428.0. Found C, 80.7; H, 7.67%. (C₁₈H₂₀O₂)_n requires C, 80.6; H, 7.5%.

Preparation of arylylene-ethynylene polymers

Poly(1,4-phenyleneethynylene), 30. A solution of 1,4diethynylbenzene 20 (2.9 g, 23 mmol), 1,4-dibromobenzene 8 (5.4 g, 22.8 mmol), Pd(PPh₃)₂Cl₂ (0.5 g, 0.71 mmol, 3.1 mol%), CuI (0.13 g, 0.68 mmol) and Prⁿ₂NH (100 ml) was stirred at 75 °C for 40 min after which time the precipitate was so thick that stirring was not possible. The solvent was removed to give a light green residue which was finely ground and suspended in a mixture of methanol (200 ml) and aqueous HCl (3 M, 100 ml). The suspension was subjected to ultra-sound for 2 h, filtered and the residue washed with methanol and then ether. Product 30 (4.5 g, 98%) was obtained as a brown solid after being dried in a desiccator at room temperature. λ_{max} (CHCl₃) 240, 330.

Poly[(2,5-di-n-butyl-1,4-phenylene)ethynylene], 31. The same method as for 30 was used, the quantities being 1,4-diethynyl-2,5-di-n-butylbenzene (1.85 g, 7.8 mmol), 1,4-dibromo-2,5diethynylbenzene, 9 (2.7 g, 7.8 mmol), Pd(PPh₃)₂Cl₂ (0.18 g, 0.26 mmol, 3.3 mol%), CuI (0.1 g, 0.53 mmol, 6.4 mol%) and Pr₂ⁿNH (100 ml). The reaction on cooling gave a solid precipitate, and on addition of methanol, more precipitate was obtained and worked up as for 30. The green powder that resulted was dissolved in chloroform, washed with water, dried over CaCO₃, filtered and the solvent removed to give a dark reddish brown solid (1.5 g). $\delta_{\rm H}$ 7.37 (2H, br m, Ar-H), 2.7 (4H, br m, Ar-CH₂), 1.64 (4H, br m, ArCH₂CH₂), 1.44 (4H, br m, CH₂CH₃), 0.98 (6H, br m, CH₃). λ_{max} (CHCl₃), 244.0, 387.0. Found, C, 83.3; H, 8.9%. (C₁₆H₂₀)_n requires C, 90.6; H, 9.4%.

Poly[(2,5-dimethoxy-1,4-phenylene)ethynylene], 32. A mixture of 22 (2.2 g, 11.8 mmol), 10 (3.5 g, 11.8 mmol), Pd(PPh₃)₂Cl₂ (0.23 g, 0.33 mmol, 2.8 mol%), CuI (0.065 g, 0.34 mmol) and Prⁿ₂NH (125 ml) was stirred at 70 °C for 16 h. The usual work-up as for 30 gave product 32 (4.4 g) as a pale yellow, insoluble polymer. λ_{max} (CHCl₃) 303, 408.

Poly[(2,5-di-n-butyloxy-1,4-phenylene)ethynylene], 33. Following the general procedure for 30 a mixture of 23 (2.0 g, 7.4 mmol), 11 (2.8 g, 7.4 mmol), Pd(PPh₃)₂Cl₂ (0.2 g, 0.28 mmol, 3.9 mol%) and CuI (0.13 g, 0.68 mmol) in Pr_2^iNH (150 ml) was stirred for 15 h at 75 °C. The usual work-up gave a reddish brown solid which was subjected to 48 h extraction with toluene in a Soxhlet extractor. This gave a soluble fraction (0.8 g) with $\delta_{\rm H}$ 7.08 (2H, br s, Ar-H), 4.02 (4H, m, OCH₂), 1.84 (4H, br m, O-CH₂CH₂), 1.63 (4H, br m, CH₂CH₃), 1.0 (6H, m, CH₃). λ_{max} (CHCl₃) 243.0, 436.0. The insoluble fraction (0.9 g) had C, 73.7; H, 7.7%. (C₁₆H₂₀)_n requires C, 78.7; H, 8.2%.

Doping experiments

Insoluble polymers. A saturated solution of FeCl₃ in nitromethane was prepared by stirring a large excess of FeCl₃ with nitromethane for 3 h. The solution was decanted by cannula under nitrogen pressure. The polymer samples (0.2 g) were thoroughly ground up and stirred for 12 h at room temperature with the FeCl₃ solution then rapidly pressed into discs using a standard IR press. The discs were kept in an active desiccator over P₂O₅ under reduced pressure prior to resistivity measurements.

Soluble polymers. Polymer (0.2 g) was dissolved in chloroform and stirred with solid FeCl₃ (0.4 g) for 15 h at room temperature. The solvent was removed and evaporated and the residues washed thoroughly with ether, dried and pressed into discs.

Acknowledgements

We thank the EPSRC for financial backing for this work.

References

Published on 03 July 2000. Downloaded by MARSHALL UNIVERSITY on 23/10/2014 00:56:17.

- 1 H. Shirakawa, J. Chem. Soc., Chem. Commun., 1977, 578.
- 2 H. Shirakawa, J. Am. Chem. Soc., 1978, 100, 1013.
- 3 J. Roncali, Chem. Rev., 1997, 97, 173.
- 4 A. Kraft, A. C. Grimsdale and A. B. Holmes, Angew. Chem., Int. Ed., 1998, 37, 402.
- 5 Handbook of Conducting Polymers, ed. T. A. Skotheim, M. Dekker Inc., New York, 1986, vol. 1 and 2.
- 6 Handbook of Organic Conductive Molecules and Polymers, ed. H. S. Nalwa, J. Wiley, New York, 1997.
- 7 A. Pelter, M. Rowlands and I. H. Jenkins, Tetrahedron Lett., 1987, 28, 5213.
- 8 A. Pelter, J. M. Maud, I. H. Jenkins, C. Sodeka and G. S. V. Coles, Tetrahedron Lett., 1989, 30, 3461.
- 9 R. J. Waltman and J. Bargon, Can. J. Chem., 1986, 64, 76.
- 10 R. J. Waltman, J. Bargon and A. F. Diaz, J. Phys. Chem., 1983, 87, 1459.
- 11 K. Sanechika, T. Yamamoto and A. Yamamoto, J. Polym. Sci., Polym. Lett. Ed., 1982, 20, 365.
- 12 A. Pelter, I. H. Jenkins and D. E. Jones, Tetrahedron, 1997, 53, 10357
- 13 I. H. Jenkins, PhD Thesis, University of Wales Swansea, 1991
- 14 G. Odian, Principles of Polymerisation, 3rd edn., J. Wiley, New York, 1991, p. 19.
- 15 J. M. G. Cowie, Polymers: Chemistry and Physics of Modern Materials, 2nd edn., Blackie and Son, London, 1991.
- 16 K. E. Schlute, J. Reisch and L. Horner, Angew. Chem., 1960, 72, 920.
- 17 K. E. Schlute, J. Reisch and L. Horner, Chem. Ber., 1962, 95, 1943.
- 18 K. E. Schlute, K. Walker and L. Rolf, Tetrahedron Lett., 1967, 4819.
- J. Reisch and K. E. Schlute, *Angew. Chem.*, 1961, **73**, 241.
 J. Reisch, K. E. Schlute and K. Walker, *Chem. Ber.*, 1965, **98**, 98.
- 21 G. Märkl and R. Potthast, Angew. Chem., Int. Ed. Engl., 1967, 6, 86. 22 K. Sonogashira, S. Takahashi and N. Hagihara, Macromolecules, 1977. 10. 897.
- 23 S. Takahashi, E. Murata, K. Sonogashira and N. Hagihara, J. Polym. Sci., Polym. Chem. Ed., 1980, 18, 661.
- 24 K. Sonogashira, K. Ohga, S. Takahashi and N. Hagihara, J. Organomet. Chem., 1980, 188, 237.
- 25 J. Manners, Chem. Br., 1996, 32, 46 and references therein.
- 26 S. J. Davies, B. F. G. Johnson, M. S. Khan and J. Lewis, J. Chem. Soc., Chem. Commun., 1991, 187.

- 27 S. Takahashi, H. Morimoto, E. Murata, S. Kataoka, K. Sonogashira and N. Hagihara, J. Polym. Sci., Polym. Chem. Ed., 1982. 20. 565.
- 28 R. J. P. Corriu, W. E. Douglas and Z. Yang, J. Polym. Sci., Polym. Chem. Ed., 1990, 28, 431.
- 29 S. Ijadi-Maghsoodi, Y. Pang and T. J. Barton, J. Polym. Sci., Polym. Chem. Ed., 1990, 28, 955.
- 30 A. S. Hay, J. Polym. Sci., Part A: Polym. Chem., 1972, 10, 975.
- 31 A. S. Hay, J. Org. Chem., 1960, 25, 1275.
 32 A. S. Hay, J. Org. Chem., 1962, 27, 3320.
- 33 C. Glaser, Chem. Ber., 1869, 2, 422
- 34 D. R. Rutherford, J. K. Stille, C. M. Elliot and V. R. Reichert, Macromolecules, 1992, 25, 2294.
- 35 D. L. Trumbo and C. S. Marvel, J. Polym. Sci., Part A: Polym. Chem., 1986, 24, 759.
- 36 D. L. Trumbo and C. S. Marvel, J. Polym. Sci., Part A: Polym. Chem., 1986, 24, 2231.
- 37 D. L. Trumbo and C. S. Marvel, J. Polym. Sci., Part A: Polym. Chem., 1986, 24, 2311.
- 38 M. Bochmann and K. Kelly, J. Polym. Sci., Part A: Polym. Chem., 1992. 30. 2503.
- 39 G. E. Wnek, J. C. W. Chien, F. E. Karasz and C. P. Lillya, Polymer, 1979. 20, 1411.
- 40 (a) J. Bastide, J. Hamelin, F. Texier and Y. Vo-Quong, Bull. Soc. Chim. Fr., 1973, 2555; J. Bastide, J. Hamelin, F. Texier and Y. Vo-Quong, Bull. Soc. Chim. Fr., 1973, 2871; (b) J. Bastide and O. Henri-Rousseau, The Chemistry of the Carbon-Carbon Triple Bond, ed. S. Patai, Wiley Interscience, New York, 1978, ch. 11, p. 447.
- 41 W. D. Huntsman, The Chemistry of Functional Groups, Supplement C, ed. S. Patai and Z. Rappaport, Wiley Interscience, New York, 1983, p. 917.
- 42 K. L. Pouwer, T. R. Vries, E. E. Havinga, E. W. Meijer and H. Wynberg, J. Chem. Soc., Chem. Commun., 1988, 1432.
- 43 W. Bracke, J. Polym. Sci., Part A-1, 1972, 10, 975.
- 44 K. Sonogashira, Y. Tohda and N. Hagihara, Tetrahedron Lett., 1975, 4467.
- 45 N. Hagihara, S. Takahashi, Y. Kuroyama and K. Sonogashira, Synthesis, 1980, 627.
- 46 A. Oponchenko, E. T. Sabourin and C. Selwitz, J. Org. Chem., 1979, **44**, 1233.
- 47 T. X. Neenan and G. M. Whitesides, J. Org. Chem., 1988, 53, 2489.
- 48 Y. Meng, W. J. Slaven IV, C.-J. Li, D. Wang, T.-J. Liu and H.-F. Chow, Tetrahedron: Asymmetry, 1998, 9, 3693.
- 49 T. J. Katz and S. J. Lee, J. Am. Chem. Soc., 1980, 102, 422.
- 50 T. Masuda, N. Sasaki and T. Higashimura, Macromolecules, 1975, 8, 717
- 51 A. Pelter, M. Stewart and D. E. Jones, unpublished observations.
- 52 H. Okawa and T. Uryu, Polym. J. (Tokyo), 1990, 22, 539.
- 53 M. S. Shvartsberg, A. A. Moroz and O. D. Kiseleva, Izv. Akad. Nauk. SSSR, Ser. Khim., 1981, 827; Chem. Abstr., 95, 114953.