# ChemComm

### **Accepted Manuscript**

### ChemComm

Chemical Communicatio



This is an *Accepted Manuscript*, which has been through the RSC Publishing peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, which is prior to technical editing, formatting and proof reading. This free service from RSC Publishing allows authors to make their results available to the community, in citable form, before publication of the edited article. This Accepted Manuscript will be replaced by the edited and formatted Advance Article as soon as this is available.

To cite this manuscript please use its permanent Digital Object Identifier (DOI®), which is identical for all formats of publication.

More information about *Accepted Manuscripts* can be found in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics contained in the manuscript submitted by the author(s) which may alter content, and that the standard **Terms & Conditions** and the **ethical guidelines** that apply to the journal are still applicable. In no event shall the RSC be held responsible for any errors or omissions in these *Accepted Manuscript* manuscripts or any consequences arising from the use of any information contained in them.

#### **RSC**Publishing

www.rsc.org/chemcomm Registered Charity Number 207890 Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxx

### 

**Communications Accepted Manuscrip** 

## **Control of Framework Interpenetration for** *in situ* **Modified Hydroxyl Functionalised IRMOFs**

Damien Rankine,<sup>*a*</sup> Antonio Avellaneda,<sup>*a*</sup> Matthew R. Hill,<sup>*b*</sup> Christian J. Doonan<sup>\*,*a*</sup> and Christopher J. Sumby<sup>\*,*a*</sup>

s Received (in XXX, XXX) Xth XXXXXXXX 20XX, Accepted Xth XXXXXXXX 20XX DOI: 10.1039/b000000x

By intimate control of reaction conditions, phase-pure crystalline porous metal-organic framework materials  $[Zn_4O(L)_3]$  with interpenetrated and non-interpenetrated <sup>10</sup> structures can be synthesised. Under certain conditions, these reactions occur with concomitant deprotection of masked alcohols located on the organic links which yield accessible 'metal-binding' functional groups within the frameworks.

Metal-organic frameworks (MOFs) are constructed by a modular 15 synthetic approach whereby organic links and metal clusters are assembled into porous extended networks via 'one-pot' reactions.<sup>1</sup> This has led to the development of design principles that yield precise control of pore dimensions and functionality by utilizing links of identical connectivity but different lengths or <sup>20</sup> non-structural functional groups.<sup>2</sup> Due to their high surface areas, tuneable structure metrics and chemically mutable organic building blocks, MOFs have been identified as materials with great potential for gas separations<sup>3</sup> and size-selective heterogeneous catalysis.<sup>4</sup> To fully realise their catalytic potential 25 MOFs with pores sufficiently large enough to simultaneously allow anchoring of catalytic moieties and diffusion of chemical reactants into the framework is requisite. Furthermore, given that the majority of the metal clusters that comprise the 'joints' of MOF structures are catalytically benign, reliable methods for

<sup>30</sup> anchoring catalytic moieties to the framework need to be established. Two major challenges arise; 1) Increasing the pores sizes of topologically identical MOFs commonly affords interpenetration<sup>5</sup> and, 2) utilizing organic links which bear metalcoordinating groups can lead to unwanted side reactions or hinder <sup>35</sup> the formation of the desired networks. Thus, frameworks directly

synthesized with free metal-coordinating groups are rare.<sup>6-8</sup>

Recently, post-synthetic modification (PSM) has been developed as a strategy to overcome these challenges and yield open framework materials imbued with novel functionality.<sup>8</sup> A 40 potential drawback of the PSM method is that performing multiple reactions on the MOF crystals can lead to structural decomposition and/or diminished surface area.9 Thus, to ensure the MOFs retain optimal porosity and crystallinity it is preferable that the most efficient synthetic procedure is employed. Here we 45 report the controlled one-pot synthesis and in situ ester hydrolysis of non-interpenetrated and interpenetrated MOFs,  $[Zn_4O(L1)_3]$ and  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>], comprised of biphenyl-2,2'-diol links (L1) (Scheme 1(a)). Notably, both materials can be synthesized in a single-step procedure. It is also noteworthy that the metal co-50 ordinating groups are freely accessible in both forms which we demonstrate by the complexation of copper ions and enhanced enthalpy of adsorption for  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] over IRMOF-1.



**Scheme 1**. (a) Synthesis of  $[Zn_4O(L1)_3]$  and  $\alpha$ - $[Zn_4O(L1)_3]$ . Inset: Space-filling representations of the pores in (b)  $[Zn_4O(L1)_3]$  and (c) <sup>55</sup>  $\alpha$ - $[Zn_4O(L2)_3]$ . (d) Images from the metallation studies to generate  $\alpha$ - $[Zn_4O(L1)_3]$  $\supset$ Cu and show accessibility of the hydroxyl groups.

This journal is © The Royal Society of Chemistry [year]

 $[Zn_4O(L1)_3]$  was synthesized by dissolving 30 mg of  $H_2L1^{Ac}$ and 85 mg of  $Zn(NO_3)_2$ · $6H_2O$  (4 eq) in *N*,*N*'-diethylformamide (DEF) (4.5 mL) in a tightly-capped 20 mL glass vial.<sup>†</sup> An aliquot of 2.5 M aqueous NaOH solution (30 µL) was then added and the

- s solution heated at 90°C for 20 mins. The solution was then transferred to a new 20 mL vial and heated at 100°C for 36 hours yielding transparent pale yellow, cubic crystals of  $[Zn_4O(L1)_3]$ with an empirical formula of  $(C_{42}H_{24}O_{19}Zn_4)$ . Other more bulky ester protected links  $(H_2L1^{iBu})$  also generated the same non-10 interpenetrated material. The structure of  $[Zn_4O(L1)_3]$  was
- determined by single crystal X-ray diffraction. As anticipated, the framework of  $[Zn_4O(L1)_3]$  is of cubic topology with  $Zn_4O(L1)_3$  clusters positioned at each of the vertices and biphenyl moieties forming the organic backbone (Scheme 1). The formation of a <sup>15</sup> non-interpenetrated 3-D network is noteworthy given the size of the pore channels (15.4 Å), and the lack of significant steric

congestion within the pores arising from the linker. To ensure that the single crystal structure was representative of the bulk material, samples of [Zn<sub>4</sub>O(L1)<sub>3</sub>] were examined by 20 powder X-ray diffraction (PXRD, Fig. S3).<sup>†</sup> The resultant peak patterns were consistent with that expected for a noninterpenetrated framework. A further noteworthy feature of  $[Zn_4O(L1)_3]$  is that the acetyl protecting groups are hydrolysed during the one-pot synthesis to afford pores decorated with 25 accessible hydroxyl functional groups. <sup>1</sup>H NMR spectra of digested [Zn<sub>4</sub>O(L1)<sub>3</sub>] reveals all links have been fully deprotected during the course of the reaction. Examples of permanently porous MOFs synthesized from alcohol functionalized links are uncommon,<sup>7, 8</sup> as the free oxygen atoms can participate in metal <sup>30</sup> coordination.<sup>10</sup> For example, we could not form a characterisable MOF from only deprotected ligand ( $H_2L1$ ) and  $Zn(NO_3)_2 \cdot 6H_2O$ , although MOFs with different topologies could be formed with other metals or by incorporating other links. The choice of reaction conditions is also critically important to the nature of the 35 product. Using an analogous procedure, but with DMF as the solvent, we obtained phase-pure interpenetrated  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] from both H<sub>2</sub>L1<sup>Ac</sup> and more sterically-demanding H<sub>2</sub>L1<sup>iBu</sup>. Unit cell determinations for  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] indicated that in this case the framework is two-fold interpenetrated. In addition, the PXRD <sup>40</sup> pattern obtained from bulk samples of  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] closely matched that of the calculated peak positions and intensities for a lower-symmetry two-fold interpenetrated framework.

Downloaded by Indiana University - Purdue University at Indianapolis on 02 September 2012

Published on 31 August 2012 on http://pubs.rsc.org | doi:10.1039/C2CC3556E

To determine the permanent porosity of  $[Zn_4O(L1)_3]$  and  $\alpha$ - $[Zn_4O(L1)_3]$  77 K N<sub>2</sub> isotherms were carried out on the respective 45 evacuated frameworks (Fig. 1). Based on their isotherms, the BET surface areas of each material were calculated to be 2631 and 1790 m<sup>2</sup>/g<sup>-1</sup> for  $[Zn_4O(L1)_3]$  and  $\alpha$ - $[Zn_4O(L1)_3]$ , respectively. The isotherm of  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] is best described as Type I, which is indicative of microporosity. A step in the 50 isotherm of  $[Zn_4O(L1)_3]$  is observed in the low pressure region between  $P/P_0$  of 0.020 and 0.045 and can be attributed to the larger pore volume expected for the non-interpenetrated framework (Scheme 1(b) and (c)).<sup>11</sup> Notably, the synthetic procedure and activation conditions utilized in the present work 55 yielded a surface area for  $[Zn_4O(L1)_3]$  that is the highest reported for a material based on an IRMOF-9 framework. Thermogravimmetric analyses indicate  $[Zn_4O(L1)_3]$  and  $\alpha$ - $[Zn_4O(L1)_3]$  are thermally stable to 600 and 720 K respectively.<sup>†</sup>

To demonstrate accessibility of the diol chelating sites,

<sup>&</sup>lt;sup>60</sup> [Zn<sub>4</sub>O(**L1**)<sub>3</sub>] and α-[Zn<sub>4</sub>O(**L1**)<sub>3</sub>] were treated with 0.05 M solutions of CuCl<sub>2</sub>·2H<sub>2</sub>O (Scheme 1(d)). Within minutes, crystalline samples of both materials took on a green colour associated with complexation of copper ions by the links. The rate of complexation is consistent with binding to the free didio Dnline <sup>65</sup> links rather than incorporation into the metal-oxide nodes of the framework.<sup>12</sup> This colour was retained upon washing. Ester protected [Zn<sub>4</sub>O(**L1**<sup>Ac</sup>)<sub>3</sub>] and α-[Zn<sub>4</sub>O(**L1**<sup>Ac</sup>)<sub>3</sub>], synthesised by the same methods for the hydrolysed MOFs but without the addition of base, absorbed copper(II) ions although these could be readily <sup>70</sup> removed by washing. Similar behaviour was also observed for α-





**Figure 1.** N<sub>2</sub> adsorption isotherms at 77 K for  $[Zn_4O(L1)_3]$  (blue), and  $\alpha$ - $[Zn_4O(L1)_3]$  (red). Filled and open circles represent <sup>75</sup> adsorption and desorption points, respectively.

The copper(II)-metallated forms,  $[Zn_4O(L1)_3]\supset Cu$  and  $\alpha$ -[Zn\_4O(L1)\_3]\supset Cu, were analysed by Energy Dispersive Spectroscopy (EDS). EDS confirmed the loading of Cu in [Zn\_4O(L1)\_3] $\supset$ Cu and  $\alpha$ -[Zn\_4O(L1)\_3] $\supset$ Cu to have Cu:Zn ratios of  $\approx -1:5$  and  $\sim 1:4$  ( $\sim 27\%$  and  $\sim 33\%$  of diol sites), respectively. EDS analysis also revealed that both materials contained no chloride and TGA-FTIR indicated that DMF, potentially within the coordination sphere of the Cu ions, was lost at high temperatures. [Zn\_4O(L1)\_3] $\supset$ Cu and  $\alpha$ -[Zn\_4O(L1)\_3] $\supset$ Cu are still permanently porous with BET surface areas of 1675 and 851 m<sup>2</sup>/g<sup>-1</sup>, respectively (Fig. S13). These reductions in surface area are also consistent with in-channel complexation of the copper species. Further evidence for in-channel copper incorporation was provided by a decrease in the pore size distributions for  $\alpha$ -<sup>90</sup> [Zn\_4O(L1)\_3] $\supset$ Cu compared to  $\alpha$ -[Zn\_4O(L1)\_3].<sup>†</sup>

To further determine diol accessibility, the effect of hydroxyl groups on CO<sub>2</sub> adsorption was determined by collecting CO<sub>2</sub> isotherms at 273 and 298 K on  $\alpha$ -[Zn<sub>4</sub>O(**L1**)<sub>3</sub>]. It is noteworthy that the polar hydroxyl groups significantly increase the enthalpy <sup>95</sup> of adsorption for CO<sub>2</sub> across the entire coverage range with respect to non-functionalised IRMOF-1 (Fig. 2).<sup>13</sup> This dramatic increase demonstrates that the polar hydroxyl groups are accessible to adsorbates and is due to the surface chemistry given the similarity in pore sizes of the respective materials.

A one-pot synthesis of a non-interpenetrated 3D pillared MOF with organic links bearing non-coordinating hydroxyl groups has been previously reported.<sup>14</sup> In that case, the authors suggest that framework interpenetration was suppressed by the steric bulk of the protecting groups. Similar observations on the control of interpenetration in the IRMOF series have been made.<sup>15,16</sup> Herein however we observe that protecting groups of the same size

<sup>2 |</sup> Journal Name, [year], [vol], oo-oo

This journal is © The Royal Society of Chemistry [year]



**Figure 2.** CO<sub>2</sub> enthalpy of adsorption for  $\alpha$ -[Zn<sub>4</sub>O(**L1**)<sub>3</sub>], and IRMOF-1.<sup>13</sup>

controllably yield non-interpenetrated and interpenetrated 5 materials but in different solvents. This led us to propose that the hydrolysis rate in the different solvents had a critical role in control of interpenetration; specifically, reactions in DMF led to faster hydrolysis and an interpenetrated product. Monitoring the rate of hydrolysis of the ester protecting group for framework <sup>10</sup> synthesis reactions using  $H_2L1^{Ac}$  in DMF and DEF revealed this was not the case (Fig. S7). In fact, crystal growth (6-8 hrs) proceeds considerably faster than link deprotection (up to 36 hrs) indicating the links are deprotected within the framework. While Kim and co-workers have demonstrated that MOF topology is 15 sensitive to small changes in the reaction pH,<sup>17</sup> we can rule out this effect for the diol systems as both  $[Zn_4O(L1)_3]$  and  $\alpha$ - $[Zn_4O(L1)_3]$  can be synthesised in the presence of base and acid. Also in contrast to previous work,<sup>2a, 18</sup> the reactions give phase pure products independent of concentration. Thus, these 20 observations, coupled with the fact that H2L1Ac and H2L1<sup>iBu</sup> form both types of frameworks, point to steric effects deriving from

- both the link and the solvent having a role in the control of interpenetration. Recently, solvent-mediated control of interpenetration has been observed for other MOF systems.<sup>19</sup>
- <sup>25</sup> This work describes the controlled 'one-pot' syntheses of MOF materials with two different pore structures bearing accessible alcohol functional groups. Our studies show that suppression of framework interpenetration and control of pore architectures is not only the result of simple steric arguments for
- <sup>30</sup> the ligand but points toward other mechanisms such as solvent 'templating'. These findings elucidate novel methodology for synthesizing alcohol functionalized MOFs with controlled pores sizes whereby high molecular weight solvents may be used to control interpenetration. We are currently exploring masking
- <sup>35</sup> group strategies and solvent combinations to facilitate simultaneous control of pore chemistry and interpenetration in MOFs constructed from longer organic links.

MRH, CJD and CJS gratefully acknowledge the Australian Research Council for funding.

#### 40 Notes and references

<sup>a</sup> School of Chemistry & Physics, The University of Adelaide, Adelaide, Australia. CJD: Phone +61 8 8303 5770. Fax. +61 8 8303 4358. Email: <u>christian.doonan@adelaide.edu.au;</u> CJS: Phone +61 8 8303 7406. Fax. +61 8 8303 4358. Email: <u>christopher.sumby@adelaide.edu.au</u>  <sup>b</sup> CSIRO Materials Science and Engineering, Clayton, VIC 3168, Australia
 † Electronic Supplementary Information (ESI) available: synthesis of

 $H_2$ L1,  $H_2$ L1<sup>Ac</sup>,  $H_2$ L1<sup>Bu</sup>, and  $H_2$ L2; synthetic details and activation conditions for the MOFs; <sup>1</sup>H NMR digestion studies; TGA and EDS data; <sup>50</sup> and crystal data and refinement details for [Zn<sub>4</sub>O(L1)<sub>3</sub>] and  $\alpha$ -[Zn<sub>4</sub>O(L2)<sub>3</sub>]. See DOI: 10.1039/b000000x/.

- S. Kitagawa, R. Kitaura, S-I. Noro, Angew. Chem. Int. Ed., 2004, 43, 2334; G. Ferey, Chem. Soc. Rev., 2008, 37, 191.
- 55 2. (a) M. Eddaoudi, J. Kim, N. L. Rosi, D. T. Vodak, J. Wachter, M. O'Keeffe, O. M. Yaghi, *Science*, 2002, **295**, 469; (b) H. Deng, C. J. Doonan, H. Furukawa, R. B. Ferreira, J. Towne, C. B. Knobler, B. Wang, O. M. Yaghi, *Science*, 2010, **327**, 846.
- K. Sumida, D. L. Rogow, J. A. Mason, T. M. McDonald, E. D.
  Bloch, Z. R. Herm, T.-H. Bae, J. R. Long, *Chem. Rev.*, 2012, 112, 724; J.-R. Li, J. Sculley, H.-C. Zhou, *Chem. Rev.*, 2012, 112, 869.
- A. Corma, H. Garcia, F. X. Llabres, I. Xamena, Chem. Rev., 2010, 110, 4607; L. Ma, C. Abney, W. Lin, Chem. Soc. Rev., 2009, 38, 1248; A. U. Czaja, N. Trukhan, U. Müller, Chem. Soc. Rev., 2009, 38, 1284.
- 5. O. M. Yaghi, Nature Materials, 2007, 6, 92.; S. R. Batten, R. Robson, Angew. Chem. Int. Ed., 1998, 37, 1460.
- J. S. Seo, D. Whang, H. Lee, S. I. Jun, J. Oh, Y. J. Jeon, K. Kim, Nature, 2000, 404, 982; C.-D. Wu, A. Hu, L. Zhang, W. Lin, J. Am.
- Chem. Soc., 2005, 127, 8940; B. Chen, L. Wang, Y. Xiao, F. R. Fronczek, M. Xue, Y. Cui, G. Qian, Angew. Chem. Int. Ed., 2009, 48, 500; X.-P. Zhou, Z. Xu, M. Zeller, A. D. Hunter, Chem. Commun., 2009, 5439; E. D. Bloch, D. Britt, C. Lee, C. J. Doonan, F. J. Uribe-Romo, H. Furukawa, J. R. Long, O. M. Yaghi, J. Am. Chem. Soc., 2010, 132, 14382.
- K. L. Mulfort, O. K. Farha, C. L. Stern, A. A. Sarjent, J. T. Hupp, J. Am. Chem. Soc., 2009, 131, 3866; T. Devic, P. Horcajada, C. Serre, F. Salles, G. Maurin, B. Moulin, D. Heurtaux, G. Clet, A. Vimont, J-M, Greneche, B. Le Ouay, F. Moreau, E. Magnier, Y. Filinchuk, J.
- Marrot, J-C, Lavalley, M. Daturi, G. Ferey, J. Am. Chem. Soc., 2010, 132, 1127; K. S. Jeong, Y. B. Go, S. M. Shin, S. J. Lee, J. Kim, O. M. Yaghi, N. Jeong, Chem. Sci., 2011, 2, 877.
- Z. Wang, S. M. Cohen, *Chem. Soc. Rev.*, 2009, **38**, 1315; S. M. Cohen, *Chem. Rev.*, 2012, **112**, 970.
- 85 9. M. J. Ingleson, J. P. Barrio, J. B. Guilbaud, Y. Z. Khimyak, M. J. Rosseinsky, *Chem. Commun.*, 2008, 23, 2680.
  - S. R. Caskey, A. G. Wong-Foy, A. J. Matzger, J. Am. Chem. Soc., 2008, 130, 10870; N. L. Rosi, J. Kim, M. Eddaoudi, B. L. Chen, M. O'Keeffe, O. M. Yaghi, J. Am. Chem. Soc., 2005, 127, 1504.
- 90 11. K. S. Walton, R. Q. Snurr, J. Am. Chem. Soc., 2007, 129, 8552.
- C. K. Brozek, M. Dincă, *Chem. Sci.*, 2012, **3**, 2110; X. Song, T. K. Kim, H. Kim, D. Kim, S. Jeong, H. R. Moon, M. S. Lah *Chem. Mater.* 2012, 10.1021/cm301605w.
  L. S. Chei, W. L. Sei, J. Kim, W. S. Libar, Kim, K. Kim,
- J.-S. Choi, W.-J. Son, J. Kim, W.-S. Ahn, *Micropor. Mesopor.* Mater. 2008, 116, 72.
- 14. T. Yamada, H. Kitagawa , J. Am. Chem. Soc., 2009, 131, 6312.
- J. M. Roberts, O. K. Farha, A. A. Sarjeant, J. T. Hupp, K. A. Scheidt, *Cryst. Growth Des.*, 2011, **11**, 4747.
- R. K. Deshpande, J. L. Minnaar, S. G. Telfer, *Angew. Chem., Int. Ed.*, 2010, **49**, 4598; R. K. Deshpande, G. I. N. Waterhouse, G. B. Jameson, S. G. Telfer, *Chem. Commun.*, 2012, **48**, 1574; A. S. Gupta, R. K. Deshpande, L. Liu, G. I. N. Waterhouse, S. G. Telfer, *CrystEngComm*, 2012, 10.1039/c2ce25854d.
- 17. H. Kim, S. Das, M. G. Kim, D. N. Dybtsev, Y. Kim, K. Kim, *Inorg. Chem.*, 2011, **50**, 3691.
  - J. Zhang, L. Wojtas, R. W. Larsen, M. Eddaoudi, M. J. Zaworotko, J. Am. Chem. Soc., 2009, 131, 17040.
  - M. Guo, Z.-M. Sun, J. Mater. Chem., 2012, 22, 15939; J. Duan, J. Bai, B. Zheng, Y. Li, W. Ren, Chem. Commun., 2011, 47, 2556; L. Ma, W. Lin, J. Am. Chem. Soc., 2008, 130, 13834; J. M. Falkowski,
- Ma, W. Lin, J. Am. Chem. Soc., 2008, 130, 13834; J. M. Falkowski,
  C. Wang, S. Liu, W. Lin, Angew. Chem. Int. Ed., 2011, 50, 8674.

This journal is © The Royal Society of Chemistry [year]

**Chemical Communications Accepted Manuscript** 



164x65mm (300 x 300 DPI)

Downloaded by Indiana University - Purdue University at Indianapolis on 02 September 2012

Published on 31 August 2012 on http://pubs.rsc.org | doi:10.1039/C2CC35565E

View Online

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxx

### ARTICLE TYPE

# **Control of Framework Interpenetration for** *in situ* **Modified Hydroxyl Functionalised IRMOFs**

Damien Rankine,<sup>a</sup> Antonio Avellaneda,<sup>a</sup> Matthew R. Hill,<sup>b</sup> Christian J. Doonan<sup>\*,a</sup> and Christopher J. Sumby<sup>\*,a</sup>

s Received (in XXX, XXX) Xth XXXXXXX 20XX, Accepted Xth XXXXXXXX 20XX DOI: 10.1039/b000000x

By intimate control of reaction conditions, phase-pure crystalline porous metal-organic framework materials  $[Zn_4O(L)_3]$  with interpenetrated and non-interpenetrated <sup>10</sup> structures can be synthesised. Under certain conditions, these reactions occur with concomitant deprotection of masked alcohols located on the organic links which yield accessible 'metal-binding' functional groups within the frameworks.

Metal-organic frameworks (MOFs) are constructed by a modular <sup>15</sup> synthetic approach whereby organic links and metal clusters are assembled into porous extended networks via 'one-pot' reactions.<sup>1</sup> This has led to the development of design principles that yield precise control of pore dimensions and functionality by utilizing links of identical connectivity but different lengths or <sup>20</sup> non-structural functional groups.<sup>2</sup> Due to their high surface areas, tuneable structure metrics and chemically mutable organic building blocks, MOFs have been identified as materials with great potential for gas separations<sup>3</sup> and size-selective heterogeneous catalysis.<sup>4</sup> To fully realise their catalytic potential <sup>25</sup> MOFs with pores sufficiently large enough to simultaneously allow anchoring of catalytic moieties and diffusion of chemical reactants into the framework is requisite. Furthermore, given that the majority of the metal clusters that comprise the 'joints' of

MOF structures are catalytically benign, reliable methods for

<sup>30</sup> anchoring catalytic moieties to the framework need to be established. Two major challenges arise; 1) Increasing the pores sizes of topologically identical MOFs commonly affords interpenetration<sup>5</sup> and, 2) utilizing organic links which bear metalcoordinating groups can lead to unwanted side reactions or hinder <sup>35</sup> the formation of the desired networks. Thus, frameworks directly synthesized with free metal-coordinating groups are rare.<sup>6-8</sup>

Recently, post-synthetic modification (PSM) has been developed as a strategy to overcome these challenges and yield open framework materials imbued with novel functionality.8 A 40 potential drawback of the PSM method is that performing multiple reactions on the MOF crystals can lead to structural decomposition and/or diminished surface area.9 Thus, to ensure the MOFs retain optimal porosity and crystallinity it is preferable that the most efficient synthetic procedure is employed. Here we 45 report the controlled one-pot synthesis and in situ ester hydrolysis of non-interpenetrated and interpenetrated MOFs, [Zn<sub>4</sub>O(L1)<sub>3</sub>] and  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>], comprised of biphenyl-2,2'-diol links (L1) (Scheme 1(a)). Notably, both materials can be synthesized in a single-step procedure. It is also noteworthy that the metal co-50 ordinating groups are freely accessible in both forms which we demonstrate by the complexation of copper ions and enhanced enthalpy of adsorption for  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] over IRMOF-1.





 $[Zn_4O(L1)_3]$  was synthesized by dissolving 30 mg of H<sub>2</sub>L1<sup>Ac</sup> and 85 mg of  $Zn(NO_3)_2$ ·6H<sub>2</sub>O (4 eq) in N,N'-diethylformamide (DEF) (4.5 mL) in a tightly-capped 20 mL glass vial.<sup>†</sup> An aliquot of 2.5 M aqueous NaOH solution (30 µL) was then added and the 5 solution heated at 90°C for 20 mins. The solution was then transferred to a new 20 mL vial and heated at 100°C for 36 hours yielding transparent pale yellow, cubic crystals of [Zn<sub>4</sub>O(L1)<sub>3</sub>] with an empirical formula of (C<sub>42</sub>H<sub>24</sub>O<sub>19</sub>Zn<sub>4</sub>). Other more bulky ester protected links (H2L1<sup>iBu</sup>) also generated the same non-<sup>10</sup> interpenetrated material. The structure of  $[Zn_4O(L1)_3]$  was determined by single crystal X-ray diffraction. As anticipated, the framework of  $[Zn_4O(L1)_3]$  is of cubic topology with  $Zn_4O$ clusters positioned at each of the vertices and biphenyl moieties forming the organic backbone (Scheme 1). The formation of a 15 non-interpenetrated 3-D network is noteworthy given the size of the pore channels (15.4 Å), and the lack of significant steric congestion within the pores arising from the linker.

To ensure that the single crystal structure was representative of the bulk material, samples of  $[Zn_4O(L1)_3]$  were examined by 20 powder X-ray diffraction (PXRD, Fig. S3).<sup>†</sup> The resultant peak patterns were consistent with that expected for a noninterpenetrated framework. A further noteworthy feature of  $[Zn_4O(L1)_3]$  is that the acetyl protecting groups are hydrolysed during the one-pot synthesis to afford pores decorated with 25 accessible hydroxyl functional groups. <sup>1</sup>H NMR spectra of digested [Zn<sub>4</sub>O(L1)<sub>3</sub>] reveals all links have been fully deprotected during the course of the reaction. Examples of permanently porous MOFs synthesized from alcohol functionalized links are uncommon,<sup>7, 8</sup> as the free oxygen atoms can participate in metal <sup>30</sup> coordination.<sup>10</sup> For example, we could not form a characterisable MOF from only deprotected ligand (H<sub>2</sub>L1) and Zn(NO<sub>3</sub>)<sub>2</sub>·6H<sub>2</sub>O, although MOFs with different topologies could be formed with other metals or by incorporating other links. The choice of reaction conditions is also critically important to the nature of the 35 product. Using an analogous procedure, but with DMF as the solvent, we obtained phase-pure interpenetrated  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] from both H<sub>2</sub>L1<sup>Ac</sup> and more sterically-demanding H<sub>2</sub>L1<sup>iBu</sup>. Unit cell determinations for  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] indicated that in this case the framework is two-fold interpenetrated. In addition, the PXRD 40 pattern obtained from bulk samples of  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] closely matched that of the calculated peak positions and intensities for a lower-symmetry two-fold interpenetrated framework.

To determine the permanent porosity of  $[Zn_4O(L1)_3]$  and  $\alpha$ -[Zn\_4O(L1)\_3] 77 K N<sub>2</sub> isotherms were carried out on the respective <sup>45</sup> evacuated frameworks (Fig. 1). Based on their isotherms, the BET surface areas of each material were calculated to be 2631 and 1790 m<sup>2</sup>/g<sup>-1</sup> for [Zn<sub>4</sub>O(L1)<sub>3</sub>] and  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>], respectively. The isotherm of  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] is best described as Type I, which is indicative of microporosity. A step in the <sup>50</sup> isotherm of [Zn<sub>4</sub>O(L1)<sub>3</sub>] is observed in the low pressure region between P/P<sub>0</sub> of 0.020 and 0.045 and can be attributed to the larger pore volume expected for the non-interpenetrated framework (Scheme 1(b) and (c)).<sup>11</sup> Notably, the synthetic procedure and activation conditions utilized in the present work <sup>55</sup> yielded a surface area for [Zn<sub>4</sub>O(L1)<sub>3</sub>] that is the highest reported for a material based on an IRMOF-9 framework.

Thermogravimmetric analyses indicate  $[Zn_4O(L1)_3]$  and  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] are thermally stable to 600 and 720 K respectively.<sup>†</sup> To demonstrate accessibility of the diol chelating sites, <sup>60</sup> [Zn<sub>4</sub>O(L1)<sub>3</sub>] and  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>] were treated with 0.05 M solutions of CuCl<sub>2</sub>·2H<sub>2</sub>O (Scheme 1(d)). Within minutes, crystalline samples of both materials took on a green colour associated with complexation of copper ions by the links. The rate of complexation is consistent with binding to the free diol <sup>65</sup> links rather than incorporation into the metal-oxide nodes of the framework.<sup>12</sup> This colour was retained upon washing. Ester protected [Zn<sub>4</sub>O(L1<sup>Ac</sup>)<sub>3</sub>] and  $\alpha$ -[Zn<sub>4</sub>O(L1<sup>Ac</sup>)<sub>3</sub>], synthesised by the same methods for the hydrolysed MOFs but without the addition of base, absorbed copper(II) ions although these could be readily <sup>70</sup> removed by washing. Similar behaviour was also observed for  $\alpha$ -[Zn<sub>4</sub>O(L2)<sub>3</sub>] containing methoxy groups on the links (H<sub>2</sub>L2).



**Figure 1.** N<sub>2</sub> adsorption isotherms at 77 K for  $[Zn_4O(L1)_3]$  (blue), and  $\alpha$ - $[Zn_4O(L1)_3]$  (red). Filled and open circles represent <sup>75</sup> adsorption and desorption points, respectively.

The copper(II)-metallated forms,  $[Zn_4O(L1)_3] \supset Cu$  and  $\alpha$ -[Zn\_4O(L1)\_3] \supset Cu, were analysed by Energy Dispersive Spectroscopy (EDS). EDS confirmed the loading of Cu in [Zn\_4O(L1)\_3] \supset Cu and  $\alpha$ -[Zn\_4O(L1)\_3]  $\supset$ Cu to have Cu:Zn ratios of  $\approx \sim 1:5$  and  $\sim 1:4$  ( $\sim 27\%$  and  $\sim 33\%$  of diol sites), respectively. EDS analysis also revealed that both materials contained no chloride and TGA-FTIR indicated that DMF, potentially within the coordination sphere of the Cu ions, was lost at high temperatures. [Zn\_4O(L1)\_3]  $\supset$ Cu and  $\alpha$ -[Zn\_4O(L1)\_3]  $\supset$ Cu are still permanently porous with BET surface areas of 1675 and 851 m<sup>2</sup>/g<sup>-1</sup>, respectively (Fig. S13). These reductions in surface area are also consistent with in-channel complexation of the copper species. Further evidence for in-channel copper incorporation was provided by a decrease in the pore size distributions for  $\alpha$ - $[Zn_4O(L1)_3] \supset$ Cu compared to  $\alpha$ -[Zn\_4O(L1)\_3].<sup>†</sup>

To further determine diol accessibility, the effect of hydroxyl groups on CO<sub>2</sub> adsorption was determined by collecting CO<sub>2</sub> isotherms at 273 and 298 K on  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>]. It is noteworthy that the polar hydroxyl groups significantly increase the enthalpy <sup>95</sup> of adsorption for CO<sub>2</sub> across the entire coverage range with respect to non-functionalised IRMOF-1 (Fig. 2).<sup>13</sup> This dramatic increase demonstrates that the polar hydroxyl groups are accessible to adsorbates and is due to the surface chemistry given the similarity in pore sizes of the respective materials.

<sup>100</sup> A one-pot synthesis of a non-interpenetrated 3D pillared MOF with organic links bearing non-coordinating hydroxyl groups has been previously reported.<sup>14</sup> In that case, the authors suggest that framework interpenetration was suppressed by the steric bulk of the protecting groups. Similar observations on the control of <sup>105</sup> interpenetration in the IRMOF series have been made.<sup>15,16</sup> Herein however we observe that protecting groups of the same size



Downloaded by Indiana University - Purdue University at Indianapolis on 02 September 2012

Published on 31 August 2012 on http://pubs.rsc.org | doi:10.1039/C2CC35565E



Figure 2. CO<sub>2</sub> enthalpy of adsorption for  $\alpha$ -[Zn<sub>4</sub>O(L1)<sub>3</sub>], and IRMOF-1.<sup>13</sup>

controllably yield non-interpenetrated and interpenetrated 5 materials but in different solvents. This led us to propose that the hydrolysis rate in the different solvents had a critical role in control of interpenetration; specifically, reactions in DMF led to faster hydrolysis and an interpenetrated product. Monitoring the rate of hydrolysis of the ester protecting group for framework <sup>10</sup> synthesis reactions using  $H_2L1^{Ac}$  in DMF and DEF revealed this was not the case (Fig. S7). In fact, crystal growth (6-8 hrs) proceeds considerably faster than link deprotection (up to 36 hrs) indicating the links are deprotected within the framework. While Kim and co-workers have demonstrated that MOF topology is 15 sensitive to small changes in the reaction pH,<sup>17</sup> we can rule out this effect for the diol systems as both  $[Zn_4O(L1)_3]$  and  $\alpha$ - $[Zn_4O(L1)_3]$  can be synthesised in the presence of base and acid. Also in contrast to previous work,<sup>2a, 18</sup> the reactions give phase pure products independent of concentration. Thus, these 20 observations, coupled with the fact that H<sub>2</sub>L1<sup>Ac</sup> and H<sub>2</sub>L1<sup>iBu</sup> form

both types of frameworks, point to steric effects deriving from both the link and the solvent having a role in the control of interpenetration. Recently, solvent-mediated control of interpenetration has been observed for other MOF systems.<sup>19</sup>

- This work describes the controlled 'one-pot' syntheses of MOF materials with two different pore structures bearing accessible alcohol functional groups. Our studies show that suppression of framework interpenetration and control of pore architectures is not only the result of simple steric arguments for
- <sup>30</sup> the ligand but points toward other mechanisms such as solvent 'templating'. These findings elucidate novel methodology for synthesizing alcohol functionalized MOFs with controlled pores sizes whereby high molecular weight solvents may be used to control interpenetration. We are currently exploring masking
- <sup>35</sup> group strategies and solvent combinations to facilitate simultaneous control of pore chemistry and interpenetration in MOFs constructed from longer organic links.

MRH, CJD and CJS gratefully acknowledge the Australian Research Council for funding.

#### 40 Notes and references

<sup>a</sup> School of Chemistry & Physics, The University of Adelaide, Adelaide, Australia. CJD: Phone +61 8 8303 5770. Fax. +61 8 8303 4358. Email: <u>christian.doonan@adelaide.edu.au;</u> CJS: Phone +61 8 8303 7406. Fax. +61 8 8303 4358. Email: <u>christopher.sumby@adelaide.edu.au</u> 45 <sup>b</sup> CSIRO Materials Science and Engineering, Clayton, VIC 3168, Australia

\*This article is part of the ChemComm 'Metal-organic frameworks' web themed issue.

 $\dagger$  Electronic Supplementary Information (ESI) available: synthesis of 50 H<sub>2</sub>L1, H<sub>2</sub>L1<sup>Ac</sup>, H<sub>2</sub>L1<sup>Bu</sup>, and H<sub>2</sub>L2; synthetic details and activation

- conditions for the MOFs; <sup>1</sup>H NMR digestion studies; TGA and EDS data; and crystal data and refinement details for  $[Zn_4O(L1)_3]$  and  $\alpha$ - $[Zn_4O(L2)_3]$ . See DOI: 10.1039/b000000x/.
- S. Kitagawa, R. Kitaura, S-I. Noro, Angew. Chem. Int. Ed., 2004, 43, 2334; G. Ferey, Chem. Soc. Rev., 2008, 37, 191.
- (a) M. Eddaoudi, J. Kim, N. L. Rosi, D. T. Vodak, J. Wachter, M. O'Keeffe, O. M. Yaghi, *Science*, 2002, 295, 469; (b) H. Deng, C. J. Doonan, H. Furukawa, R. B. Ferreira, J. Towne, C. B. Knobler, B. Wang, O. M. Yaghi, *Science*, 2010, 327, 846.
- K. Sumida, D. L. Rogow, J. A. Mason, T. M. McDonald, E. D. Bloch, Z. R. Herm, T.-H. Bae, J. R. Long, *Chem. Rev.*, 2012, **112**, 724; J.-R. Li, J. Sculley, H.-C. Zhou, *Chem. Rev.*, 2012, **112**, 869.
- A. Corma, H. Garcia, F. X. Llabres, I. Xamena, *Chem. Rev.*, 2010,
  110, 4607; L. Ma, C. Abney, W. Lin, *Chem. Soc. Rev.*, 2009, 38, 1248; A. U. Czaja, N. Trukhan, U. Müller, *Chem. Soc. Rev.*, 2009, 38, 1284.
- 5. O. M. Yaghi, Nature Materials, 2007, 6, 92.; S. R. Batten, R. Robson, Angew. Chem. Int. Ed., 1998, 37, 1460.
- <sup>70</sup> 6. J. S. Seo, D. Whang, H. Lee, S. I. Jun, J. Oh, Y. J. Jeon, K. Kim, *Nature*, 2000, **404**, 982; C.-D. Wu, A. Hu, L. Zhang, W. Lin, *J. Am. Chem. Soc.*, 2005, **127**, 8940; B. Chen, L. Wang, Y. Xiao, F. R. Fronczek, M. Xue, Y. Cui, G. Qian, *Angew. Chem. Int. Ed.*, 2009, **48**, 500; X.-P. Zhou, Z. Xu, M. Zeller, A. D. Hunter, *Chem. Commun.*,
- <sup>75</sup> 2009, 5439; E. D. Bloch, D. Britt, C. Lee, C. J. Doonan, F. J. Uribe-Romo, H. Furukawa, J. R. Long, O. M. Yaghi, *J. Am. Chem. Soc.*, 2010, **132**, 14382.
- K. L. Mulfort, O. K. Farha, C. L. Stern, A. A. Sarjent, J. T. Hupp, J. Am. Chem. Soc., 2009, 131, 3866; T. Devic, P. Horcajada, C. Serre,
- F. Salles, G. Maurin, B. Moulin, D. Heurtaux, G. Clet, A. Vimont, J-M, Greneche, B. Le Ouay, F. Moreau, E. Magnier, Y. Filinchuk, J. Marrot, J-C, Lavalley, M. Daturi, G. Ferey, *J. Am. Chem. Soc.*, 2010, 132, 1127; K. S. Jeong, Y. B. Go, S. M. Shin, S. J. Lee, J. Kim, O. M. Yaghi, N. Jeong, *Chem. Sci.*, 2011, 2, 877.
- 85 8. Z. Wang, S. M. Cohen, *Chem. Soc. Rev.*, 2009, **38**, 1315; S. M. Cohen, *Chem. Rev.*, 2012, **112**, 970.
- M. J. Ingleson, J. P. Barrio, J. B. Guilbaud, Y. Z. Khimyak, M. J. Rosseinsky, *Chem. Commun.*, 2008, 23, 2680.
- S. R. Caskey, A. G. Wong-Foy, A. J. Matzger, J. Am. Chem. Soc.,
  2008, 130, 10870; N. L. Rosi, J. Kim, M. Eddaoudi, B. L. Chen, M. O'Keeffe, O. M. Yaghi, J. Am. Chem. Soc., 2005, 127, 1504.
- 11. K. S. Walton, R. Q. Snurr, J. Am. Chem. Soc., 2007, 129, 8552.
- C. K. Brozek, M. Dincă, *Chem. Sci.*, 2012, **3**, 2110; X. Song, T. K. Kim, H. Kim, D. Kim, S. Jeong, H. R. Moon, M. S. Lah *Chem. Mater.* 2012, 10.1021/cm301605w.
- J.-S. Choi, W.-J. Son, J. Kim, W.-S. Ahn, *Micropor. Mesopor.* Mater. 2008, 116, 72.
- 14. T. Yamada, H. Kitagawa , J. Am. Chem. Soc., 2009, 131, 6312.
- J. M. Roberts, O. K. Farha, A. A. Sarjeant, J. T. Hupp, K. A. Scheidt, *Cryst. Growth Des.*, 2011, **11**, 4747.
- R. K. Deshpande, J. L. Minnaar, S. G. Telfer, *Angew. Chem., Int. Ed.*, 2010, **49**, 4598; R. K. Deshpande, G. I. N. Waterhouse, G. B. Jameson, S. G. Telfer, *Chem. Commun.*, 2012, **48**, 1574; A. S. Gupta, R. K. Deshpande, L. Liu, G. I. N. Waterhouse, S. G. Telfer, *CrystEngComm*, 2012, 10.1039/c2ce25854d.
  - H. Kim, S. Das, M. G. Kim, D. N. Dybtsev, Y. Kim, K. Kim, *Inorg. Chem.*, 2011, **50**, 3691.
  - J. Zhang, L. Wojtas, R. W. Larsen, M. Eddaoudi, M. J. Zaworotko, J. Am. Chem. Soc., 2009, 131, 17040.
- M. Guo, Z.-M. Sun, J. Mater. Chem., 2012, 22, 15939; J. Duan, J. Bai, B. Zheng, Y. Li, W. Ren, Chem. Commun., 2011, 47, 2556; L. Ma, W. Lin, J. Am. Chem. Soc., 2008, 130, 13834; J. M. Falkowski, C. Wang, S. Liu, W. Lin, Angew. Chem. Int. Ed., 2011, 50, 8674.