Catalytic reaction of methane with CBrF₃

Kai Li,^a Eric Kennedy,^{*a} Bogdan Dlugogorski^a and Russell Howe^b

^a Department of Chemical Engineering, University of Newcastle, Callaghan, NSW 2308, Australia.
 E-mail: cgek@cc.newcastle.edu.au ^b School of Chemistry, University of New South Wales, Sydney, NSW 2052, Australia

Received (in Cambridge, UK) 4th February 1999, Accepted 10th March 1999

The catalytic reaction of CH_4 with $CBrF_3$ over Co, Cu and Mn ZSM-5 zeolites is described; major products (at low temperatures) are those expected for simple hydrodebromination: CH_3Br and CHF_3 .

The hydrodehalogenation reaction of chlorofluorocarbons (CFCs) and bromofluorocarbons or bromochlorofluorocarbons (halons) are potentially important reactions for both disposal of ozone depleting chemicals and production of hydrofluorocarbon replacements. Previous work in this area has focussed on reactions of CFCs with hydrogen over supported palladium catalysts.^{1–12} Little attention has been paid to the corresponding hydrodebromination of halons. Here we describe for the first time the catalytic reaction of halon 1301 (CBrF₃) with methane over transition metal exchanged ZSM-5 zeolites. This novel catalytic reaction offers potential new routes to hydrofluorocarbons using methane as the hydrogen source.

Cobalt, copper and manganese exchanged ZSM-5 zeolites were prepared from a commercial ZSM-5 (PQ, Si/Al = 25), and charged into an alumina plug flow microreactor. Reactant gas stream (CH₄–CBrF₃–N₂ = 1:1:10) was flowed over the catalyst at a GHSV of 3500 h^{-1} , and products were analyzed by on-line gas chromatography after passing through a caustic scrubber.

Fig. 1 shows typical CBrF₃ conversions versus time on stream over four different zeolite catalysts at 873 K. Also shown is the corresponding conversion in the homogeneous reaction, as reported elsewhere.13 The gas phase reaction between CH₄ and CBrF₃ begins at ca. 800 K, and increases dramatically above 900 K. A striking feature of the reaction in the presence of zeolite catalysts is the initial high conversion of CBrF3 which then falls to a steady state value. Our preliminary investigations of this breakthrough period suggest reaction of CBrF3 with the zeolite which generates the active phase for the hydrodehalogenation reaction. ²⁷Al MAS NMR measurements show that framework tetrahedral aluminium in the zeolite is completely transformed into an as yet unidentified form, although XRD analysis shows no change in the zeolite structure. In the case of HZSM-5, the steady state conversion approaches that found in the absence of catalyst. For the transition metal



Fig. 1 Conversion of CBrF₃ versus time on stream at 873 K over various catalysts.



Fig. 2 Steady state conversion of $CBrF_3$ and CH_4 versus temperature over MnZSM-5.

exchanged zeolites, however, there is a very evident influence of catalyst on the steady state conversion. It is important to note that zeolite crystallinity is fully retained during this reaction, even after 36 h on stream.

Fig. 2 plots the steady state $CBrF_3$ and CH_4 conversions *versus* reaction temperature over MnZSM-5; similar profiles were measured for the other transition metal zeolites. The $CBrF_3$ conversion exceeds that of CH_4 at all temperatures, suggesting that the reaction pathway is more complex than that predicted for the simple 1:1 stoichiometry of reaction (1):

$$CBrF_3 + CH_4 \rightarrow CH_3Br + CHF_3 \tag{1}$$

In separate experiments, we have noted that CBrF₃ undergoes pyrolysis reactions over the same catalysts, producing C_2F_6 and Br₂,¹⁴ and C_2F_6 was detected as a minor product also in the reactions with methane. The major reaction products detected in the reactions with methane at lower temperatures are those expected from reaction (1), as illustrated in Fig. 3. Above 873 K, however, the yield of CH₃Br declines, and other reaction products appear, (notably hydrocarbons C_2H_4 and C_2H_2), due to further reaction of CH₃Br. Other products identified include $C_2H_2F_2$, C_2H_3Br , CH₂BrF, and trace (less than 5 ppm) quantities of $C_2HBr_2F_3$, CH₂Br₂, C_2F_6 , $C_2H_3F_3$, C_6H_5Br and H₂. Mass balances for all reactions were generally better than ±



Fig. 3 Steady state conversion of $CBrF_3$ to major products CHF_3 and CH_3Br versus temperature over MnZSM-5.

3% and usually \pm 1%, and suggest any as-yet unidentified species represent only a small fraction of reaction products.

The reaction mechanisms involved in this intriguing chemistry are not yet clear. The high initial conversions of CBrF₃, and the results of preliminary characterization experiments on catalysts exposed to CBrF₃ plus CH₄ or CBrF₃ alone for short periods¹⁴ suggest that initial reaction of CBrF₃ with fresh catalysts generates the catalytically active species. The high reaction selectivity (at low temperatures) may result from the selective cleavage of C–Br bonds in preference to C–F bonds in CBrF₃, and reflects the lower relative strength of the C–Br bond (295 kJ mol⁻¹)¹⁵ compared with C–F bonds (*ca.* 460 kJ mol⁻¹, estimated from analogous F–CF₂Cl bond strength) in CF₃Br. Low temperature cleavage of C–Br would occur before evidence of C–F bond cleavage, leaving the CF₃ moiety intact.

Further work is needed to optimize catalysts, identify active sites and determine reaction pathways. At present we are also investigating the reactions of CFCs and other halocarbons with methane. The results presented here offer a new route for methane utilization in the disposal and upgrading of ozone depleting materials.

This work has been supported by the Australian Research Council.

Notes and references

1 C. Gervasutti, L. Marangoni and W. Marra, J. Fluorine Chem., 1981/82, 19, 1.

- 2 B. Coq, J.-M. Cognion, F. Figuras and D. Tournigant, J. Catal., 1993, 141, 21.
- 3 B. Coq, F. Figuras, S. Hub and D. Tournigant, J. Phys. Chem. 1995, 99, 11 159.
- 4 A. Wiersma, E. J. A. X. van de Sandt, M. Makkee, C. P. Luteijn, H. van Bekkum and J. A. Moulijn, *Catal. Today*, 1996, **27**, 257.
- 5 E. J. A. X. van de Sandt, A. Wiersma, M. Makkee, H. van Bekkum and J. A. Moulijn, *Catal. Today*, 1997, **35**, 163.
- 6 E. J. A. X. van de Sandt, A. Wiersma, M. Makkee, H. van Bekkum and J. A. Moulijn, Appl. Catal. A, 1997, **155**, 59.
- 7 Z. Karpinski, K. Early and J. L. d'Itri, J. Catal., 1996, 164, 378.
- 8 W. Juszczyk, A. Malinowski and Z. Karpinski, Appl. Catal. A, 1998,
- 166, 311.
 9 B. Coq, S. Hub, F. Figuras and D. Tournigant, *Appl. Catal. A*, 1993, 101, 41.
- 10 R. Onishi, I. Suzuki and M. Ichikawa, Chem. Lett., 1991, 841.
- 11 R. Onishi, W. L. Wang and M. Ichikawa, Appl. Catal. A, 1994, 113, 29.
- 12 A. Malinowski, W. Juszczyk, M. Bonarowska, J. Pielaszek and Z. Karpinski, J. Catal., 1998, 177, 153.
- 13 K. Li, E. Kennedy, B. Dlugogorski and B. Moghtaderi, Proceedings of 25th Australian and New Zealand Chemical Engineering Conference, CHEMECA 97, Rotorua, New Zealand, 1997, p. SF4a.
- 14 K. Li, F. Oghanna, E. M. Kennedy, B. Z. Dlugogorski, A. Fazeli, S. Thomson and R. F. Howe, to be published.
- 15 Handbook of Chemistry and Physics, ed. R. C. Weast and M. J. Astle, CRC Press, Boca Raton, FL, 63rd edn., 1982, F-199, Table 3.

Communication 9/00972H