Selective Coupling of Methanol and 2-Methylpropan-1-ol to give 1-Methoxy-2methylpropane (Methyl Isobutyl Ether)

John Nunan, Kamil Klier,* and Richard G. Herman

Seeley G. Mudd Building 6, Department of Chemistry, Lehigh University, Bethlehem, PA 18015, U.S.A.

The superacid Nafion-H resin selectively catalyses the coupling of the two alcohols methanol and 2-methylpropan-1-ol to give methyl isobutyl ether.

The selective synthesis of ethers in the C_5 to C_6 range, *viz.* methyl t-butyl ether (MTBE) and methyl t-pentyl ether (MTPE), where methanol is combined with the corresponding C_4 or C_5 tertiary alkene, has received much attention in recent years¹⁻⁵ owing to the use of these ethers as effective anti-knock replacements for lead in gasoline. We now report on the synthesis of an ether related to MTBE, *i.e.* methyl isobutyl ether (MIBE), which was found to be selectively formed through the direct coupling of methanol and 2-methylpropan-1-ol (BuⁱOH) over the Nafion-H resin catalyst [reaction (1)].

$$\begin{array}{c} \text{MeOH} + \text{Me}_2\text{CHCH}_2\text{OH} \rightarrow \text{MeOCH}_2\text{CHMe}_2 + \text{H}_2\text{O} \\ \text{BuiOH} & \text{MIBE} \end{array}$$
(1)

The catalyst used was a perfluorinated sulphonic acid resin having high thermal stability and acid strength in the superacid range. Nafion-H has been used by Olah and co-workers in extensive studies of alkylation reactions^{6–8} and alcohol dehydration to form alkenes and ethers^{6,9} in which carbenium ions were considered to be important intermediates. The coupling of MeOH and BuⁱOH to MIBE using either resins or other heterogeneous catalysts has not been reported. The absence of MTBE as a product in the present work (g.c.-mass spectrometry) suggests a mechanism not involving carbenium ions but rather the intermediacy of oxonium ions or sulphonic esters.

The reaction of MeOH with BuⁱOH was carried out in a stainless steel flow reactor under $101.3-7.6 \times 10^3$ kPa (1 atm = 101.325 kPa) total pressure, with nitrogen as a carrier

gas; the reactor and mode of product analysis have been described.^{10,11} Preliminary studies showed that maximum selectivity for MIBE was achieved using a mole ratio of MeOH to BuⁱOH of 2:1 and results using this molar ratio are presented here. Other products included water, Me₂O, butenes, and to a lesser extent, octenes and Buⁱ₂O. We used both the regular gel form of the the resin (Nafion-H) and a porous form (Nafion-H Micro-Saddles). Both forms possessed an ion-exchange capacity of 0.9 mequiv./g and were in the fully acid form.

Figure 1 shows the effect of alcohol partial pressure $(P_{alc.})$ on the reaction rate, together with data for MeOH and BuiOH alone over the Nafion-H for comparison. Methanol gave only Me₂O and water, but MeOH-BuiOH and BuiOH produced both ethers and alkenes. For both methanol and the alcohol mixture, the rate increased rapidly with pressure to $P_{\rm alc.} = 86.2$ kPa, but most dramatically for the alcohol mixture, whereas BuiOH showed a distinctly inverse dependence on alcohol partial pressure. Figure 2 shows the product composition as a function of alcohol pressure for the BuiOH-MeOH mixture, and indicates that the rapid rise of rate with increasing pressure observed in Figure 1 is due almost solely to a rapid and selective increase in the rate of MIBE formation as a function of alcohol partial pressure. Further, if the etherforming reaction were to proceed with equal reactivity for BuiOH and MeOH statistically, a product ratio of MIBE: $Me_2O: Bu_2O of 4:4:1$ would be expected from the MeOH: BuiOH ratio of 2: 1 employed. Remarkably however, the MIBE: Me₂O: Buⁱ₂O product ratio was 19:9:1 at pressures > 150 kPa, significantly in favour of the mixed ether,

677





Figure 1. Effect of alcohol partial pressure $(P_{alc.})$ on the steady state reaction rates. Total pressure, 1.344×10^3 kPa; feed rate of N₂ + alcohol, 250 mol (kg cat.)⁻¹ h⁻¹; catalyst (Nafion-H) wt., 2.0 g. \bullet , MeOH; \blacksquare , MeOH–BuⁱOH (2:1); \blacktriangle , BuⁱOH.

Figure 2. Effect of alcohol mixture (MeOH-BuⁱOH, 2:1) partial pressure ($P_{alc.}$) on the steady-state rates of conversion into: \bigcirc , MIBE; \blacksquare , Me₂O; \blacktriangle , butenes; \bigcirc , Buⁱ₂O. Total pressure, 1.344 × 10³ kPa; *T*, 396 K; feed of N₂ + alcohol, 250 mol (kg cat.)⁻¹ h⁻¹; catalyst (Nafion-H) wt., 2.0 g.



Figure 3. Variation of product yield with alcohol mixture partial pressure at a steady-state reaction rate. Reactants, MeOH-BuⁱOH (2:1); alcohol feed, 15.59 mol (kg cat.)⁻¹ h⁻¹; N₂ feed, 186 mol (kg cat.)⁻¹ h⁻¹; catalyst (Nafion-H Micro-Saddles) wt., 1.0 g; *T*, 389 K. \bigcirc , MIBE; \blacksquare , Me₂O; \blacktriangle , butenes; \Box , octenes; \triangle , Buⁱ₂O.

Table 1. Apparent activation energies E_A^{App} for alcohol dehydration to ethers and alkenes. Catalyst, Nafion-H; N₂ feed, 186 mol (kg cat.)⁻¹ h⁻¹; catalyst wt., 2.0 g.

	Reactant $E_A^{App.}/kJ \text{ mol}^{-1}$		
Product	MeOHª	Bu ⁱ OH ^b	MeOH– Bu ⁱ OH ^c
Me ₂ O	87.5	_	84.2
MIBE			84.3
Butenes + octenes	—	169.0	144.6
Bu ⁱ ₂ O	_	84.7	97.0

^a P_{alc.} 146.8 kPa; T 362—388 K. ^b P_{alc.} 64.1 kPa; T 380—410 K. ^c P_{alc.} 101.3 kPa; T 359—402 K.

MIBE. This result indicates that one of the two alcohols is preferentially activated, *e.g.* by proton attachment to form an oxonium ion or by esterification of the resin SO_3H group, which then reacts preferentially with the second alcohol.

Good Arrhenius plots were observed for ether and alkene formation, the resulting apparent activation energies being presented in Table 1. The activation energy for ether formation is much lower than for alkene formation, thus explaining the higher selectivity for ether formation at low temperatures but also predicting an increase in alkene formation with increasing temperature. The dehydration of the alcohol mixture over Nafion-H Micro-Saddles was studied over a wide pressure and temperature range as shown in Figures 3 and 4. Again, an initial large increase of the steady-state rate of MIBE formation with increasing pressure was observed, accompanied by a substantial suppression of



Figure 4. Effect of temperature on the reaction rate. Reactants, MeOH-BuiOH (2:1); alcohol feed, 15.59 mol (kg cat.)⁻¹ h⁻¹; N₂ feed, 186 mol (kg cat.)⁻¹ h⁻¹; catalyst (Nafion-H Micro-Saddles) wt., 1.0 g; total pressure, 7.582×10^3 kPa. \bullet , MIBE; \blacksquare , Me₂O; \bigcirc , butenes; \Box , octenes; \blacktriangle , Bui₂O.

alkene formation (compare Figures 2, 3, and 4). Increasing temperature increased the rates of both ether and alkene formation (Figure 4), but the selectivity for alkene formation increased rapidly at higher temperatures, as predicted by the activation energy data. In conclusion, high selectivity for MIBE formation (42.0 mol% of product mixture at 430 K) with accompanying high yields [230 g (kg cat.)⁻¹ h⁻¹] can be achieved under mild conditions. Further, no catalyst deactivation was observed over the several weeks of carrying out the coupling reaction with both the regular gel and the porous forms of Nafion-H.

The authors appreciate Professor T. E. Young's suggestion that the alcohol activation may involve the sulphate ester. We thank the U.S. Department of Energy for financial assistance.

Received, 6th February 1985; Com. 165

References

- 1 F. Ancillotti, M. M. Mauri, and E. Pescarollo, J. Catal., 1977, 46, 49.
- 2 A. Gicaquel and B. Torck, J. Catal., 1983, 83, 9.
- 3 F. Ancillotti, S. D. Milanese, G. Oriani, and E. Pescarollo, U.S. Pat. 3 979 461 (Sept. 7, 1976); K. Oyama and K. Kihara, Br. Pat. 2 075 019 (Nov. 11, 1981); G. A. Olah, Br. Pat. 2 082 177 (Mar. 3, 1982).
- 4 L. S. Bitar, E. H. Hazbun, and W. J. Piel, *Hydrocarbon Proc.*, 1984, **63**(10), 63.
- 5 J. D. Chase, in 'Catalytic Conversions of Synthesis Gas and Alcohols to Chemicals,' ed. R. G. Herman, Plenum Press, New York, 1984, p. 307.
- 6 G. A. Olah, J. Kaspi, and J. Bukala, J. Org. Chem., 1977, 42, 4187.
- 7 J. Kaspi, D. D. Montgomery, and G. A. Olah, J. Org. Chem., 1978, 43, 3147.
- 8 G. A. Olah, D. Meidar, R. Malhotra, J. A. Olah, and S. C. Narang, J. Catal., 1980, 61, 96.
- 9 J. Kaspi and G. A. Olah, J. Org. Chem., 1978, 43, 3142.
- 10 R. G. Herman, K. Klier, G. W. Simmons, B. P. Finn, J. B. Bulko, and T. P. Kobylinski, *J. Catal.*, 1979, 56, 407.
- 11 G. A. Vedage, R. Pitchai, R. G. Herman, and K. Klier, Proc. 8th Intern. Congr. Catal., 1984, Vol. II, p. 47.