



Surface-enhanced Raman scattering on nanoporous Au

S. O. Kucheyev, J. R. Hayes, J. Biener, T. Huser, C. E. Talley, and A. V. Hamza

Citation: Applied Physics Letters **89**, 053102 (2006); doi: 10.1063/1.2260828 View online: http://dx.doi.org/10.1063/1.2260828 View Table of Contents: http://scitation.aip.org/content/aip/journal/apl/89/5?ver=pdfcov Published by the AIP Publishing

Articles you may be interested in

Recyclable surface-enhanced Raman scattering template based on nanoporous gold film/Si nanowire arrays Appl. Phys. Lett. **105**, 011905 (2014); 10.1063/1.4889850

ZnO/Si arrays decorated by Au nanoparticles for surface-enhanced Raman scattering study J. Appl. Phys. **111**, 033104 (2012); 10.1063/1.3682462

Geometric effect on surface enhanced Raman scattering of nanoporous gold: Improving Raman scattering by tailoring ligament and nanopore ratios Appl. Phys. Lett. **94**, 213109 (2009); 10.1063/1.3143628

Large surface enhanced Raman scattering enhancements from fracture surfaces of nanoporous gold Appl. Phys. Lett. **92**, 093113 (2008); 10.1063/1.2890164

Surface enhanced Raman scattering of nanoporous gold: Smaller pore sizes stronger enhancements Appl. Phys. Lett. **90**, 153120 (2007); 10.1063/1.2722199



Surface-enhanced Raman scattering on nanoporous Au

S. O. Kucheyev,^{a)} J. R. Hayes, J. Biener, T. Huser,^{b)} C. E. Talley, and A. V. Hamza *Lawrence Livermore National Laboratory, Livermore, California 94551*

(Received 31 March 2006; accepted 13 June 2006; published online 31 July 2006)

Colloidal solutions of metal nanoparticles are currently among the most studied substrates for sensors based on surface-enhanced Raman scattering (SERS). However, such substrates often suffer from not being cost-effective, reusable, or stable. Here, we develop nanoporous Au as a highly active, tunable, stable, biocompatible, and reusable SERS substrate. Nanoporous Au is prepared by a facile process of free corrosion of AgAu alloys followed by annealing. Results show that nanofoams with average pore widths of ~250 nm exhibit the largest SERS signal for 632.8 nm excitation. This is attributed to the electromagnetic SERS enhancement mechanism with additional field localization within pores. © 2006 American Institute of Physics. [DOI: 10.1063/1.2260828]

Surface-enhanced Raman scattering (SERS) spectroscopy probes bond vibrations of molecules in the proximity of metallic nanostructures.¹ This technique has regained considerable interest in recent years stimulated by an explosive development of nanotechnology¹ and superior sensitivity of SERS, in some cases possibly approaching the single molecule detection limit.^{2,3}

Despite numerous previous reports demonstrating the SERS effect for different molecules and substrates, there is still an ongoing search for better substrates for SERS-based chemical sensors.¹ Indeed, colloidal solutions of Au or Ag with particle sizes in the submicron range are currently among the most studied SERS-active substrates. However, such substrates are not reusable and, hence, not cost-effective. This fact and the limited stability and reproducibility of metal colloids often hamper their practical use.¹

In this letter, we report on the development of nanoporous Au (np-Au) as a highly active, stable, tunable, biocompatible, reusable, and affordable (particularly when used as a thin nanoporous Au film on a low-cost substrate) SERS substrate. Additional attractiveness of np-Au comes from the fact that it is compatible with well-studied self-assembled monolayers of thiols, which can be used as linking layers in advanced sensor applications. We show that the largest SERS enhancement factors, with crystal violet as a test molecule and 632.8 nm laser excitation, are observed for np-Au with an average pore width of ~250 nm.

Nanoporous Au samples, $\sim 5.0 \times 5.0 \times 0.3 \text{ mm}^3$ in size, were prepared by free corrosion of a Ag_{0.7}Au_{0.3} starting alloy in 70% HNO₃ for 48 h at room temperature. Such a procedure results in selective dissolution of Ag and the surfacediffusion-limited self-assembly of the remaining Au atoms into np-Au with a relative density of ~30% and an open-cell spongelike morphology with elongated pores with an average width of ~25 nm [see a scanning electron microscopy (SEM) image in Fig. 1(a)].

Ligament and pore sizes were tuned by thermal annealing of as-dealloyed foams in an Ar atmosphere for 2 h in the temperature range of 100-600 °C, as illustrated in SEM images of the surfaces of np-Au in Fig. 1 (for selected annealing temperatures. The dependence of the average pore width, obtained from statistical analysis of SEM images such as illustrated in Fig. 1, on annealing temperature is shown in Fig. 2. It is seen from Figs. 1 and 2 that, with increasing annealing temperature above ~ 400 °C, the size of pores and ligaments rapidly increases. In addition, the aspect ratio of the pores intersecting the sample surface decreases with increasing annealing temperature (i.e., pores and ligaments become less elongated). The inset in Fig. 2 illustrates a relatively wide pore size distribution for a sample annealed at 450 °C, which is representative of all the other samples studied here and is consistent with a previous report.⁴

Raman scattering was studied in Jobin Yvon Raman spectrometer (model HR800) equipped with a He–Ne (632.8 nm) laser as an excitation source. Crystal violet (CV) 10B was used as a test molecule with methanol as a solvent. After a linear background subtraction, all spectra were normalized to the intensity of a methanol-related Raman band centered on ~ 1035 cm⁻¹. Both (exterior) sample surfaces and cross sections (prepared by simple fracturing since np-Au is macroscopically brittle) revealed overall the same data trends. Hence, in this letter, we will show data from the surfaces only.

Figure 3 shows typical SERS spectra from np-Au annealed at different temperatures. These Raman spectra consist of a methanol-related peak centered on ~ 1035 cm⁻¹ and



FIG. 1. Typical SEM images (primary electron energy is 5 keV) illustrating the surface morphology of as-dealloyed np-Au (a) and np-Au annealed for 2 h at 300 °C (b), 450 °C (c), and 550 °C (d). The scale bar is 1 μ m in all four images.

^{a)}Electronic mail: kucheyev@llnl.gov

^{b)}Present address: Department of Internal Medicine and NSF Center for Biophotonics, University of California, Davis, CA 95817.



FIG. 2. Dependence of the average pore width on annealing temperature of np-Au. The inset shows the distribution of pore widths in np-Au annealed at 450 °C.

a series of CV-related SERS bands. Note that no measurable SERS signal was observed from flat Au surfaces (Au deposited on glass slides) even for the largest CV concentration used (a 10^{-5} *M* molar methanolic solution). It is seen from Fig. 3 that the SERS enhancement strongly depends on the annealing temperature and, hence, on the average size of pores and/or ligaments (see Figs. 1 and 2). In particular, samples annealed at temperatures around 500 °C exhibit the maximum SERS signal.

To better correlate SERS signal enhancement with the morphology of np-Au, Fig. 4 shows the dependence of SERS intensity on the average pore [Fig. 4(a)] or ligament [Fig. 4(b)] width. Note that, in Figs. 4(a) and 4(b), different data points for the same pore or ligament size^{5,6} represent Raman spectra taken from different areas of the same sample. Figure 4 clearly illustrates the effect of average pore and ligament sizes on SERS intensity, the range of average pore and ligament sizes studied, and the scatter of data points for different spots on the same sample. Figure 4(b) reveals no clear correlation between SERS intensity and the average ligament size. For the same set of nanofoams as in Fig. 4(b), however, Fig. 4(a) shows that SERS intensity is maximum for foams with an average pore width of \sim 250 nm. With this pore size, we could readily detect a SERS signal from $10^{-7} M$ molar methanolic solutions of CV. Note that the length scale dependence revealed by Fig. 4 suggests that np-Au could be a tunable SERS substrate when the SERS response is optimized for any given excitation source by adjusting the pore width in a straightforward thermal annealing step.

Data from Fig. 4 provide clear evidence that SERS enhancement better correlates with the average pore size rather



FIG. 3. (Color online) Representative SERS spectra (for a $10^{-6}M$ solution of crystal violet) from np-Au annealed at different temperatures, as indicated Spectra are offset for clarity. A methanol-related peak is labeled "MeOH."



FIG. 4. Dependence of SERS intensity (defined as the integral intensity of the band centered on $\sim 1175 \text{ cm}^{-1}$) on the average pore (a) or ligament (b) width. Different data points for the same pore or ligament size represent spectra taken from different areas of the same sample. All data are for a $10^{-6}M$ solution of crystal violet.

than with the ligament size. Hence, we attribute efficient SERS from np-Au to the well-established electromagnetic SERS enhancement mechanism related to an efficient excitation and trapping of surface plasmons,¹ but with an additional effect of field localization in the pore regions. Our experimental finding is, qualitatively, consistent with several previous experimental^{1,3,7-11} and theoretical^{1,12-18} reports on the additional SERS enhancement resulting from electromagnetic field localization in regions between nanoparticles or in surface cavities/pores (with negative curvature). However, the specific optimal pore size of ~ 250 nm, revealed in the present study, is unexpected. For example, several previous experimental observations^{8,10} and theoretical calculations^{8,14} for isolated (but electromagnetically coupled) nanoparticles have suggested that SERS enhancement generally increases with decreasing average interparticle distance. Such results for nanoparticles, however, cannot be directly applied for a complex coupled system such as np-Au. Somewhat more relevant calculations for a two-dimensional lattice of buried spherical voids recently reported by Teperik et al.¹⁷ have shown that there are optimal conditions for the most favorable light-plasmon coupling which depend on the properties of the metal, the dielectric filling the pores, as well as the size, shape, and geometrical arrangement of nanovoids. Hence, theoretical studies taking into account the specific morphology of np-Au (illustrated in Fig. 1) are currently needed in order to explain the pore size dependence reported here.

It should be noted that the scatter in effective SERS enhancement factors for different areas of the same sample, as clearly illustrated in Fig. 4, is not unexpected. Indeed, most of the signal from np-Au appears to originate from the so called hot spots whose size, according to a very recent report by Dixon,¹⁹ is comparable with the laser beam spot size used in our experiments (ideally, ~2 μ m, estimated based on the parameters of the microscope objective used). The appearance of such hot spots is also consistent with a relatively wide pore size distribution in np-Au (see the inset of Fig. 2) and the fact that the irregular, nanoscale morphology of the np-Au surface could result in complex patterns of electromagnetic field enhancement.¹

Finally, SERS cross sections and, hence, SERS enhancement factors can be estimated by comparing the intensities of the methanol Raman peak at $\sim 1035 \text{ cm}^{-1}$ and a CV SERS band at $\sim 1175 \text{ cm}^{-1}$. In such estimations, we take into account that all methanol molecules from the probed volume (whose minimum bound of ~ 60 fl is estimated as the volume of a cylinder with the length equal to the depth of field and the diameter equal to the ideal beam spot size) contribute to the methanol Raman peak, while CV molecules from only a thin layer of thickness h of the solution on the np-Au surface contribute to the SERS signal.²⁰ Assuming that h is ~300 nm (which is a very conservative assumption based on experiments of Murray *et al.*,²¹ suggesting that *h* could be ~10 nm), one obtains enhancement factors of ~ $10^9 - 10^{11}$ for data from Fig. 4. These numbers, however, should be viewed as a lower bound for the enhancement factors given our conservative assumptions and the existence of hot-spot effects in the SERS response of np-Au.¹⁹

In conclusion, we have demonstrated nanoporous Au as a highly active, tunable SERS substrate. Although asdealloyed np-Au shows a weak SERS signal, subsequent thermal processing, increasing the average pore width to \sim 250 nm, dramatically improves the SERS response. This has been attributed to effects of plasmon trapping and electromagnetic field localization within pores.

The authors thank R. J. Anderson, C. A. Cox, J. L. Ferreira, R. T. Graff, A. M. Hodge, C. A. Orme, and E. M. Sedillo for useful discussions and/or technical assistance. This work was performed under the auspices of the U.S. DOE by the University of California, LLNL under Contract No. W-7405-Eng-48.

- ¹See, for example, reviews by M. Moskovits, Rev. Mod. Phys. **57**, 783 (1985); A. Campion and P. Kambhampati, Chem. Soc. Rev. **27**, 241 (1998); MRS Bull. **30**, 338 (2005).
- ²K. Kneipp, Y. Wang, H. Kneipp, L. T. Perelman, I. Itzkan, R. Dasari, and M. S. Feld, Phys. Rev. Lett. **78**, 1667 (1997).
- ³S. Nie and S. R. Emory, Science **275**, 1102 (1997).
- ⁴R. Li and K. Sieradzki, Phys. Rev. Lett. **68**, 1168 (1992).
- ⁵Note that the large difference between average ligament sizes for np-Au

samples with similar average pore sizes, illustrated in Fig. 4, is related to the fact that the surfaces of samples annealed at 400-600 °C were "contaminated" with silica-containing nanoparticles, which are clearly visible as small bright spots in SEM images in Figs. 1(c) and 1(d). This effect has been observed consistently for all the foams annealed in two different tube furnaces and seems to be more pronounced when annealing is done in an O₂-containing atmosphere. Noting that the temperature required for the "development" of such nanoparticles on the np-Au surface coincides with the onset of a very rapid diffusion of Si in Au (Ref. 6), we attribute this effect to the outdiffusion, precipitation, and oxidation of Si impurities (in the starting alloy) during the surface-diffusion-limited evolution of Au nanofoams upon annealing. Interestingly, this initially undesirable formation of silica nanoparticles, affecting the evolution of surface morphology of nanofoams, turned out to be very useful for independently controlling the average pore and ligament sizes and helped us unravel the critical role of nanopores in the SERS response from np-Au. It should also be noted that the overall conclusions of this work are not affected by the presence of such silica nanoparticles since similar SERS response has been observed for both surfaces and cross sections (where no silica particles were observed) of np-Au with the same average pore widths.

⁶See, for example, A. K. Green and E. Bauer, J. Appl. Phys. **47**, 1284 (1976).

- ⁷A. M. Michaels, J. Jiang, and L. Brus, J. Phys. Chem. B **104**, 11965 (2000).
- ⁸L. Gunnarsson, E. J. Bjerneld, H. Xu, S. Petronis, B. Kasemo, and M. Kall, Appl. Phys. Lett. **78**, 802 (2001).
- ⁹B. Nikoobakht and M. A. El-Sayed, J. Phys. Chem. A **107**, 3372 (2003).
 ¹⁰Z. Zhu, T. Zhu, and Z. Liu, Nanotechnology **15**, 357 (2004).
- ¹¹S. Coyle, M. C. Netti, J. J. Baumberg, M. A. Ghanem, P. R. Birkin, P. N. Bartlett, and D. M. Whittaker, Phys. Rev. Lett. **87**, 176801 (2001); J. J. Baumberg, T. A. Kelf, Y. Sugawara, S. Cintra, M. E. Abdelsalam, P. N. Bartlett, and A. R. Russell, Nano Lett. **5**, 2262 (2005).
- ¹²E. V. Albano, S. Daiser, G. Ertl, R. Miranda, K. Wandelt, and N. Garcia, Phys. Rev. Lett. **51**, 2314 (1983).
- ¹³H. Seki, T. J. Chuang, J. F. Escobar, H. Morawitz, and E. V. Albano, Surf. Sci. **158**, 254 (1985).
- ¹⁴F. J. Garcia-Vidal and J. B. Pendry, Phys. Rev. Lett. **77**, 1163 (1996).
- ¹⁵E. Y. Poliakov, V. A. Markel, V. M. Shalaev, and R. Botet, Phys. Rev. B 57, 14901 (1998).
- ¹⁶J. Jiang, K. Bosnick, M. Maillard, and L. Brus, J. Phys. Chem. B 107, 9964 (2003).
- ¹⁷T. V. Teperik, V. V. Popov, and F. J. Garcia de Abajo, Phys. Rev. B **71**, 085408 (2005).
- ¹⁸K. J. Webb and J. Li, Phys. Rev. B **73**, 073404 (2006).
- ¹⁹M. C. Dixon, Ph. D. thesis, Pennsylvania State University, 2005.
 ²⁰An assumption that SERS is caused by a monolayer of CV molecules chemi-and/or physisorbed on the Au surface in the solution is not supported by our results showing that SERS intensity increases with increasing CV concentration in methanolic solutions.
- ²¹C. A. Murray, D. L. Allara, and M. Rhinewine, Phys. Rev. Lett. **46**, 57 (1981).