

# A Journal of the Gesellschaft Deutscher Chemiker A Deutscher Chemiker GDCh International Edition www.angewandte.org

## **Accepted Article**

Title: Novel Terpolymers from Borane Initiated Copolymerization of Triphenyl Arsonium and Sulfoxonium Ylides: An Unexpected Light Emission

Authors: Nikos Hadjichristidis and De Wang

This manuscript has been accepted after peer review and appears as an Accepted Article online prior to editing, proofing, and formal publication of the final Version of Record (VoR). This work is currently citable by using the Digital Object Identifier (DOI) given below. The VoR will be published online in Early View as soon as possible and may be different to this Accepted Article as a result of editing. Readers should obtain the VoR from the journal website shown below when it is published to ensure accuracy of information. The authors are responsible for the content of this Accepted Article.

To be cited as: Angew. Chem. Int. Ed. 10.1002/anie.201901094 Angew. Chem. 10.1002/ange.201901094

Link to VoR: http://dx.doi.org/10.1002/anie.201901094 http://dx.doi.org/10.1002/ange.201901094

## WILEY-VCH

## Novel Terpolymers from Borane Initiated Copolymerization of Triphenyl Arsonium and Sulfoxonium Ylides: An Unexpected Light Emission

De Wang\*<sup>[a]</sup> and Nikos Hadjichristidis\*<sup>[b]</sup>

Abstract: We report the first synthesis of well-defined poly[(phenylmethylene-co-methylpropenylene)-b-methylene, [(C1-co-C3)-b-C1], terpolymers via one-pot borane initiated random copolymerization of  $\omega$ -methylallyl (C3 units, chain is growing by three carbon atoms at a time) and benzyltriphenylarsonium (C1 units, chain is growing by one carbon atom at a time) ylides, followed by polymerization of sulfoxonium methylide (C1 units). Other substituted arsonium ylides, such as prenyltriphenyl, propyltriphenyl and (4used fluorobenzyl)triphenyl can also be instead benzyltriphenylarsonium. The obtained terpolymers are well-defined, possess a predictable molecular weight and low polydispersity ( $M_{n,NMR}$ =  $1.83-9.68 \times 10^3$  g/mol, D = 1.09-1.22). An unexpected light emission phenomenon was discovered in these non-conjugated terpolymers as proved by fluorescence and NMR spectroscopy. This phenomenon can be explained by the isomerization of the double bonds of allylic monomeric units along the chain of the terpolymers (isomerizationinduced light emission).

Boron compounds have been used as initiators in the polymerization of dimethylsulfoxonium methylide, a living C1 polymerization (chain is growing by one carbon atom at a time) discovered by Shea et al and coined the name polyhomologation.<sup>1</sup> This polymerization, leading to well-defined ω-hydroxyl polymethylene (PM, equivalent to polyethylene), was used to synthesize PM-based homo- and block copolymers with different topology (linear, star, cyclic, etc).<sup>2</sup> Our group was also used polyhomologation of dimethylsulfoxonium methylide to obtain well-defined PM-based linear, miktoarm star and brush copolymers by designing/synthesizing novel borane initiators or by combining polyhomologation with other living/controlled living polymerization methods such as anionic, cationic, atom transfer radical. ring-opening, and ring-opening metathesis polymerization.<sup>3</sup> Later, efforts were focused in the synthesis of substituted ylides, such as dimethylaminophenyloxosulfoxoniu methvlide. diethylsulfoxonium methvlide. (dimethylamino)tolyloxosulfoxonium cyclopropylide, with the

[a] Associate Professor Dr. De Wang, Ocean University of China, School of Medicine and Pharmacy, Qingdao, Shandong Province, 266071, China. E-mail: wangde@ouc.edu.cn
[b] Professor Dr. Nikos Hadjichristidis King Abdullah University of Science and Technology (KAUST), Physical Sciences and Engineering Division, KAUST Catalysis Center, Polymer Synthesis Laboratory Thuwal 23955, Kingdom of Saudi Arabia E-mail: nikolaos.hadjichristidis@kaust.edu.sa

Supporting information for this article is available on the WWW under http://www.angewandte.org or from the author.

hope of obtaining poly(substituted methylene).<sup>4</sup> Although the homopolymerization of substituted sulfoxonium ylides were unsuccessful (due to the steric hindrance around boron centers), however, the copolymerization of these subsituted ylide monomers with sulfoxonium methylide was successful. Limited by the synthetic difficulty and diversity of sulfoxonium ylides, the development of new ylide monomers in boron-catalyzed polymerization was highly demanded.

In 2003, Mioskowski et al reported that 2-methylallyltriphenyl vlide is compatible with borane arsonium initiated polymerization.<sup>5a</sup> However, this monomer did not lead to polymer substituted on every one carbon atom (C1), but rather on every three carbon atoms (C3 polymerization), meaning that the chain is growing by three carbon atoms at a time. In 2005, the same authors realized that a few others 2-allylsubstituted triphenylarsonium ylides show the same behavior.<sup>5b</sup> Later, Mioskowski et al discovered that by using a non-substituted allylarsonium ylide as monomer a C1/C3 random copolymer was obtained, whereas by using terminal dimethyl substituted allylic arsonium ylide a C1 homopolymer was obtained.<sup>6</sup> They explained the differences by using sigmatropic rearrangement arguments. Encouraged by this work, our group discovered that 3methylallyltriphenylarsonium ylide, а ω-monosubstituted allylarsonium ylide, leads also to C3 polymerization. Moreover, by combining  $\omega$ -monosubstituted allylic arsonium ylide (C3) with sulfoxonium methylide (C1) we were able to synthesize welldefined methylene/3-methylpropenylene block and random copolymers (Scheme 1, A).<sup>7</sup> Encouraging by these discoveries we started exploring the borane initiating polymerization of other arsonium ylides hoping to obtain novel polymeric materials with unprecedented properties (Scheme 1, B).



and random ese discoveries ization of other materials with



## COMMUNICATION

In this communication, we report the design/synthesis of several novel non-allylic triphenylarsonium ylides and explore their homoand copolymerization with  $\omega$ -methylallyltriphenylarsonium ylide using triethylborane as the initiator. Moreover, we report the synthesis of well-defined diblock terpolymers having C1-co-C3 and PM blocks. These terpolymers despite the fact that they don't possess conjugated double bonds emit light. This unexpected phenomenon, investigated by fluorescence and NMR spectroscopy, revealed that the isomerization of the double bonds of the C3 units, leading to conjugated double bonds, is the cause of the emission. This phenomenon (isomerization-induced light emission) is not present either in polybutadiene-1,4 or polyisoprene-1,4 (C4 polymerization, chain growing by four carbon atoms at a time) since the double bonds, unlike in our C3 polymers, are in every four carbons and thus their isomerization does not lead to conjugated double bonds.

We first synthesized benzyltriphenylarsonium tetrafluoroborate salt (Scheme S1 and Figure S1-S4, ESI), which can be transformed to benzyltriphenylarsonium vlide monomer, by treatment with *n*-butyllithium. The homopolymerization of benzyltriphenylarsonium ylide with triethyl borane was failed due to the steric congestion around the boron complex. The copolymerization of benzyltriphenylarsonium ylide and sulfoxonium methylide with triethylborane was also unsuccessful, even after refluxing the mixture of monomers for 3 days (pH>7.0, phenolphthalein indicator) due to the same steric reason. In contrary, the copolymerization of benzyltriphenylarsonium ylide with 3-methylallyltriphenylarsonium ylide was successful because the 1,3-sigmatropic rearrangement releases the steric hindrance around boron. The general reactions for the synthesis of poly[(methylpropenylene-co-phenylmethylene)-b-methylene]

terpolymers [(PA-co-PBz)-b-PM] are given in Scheme 2. Treatment of benzyltriphenylarsonium and allyltriphenylarsonium tetrafluoroborate salts in tetrahydrofuran (THF) with n-butyllithium at -78 °C under argon, resulted in a clear red solution proving the in situ generations of the corresponding ylide monomers. The red solution was allowed to warm up to room temperature slowly (about 2 hours), and then triethylborane was added, followed by heating at 60 °C for two hours. A clear colorless and neutral solution (pH=7.0, the absence of monomer) was obtained and used to initiate the polyhomologation of sulfoxonium methylide at 80 °C for twenty minutes until the solution became neutral (pH=7.0). The terpolymers (PA-co-PBz)-b-PM were obtained after oxidation/hydrolysis with trimethylamine N-oxide dihydrate (TAO·2H<sub>2</sub>O) [Scheme S3, ESI]. The <sup>1</sup>H NMR spectrum of sample corresponding to polymer 3 (Table 1), a representative example, clearly shows the signals of the corresponding monomeric units (Figure S5, ESI). The aromatic protons are appeared at 7.10-7.41 ppm, the peak at  $\delta$  = 5.40 ppm assigned to the allylic double bond protons, the aliphatic protons are appeared at 1.11-1.65 ppm and 2.51-2.83 ppm, in agreement with the previous report.<sup>7</sup> The chainend protons assigned to -CH2- connected to the hydroxy group at  $\delta$  = 3.66 ppm can be used to calculate the degree of polymerization. The peak at 970 cm<sup>-1</sup> (FT-IR spectrum) indicates that the double bonds (C3 segment) possess the E-configuration (trans), and the two peaks at 699 and 758 cm<sup>-1</sup> further indicate the aromatic ring (phenyl group) existence (Figure S6, ESI).



Scheme 2. General reaction for the synthesis of diblock terpolymers [(PA-co-PBz)-b-PM].

 Table 1. Molecular characteristic and melting temperatures of the synthesized
 [(PA-co-PBz)-b-PM) diblock terpolymers

ymer	DP <sub>cal</sub> a (A/Bz/M)	DP <sub>NMR</sub> <sup>b</sup> (A/Bz/M)	M <sub>n,NMR</sub> <sup>b</sup> ×10 <sup>3</sup>	PDI <sup>c</sup> ( <i>M</i> <sub>w</sub> / <i>M</i> <sub>n</sub> )	Yield <sup>d</sup> (%)	T <sub>m</sub> (°C)
Bz <sub>3</sub> -b-PM <sub>88</sub>	5/5/60	5/3/88	1.83	1.09	71	89.4
Bz <sub>11</sub> -b-PM <sub>171</sub> 1	7/17/100	14/11/186	4.35	1.15	58	100.8
Bz <sub>15</sub> -b-PM <sub>186</sub> 2	27/17/100	20/15/171	4.88	1.10	67	108.3
Bz <sub>32</sub> -b-PM <sub>370</sub> 2	20/27/250	29/32/370	9.68	1.17	65	114.9
	ymer Bz <sub>3</sub> - <i>b</i> -PM <sub>88</sub> Bz <sub>11</sub> - <i>b</i> -PM <sub>171</sub> 1 Bz <sub>15</sub> - <i>b</i> -PM <sub>186</sub> 2 Bz <sub>32</sub> - <i>b</i> -PM <sub>370</sub> 2	ymer         DP <sub>cal</sub> <sup>a</sup> (A/Bz/M)           Bz <sub>3</sub> -b-PM <sub>88</sub> 5/5/60           3z <sub>11</sub> -b-PM <sub>171</sub> 17/17/100           3z <sub>15</sub> -b-PM <sub>186</sub> 27/17/100           3z <sub>32</sub> -b-PM <sub>370</sub> 20/27/250	ymer         DP <sub>cal</sub> <sup>a</sup> DP <sub>NMR</sub> <sup>b</sup> (A/Bz/M)           Bz <sub>3</sub> -b-PM <sub>88</sub> 5/5/60         5/3/88           3z <sub>1</sub> -b-PM <sub>171</sub> 17/17/100         14/11/186           3z <sub>15</sub> -b-PM <sub>186</sub> 27/17/100         20/15/171           3z <sub>32</sub> -b-PM <sub>370</sub> 20/27/250         29/32/370	Vmer         DP <sub>cal</sub> <sup>a</sup> (A/Bz/M)         DP <sub>NMR</sub> <sup>b</sup> (A/Bz/M)         M <sub>n,NMR</sub> <sup>b</sup> ×10 <sup>3</sup> Bz <sub>3</sub> -b-PM <sub>88</sub> 5/5/60         5/3/88         1.83           3z <sub>1</sub> -b-PM <sub>171</sub> 17/17/100         14/11/186         4.35           3z <sub>1</sub> -b-PM <sub>186</sub> 27/17/100         20/15/17/1         4.88           3z <sub>32</sub> -b-PM <sub>370</sub> 20/27/250         29/32/370         9.68	Vmer         DP cel <sup>8</sup> (A/BZ/M)         DP NMR <sup>b</sup> (A/BZ/M)         M <sub>n,NMR<sup>b</sup></sub> (A/BZ/M)         PDI <sup>6</sup> (M <sub>m</sub> /M <sub>n</sub> )           Bz <sub>3</sub> -b-PM <sub>88</sub> 5/5/60         5/3/88         1.83         1.09           3z <sub>11</sub> -b-PM <sub>171</sub> 17/17/100         14/11/186         4.35         1.15           3z <sub>15</sub> -b-PM <sub>186</sub> 27/17/100         20/15/171         4.88         1.10           3z <sub>32</sub> -b-PM <sub>370</sub> 20/27/250         29/32/370         9.68         1.17	ymer         DP cell <sup>a</sup> DP NMR <sup>b</sup> M <sub>n,NMR<sup>b</sup></sub> PDI <sup>c</sup> Yield <sup>d</sup> 8z <sub>3</sub> -b-PM <sub>88</sub> 5/5/60         5/3/88         1.83         1.09         71           3z <sub>11</sub> -b-PM <sub>171</sub> 17/17/100         14/11/186         4.35         1.15         58           3z <sub>15</sub> -b-PM <sub>186</sub> 27/17/100         20/15/171         4.88         1.10         67           3z <sub>32</sub> -b-PM <sub>370</sub> 20/27/250         29/32/370         9.68         1.17         65

<sup>a</sup> DP<sub>cal</sub> is the degree of polymerization, calculated by [M]/[I]. <sup>b</sup>  $M_{n,NMR}$  and DP<sub>NMR</sub> were determined by <sup>1</sup>H NMR (1,1,2,2-tetrachloreothane- $d_x$ , 90 °C, 600MHz),  $M_{n,NMR} = M_{E1} + xM_{CH2} + yM_{CH2} + yM_{CH2} + zM_{M} + M_{CH2} + zM_{M} + M_{CH2} + zM_{M} + M_{M} + M$ 

The molecular characteristics of three more terpolymers (1, 2 and 4, Table 1) synthesized following the same general procedure described previously, are given in Table 1 and the corresponding GPC traces in Figure 1A. It is clear that the synthesized terpolymers ( $M_{n, NMR} = 1.83-9.68 \times 10^3$  g/mol) posses monomodal and narrow GPC traces (D = 1.09-1.17). In addition, a clear shift of the elution peak from low to high molecular weight was observed, in accordance with the increased degree of polymerization (DP) as determined by NMR. The DP<sub>NMR</sub> of PM is higher than the calculated values and this could be attributed to the oxidation/decomposition of a part of the 3-arm boron macroinitiator during the addition of sulfoxonium methylide.<sup>3,7</sup> The DSC traces of the diblock terpolymers are shown in Figure 1B. For the low molecular weight (Table 1, entry 1,  $M_{n, NMR} = 1.83 \times 10^3$ g/mol) terpolymer, the melting temperature  $(T_m)$  corresponding to PM is 89.4 °C with a crystallinity of about 44%. By increasing the molecular weight (Table 1, entries 2-4,  $M_{n, NMR} = 4.17-9.68 \times 10^3$ g/mol) of PM, the melting temperature ( $T_m$ ) increases to 114.9 °C, as expected, with a slight decrease of crystallinity (29-35%). It seems that the existence of the "soft" segments (C3 and substituted C1 segments) exercises a small influence on the crystallization.8



Figure 1. (A) HT-GPC traces (TCB at 150  $^{\circ}$ C, PS standard); (B) DSC traces of terpolymers under nitrogen at a heating rate at 10  $^{\circ}$ C/min.

#### WILEY-VCH

### COMMUNICATION

Having shown that the benzyltriphenylarsonium ylide can be used as substituted C1 monomer in the copolymerization with  $\omega$ methylallylarsonium ylide initiated with triethylborane, we synthesized and investigated other substituted ylides such as propyltriphenylarsonium, (3-methylbut-2-en-1yl)triphenylarsonium and (4-fluorobenzene)triphenylarsonium ylide (Figure S7-8, ESI). For the synthesis of the corresponding terpolymers 5-7 (monomer to initiator mole ratio was  $[M_{As,R}]/[[M_{As,Allvl}]/[M_s]/[[I] = 17/17/100/1)$ , the same procedure as of terpolymer (PA-co-PBz)-b-PM was followed. The <sup>1</sup>H NMR spectra displayed the expected signals corresponding to the two arsonium ylides and sulfoxonium methylide (Figure S9-10, ESI). The molecular weights of terpolymers 5-7 were determined by <sup>1</sup>H NMR end group analysis ( $M_n = 4.3-9.1 \times 10^3$  g/mol) and polydispersities were detected by HT-GPC with polystyrene as standards (D = 1.16 - 1.22). The HT-GPC traces were monomodal with narrow dispersity, proving that our strategy is efficient and powerful for the construction C1/C3 terpolymers (Figure 2A). Representative <sup>1</sup>H NMR, <sup>19</sup>F NMR spectra, corresponding to polymer 7, are shown in Figure 2B. The peak at  $\delta = -116.39$  ppm (<sup>19</sup>F NMR) further proving the introduction of substituted C1 segment to polymer chain.



Figure 2. (A) Synthetic route to terpolymers 5, 6, 7 and their HT-GPC traces (TCB, 150 °C); (B) 1H NMR Spectra of terpolymer 7, inset is the <sup>19</sup>F NMR of the terpolymer (<sup>1</sup>H NMR and <sup>19</sup>F NMR at 600 MHz in CDCl<sub>2</sub>CDCl<sub>2</sub> at 90 °C).

Then, we investigated the non-conjugated terpolymer fluorescence properties since we thought that potential  $\pi$ - $\pi$  stacking (aromatic phenyl rings) in molecular crystals or aggregates may produce emission.<sup>9</sup> To our surprise, the photoluminescence (PL) of terpolymer **3** showed a clear emission

peak centered at 473 nm upon photoexcitation (Figure 3A). The no emission of monomers (all arsonium ylides used in this paper) or the related compounds (triphenylarsine or triphenylarsine oxidizer) excludes the potential contaminant effect and further confirm the emission comes from the terpolymer (Figure S11, ESI). The associated UV-Vis spectra reveal an absorption peak at 295 nm, proving the existence of the phenyl rings and conjugated double bonds (Figure 3B). As shown in Figure 3C, the solutions of the four terpolymers in TCB (cloudy at room temperature because of insolubility of PM) emit blue light under UV light (365 nm) irradiation. Similar photoluminescence behavior was also found in bulk sample and film (Figure S12, ESI). Copolymers **5-7** also shown a similar light emission phenomenon under UV light irradiation (Figure S13, ESI).

After careful study of the structure of the copolymers, we concluded that the unexpected fluorescence phenomenon most probably induced by isomerization (isomerization-induced emission) of allylic double bond. The allylic double bond isomerization is driven by either light or heat. To prove that we placed the NMR tube, containing the terpolymer (PA-co-PBz)-b-PM (polymer 3 was used in this case) in deuterated 1.1.2.2tetrachloroethane- $d_2$  (CDCl<sub>2</sub>CDCl<sub>2</sub>), under UV light for 5 days. The proton of the allyl ( $\delta$  = 5.4 ppm) became broad and shifted to low magnetic field area, indicating the existence of conjugation (Figure 4A). The PL spectra clearly show that the fluorescence intensity increased remarkably after 5 days irradiation under UV light (Figure S14, polymer 7 was used in this case). We also test the temperature effect, by heating the terpolymer 7 in CDCl<sub>2</sub>CDCl<sub>2</sub> for 24 h at 90 °C, no remarkable changes were detected in both <sup>1</sup>H NMR and PL spectra (Figure S15, ESI). These results indicate that the terpolymer is a light-sensitive but thermodynamics stable polymer. The homo C3 polymer (polymer 8, for synthesis see our previous work,7 for the 1H NMR see Figure S16, ESI), gave an emission at 450 nm in THF solution (Figure 4B). Another two homopolymers (polymer 9 and 10) obtained by polymerization of reported allylic arsonium ylide5a, 6 have similar emission behavior (Figure S17, ESI). The <sup>1</sup>H NMR of C3 polymer 8 compared with UV irradiated one also showed a clear isomerization phenomenon (Figures S18, ESI). All above evidence proved that the lightinduced isomerization plays a key role in the light emission phenomenon.



Figure 3. (A) PL spectra of diblock terpolymer 3 (Table 1) in toluene. concentration: 3 mg/mL. Excitation wavelength: 342 nm; (B) UV-Vis spectrum of diblock terpolymer 3 (Table 1) in toluene; (C) Photographs of polymer in 1, 2, 4-trichlorobenzene (TCB) taken at UV (365 nm) light and daylight.

#### WILEY-VCH

## COMMUNICATION



Figure 4. (A) Proposed mechanism of isomerization and <sup>1</sup>H NMR proof under UV irradiation (365 nm) and (B) PL spectrum of homopolymer 8 (C3 polymer), the inset is polymer 8 in THF under daylight or UV light (365 nm). Concentration: 2 mg/mL, Excitation: 342 nm.

In summary, a novel method for construction of well-defined C3/C1 containing diblock terpolymers by copolymerization of two arsonium ylides followed by sequential copolymerization of dimethylsulfoxonium methylide was successfully reported for the first time. The successful application of substituted arsonium ylides as C1 building blocks will widely extend the boron-catalyzed polymerization of ylide chemistry. An unexpected light emission phenomenon of this non-conjugated terpolymer has been observed for the first time. The light emission can be explained by the formation of short conjugated sites along the chain under irradiation. We believe that these C3/C1 copolymers belong to a new family of polymeric materials with interesting properties.

#### **Author Information**

#### **Corresponding authors**

\*E-mail: nikolaos.hadjichristidis@kaust.edu.sa \*E-mal: wangde@ouc.edu.cn

#### ORCID

De Wang: 0000-0002-3737-6621 Nikos Hadjichristidis: 0000-0003-1442-1714

#### Acknowledgments

The research reported in this publication was supported by King Abdullah University of Science and Technology (KAUST).

**Keywords:** Arsonium ylides, sulfoxonium ylide, borane, copolymerization, photoluminescence.

- K. J. Shea, J. W. Walker, H. Zhu, M. M. Paz, J. Greaves, J. Am. Chem. Soc. 1997, 119, 9049–9050.
- (a) J. Luo, K. J. Shea, Acc. Chem. Res. 2010, 43, 1420-1433; (b) B. B. [2] Busch, M. M. Paz, K. J. Shea, C. L. Staiger, J. M. Stoddard, J. R. Walker, X.-Z. Zhou, H. Zhu, J. Am. Chem. Soc. 2002, 124, 3636-3646; (c) X.-Z. Zhou, K. J. Shea, J. Am. Chem. Soc. 2000, 122, 11515-11516; (d) R. Sulc, X.-Z. Zhou, K. J. Shea, Macromolecules 2006, 39, 4948-4952; (e) J. Bai, L. D. Burke, K. J. Shea, J. Am. Chem. Soc. 2007, 129, 4981-4991; (f) J. Bai, K. J. Shea, Macromol. Rapid Commun. 2006, 27, 1223-1228; (g) J. Li, Q.-L. Zhao, J.-Z. Chen, L. Li, J. Huang, Z. Ma, Y.-W. Zhong, Polym. Chem. 2010, 1, 164-167; (h) J.-Z. Chen, K. Cui, S.-Y. Zhang, P. Xie, Q.-L. Zhao, J. Huang, L.-P. Shi, G.-Y. Li, Z. Ma, Macromol. Rapid Commun. 2009, 30, 532-538; (i) J.-Z. Chen, Q.-L. Zhao, L.-P. Shi, J. Huang, G.-Y. Li, S.-Y. Zhang, Z. Ma, J. Polym. Sci.Part A Polym. Chem. 2009, 47, 5671-5681; (j) C. Yuan, H.-C. Lu, Q.-Z. Li, S. Yang, Q.-L. Zhao, J. Huang, L.H. Wei, Z. Ma, J. Polym. Sci. Part A Polym. Chem. 2012, 50, 2398-2405; (k) H.-C. Lu, Y. Xue, Q.-L. Zhao, J. Huang, S.-G. Xu, S.-K. Cao, Z. Ma, J. Polym. Sci. Part A: Polym. Chem. 2012, 50, 3641-3647; (I) Y. Xue, H.-C. Lu, Q.-L. Zhao, J. Huang, S.-G. Xu, S.-K. Cao, Z. Ma, Polym. Chem. 2013, 4, 307-312; (m) Y. Xue, S.-S. Zhang, K. Cui, J. Huang, Q.-L. Zhao, P. Lan, S.-K. Cao, Z. Ma, RSC Adv. 2015, 5, 7090-7097; (n) F. Xu, P. Dong, K. Cui, S.-Z. Bu, J. Huang, G.-Y. Li, T. Jiang, Z. Ma. RSC Adv., 2016, 6, 69828-69835.
- [3] (a) H. Zhang, N. Alkayal, Y. Gnanou, N. Hadjichristidis, *Macromol. Rapid Commun.* 2014, *35*, 378–390; (b) H. Zhang, N. Alkayal, Y. Gnanou, N. Hadjichristidis, *Chem. Commun.* 2013, *49*, 8952–8954; (c) H. Zhang, Y. Gnanou, N. Hadjichristidis, *Polym. Chem.* 2014, *5*, 6431–6434; (d) H. Zhang, Y. Gnanou, N. Hadjichristidis, *Macromolecules* 2015, *48*, 3556–3562; (e) Z. Zhang, H. Zhang, Y. Gnanou, N. Hadjichristidis, *Chem. Commun.* 2015, *51*, 9936–9938; (f) H. Zhang, N. Hadjichristidis, *Macromolecules* 2016, *49*, 1590-1596; (g) N. Alkayal, N. Hadjichristidis, *Polym. Chem.* 2015, *6*, 4921-4926; (h) N. Alkayal, N. Hadjichristidis, N. Hadjichristidis, *Chem.* 2016, *7*, 2986-2991; (i) D. Wang, N. Hadjichristidis, *Chem. Commun.* 2017, *53*, 1196-1199; (j) Z. Zhang, Y. Gnanou, N. Hadjichristidis, *Polym. Chem.* 2016, *7*, 5507-5511.
- [4] (a) R. Sulc, X.-Z. Zhou, K. J. Shea, *Macromolecules* 2006, *39*, 4948-4952; (b) R. Zhao, K. J. Shea, *ACS Macro Lett.* 2015, *4*, 584-587.
- [5] (a) J.-P. Goddard, P. Lixon, T. Le Gall, C. Mioskowski, *J. Am. Chem. Soc.* 2003, *125*, 9242-9243; (b) R. Mondiere, J.-P. Goddard, G. Carrot, T. Le
   Gall, C. Mioskowski, *Macromolecules* 2005, *38*, 663–668.
- [6] R. Mondiere, J.-P. Goddard, M. Huiban, G. Carrot, T. Le Gall, C. Mioskowski, Chem. Commun. 2006, 42, 723-725.
- [7] D. Wang, Z. Zhang, N. Hadjicristidis, ACS Macro Lett. 2016, 5, 387-390.
- [8] (a) Y.-L. Loo, R. A. Register, *Macromolecules* 2002, 35, 2365–2374; (b)
   H. Kaneyoshi, Y. Inoue, K. Matyjaszewski, *Macromolecules* 2005, 38, 5425–5435.
- [9] For non-conjugated polymers photoluminescence, see: (a) E. Zhao, J.
  W. Y. Lam, L. Meng, Y. Hong, H. Deng, G. Bai, X. Huang, J. Hao, B. Z.
  Tang, *Macromolecules* 2015, *48*, 64-71; (b) R. Ye, Y. Liu, H. Zhang, H.
  Su, Y. Zhang, L. Xu, R. Hu, R. T. K. Kwok, K. S. Wong, J. W. Y. Lam, W.
  A. Goddard III, B. Z. Tang, *Polym. Chem.*, 2017, *8*, 1722-1727; (c) J. Yan,
  B. Zheng, D. Pan, R. Yang, Y. Xu, L. Wang, M. Yang, *Polym. Chem.*2015, *6*, 4240-4251; (d) J. Yan, Z.-K. Wang, X.-S. Lin, C.-Y. Hong, H.-J.
  Liang, C.-Y. Pan, Y.-Z. You, *Adv. Mater.* 2012, *24*, 5617-5624; (e) B.
  Saha, K. Bauri, A. Bag, P. K. Ghorai, P. De *Polym. Chem.*, 2016, *7*, 6895-6900; For select photoluminescence reviews, see: (f) S. Zhu, Y. Song, J.
  Shao, X. Zhao, B. Yang, *Angew. Chem., Int. Ed.* 2015, *54*, 14626-14637; (g) J. Mei, N. L. C. Leung, R. T. K. Kwok, J. W. Y. Lam, B. Z. Tang, *Chem. Rev.* 2015, *115*, 11718-11940.

#### WILEY-VCH

### COMMUNICATION

#### COMMUNICATION

The first synthesis of well-defined poly[(substituted methylene-copropenylene)-b-methylene)] terpolymers via borane-initiated copolymerization of arsonium and sulfoxonium ylides is presented. An unexpected light emission phenomenon, due to the isomerization-induced emission of the double bonds of the propenylene units was discovered these non-conjugated in terpolymers.



De Wang<sup>\*[a]</sup> and Nikos Hadjichristidis<sup>\*[b]</sup>

#### Page No. – Page No.

Novel Terpolymers from Borane Initiated Copolymerization of Triphenyl Arsonium and Sulfoxonium Ylides: An Unexpected Light Emission