



In situ generation of redox active peptides driven by selenoester mediated native chemical ligation†

Dnyaneshwar B. Rasale, Indrajit Maity and Apurba K. Das*

Cite this: *Chem. Commun.*, 2014, 50, 11397Received 20th May 2014,
Accepted 29th July 2014

DOI: 10.1039/c4cc03835e

www.rsc.org/chemcomm

Redox active peptides are generated through selenoester mediated native chemical ligation (NCL). Distinct nanostructures, such as nanotubes to nanofibrillar architectures, were observed for self-assembling soft materials.

In nature, complex soft materials are created through hierarchical self-assembly of nanoscale biomolecules.¹ Low molecular weight organic molecules are used in directed self-assembly, which further forms three-dimensional network structures. Various functional groups can be incorporated into the molecular structure² to mimic and develop biological processes in the laboratory. However, rational and universal molecular design remained a challenge to make them suitable for biomaterial applications. Self-assembly of short peptides has received significant attention because of their vast applications in drug delivery,³ tissue engineering⁴ and supramolecular electronics.⁵ Several physical stimuli,⁶ such as pH, temperature, light and enzymes, are used to explore peptide self-assembly.⁷

Redox active peptide self-assembly still remains an area of interest because of its potential application in drug delivery. Redox reactions are prevalent in nature to regulate various biological functions. Redox active⁸ nature mimicking dynamic self-assembly could be achieved using chemoselective native chemical ligation (NCL) reactions. Peptide self-assembly could be explored through native chemical ligation reaction because (i) this method is orthogonal, (ii) self-assembly through NCL reaction is particularly interesting for the development of controlled dynamic self-assembly and (iii) the presence of free sulfhydryl groups in peptides that can offer multiple applications after NCL reactions.

NCL reactions are the most revolutionary method for the complete or semi synthesis of proteins.⁹ In addition to its useful application in protein synthesis, NCL reactions can be used as effective and efficient methods for the development of soft biomaterials. Collier *et al.* reported an excellent method for the

stiffening of a hydrogel *via* thioester mediated NCL reaction.¹⁰ Messersmith and coworkers described a strategy that forms covalently cross-linked polymer hydrogels.¹¹ In general, the conceptual approach for NCL is based on the reaction between two unprotected peptides, one bearing C-terminal thioester and another N-terminal cysteine residue based peptide. The sulfhydryl group of N-terminal cysteine residue undergoes *trans*-thioesterification with C-terminal thioester¹² and forms a thioester-linked intermediate. A thioester-linked intermediate simultaneously and rapidly undergoes intramolecular S → N acyl transfer to form a native amide bond.¹³

Inspired by this chemoselective ligation reaction,¹⁴ our objective was to develop a simple and efficient approach that can direct dynamic peptide self-assembly. To achieve this goal, we have synthesized compounds 1–4 with an N-terminal capped with an aromatic naphthalene-2-methoxycarbonyl (Nmoc) group. The C-terminals of 1–4 are protected with phenyl selenoester, which can readily undergo NCL reaction at room temperature with N-terminal cysteine and N-terminal cysteine based peptide Cys-Gly. Selenoesters are efficient acyl donors and are easier to synthesise than the corresponding thioesters because of the better leaving group characteristics of a selenolate *versus* a thiolate.¹⁵

L-Cysteinylglycine, a pro-oxidant, is generated from extracellular glutathione through the catalytic activity of an enzyme γ -glutamyltransferase.¹⁶ Cys-Gly is known to be a highly reactive metabolite that is directly related to induce the oxidative stress¹⁷ in cells. Lin *et al.* reported that higher cysteine glycine levels were marginally associated with an increased risk of breast cancer in women.¹⁸ Here, we have used Cys-Gly dipeptide in the development of dynamic peptide self-assembly through the NCL reaction. The selenoester easily undergoes NCL reaction with Cys-Gly dipeptide, which could be an assay in further clinical research.

The NCL reaction proceeds through the thioester-linked intermediate where acyl transfers from Se → S¹⁵ are followed by intramolecular S → N acyl transfer to give a peptide bond (Fig. 1). Compounds 1–4 (20 mmol L⁻¹) were dissolved in 100 μ L of ethanol and Cys or Cys-Gly (20 mmol L⁻¹) was dissolved in 900 μ L of phosphate buffer (pH = 8, 100 mmol L⁻¹). 900 μ L of Cys (C) or

Department of Chemistry, Indian Institute of Technology Indore, Indore 452017, India. E-mail: apurba.das@iiti.ac.in

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c4cc03835e




Fig. 1 Selenoester mediated native chemical ligation. Ligated products were formed upon the NCL of selenoesters **1–4** with Cys-Gly and cysteine at pH ~ 8. NmYCG self-assembled in its reduced form while oxidized NmFC(SePh)G (sulfur linked with selenophenol) and (NmFC)₂ self-assembled to form self-supporting soft materials.

Cys-Gly (CG) was added to the reaction vial containing compounds **1** to **4** (entries 1–8). The reaction vial was left undisturbed, and self-supporting gels were observed after 1 h of reaction for entries **1**, **2** and **6**. The ligation reactions of Nmoc (Nm) capped amino acid based selenoesters with Cys or Cys-Gly was monitored with reverse phase high performance liquid chromatography (HPLC), and the corresponding products were analyzed by ESI-MS (Fig. 2C and Fig. S4–S30, ESI⁺). We also monitored the visual changes of solution **1** upon mixing with dipeptide Cys-Gly in phosphate buffer (Fig. 2B). The gels were stable in the pH range of 4–10, and the minimum gelation concentration for NmYCG, NmFC(SePh)G and (NmFC)₂ gels was 5 mmol L⁻¹. Gel melting temperature (T_{gel}) was also measured by the test tube inversion method at different concentrations of gelators. T_{gel} was observed as 70 °C, 71 °C and 65 °C for NmYCG, NmFC(SePh)G and (NmFC)₂ gels, respectively, at 20 mmol L⁻¹ (Table S1, ESI⁺) concentration.

The self-assembly of small peptides bearing N-terminal naphthalene moieties has been reported by several groups.¹⁹ Compound **1** gives >99% ligated peptide with Cys-Gly and gives >99% with cysteine (Table 1). Thus, NCL reaction with selenoesters is the easiest and simplest way to synthesise peptides. However, the thioesters with similar amino acid sequences (compounds **5–8**) yielded poor conversion (Fig. S2 and S3, ESI⁺) of peptides (Table S2, ESI⁺) and were unable to form gel under similar conditions. The control experiment with Nmoc capped valine selenoester **3** with alanine confirms the requirement of a C-terminal cysteine group in ligation reaction with selenoester (ESI⁺).

Typically, NCL reactions were carried out in the presence of a reductant such as tris(2-carboxyethyl)phosphine (TCEP) and dithiothreitol (DTT). TCEP or DTT helps to avoid the formation of disulfides. Surprisingly, we have not used any reductant for the reaction of compound **1** with Cys-Gly (entry 1). The reduced form of NmYCG was observed after 16 h in aerobic conditions (Fig. S4, ESI⁺).²⁰




Fig. 2 (A) Dynamic self-assembly of (NmFC)₂. NCL reaction of compound NmFSePh **2** with cysteine gives NmFC under inert atmosphere and subsequently formed dynamic (NmFC)₂ gel upon exposure to air. (B) Visual changes of reaction progress initially mixing of compound NmYSePh **1** (20 mmol L⁻¹) with Cys-Gly (20 mmol L⁻¹) in phosphate buffer at pH 8. (i) Milky white solution at 5 min, (ii) turbid at 10 min, (iii) colorless solution at 15 min, (iv) colorless viscous solution at 30 min and (v) self-supporting gel formed after 60 min. (C) HPLC trace analysis of a representative ligation of compound **1** with Cys-Gly with corresponding ESI-MS of ligated product after 1 h and **2** with Cys-Gly and cysteine after 1 h with corresponding ESI-MS of ligated products.

Table 1 Native chemical ligation under inert as well as air conditions

Entry	Substrate	CG ^a and C ^b	Conversion in inert atm. ^c [%]	Conversion in air ^c [%]	Gel ^d
1	1	CG	> 99 NmYCG	> 99 NmYCG	G
2	2	CG	22.64/76 ^e NmFCG/ NmFC(SePh)G	77.36 NmFC(SePh)G	G
3	3	CG	> 99 NmLCG	> 99 (NmLCG) ₂	S
4	4	CG	65.79 NmVCG	63.35 (NmVCG) ₂	S
5	1	C	> 99 NmYC	95.09 (NmYC) ₂	S
6	2	C	94.31 NmFC	84.90 (NmFC) ₂	G
7	3	C	> 99 NmLC	> 99 (NmLC) ₂	S
8	4	C	> 99 NmVC	79.28 (NmVC) ₂	S

^a CG = Cys-Gly dipeptide. ^b C = cysteine. ^c The percentage conversions were calculated by integrating the peak areas from HPLC. ^d G = gel, S = solution, Nm = Nmoc. ^e Entry 2 yield in inert atm.: the combined yield for NmFCG and NmFC(SePh)G is 98.64% (22.64% + 76%).

However, entries **3–8** showed exactly reverse behavior to entry **1**. Oxidized forms of NCL products were observed for entries **3–8** in similar conditions to the NCL reaction of entry **1** (Table 1). A self-supporting gel for entry **1** was observed with 99% synthesized peptide NmYCG. Another self-supporting gel for entry **6** was also observed for the newly synthesized 84.9% oxidized peptide (NmFC)₂.

However, in the case of entry 2, a dipeptide Cys-Gly reacted with compound 2 and formed the corresponding tripeptide, NmFCG. NmFCG further reacted with cleaved selenophenol and formed a sulfur-selenium bond (Fig. 1). The resulting product NmFC(SePh)G turned into a self-supporting gel. Our data indicate that reduced and oxidized forms of ligated peptides can self-assemble and lead to self-supporting gels.²¹ The self-assembly of ligated products drives self-selection and self-organization into the reduced and oxidized form of peptides.

The disassembly phenomenon of (NmFC)₂ was observed using a reductant TCEP (40 mmol L⁻¹) after 2 h, which further explores gelators as versatile candidates for drug delivery (Fig. 2A). The dynamic gel-sol reversal behaviour of (NmFC)₂ was monitored by HPLC and rheology measurements (Fig. 3A and Fig. S37, ESI[†]). The HPLC analysis of (NmFC)₂ after the addition of TCEP showed an 87% conversion of NmFC after 6 h of reaction. The rheology experiment showed that the gel starts to break after 1 h of TCEP addition. Gel formation for (NmFC)₂ upon NCL reaction was indicated by time sweep experiment (Fig. S36, ESI[†]). The disulfide reduction leads to the gel-sol transition of (NmFC)₂, which was also monitored with an oscillatory time sweep experiment after the addition of TCEP (Fig. S37, ESI[†]).

Circular dichroism (CD) was used to elucidate peptide conformation in a gel phase medium (Fig. 3B). The CD spectrum of NmYCG (entry 1) shows a positive peak at 208 nm and a negative peak at 221 nm, corresponding to the coexistence of a random-coil and β -sheet conformation.²² However, CD spectra of NmFC(SePh)G and (NmFC)₂ in gel state show characteristics of a twisted conformation. The two negative peaks at 222 nm and 205 nm indicate the twisted conformation of self-assembled peptides, which may be attributed to the supramolecular ordering of peptide molecules.²³ The CD spectrum of gel (NmFC)₂ upon treatment with TCEP indicates the change in the conformation of the reduced disassembled peptide (Fig. S38, ESI[†]). Fourier transform infrared spectroscopy (FTIR) was also used to support the secondary structures of self-assembled peptides (Table S3, ESI[†]). The ligated peptide NmYCG shows peaks at 1640 cm⁻¹ and 1688 cm⁻¹, which correspond to the turn type structures.

Fluorescence spectra were recorded to determine the molecular arrangement of NmYCG, NmFC(SePh)G and (NmFC)₂ in gel phase. The characteristic emission peak for naphthalene

double rings and aromatic side chains appears in the range of 310–330 nm in solution (Fig. S40, ESI[†]). NmYCG gel showed an emission peak at 337 nm and a broad emission peak at 461 nm, indicating efficient overlapping of naphthalene double rings and higher order π - π stacking aggregation in gel phase medium (Fig. S41, ESI[†]). Similarly, NmFC(SePh)G and (NmFC)₂ gels showed emission peaks at 337 nm and 334 nm, respectively. The broad emission peak at 465 nm suggests a higher order aggregate state for NmFC(SePh)G gel (Fig. S41, ESI[†]). Here, the aromatic naphthalene ring plays a pivotal role in the self-assembly process *via* π - π stacking interactions.

Wide angle powder X-ray diffraction studies were performed to examine the self-assembly of NmYCG, NmFC(SePh)G and (NmFC)₂ in gel phase (Fig. S42–S44, ESI[†]). The diffraction peak appeared at $2\theta = 18.13^\circ$, 19.53° , and 17.99° with corresponding d spacing of 4.88 Å, 4.5 Å and 4.9 Å for NmYCG, NmFC(SePh)G, and (NmFC)₂ dried gels, respectively. These values indicate the spacing between two peptides within the β -sheet structures. The reflection peak appeared at $2\theta = 23.14^\circ$, 24.46° , and 24.16° with the corresponding d spacing values of 3.84 Å, 3.64 Å, and 3.68 Å for dried gels of NmYCG, NmFC(SePh)G and (NmFC)₂, respectively.²⁴ These values clearly show the π - π stacking interaction among the self-assembled peptides. The self-assembly mechanism is shown in Fig. S31 (ESI[†]).

A time resolved fluorescence study was employed to investigate the higher order aggregation of the fluorophore groups (Nmoc) of NmYCG, NmFC(SePh)G and (NmFC)₂ gels. We measured fluorescence decay traces of the gels at an excitation of 376 nm, and the emission was monitored at 470 nm. The average lifetime of 1.14 ns for NmYCG, 3.39 ns for NmFC(SePh)G and 1.06 ns for (NmFC)₂ were observed (Table S4 and Fig. S45, ESI[†]). The average fluorescence lifetime of the gel samples indicates a denser aggregated nanofibrous network in the gel state.

Transmission electron microscopy (TEM) was used to characterize the morphology of the self-assembled architectures in gel phase. The nanotubular²⁵ structures were observed for a gel formed by NmYCG (entry 1) with an average diameter of 150 nm. The average inner diameter of nanotubes was observed to be 20 nm in the TEM image (Fig. 4B). However, gels formed by NmFC(SePh)G (entry 2) and (NmFC)₂ (entry 6) showed entangled nanofibrillar networks with diameters ranging from 10 to 60 nm (Fig. S47, ESI[†]). The atomic force microscopy (AFM) studies of the gels also showed nanofibrillar morphology (Fig. 4). The NmYCG gel exhibited highly aligned nanostructures in gel phase medium with a height of 3 to 6 nm (Fig. 4A). However, the gel formed by NmFC(SePh)G showed elongated thin nanofibrous morphology with an average width of 2 nm. The AFM analysis of (NmFC)₂ indicated that nanofibers originated from thick fibers. The AFM result for gel-sol transition indicates the breaking of nanofibers, which leads to the disassembly of the self-assembled gel (NmFC)₂ (Fig. S46, ESI[†]).

In summary, we have demonstrated selenoester mediated native chemical ligation to explore dynamic redox active peptide self-assembly. Selenoester mediated native chemical ligation is a rapid ligation process over thioester mediated native chemical ligation. Cysteine and Cys-Gly peptides have provided mechanistic




Fig. 3 (A) Real time HPLC analysis for (NmFC)₂ formation upon exposure to air followed by the addition of TCEP at 90% showed conversion back to the reduced form of NmFC. (B) CD spectra of self-assembled peptides (i) NmYCG, (ii) NmFC(SePh)G and (iii) (NmFC)₂ (concentration = 2 mmol L⁻¹) formed upon NCL reaction at pH ~ 8.




Fig. 4 AFM images indicate the nanofibrillar structures of the self-assembled gels of (A) NmYCG, (C) NmFC(SePh)G and (D) (NmFC)₂. (B) TEM image indicates the nanotubular structure of the self-assembled gels NmYCG with an inner diameter of 20 nm and outer diameter of 150 nm.

insight into the NCL driven self-assembly process. We have also shown the redox active dynamic peptide gels, which are formed *via* the oxidation and reduction of the Nmoc-protected peptide synthesized *via* NCL reactions. Here, gel–sol transition is highly dependent on the oxidation and reduction of cysteine and cysteine based peptides. Peptides are self-assembled *via* hydrogen bonding and π – π stacking interactions, and peptides are redox active in nature. Here, selenoester mediated NCL reactions are responsible for nanofibrillar structure.

AKD sincerely acknowledges CSIR, New Delhi, India, for financial support. DBR and IM are indebted to CSIR, New Delhi, India, for their fellowships. We thank SAIF, IITB and SAIF, NEHU, Shillong for the assistance of EM facility.

Notes and references

- G. M. Whitesides and B. Grzybowski, *Science*, 2002, **295**, 2418.
- R. V. Ulijn and A. M. Smith, *Chem. Soc. Rev.*, 2008, **37**, 664.
- M. M. Stevens and J. H. George, *Science*, 2005, **310**, 1135.
- J. Kopecek and J. Yang, *Angew. Chem., Int. Ed.*, 2012, **51**, 7396.
- J. D. Tovar, *Acc. Chem. Res.*, 2013, **46**, 1527.
- (a) A. Ghosh, M. Haverick, K. Stump, X. Yang, M. F. Tweedle and J. E. Goldberg, *J. Am. Chem. Soc.*, 2012, **134**, 3647; (b) R. P. Nagarkar, R. A. Hule, D. J. Pochan and J. P. Schneider, *J. Am. Chem. Soc.*, 2008, **130**, 4466; (c) I. Hwang, W. S. Jeon, H. J. Kim, D. Kim, H. Kim, N. Selvapalam, N. Fujita, S. Shinkai and K. Kim, *Angew. Chem., Int. Ed.*, 2007, **119**, 214; (d) A. M. Kloxin, A. M. Kasko, C. N. Salinas and K. S. Anseth, *Science*, 2009, **324**, 59; (e) M. O. Guler and S. I. Stupp, *J. Am. Chem. Soc.*, 2007, **129**, 12082.
- E. Gazit, *Chem. Soc. Rev.*, 2007, **36**, 1263.
- (a) M. Ikeda, T. Tanida, T. Yoshii and I. Hamachi, *Adv. Mater.*, 2011, **23**, 2819; (b) A. J. Wain, H. N. L. Do, H. S. Mandal, H. B. Kraatz and F. Zhou, *J. Phys. Chem. C*, 2008, **112**, 14513.
- (a) E. C. B. Johnson and S. B. H. Kent, *J. Am. Chem. Soc.*, 2006, **128**, 6640; (b) P. E. Dawson, T. W. Muir, I. Clark-Lewis and S. B. H. Kent, *Science*, 1994, **266**, 776; (c) S. B. H. Kent, *Chem. Soc. Rev.*, 2009, **38**, 338; (d) Q. Wan, J. Chen, Y. Yuan and S. J. Danishefsky, *J. Am. Chem. Soc.*, 2008, **130**, 15814.
- J. P. Jung, J. L. Jones, S. A. Cronier and J. H. Collier, *Biomaterials*, 2008, **29**, 2143.
- B. H. Hu, J. Su and P. B. Messersmith, *Biomacromolecules*, 2009, **10**, 2194.
- (a) Y. Shin, K. A. Winans, B. J. Backes, S. B. H. Kent, J. A. Ellman and C. R. Bertozzi, *J. Am. Chem. Soc.*, 1999, **121**, 11684; (b) S. Batjargal, Y. J. Wang, J. M. Goldberg, R. F. Wissner and E. J. Petersson, *J. Am. Chem. Soc.*, 2012, **134**, 9172; (c) M. A. Shmilovici, K. Mandal, Z. P. Gates, N. B. Phillips, M. A. Weiss and S. B. H. Kent, *J. Am. Chem. Soc.*, 2013, **135**, 3173.
- (a) J. Chen, Q. Wan, Y. Yuan, J. Zhu and S. J. Danishefsky, *Angew. Chem., Int. Ed.*, 2008, **47**, 8521; (b) J. Hentschel, E. Krause and H. G. Borner, *J. Am. Chem. Soc.*, 2006, **128**, 7722; (c) K. M. Cergol, R. E. Thompson, L. R. Malins, P. Turner and R. J. Payne, *Org. Lett.*, 2014, **16**, 290; (d) J. Dheur, N. Ollivier, A. Vallin and O. Melnyk, *J. Org. Chem.*, 2011, **76**, 3194; (e) P. Siman, S. V. Karthikeyan and A. Brik, *Org. Lett.*, 2012, **14**, 1520.
- (a) G. A. Lemieux and C. R. Bertozzi, *Trends Biotechnol.*, 1998, **16**, 506; (b) E. C. Rodriguez, K. A. Winans, D. S. King and C. R. Bertozzi, *J. Am. Chem. Soc.*, 1997, **119**, 9905; (c) M. J. Weissenborn, R. Castangia, J. W. Wehner, R. Sardzik, T. K. Lindhorst and S. L. Flitsch, *Chem. Commun.*, 2012, **48**, 4444; (d) G. M. Fang, J.-X. Wang and L. Liu, *Angew. Chem., Int. Ed.*, 2012, **124**, 10493.
- T. Durek and P. F. Alewood, *Angew. Chem., Int. Ed.*, 2011, **50**, 12042.
- M. J. Dirx, P. A. Van den Brandt, R. A. Goldbohm and L. H. Lumey, *Cancer*, 2003, **97**, 46.
- N. Couto, N. Malys, S. J. Gaskell and J. Barber, *J. Proteome Res.*, 2013, **12**, 2885.
- J. Lin, J. E. Manson, J. Selhub, J. E. Buring and S. M. Zhang, *Cancer Res.*, 2007, **67**, 11123.
- (a) Z. Yang, G. Liang, L. Wang and B. Xu, *J. Am. Chem. Soc.*, 2006, **128**, 3038; (b) L. Chen, S. Revel, K. Morris, L. C. Serpell and D. J. Adams, *Langmuir*, 2010, **26**, 13466; (c) H. Wang, C. Yang, M. Tan, L. Wang, D. Konga and Z. Yang, *Soft Matter*, 2011, **7**, 3897; (d) S. K. M. Nalluri and R. V. Ulijn, *Chem. Sci.*, 2013, **4**, 3699.
- S. Singh, F. Topuz, K. Hahn, K. Albrecht and J. Groll, *Angew. Chem., Int. Ed.*, 2013, **52**, 3000.
- X. Miao, W. Cao, W. Zheng, J. Wang, X. Zhang, J. Gao, C. Yang, D. Kong, H. Xu, L. Wang and Z. Yang, *Angew. Chem., Int. Ed.*, 2013, **52**, 7781.
- C. S. Chen, T. J. Ji, X. D. Xu, X. Z. Zhang and R. X. Zhuo, *Macromol. Rapid Commun.*, 2010, **31**, 1903.
- (a) E. F. Banwell, E. S. Abelardo, D. J. Adams, M. A. Birchall, A. Corrigan, A. M. Donald, M. Kirkland, L. C. Serpell, M. F. Butler and D. N. Woolfson, *Nat. Mater.*, 2009, **8**, 596; (b) S. G. Tarasov, V. Gaponenko, O. M. Z. Howard, Y. Chen, J. J. Oppenheim, M. A. Dyba, S. Subramaniam, Y. Lee, C. Michejda and N. I. Tarasova, *Proc. Natl. Acad. Sci. U. S. A.*, 2011, **108**, 9798; (c) L. Qin, P. Duan, F. Xie, L. Zhang and M. Liu, *Chem. Commun.*, 2013, **49**, 10823.
- (a) S. Basak, J. Nanda and A. Banerjee, *Chem. Commun.*, 2013, **49**, 6891; (b) I. Maity, D. B. Rasale and A. K. Das, *Soft Matter*, 2012, **8**, 5301.
- A. K. Das, R. Collins and R. V. Ulijn, *Small*, 2008, **4**, 279.