This article was downloaded by: [Stanford University Libraries] On: 16 May 2012, At: 04:09 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information: http://www.tandfonline.com/loi/gmcl16

Study of New Liquid Crystal Materials (II): Synthesis and Mesomorphic Properties of Alkoxymethylene Substituted Phenyl Cyclohexanecarboxylates

Teruo Kitamura^a, Akio Mukoh^a, Susumu Era^a & Tsunenori Fujii^b

^a Hitachi Research Laboratory, Hitachi Ltd., 4026 Kuji, Hitachi, Ibaraki, Japan, 319-12

^b Central Research Laboratory, Kanto Chemical Co., Inc. 2048 Inari, Soka, Saitama, Japan, 340

Available online: 20 Apr 2011

To cite this article: Teruo Kitamura, Akio Mukoh, Susumu Era & Tsunenori Fujii (1984): Study of New Liquid Crystal Materials (II): Synthesis and Mesomorphic Properties of Alkoxymethylene Substituted Phenyl Cyclohexanecarboxylates, Molecular Crystals and Liquid Crystals, 112:3-4, 319-324

To link to this article: <u>http://dx.doi.org/10.1080/00268948408071842</u>

PLEASE SCROLL DOWN FOR ARTICLE

Full terms and conditions of use: <u>http://www.tandfonline.com/page/terms-and-conditions</u>

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden.

The publisher does not give any warranty express or implied or make any representation that the contents will be complete or accurate or up to date. The accuracy of any instructions, formulae, and drug doses should be independently verified with primary sources. The publisher shall not be liable for any loss, actions, claims, proceedings, demand, or costs or damages whatsoever or howsoever caused arising directly or indirectly in connection with or arising out of the use of this material.

Mol. Cryst. Liq. Cryst., 1984, Vol. 112, pp. 319-324

0026-8941/84/1124-0319/\$15.00/0 © 1984 Gordon and Breach, Science Publishers, Inc. and OPA Ltd. Printed in the United States of America

Study of New Liquid Crystal Materials (II): Synthesis and Mesomorphic Properties of Alkoxymethylene Substituted Phenyl Cyclohexanecarboxylates

TERUO KITAMURA, AKIO MUKOH, SUSUMU ERA

Hitachi Research Laboratory, Hitachi Ltd. 4026 Kuji, Hitachi, Ibaraki, Japan 319-12

and

TSUNENORI FUJII

Central Research Laboratory, Kanto Chemical Co., Inc. 2048 Inari, Soka, Saitama, Japan 340

(Received July 20, 1984)

The properties of alkoxymethylene-substituted-phenyl alkylcyclohexanecarboxylates are described. Such phenyl cyclohexanecarboxylates exhibit either a monotropic or an enantiotropic nematic phase. Their clearing points were lower than those of alkoxysubstituted-phenyl alkylcyclohexanecarboxylates, an effect considered to be due to the flexibility of the alkoxymethylene groups.

Almost all nematic mesogens have a hard-rod core and two terminal groups.¹ We have described nematic mesogens which are alkoxymethylene-substituted-phenyl alkylcyclohexanes (I).² These species exhibited monotropic nematic or smectic phases, and their clearing points were lower than those of alkoxy-substituted-phenyl cyclohexanes.³ This indicated that introduction of alkoxymethylene groups into the mesogens had a remarkable influence on their properties. It is interesting at this point to investigate the properties of alkoxymethylene derivatives having another hard-rod core.



FIGURE 1 Synthetic route.

In this paper, we deal with alkoxymethylene-substituted-phenyl alkylcyclohexanecarbonxylates (II), and compare their properties with those of alkoxyl-substituted-phenyl alkylcyclohexanecarboxylates (III).⁴

The alkoxymethylene series (II) was prepared as shown in Figure 1. 4-Alkoxymethylphenols (n = 1) were prepared from 4-formylphenol; 4-alkoxyethylphenol (n = 2) was prepared from 2-phenylethanol. 4-Alkoxypropylphenol (n = 3) and 4-alkoxypentyl phenol (n = 5) were prepared from appropriate phenylalkyl bromides. These phenols were esterified with appropriate *trans*-4-alkylcyclohexane-1-carboxylic acids.⁵ Details of the procedures will be reported elsewhere.

$$R - H - (CH_2)_n OR' \qquad (I)$$

$$R - H - CO_2 - (CH_2)_n OR' \qquad (II)$$

$$R - H - CO_2 - OR' \qquad (II)$$

$$(R, R' : -alkyi)$$

The transition temperatures of the alkoxymethylene series (II) are shown in Table I. These species exhibit either a monotropic or an enantiotropic nematic phase. Although the phenylcyclohexane series $(I)^2$ exhibited a smectic phase, in series (II), the smectic phase was not observed, even for long alkyl chains. The first enantiotropic transition was observed at n = 5 for this series (No. 18, 19). These are the first examples to exhibit enantiotropic transitions in alkoxymethylene substituted mesogens.

The members of series (II) generally show lower transition temperatures than the alkoxyphenyl esters (III), with clearing points below 40° C. In particular, the clearing points were below -10° C at n = 1. The examples shown in Figure 2 illustrate the magnitude of the effect of terminal groups on clearing points. The compounds are all similar in length, but the three alkoxymethylene species (series II) have lower

T,	4	B	L	E	I

Transition Temperatures of

~	28-1			- <u>2</u> ·n-y 2	/+1
NQ.	n	x	У	Transition C−N∕I	Temp.(℃) N – I
1	1	3	1	27	(18)
2	1	3	2	19	(-11)
3	1	3	3	4	(-15)
4	1	3	4	1	(-22)
5	1	3	5	4	(-15)
6	1	3	6	12	(-24)
7	1	3	7	13	(-12)
8	1	4	1	39	(-13)
9	1	5	1	53	(-34)
10	1	5	3	6	(4.5)
11	1	6	1	43	(29)
12	1	7	1	49	(34)
13	1	7	2	18	(19)
14	1	7	3	19	(14)
15	2	5	1	20	(11)
16	2	5	2	30	(15)
17	3	5	1	42	(32)
18	5	3	1	27	29
19	5	5	1	32	38

 C_xH_{2x+1} - H $-CO_2$ - O - $(CH_2)_nOC_yH_{2y+1}$

(): Monotropic Transition



FIGURE 2 Transition temperatures vs terminal groups.

clearing points than the alkoxy species (series III). This result agrees approximately with that previously reported for the phenylcyclohexane series.²

Figure 3 shows a plot of the clearing points as a function of the length of the terminal chain. In the alkoxy series (III),⁴ the relationship between clearing points and chain length had a pattern generally observed for nematic mesogens.⁶ On the other hand, the alkoxymethylene series (II) did not show a similar behavior; the clearing points decreased steeply from y = 1 to y = 2 and then showed a general alternating but diverging pattern. These relationships illustrate the difference in behavior between alkoxymethylene groups and alkoxy groups in mesogenic molecules. One reason for this is attributed to the degree of flexibility in these groups. The flexibility of alkoxymethylene groups is considered to be larger than that of alkoxy groups because free rotation about the aliphatic C–O bond is easier than that about the C–C bond.⁷ The alkoxymethylene group has two



FIGURE 3 Clearing points vs y-number of terminal chain.

aliphatic C-O bonds and the alkoxy group has one. Conformational changes based on such free rotations are illustrated below.



The methoxymethyl group (b) has two C-O bonds, but rotation about $O-C^3$ does not affect the conformational situation. Therefore, the degree of conformational effect in (b) is the same as that in the alkoxy group (a). However, when the y-number is 2 or above, rotation of $O-C^3$ becomes significant as in (c), and the degree of conformational

effect becomes higher. Differences in the conformational possibilities such as those given above may explain the differences in behaviour shown in Figure 3.

From these results, it was concluded that the alkoxymethylene group has a remarkable influence on the mesomorphic properties, particularly the phase transition temperatures. Studies to examine the effects on other properties, including viscosity and birefringence, are now being carried out.

References

- 1. D. Demus, H. Demus, and H. Zaschke, *Flussige Kristalle in Tabellen* (VEB Deutscher Verlag, Leipzig, 1974).
- 2. T. Kitamura, A. Mukoh, and T. Fujii, Mol. Cryst. Liq. Cryst. 108, 333 (1984).
- R. Eidenschink, D. Erdmann, J. Krause, and L. Pohl, paper presented at the 8th Int. National Liq. Cryst. Conference, Kyoto (1980).
- 4. H. J. Deutscher, B. Laaser, W. Dolling, and H. Schubert, J. prakt. Chem. 320, 191 (1978).
- 5. H. Schubert, V. Uhlig, and R. Dehne, Z. Chem. 12, 219 (1972).
- G. W. Gray, Molecular Structure and the Properties of Liquid Crystals (Academic Press, London, 1962).
- 7. H. Azumi, Quantum Chemistry (Baifuukan, Tokyo, 1951), p. 221.