Journal of Alloys and Compounds 580 (2013) S144-S148

Contents lists available at SciVerse ScienceDirect

Journal of Alloys and Compounds

journal homepage: www.elsevier.com/locate/jalcom

Hydrogen absorption study of high-energy reactive ball milled Mg composites with palladium additives



South African Institute for Advanced Materials Chemistry, Faculty of Natural Sciences, University of the Western Cape, Private Bag X17, Bellville 7535, South Africa

ARTICLE INFO

Article history: Available online 30 January 2013

Keywords: Composite materials Magnesium hydride Mechanochemical processing Kinetics X-ray diffraction

ABSTRACT

Hydrogenation behaviour, structure, morphology and dehydrogenation/re-hydrogenation performances of Mg–Pd nanocomposites prepared by high-energy reactive ball milling in H₂ (HRBM) of Mg in the presence of amorphous and crystalline Pd black (0.1–5 wt.%) were studied. Improvements of hydrogenation kinetics during HRBM were observed only for the materials prepared using crystalline Pd black. The obtained nanocomposites were characterised by modest improvements in their dehydrogenation and re-hydrogenation performances associated with the formation of Mg–Pd intermetallides.

© 2013 Elsevier B.V. All rights reserved.

1. Introduction

Over the last two decades, numerous studies were undertaken in an effort to enhance Mg hydrogenation rates [1]. One of the most promising approaches was found to be mechanical milling (MM). The products of MM often exhibit unusual physical and chemical properties and enhanced reactivity, in particular with respect to hydrogen. The enhancements are especially pronounced for Mg-based materials where nanostructuring and surface modification result in dramatic improvements in the hydrogenation kinetics [2]. Additional improvement of the hydrogenation performances of Mg was observed upon introduction of catalytic additives, including transition metals, alloys and intermetallic compounds [3–9]. High energy reactive ball milling (HRBM) of Mg with catalytic additives in H₂ has been proven to be the most efficient way to further improve the re-hydrogenation process [6,7].

The catalytic effect of the metallic additives, most probably, relates to facilitation of the reactions of hydrogen transfer, including dissociative chemisorption and associative desorption of H_2 molecules. One of the most efficient catalysts for these processes is palladium. Indeed, Pd-coated magnesium thin films were shown to be characterised by significantly improved kinetics of hydrogenation of Mg and dehydrogenation of the formed MgH₂ [10–12]. At the same time, HRBM of Mg with Pd additive was shown to inhibit both hydrogenation and re-hydrogenation of Mg [13].

In this work we report about investigation of HRBM of Mg in the presence of a Pd black catalyst.

2. Experimental

Mg powder (–20 \ldots +100 mesh, 99.8%; metal basis) was purchased from Alfa-Aesar.

Pd black was prepared as follows. PdCl₂:xH₂O (1.0 g) and concentrated HCl (1 mL) were dissolved in 100 mL of the de-ionised water. The solution was heated to ~70 °C under vigorous stirring, followed by drop-wise addition of 3–4 mL of N₂H₄:xH₂O, or 10 g/L aqueous solution of NaH₂PO₂, which resulted in the formation of black precipitates. The reduction of Pd black was driven to completion with an excess of N₂H₄, or NaH₂PO₂. The deposit was collected by gravity filtration, washed with copious quantities of water, and dried at 120 °C for 12 h in air. XRD studies confirmed that Pd black obtained using N₂H₄:xH₂O as a reducing agent was crystal-line, and that prepared by reduction with NaH₂PO₂ was amorphous, in accordance with literature data and our earlier observations [14].

The Mg-xPd mixtures (x = 0.1,0.5,1,2 and 5 wt.%) containing crystalline (reduced with N₂H₄) and amorphous (reduced with NaH₂PO₂) Pd black, were ball milled in H₂ using a Retsch PM 100 ball mill and 220 mL hardened steel vial with pressure-temperature monitoring system (Evico Magnetics GmbH). The milling was performed with a ball-to-powder-ratio of 40:1 (82 steel balls, 10 mm in diameter) at 500 rpm, for 6 h in total. Prior to the milling, the vial was evacuated followed by filling with H₂ gas ($P \sim 30$ bar) supplied from a metal hydride hydrogen storage and supply unit on the basis of AB₅-type alloy. The hydrogen pressure in the vial was kept above 20 bar by refilling each time ($P \sim 30$ bar) when the pressure dropped below this value. When the vial temperature approached 70 °C, the milling was stopped and resumed again after cooling the vial to room temperature. The amount of hydrogen absorbed in the sample was calculated starting from actual pressure-temperature values (with the correction to hydrogen compression factor) and plotted versus milling time.

A High Resolution Transmission Electron Microscope (HRTEM), FEI Tecnai 30, operating at 120 kV was used to analyze the morphology of the as-prepared and re-hydrogenated samples. The sample holder was cooled to \sim 90 K.

XRD studies were performed using Bruker AXS D8 Advance diffractometer with Cu K α radiation ($\lambda_1 = 1.5406$ Å, $\lambda_2 = 1.5444$ Å, $\lambda_2/\lambda_1 = 0.5$). The Bragg angle range was $2\theta = 20-90^\circ$, and scan rate was $1.2^\circ/\text{min}$ with a step size of 0.02°. The collected XRD data were refined by Rietveld whole-profile refinement using CSAS software [15], where the peak shapes were described using the Thompson-Cox-Hastings pseudo-Voight-type function (CW profile function 2). A standard α -Al₂O₃ sample was used for the determination of the instrumental contribution into peak profile







^{*} Corresponding author. Tel.: +27 21 959 9314; fax: +27 21 959 9312. *E-mail address:* mlototskyy@uwc.ac.za (M. Lototskyy).

^{0925-8388/\$ -} see front matter @ 2013 Elsevier B.V. All rights reserved. http://dx.doi.org/10.1016/j.jallcom.2013.01.086

Composite	mposite Maximum H capacity (wt.% H)		Time of 90% hydrogenation (min)		TDS peak ^b (°C)
	HRBM	Re-hydrogenation ^a	HRBM	Re-hydrogenation ^a	
Mg	7.69	3.41	221	110	375
Mg-0.1Pd	6.42	-	460	-	-
Mg-0.5Pd	7.10	5.13	113	26	350
Mg-2Pd	7.65	4.88	218	38	341
Mg-5Pd	7.59	5.56	162	52	345

Table 1		
Characteristics of HRBM Mg and Mg	-Pd composites prepared	l using crystalline Pd black.

^a 15 bar H₂/230 °C, after TDS of the re-hydrogenated material.

^b For the re-hydrogenated sample.



Fig. 1. H absorption during HRBM of Mg with amorphous (A) and crystalline (B) Pd black.

parameters. During refinement, Gaussian profile parameters (GU, GV and GW) were fixed (kept the same as for the Al_2O_3 standard), and only two Lorentzian profile parameters were refined, LX (size broadening) and LY (strain broadening).¹ The refinements yielded lattice periods of the constituent phases, as well as estimations of their abundances and crystalline sizes. The latter were calculated using the formula [15]:

$$D_V = \frac{18,000 \, K\lambda}{\pi X} \tag{1}$$

where D_V is a volume-weighted crystallite size, K is the Scherrer constant (assumed to be equal to 1), X is a Lorentzian profile parameter LX.

Dehydrogenation and re-hydrogenation performances of the materials after HRBM were studied using a Sieverts-type volumetric setup. 200 mg of the sample powder was loaded into the reactor which, together with the measurement system, was further evacuated to <10⁻⁴ mbar. Thermal desorption measurements (TDS) were carried out by heating the reactor at a heating rate of 5 °C/min from 25 to 460–470 °C under dynamic vacuum conditions; the vacuum sensor was calibrated on the flow rate of H₂ supplied into the measurement system. Further re-hydrogenation was carried out at ~15 bar H₂ and 230 °C for ~4 h followed by cooling down to room temperature. Two TDS – re-hydrogenation cycles were performed for each sample.

3. Results and discussion

Table 1 summarises the data on hydrogenation (during HRBM), re-hydrogenation and dehydrogenation performances of the studied composites. The selected data on H absorption during HRBM are presented in Fig. 1.

For Mg–*x*Pd minor improvements of the performances were observed only when using crystalline Pd black introduced in the amount $x \ge 0.5$ wt.%. The increase of the Pd content above this

threshold does not result in a noticeable increase of hydrogenation and re-hydrogenation rates, as well as in a noticeable decrease of TDS peak temperature.

As illustrated by TEM images (Fig. 2), the as-milled powders consist of agglomerates of polycrystalline MgH_2 particles, 100–200 nm in size. Twinning, whose appearance is typical for ball-milled MgH_2 [16], was also observed.

Bright- (Fig. 2A and B) and dark-field (Fig. 2C and D) TEM micrographs indicate the presence, in addition to MgH₂, of less electrontransparent phase(s) containing noticeable amounts of Pd. The average Pd content in the sample determined by EDS was of 3.43 wt.% corresponding well to the starting sample composition. Since neither Pd, nor PdH could be detected through XRD refinement (see below), the appearance of the less electron-transparent areas could be accredited to new phase(s) containing both Mg and Pd (i.e. Mg–Pd intermetallides).

It is seen from the low magnification bright-field image (Fig. 2A) that dark inclusions presenting Pd-rich particles are uniformly distributed in the MgH₂ matrix. The inclusions vary in size: few relatively big (50–100 nm; delimited by circle) and majority very small (<10 nm; shown by arrows). In the dark field images (Fig. 2C and D) it is visible that a separate phase exists in the Mg matrix, as evidenced by the areas of bright contrast. This new phase exhibits a basal plane alignment which has long-range arrangement (Fig. 2D; the corresponding region is delimited by a rectangle).

Fig. 3 shows XRD patterns of the as-milled (A) and re-hydrogenated (B) Mg–5Pd (crystalline). Results of refinement of the typical XRD patterns are summarised in Table 2.

The patterns of the as-milled samples (see Fig. 3A as an example) exhibit broad peaks of tetragonal α - and orthorhombic

 $^{^1\,}$ In the ball milled samples, the LX and LY for $\alpha\text{-}$ and $\gamma\text{-}modifications$ of MgH_2 were constrained to be equal.



Fig. 2. Bright (A and B) and dark (C and D) field TEM micrographs of as-milled sample Mg-5 wt.% of crystalline Pd black. Circle delimits a typical large particle of Pdcontaining phase, arrows show examples of small Pd-containing particles, and rectangle delimits region of Pd-containing phase exhibiting long-range basal plane alignment.

 γ -modifications of MgH₂ with lattice periods corresponding well to the literature data [17,18], and crystallite size of 10–12 nm, with the trend of a slight increase with increasing Pd content in the composite. Palladium and palladium hydride were not observed in the patterns. However, for the samples containing ≥2 wt.% of Pd black, the better refinement was obtained assuming presence of a poorly-crystallized MgPd intermetallide (CsCl-type; space group # 221; *a* = 3.12 Å [19]), crystallite size below 10 nm. For Mg–5 wt.% Pd, the refinement was further improved assuming the presence of Mg_{0.9}Pd_{1.1} (AuCu-type; space group # 123; *a* = 3.03 Å, *c* = 3.42 Å [20]) with quite large crystallites (75 nm). The estimated abundances and crystallite sizes of Pd-containing phases in Mg–5 wt.% Pd (Table 2) are in good correspondence with TEM observations (Fig. 2A).

The re-hydrogenated samples (see example in Fig. 3B) contained major phase of α -MgH₂; abundance >75 wt.%, and crystallite size about 90 nm. A significant amount (10–17 wt.%) of non-hydrogenated Mg, crystallite size above 100 nm, was observed as well. The patterns of the re-hydrogenated samples containing ≥ 2 wt.% Pd exhibit well-resolved peaks belonging to the impurity of Mg₆Pd (space group # 216; *a* = 20.108 Å [21]). The most intensive peaks of Mg₆Pd are marked by arrows in Fig. 3B. Furthermore,

better refinement was obtained assuming additional presence of poorly-crystallized MgPd (Fig. 3A, Table 2), but in lesser amounts than in the as-milled sample. The fitted lattice period of MgPd corresponded well to the literature data [19]. Finally, the XRD patterns of the re-hydrogenated samples exhibited the presence of MgO formed due to oxidation of the sample.

Our observations allow us to conclude that mechanical alloying of magnesium with palladium takes place already during HRBM. Most probably, this process starts from the formation of Mg_{0.9}Pd_{1.1}, the most stable intermetallide in Mg–Pd system [22], on the surface of Pd particles. During the milling followed by dehydrogenation/re-hydrogenation, due to diffusion of Mg, this phase is enriched with Mg to form MgPd and, further, Mg₆Pd. Similar results were obtained by Roquefere et al. [23] who prepared Mg₆Pd by MM of stoichiometric mixture of Mg and Pd, and Pasquini et al. [24] who observed the formation of MgPd, Mg₅Pd₂ and Mg₃Pd in the course of PVD of Pd onto Mg nanoparticles.

In summary, the Mg–xPd nanocomposites are characterised by modest improvements of their dehydrogenation and re-hydrogenation behaviour as compared to HRBM Mg (Table 1). The reason for that seems to be in the high "metallurgical affinity" between Mg and Pd forming a wide spectrum of intermetallic compounds

Table 2

Characteristics of constituent phases in Mg-Pd composites prepared using crystalline Pd black.

Sample characteristics	Constituent phases					
Mg-1Pd HRBM	α -MgH $_2$	γ -MgH ₂				
Abundance (wt.%) Unit cell parameters (Å)			87.3(-) a = 4.517(1) c = 3.016(1)			12.7(4) a = 4.479(5) b = 5.544(5) c = 4.931(4)
Crystallite size, <i>D_V</i> (nm)			10			
Mg–2Pd HRBM		α-MgH ₂ γ-		γ -MgH ₂		MgPd
Abundance (wt.%) Unit cell parameters (Å)	ndance (wt.%) 89.0(-) : cell parameters (Å) $a = 4.5197(9)$ c = 3.0186(7)		10.4(3) a = 4.483(5) b = 5.542(7) c = 4.941(4)			0.6(1) <i>a</i> = 3.000(3)
Crystallite size, $D_V(nm)$	1	1				8
Mg–5Pd HRBM	α -MgH ₂		$\gamma\text{-}MgH_2$		MgPd	$Mg_{0.9}Pd_{1.1}$
Abundance (wt.%) Unit cell parameters (Å)	78.5(-) a = 4.5188(6) c = 3.0235(6)	I	14.5(3) a = 4.527(5) b = 5.435(5) c = 4.957(4)		5.0(1) <i>a</i> = 3.023(3)	2.0(1) a = 3.107(4) c = 3.284(7)
Crystallite size, $D_V(nm)$	12				7	74
Mg–2Pd re-hydrogenated	α -MgH ₂	Mg		Mg ₆ Pd	MgPd	MgO
Abundance (wt.%) Unit cell parameters (Å)	82.0(-) a = 4.5130(3) c = 3.0182(2)	10.6(3) a = 3.2090(4) c = 5.2098(8)	1	1.4(1) a = 20.198(5)	0.3(1) <i>a</i> = 3.151(7)	5.7(3) a = 4.228(2)
Crystallite size, <i>D_V</i> (nm)	89	117		123	10	16
Mg–5Pd re-hydrogenated	α -MgH ₂	Mg		Mg ₆ Pd	MgPd	MgO
Abundance (wt.%) Unit cell parameters (Å)	76.1(-) a = 4.5121(3) c = 3.0177(3)	16.7(5) a = 3.2077(5) c = 5.213(1))	4.5(2) <i>a</i> = 20.202(4)	0.6(1) <i>a</i> = 3.146(2)	2.1(3) <i>a</i> = 4.214(2)
Crystallite size, $D_V(nm)$	90	118		138	29	33



Fig. 3. XRD patterns of as-milled (A) and re-hydrogenated (B) samples Mg–5 wt.% of crystalline Pd black. The most intensive well-resolved peaks of Mg₆Pd (B) are labelled by arrows.

[22]. Hydrogenation of Mg–Pd intermetallides is quite difficult: so far it was reported about formation of α -solid solution Pd₃MgH_{0.7} [25] and ternary hydride PdMg₂H [26]; reaction of Mg₆Pd with H₂ yielding Mg_{3.65}Pd and MgH₂ proceeds very slowly [23]. We suppose that the formation of Mg–Pd intermetallides observed in the course of the XRD studies results in the lowering of the catalytic activity of initial Pd particles thus exhibiting the minor (if any) effect of improvement of hydrogen sorption performances of the Mg-based nanocomposites.

4. Conclusions

Improvements of hydrogenation kinetics during HRBM of Mg–Pd, as compared to HRBM Mg, were observed only for the materials prepared using crystalline Pd black (≥ 0.5 wt.%). The obtained nanocomposites were characterised by modest improvements of their dehydrogenation and re-hydrogenation performances associated with the formation of Mg–Pd intermetallides that results in the lowering of the catalytic activity of initial Pd particles.

Acknowledgements

This development was funded by Department of Science and Technology of South Africa via HySA Program, Project KP3-S04. ML also thanks National Research Foundation of South Africa (NRF) for the support via Incentive Funding Grant.

References

- [1] I.P. Jain, C. Lal, A. Jain, Int. J. Hydrogen Energy 35 (2010) 5133-5144.
- A. Zaluska, L. Zaluski, J.O. Ström-Olsen, J. Alloys Comp. 288 (1999) 217–225.
 G. Liang, J. Huot, S. Boily, A. Van Neste, R. Schulz, J. Alloys Comp. 292 (1999)
- 247-252.
- [4] J. Charbonnier, P. de Rando, D. Fruchart, S. Miraglia, L. Pontonnier, S. Rivoirard, N. Skryabina, P. Vulliet, J. Alloys Comp. 383 (2004) 205–208.
- [5] M.Y. Song, S.N. Kwon, H.R. Park, J.L. Bobet, Int. J. Hydrogen Energy 36 (2011) 12932-12938.
- [6] J.L. Bobet, B. Chevalier, M.Y. Song, B. Darriet, J. Etourneau, J. Alloys Comp. 336 (2002) 292–296.
- [7] M.V. Lototsky, R.V. Denys, V.A. Yartys, Int. J. Energy Res. 33 (2009) 1114–1125.
- [8] Y.B. Pan, Y.F. Wu, Q. Li, Int. J. Hydrogen Energy 36 (2011) 12892–12901.
- [9] N. Mahmoudi, A. Kaflou, A. Simchi, J. Power Sources 196 (2011) 4604–4608.
- [10] A. Krozer, B. Kasemo, J. Phys.: Condens. Matter I (1989) 1533–1538.
- [11] J. Dufour, J. Huot, J. Alloys Comp. 439 (2007) L5–L7.
- 11] J. Duloui, J. Huot, J. Alloys Collip. 459 (2007) L3-L7.

- [12] J. Qu, B. Sun, J. Zheng, R. Yang, Y. Wang, X. Li, J. Power Sources 195 (2010) 1190–1194.
- [13] A.Ye. Yermakov, N.V. Mushnikov, M.A. Uimin, V.S. Gaviko, A.P. Tankeev, A.V. Skripov, A.V. Soloninin, A.L. Buzlukov, J. Alloys Comp. 425 (2006) 367–372.
- [14] M.V. Lototsky, M. Williams, V.A. Yartys, Ye.V. Klochko, V.M. Linkov, J. Alloys Comp. 509 (2011) S555–S561.
- [15] A.C. Larson, R.B. Von Dreele, General Structure Analysis System (GSAS), Los Alamos National Laboratory Report LAUR, 86–748, 2004.
- [16] M. Danaie, D. Mitlin, J. Alloys Comp. 476 (2009) 590-598.
- [17] J.M. Haschke, M.R. Clark, High Temp. Sci. 7 (1975) 152-158.
- [18] M. Bortz, B. Bertheville, G. Böttger, K. Yvon, J. Alloys Comp. 287 (1999) L4–L6.
- [19] H.H. Stadelmaier, W.K. Hardy, Z. Metallk. 52 (1961) 391–396.
 [20] P.I. Kripyakevich, E.I. Gladyshevskii, Sov. Phys. Crystallogr. 5 (1960) 552–554. translated from Kristallografiya.
- [21] S. Samson, Acta Crystallogr., B 28 (1972) 936-945.
- [22] A.A. Nayeb Hashemi, J.B. Clark, Mg-Pd (Magnesium-Palladium), in: T.B. Massalski (Ed.), Binary Alloy Phase Diagrams, vol. 3, second ed., Springer, Berlin, 1990, pp. 2535–2536.
- [23] J.-G. Roquefere, J. Lang, A. Yonkeu, J. Dufour, J. Huot, Int. J. Hydrogen Energy 36 (2011) 2165–2169.
- [24] L. Pasquini, E. Callini, M. Brighi, F. Boscherini, A. Montone, T.R. Jensen, C. Maurizio, M.V. Antisari, E. Bonetti, J. Nanopart. Res. 13 (2011) 5727–5737.
- [25] H. Kohlmann, G. Renaudin, K. Yvon, C. Wannek, B. Harbrecht, J. Solid State Chem. 178 (2005) 1292–1300.
- [26] Y. Goto, H. Kakuta, A. Kamegawa, H. Takamura, M. Okada, J. Alloys Comp. 404– 406 (2005) 448–452.