This article was downloaded by: [Michigan State University] On: 08 February 2015, At: 04:38 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



Molecular Crystals and Liquid Crystals Science and Technology. Section A. Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information: http://www.tandfonline.com/loi/gmcl19

Benzotriazol Type Liquid Crystals

Yinfa Yan ^a & Lijuan Hu ^b

^a 822 Carriage Hill Drive, Athens, 45701, USA

^b Department of Chemistry, Ohio University, Athens, OH, 45701, USA

Published online: 04 Oct 2006.

To cite this article: Yinfa Yan & Lijuan Hu (1995) Benzotriazol Type Liquid Crystals, Molecular Crystals and Liquid Crystals Science and Technology. Section A. Molecular Crystals and Liquid Crystals, 265:1, 55-59, DOI: <u>10.1080/10587259508041678</u>

To link to this article: <u>http://dx.doi.org/10.1080/10587259508041678</u>

PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform. However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness, or suitability for any purpose of the Content. Any opinions and views expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with primary sources of information. Taylor and Francis shall not be liable for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms & Conditions of access and use can be found at http://www.tandfonline.com/page/terms-and-conditions

BENZOTRIAZOL TYPE LIQUID CRYSTALS

YINFA YAN 822 Carriage Hill Drive, Athens, OH 45701, USA

and

LIJUAN HU Department of Chemistry, Ohio University, Athens, OH 45701, USA

<u>Abstract</u> A new series of liquid crystals (LCs), benzotriazol type which have high absorptivities to ultraviolet (UV) light within the wavelength range from 290 to 350 nm were synthesized. Their syntheses and liquid crystalline properties are reported in this paper.

INTRODUCTION

Many types of liquid crystal materials have already been synthesized and most of them have been used in LC displaying devices. Many of them, however, shorten the service life of displaying components due to the decomposition or polymerization under sunshine for long periods of time. In order to improve the photo-stability, some UV-absorbents have been used in the materials of mixed liquid crystals to prolong their service life.¹

The benzotriazol type compounds have been widely used in many organic synthesized materials as UV-absorbents.² They can change photo-energy to thermal-energy and release it. Thus, the destruction to the molecular structure of the materials caused by UV-light is greatly improved by adding a small amount of UV-absorbents. The synthesis of benzotriazol type liquid crystals, however, has not been reported. This paper reports the syntheses and properties of this new series of liquid crystals. These materials have a strong UV absorption at 290-350 nm.³ Therefore, the service life for displaying components can be extended by adding these new UV-absorbing liquid crystals.⁴



SCHEME 1 Syntheses of Benzotriazol Type Liquid Crystals

EXPERIMENTAL

The synthetic routes used to prepare the reported compounds in this paper and their molecular structures are outlined in Scheme 1. All these compounds were prepared by the methods reported in reference 3. The intermediate A reacted with the corresponding acyl chlorides in toluene under the catalysis of pyridine to yield 4PHPBZ, 4PMPBZ, 5OPMPBZ, 7OPMPBZ, 7OPCPBZ and 7OPCPBZ; or reacted with the corresponding alkyl bromides in alcohol by using KOH as catalyst to yield 12MPT and 7ClPT, respectively (see Scheme 1.2 and 1.3). All products were recrystalized with alcohol until the clear point remained constant. The results of differential scanning calorimetry (DSC) analyses are shown in Table I (sensitivity: 5 mV/cm; the rate of increasing temperature: 2°C/min).

RESULTS AND DISCUSSION

The DSC analyses show that the eight compounds synthesized all have liquid crystalline phases (TABLE I).

	Compounds	K-S(°C)	S-N(°C)	N-I(°C)
1	12MPT	74		77
2	7CIPT	94		101
3	4PHPBZ	114		155
4	4PMPBZ	159		191
5	50PMPBZ	148		213
6	70PMPBZ	126		200
7	5OPCPBZ	149	175	231
8	70PCPBZ	115	190	216

TABLE I Temperature of Phase-transition

The authors also synthesized the compound 7MPT in which the R terminal was nheptyl and R' methyl (see Scheme 1) and did not find the existence of mesophase. The

58/[2624]

cause of this behavior is that there is no strong polar group in the molecule. Therefore the liquid crystalline phase does not appear when the alkyl chain at the other terminal is not long enough. The narrow range of liquid crystalline phase was observed when the alkyl chain is long enough (e.g., when R is n-dodecyl, the range of the liquid crystalline phase is 3 °C). The mesophase range increased greatly when a strong polar group such as ester was introduced. When R' (CH₃) was replaced by Cl, the mesophase range increased obviously and the smectic phase appeared. For instance, the mesophase range of 50PMPBZ was 148~213°C (65°C) and 70PMPBZ 126~200°C (74°C), while 50PCPBZ 149~231°C (82°C) and 70PCPBZ 115~216°C (101°C) and smectic phases were observed at 175 and 190°C respectively. As mentioned above, 7MPT did not exhibit a liquid crystalline phase while 7ClPT did and the mesophase range was 94~101°C. When R' was H, the mesophase temperature was lower than that when R' was methyl. The K-N point of 4PHPBZ (R' = H) was 114°C while 4PMPBZ (R' = CH₃) 159°C.

The UV-absorption spectra of 12MPT, 5OPMPBZ and 4PMPBZ showed that each compound exhibited a strong absorption peak at the wavelength range of 290~350 nm.³ The reason is that in the molecule, a benzotriazol group which has high UV absorptivity was bounded. The modification of the molecular structure did not change the ability of benzotriazol group to absorb the UV light. The clear point's decreasing and the appearance's yellowing of biphenyl liquid crystals under long period sunshine were improved significantly by adding a small amount of synthesized liquid crystals.⁴

This paper reports the primary experimental results of benzotriazol type compounds as both liquid crystal materials and UV-absorbents. When the terminal group R' is replaced by a strong polar group such as cyano group, an ideal temperature range of liquid crystal phase may appear.

Acknowledgement

The authors thank H. Zhu, Y. Wang and J. Zhang in Beijing Institute of Chemical Reagents for analyses of the products. We also thank Dr. P. de B. Harrington in Ohio University for his helpful comments and criticisms.

References

1. Japanese patent: JP 01261495 (89261495).

- 2. S. Li, A. Gupta and D. Vogl, Monatsh Chem., 114, 937 (1983).
- 3. Y. Yan, Z. Niu, X. Han and B. Fan, Chem. Reagent (CHN), 15, 149 (1993).
- Y. Yan, Z. Niu, Y. Chen and B. Fan, <u>Symp. of the 6th National LC Conference</u>, CH-9, Shenzhen, China, 1991.