This article was downloaded by: [The University of Texas at El Paso]

On: 01 January 2015, At: 19:38 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



Phosphorus, Sulfur, and Silicon and the Related Elements

Publication details, including instructions for authors and subscription information: http://www.tandfonline.com/loi/gpss20

New Phosphorus-Fluorocarbon Hybrid Polymer Systems

Robert H. Neilson , Junmin Ji , Sridevi Narayan-Sarathy , Dennis W. Smith & David A. Babb

^a Department of Chemistry , Texas Christian University , Fort Worth, TX 76129

^b Department of Chemistry , Texas Christian University , Fort Worth, TX 76129

^c Department of Chemistry , Texas Christian University , Fort Worth, TX 76129

^d Central & New Businesses Research and Development , The Dow Chemical Company, Freeport, TX 77541

^e Central & New Businesses Research and Development, The Dow Chemical Company, Freeport, TX 77541 Published online: 17 Mar 2008. To cite this article: Robert H. Neilson , Junmin Ji , Sridevi Narayan-Sarathy , Dennis W. Smith & David A. Babb (1999) New Phosphorus-Fluorocarbon Hybrid Polymer Systems, Phosphorus, Sulfur, and Silicon and the Related Elements, 144:1, 221-224, DOI: <u>10.1080/10426509908546222</u>

To link to this article: <u>http://dx.doi.org/10.1080/10426509908546222</u>

PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform. However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness, or suitability for any purpose of the Content. Any opinions and views expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with primary sources of information. Taylor and Francis shall not be liable for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms & Conditions of access and use can be found at http://www.tandfonline.com/page/terms-and-conditions

New Phosphorus-Fluorocarbon Hybrid Polymer Systems

ROBERT H. NEILSON^a, JUNMIN JI^a, SRIDEVI NARAYAN-SARATHY^a, DENNIS W. SMITH^b and DAVID A. BABB^b

^aDepartment of Chemistry, Texas Christian University, Fort Worth, TX 76129 and ^bCentral & New Businesses Research and Development, The Dow Chemical Company, Freeport, TX 77541

The thermally-induced cyclodimerization of aryl-trifluorovinyl ethers (TFVE, 1) readily affords highly stable and processible perfluorocyclobutane (PFCB, 2) polymers, many of which have useful optical, mechanical, and/or surface properties. We report here on the synthesis and characterization of some novel TFVE and PFCB functionalized phosphorus-based polymers systems. These new polymers have been prepared by three general methods: (1) condensation polymerization of appropriate TFVE-substituted Si-N-P precursors, (2) deprotonation-substitution reactions of preformed poly(methylphenyl-phosphazene), and (3) cyclodimerization-polymerization of various TFVE-substituted phosphorus derivatives.

Keywords: phosphazene; fluorocarbon; polymer; trifluorovinyl; phosphoranimine

INTRODUCTION

Perfluorocyclobutane (PFCB) polyarylethers represent a unique class of fluoropolymers which combine the processibility and durability of engineering thermoplastics with the optical, electrical, thermal stability, and chemically resistant properties of fluoropolymers. Such polymers (2) are prepared by the step growth, radical mediated $[2\pi + 2\pi]$ thermal cyclopolymerization of trifluorovinyl ethers (1). They comprise a variety of thermoplastic and thermosetting materials with a tunable range of performance.^[1-5] In addition, PFCB chemistry offers a single component condensate- and catalyst-free cure option in contrast to most other inorganic/organic hybrid materials.



Recently the synthesis and characterization of new siloxane-containing PFCB hybrid systems where the PFCB ring is contained within the main chain as well as other PFCB hybrid systems containing organosilane units have been prepared.^[3-5] This previous work, and that reported herein, makes use of a versatile intermediate strategy of

delivering the trifluorovinyl ether group, in tact, to a substrate monomer or polymer. We have found that useful Grignard (4) and lithium (5) reagents^[6] can be easily obtained from the aryl bromide (3). The remarkable stability of the Grignard and lithium derivatives in the presence of the extremely electrophilic trifluorovinyl ether group has been rationalized by theoretical calculations from which it is predicted that the trifluorovinyl ether group stabilizes the aryl-TFVE anion by ca. 11 kcal/mol vs. the aryl-methoxy analog.^[6]



RESULTS and DISCUSSION

We report here on the synthesis and characterization of some novel TFVE and PFCB functionalized phosphorus-based polymers systems. These new polymers have been prepared by three general methods as described in the following sections. Full details of the synthesis and characterization of these new polymers and their precursors will be reported elsewhere.

Polymerization of TFVE-Substituted Si-N-P Precursors. The synthesis of poly(alkyl/aryl)phosphazenes, $[R_2P=N]_n$, via the condensation polymerization of suitable N-silylphosphoranimines, Me₃SiN=PR₂X, is now a well established procedure.^[7] Typically, this process utilizes the P-trifluoroethoxy (X = OCH₂CF₃) or P-phenoxy (X = OPh) derivatives to afford high molecular weight *polymeric* phosphazene products. In contrast, the P-halo analogs (X = Cl, Br) generally yield *cyclic* phosphazene products. By using the organometallic reagents (i.e., 4 and 5 above) and synthetic methodology reported recently,^[6] we have prepared a series of new Si-N-P compounds (e.g., 6) containing the TFVE group (i.e., R = *p*-C₆H₄-OCF=CF₂).



Thermolysis studies indicated that, while the P-OCH₂CF₃ and P-OPh analogs were very thermally stable, the P-chloro compound 6 did yield a novel TFVE-functionalized polymer 7 and copolymers such as 8 and 9. Polymers 7-9 were soluble, film-forming, thermoplastics with molecular weights in the $10^4 - 10^5$ range and glass transition temperatures (T_g) between -5 and 33°C.

Derivatization of Preformed Polyphosphazenes. Work by Wisian-Neilson and coworkers^[8] has shown that poly(alkyl/arylphosphazenes) such as $[Ph(Me)P=N]_n$ readily undergo deprotonation at the P-Me sites to afford reactive polymeric anions. Subsequent addition of electrophiles leads to a wide variety of organic and/or inorganic functionalized poly(alkyl/arylphosphazenes). We have utilized this general approach to attach the TFVE group to the phosphazene backbone through organosilicon spacer units (e.g., 10 and 11). The TFVE-organosilicon reagents were first prepared by treating the appropriate dichlorosilanes with the lithium reagent 5.^[6]



When heated at about 160°C for 12 hrs, all of these new TFVE-substituted polyphosphazenes (7 - 11) are converted from soluble, flexible thermoplastics to much harder, tougher, insoluble resins. This transformation is undoubtedly due to the facile thermal cyclodimerization of the pendant TFVE groups to generate crosslinks via PFCB (perfluorocyclobutane) units. The flexibility and other physical properties of these phosphazene-fluorocarbon resins can be controlled and, to some extent, tailored by varying the degree of TFVE substitution along the backbone and/or the length of the spacer between the polymer backbone and the TFVE group.

Cyclodimerization-Polymerization of TFVE-Phosphorus Monomers. As noted earlier, when compounds of type 1 are heated, cyclodimerization of the TFVE groups results in a polymerization reaction that yields linear PFCB polymers of type 2. In order to apply this process to the synthesis of novel phosphorus-PFCB hybrid polymers, we first prepared a series of bis-TFVE phosphorus monomers (12 - 14) by treatment of the appropriate dichlorophosphoryl derivatives with two equivalents of the TFVE lithium reagent 5. The analogous phosphines (E = nothing) were similarly prepared.

Subsequent heating (180°C, 12 hrs) of these neat liquid monomers resulted in their smooth polymerization to afford the new PFCB-phosphorus copolymers 15 - 17 in high yield. These new materials were isolated as hard, glassy polymers that were soluble in common organic solvents. The molecular weights, however, were relatively low (ca. 2,000 - 20,000), possibly due to the substantial increase in viscosity as the polymerization process occurred. Polymers 15 - 17 were hard, amorphous materials with T_g values above 150°C. The analogous P-III precursors (E = nothing) also

underwent cyclodimerization but, surprisingly, the products were very insoluble and thus not fully characterized.



Further studies of all of the new polymeric materials reported here and their TFVEphosphorus precursors are continuing in our laboratory and complete results will be reported in due course.

Acknowledgment. The authors thank the Texas Higher Education Coordinating Board (Advanced Technology Program) and The Robert A. Welch Foundation for generous financial support of the work at Texas Christian University.

References

- Babb, D. A.; Ezzell, B. R.; Clement, K. S.; Richey, W. F.; Kennedy, A. P. J.Polym.Sci., Part-A, Polym. Chem. 1993, 31, 3465.
- [2] Smith, D. W., Jr.; Babb, D. A. Macromolecules 1996, 29, 852.
- [3] Neilson, R. H.; Ji, J.; Narayan-Sarathy, S.; Oxley, J. D.; Smith, D. W., Jr. Abstract of Papers, 30th Organosilicon Symp.: London, Ontario, 1997.
- [4] Narayan-Sarathy, S; Ji, J; Neilson, R. H.; Smith, D. W., Jr Polym. Prepr. (Am. Chem. Soc., Div. Polym. Chem.) 1998, 39, 609.
- [5] Narayan-Sarathy, S.; Ji, J.; Neilson, R. H.; Smith, D. W., Jr. Polym. Prepr., (Am. Chem. Soc. Div. Polym. Chem.) 1998, 39, 530.
- [6] Ji, J.; Narayan-Sarathy, S.; Neilson, R. H.; Oxley, J. D.; Smith, D. W., Jr.; Babb, D. A.; Rondan, N. G. Organometallics 1998, 17, 783.
- [7] See, for example, the following and references cited therein: (a) Neilson, R.H.; Wisian-Neilson, P. Chem. Rev. 1988, 88, 541. (b) Neilson, R.H.; Jinkerson, D. L.; Kucera, W. R.; Longlet, J.J.; Samuel, R.C.; Wood, C.E. ACS Symposium Series 1994, 572, 232. (c) Wisian-Neilson, P. Encyclopedia of Inorganic Chemistry, King, R. B., Ed.; Wiley: Chichester, England, 1994, Vol. 7, 3371.
- [8] Wisian-Neilson, P.; Koch, K. A.; Zhang, C. Macromolecules 1998, 31, 1808 and references cited therein.