This article was downloaded by: [University of Otago] On: 12 July 2015, At: 13:44 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: 5 Howick Place, London, SW1P 1WG



Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information: <u>http://www.tandfonline.com/loi/gmcl20</u>

Inorganic-Organic Hybrids Basedon Cyclotetraphosphazenes

Galina Popova^a, Vjacheslav Kireev^a, Alexander Spitsyn^a, Hirotaka Ihara^b, Maxim Scherbina^c & Sergei Chvalun^c

^a Research Laboratory "Molecular Materials" ,
Mendeleyev Univ. Chem. Technology , Miusskaya sq.,
9, Moscow , 125190 , Russia

^b Dept. Applied Chemistry & Biochemistry , 2-39-1, Kumamoto , 860-8555 , Japan

^c State Research Centre , Karpov Inst. of Physical Chemistry , Vorontzovo pole, 10, Moscow , 103064 , Russia

Published online: 18 Oct 2010.

To cite this article: Galina Popova, Vjacheslav Kireev, Alexander Spitsyn, Hirotaka Ihara, Maxim Scherbina & Sergei Chvalun (2003) Inorganic-Organic Hybrids Basedon Cyclotetraphosphazenes, Molecular Crystals and Liquid Crystals, 390:1, 91-96, DOI: <u>10.1080/15421400390193459</u>

To link to this article: http://dx.doi.org/10.1080/15421400390193459

PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform. However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness, or suitability for any purpose of the Content. Any opinions and views

expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with primary sources of information. Taylor and Francis shall not be liable for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms & Conditions of access and use can be found at <u>http://www.tandfonline.com/page/terms-and-conditions</u>



INORGANIC-ORGANIC HYBRIDS BASED ON CYCLOTETRAPHOSPHAZENES

Galina Popova, Vjacheslav Kireev, and Alexander Spitsyn Research Laboratory "Molecular Materials", Mendeleyev Univ. Chem. Technology, Miusskaya sq., 9, Moscow 125190, Russia

Hirotaka Ihara Dept. Applied Chemistry & Biochemistry, 2-39-1, Kumamoto 860-8555, Japan

Maxim Scherbina and Sergei Chvalun State Research Centre, Karpov Inst. of Physical Chemistry, Vorontzovo pole, 10, Moscow 103064, Russia

Organic cyclic and oligoaminoacid derivatives of cyclotetraphosphazenes were synthesized and characterized. WAXS and DSC methods were applied to the bulk and LB-films study, being different crystalline structures are shown both for initial cyclotetraphosphazenes and for their organic hybrids.

Keywords: cyclotetraphosphazenes; oligoaminoacids; crystalline structure

INTRODUCTION

Cyclophosphazenes and their derivatives are attractive subjects for current chemical, physical and biological study. Structures of the unique polymers, such as dendrimers and arborols can be obtained on the cyclophosphazene basis [1]. On the other hand, the unusual low molecular compounds (f. ex. adamantane and triptamines derivatives) were prepared by chlorine atoms substitution in cyclophosphazenes [2,3]. These Research permit to investigate different properties, thermal and oxidative stability, lipophilicity, bioactivity and biocompability. Taking in account great amount of papers concerning cyclotriphosphazene modification, we concentrated attention

This work was supported by Russian Fond of Basic Research (grants 00-03125 and 01-03-32652) and JSPS Grants (Japan).

on octachlorocyclotetraphosphazene (OCTP) transformation. It was necessary to prepare pure crystalline OCTP and substituted CTP as initial reagents. We described as well 5-methoxytryptamine containing cyclotetraphosphazene, olygoalanyl- and olygoglutamyl- derivatives of cyclotetraphosphazene. WAXS data shown discotic-like structures for few compounds, the loss of crystalinity is noticed for olygomeric forms of CTP, although their LB-films can contain some crystalline domains.

SUBSTITUTION IN OCTACHLOROCYCLOTETRA-PHOSPHAZENE BY LOW MOLECULAR COMPOUNDS

General conversion of cyclotetraphosphazenes and synthesis of inorganic low molecular synthons are represented by Scheme 1.

We could use two ways at least for our purposes: the substitution of chlorine atoms in OCTP directly or in defined non-geminal intermediate compounds for variant isomers decreasing.

Early we have described OCTP preparation by cyclo-widening reaction in fusion [4]. The yield of tetramer is depended upon purity and ideal crystallinity of initial cyclophosphazenes (mixture of tri- and tetra-) strongly. Analysis of publications and own results on morphological and optical investigations confirmed symmetry of OCTP as tetragonic syngony, trimer possess rhombic syngony, both compounds relate to planexial type with D_{4R} (4/mmm). Optical constants are different, being OCTP has bright interference, Figure 1.

Using of non-geminal tetraphenyltetrachlorocyclotetraphosphazene (TPTCP) is more suitable, than OCTP, so we can carry out easy two next



SCHEME 1 Conversion of cyclotetraphosphazenes. Synthons preparation.



FIGURE 1 1a. Microphotography of crystalline piece of hexachlorocyclotriphosphazene with octochlorocyclotetraphosphazene inclusion (500x increasing polarization microscope). 1b. Ideal monocrystal of high-pure hexachlorocyclotriphosphazene.

reactions: tetraamine - and tetrraisocyanate - functional cyclophosphazene preparation, Scheme 1, Table 1.

Aminolysis of TPTCP by 5-methoxytriptamine and 1-pyrenylbutirylhydrazide result to di- and tetrasubstituted tetraphenylcyclotetraphosphazene, Figure 2.

OLIGOAMINOACID DERIVATIVES OF CYCLOTETRA-PHOSPHAZENE

N-Carboxyanhydrides of γ -methylglutamate (γ -Me-Gly-NCA) and Alanine were polymerizated by action with tetraphenyltetraaminocyclotetrapho-

	Yield, %	М.р., °С	IR, cm^{-1}	³¹ P NMR	¹ H NMR
(P=N) ₄ Ph ₄ (NCS) ₄	85–90	154	1990–2000 (NCS) 1440 (P-Ph) 1200 (P-N)	-12.1 (singl.)	8.2 (Ph)
(P=N) ₄ Ph ₄ (NH ₂) ₄	30–50	225	$\begin{array}{c} 1300 \ (P=N) \\ 3400 \ (NH_2) \\ 3380 \ (NH_2) \\ 1440 \ (P-Ph) \\ 1300 \ (P=N) \end{array}$	-3 (singl.)	8.8 (NH ₂) 6.5–7.1 (Ph)

TABLE 1 Properties of Synthesized Synthons



FIGURE 2 Chemical structures of the cyclotetraphosphazenes.

sphazene (TATP) as initiator, Figure 2. Reaction is existed in dimethylformamide at room temperature under an atmosphere of dry argon and at different molar rations of NCA/TATP. The molecular weight of olygomers calculated from the NMR-¹H data and gel-permittion chromatography measurement, n = 40, MM = 6000, n = 20, MM = 3100. Symmetric replacement of olygoaminoacid chains on the inorganic plate could result to induction of α -helical conformation (4-helix bundle) that was noticed for porphirine and pyridine – functionalized templates [5]. This event is achieved when metallocompounds taked place inside cycliophosphazene.

STRUCTURAL PROPERTIES

We compared initial tetrasubstituted and olygoaminoacid derivatives of cyclotetraphosphazene. As it was shown by X-ray method the synthesized species are crystalline with different degree of crystallinity. Aminosubstituted cyclotetraphosphazene is powder with large grain morphology. Its WAXS pattern contains up to 18 reflection, Figure 3, Table 2.

Isocyanate derivatives is rather crystalline also (about 7 distinct reflections). Olygoaminoacid derivatives (polymerization degree ≤ 40) have broad diffuse reflections, that is in accordance with loss of crystallinity. The ratio of d-spacing is approximately 1:2:3:4 pointing to the layered structure. The layer width is 7.8Å which is consistent with voluemn





FIGURE 3 The scattering profile of (P=N)₄Ph₄(NH₂)₄.

of cyclic tetraphosphazene fragment. It was proposed the discotic shape of cyclotetraphosphazene derivatives.

DSC study is agreed with X-ray data. On the DSC curve of the most crystalline NH_2 -substituted there are three endothermic peaks at 208, 236, 250°C. Polyaminoacid chains (n ≤ 40) lead to the less of crystallinity there is one very weak peak only, at 55°C, Figure 4.

Polyalanylderivatives have bad solubility in common solvents, however form monolayers. Polyglutamylcyclotetraphosphazene form stable monolayers and LB-films (~40 monolayers). Character π /A isotherm is not simple, Figure 4b. Perhaps, it demonstrates crystallization domains on the surface [6], that was noticed for polyglutamic derivatives [7].

TABLE 2 D-Spacing, A

$-NH_2$	10.5	7.6	5.5	5.2	4.6	4.4	3.7	3.4	3.1	2.9	2.7	2.5	2.3	2.2	2.1	2.0	1.9
-NCS	7.8	4.9	4.6	4.2	3.9												
-n-Ala	7.5	5.3	4.5	3.7													

D8Advance Bruker, expose 4-5 h.



FIGURE 4 1a. DSC Data: 1 - NH₂-derivative has 3 endothermic peaks at 208, 236 and 250°C. 2 - n-Ala (n=20) has 1 very weak peak at 55°C. Mettler 1000, Scan rate of 20°C/min at of (-50) -300°C. 1b. Langmuir isotherm of $(P=N)_4Ph_4(Glu)_n$, n=20; 40.

REFERENCES

- [1] Majoral, J.-P. & Caminade, M. (1999). Chem. Rev., 99, 3, 858-880.
- [2] Krause, W., Parvez, M., Visscher, K., & Allcock, H. (1996). Inorg. Chem., 35, 6337–6338.
- [3] Alapishvili, M., Popova, G., Vorontzov, E., Kireev, V., & Suvorov, N. (1983). Zorn. Obz. Chem. (Rus), 53, 5, 1040–1044.
- [4] Melashvili, I., Kireev, V., & Goldin, J. (1983). Rus. Pat. 1018914.
- [5] Schneider, J. & Kelly, J. W. (1995). Chem. Rev., 95, 2169-2187.
- [6] Chi, L. F., Anders, M., Fuchs, H., Johnston, R. R., & Ringsdorf, H. Jan. 8. (1993). Science, 259.
- [7] Sohn, D., Kitaev, V., & Kumacheva, E. (1999). Langmiur, 15, 1968-1702.