

Synthesis and phase behavior of dendrons derived from 3,4,5-tris(tetradecyloxy)benzoic acid with different functional groups in focal point

MATVEY GRUZDEV^{a,*}, ULYANA CHERVONOVA^a, OLGA AKOPOVA^b and ARKADIY KOLKER^a

^aG A Krestov Institute of Solution Chemistry of the Russian Academy of Sciences, Ivanovo 153045, Russia ^bNanomaterials Research Institute, Ivanovo State University, Ivanovo 153025, Russia e-mail: gms@isc-ras.ru

MS received 18 February 2015; revised 12 May 2015; accepted 20 July 2015

Abstract. A number of dendrons of various chain lengths derived from the esters of 3,4,5-tris(tetradecyloxy)benzoic acid were synthesized. These esters were used as building blocks in the design of polyester molecules. Intermediate products, such as branched compounds with variation of functional groups in focal point (aromatic acids and their benzyl esters, aldehydes of different generation) were obtained. The structure and purity of all the compounds were determined by elemental analysis, FT-IR, NMR spectroscopy, mass spectrometry (MALDI-ToF). The phase behavior was investigated by differential scanning calorimetry and confirmed by polarized optical microscopy. Consequently, it was established that the liquid-crystalline properties of this series of dendrons arise from the degree of branching. This behavior can be explained by the formation of hydrogen bonds, as well as microsegregation processes of the links of the macromolecule.

Keywords. Dendron; building block; derivatives of benzoic acids; liquid crystalline properties; branching degree; microsegregation.

1. Introduction

Dendrimers and dendrons are highly branched globular macromolecules with precise structures, prepared through iterative synthesis.¹ Current architectures that enable the elaboration of self-assembling dendrons that provide supramolecular dendrimers which are able to self-organize in periodic arrays² are elaborated from dendrons containing anisotropic mesogenic repeat units,³⁻⁵ mesogenic dendrons and dendrimers,⁶ amorphous or liquid dendrimers containing mesogenic groups on their periphery and from polymer backbones dendronized with self-assembling dendrons.^{7,8} It is known that altering the end group functionality,^{9,10} as well as other structural modifications,¹¹ influence the thermal properties of the dendritic molecules. The thermotropic liquid crystal mesophases of dendritic molecules containing 3,4-bis-dodecyloxybenzoic acid, 3,5-bis-dodecyloxybenzoic acid or 3,4,5-trisubstituted benzyl ether monodendrons moieties, in the periphery and as monodendrons, and other feasible monodendrons, have been studied extensively by Percec *et al*. 10, 12-14

Commonly, branched oligomers can be described as calamitic molecules with disturbed linearity. One of the factors which promotes the development of mesomorphic properties, along with formation of dimers by hydrogen bonds,¹⁵ is microsegregation¹⁶ of the flexible nonpolar periphery and the rigid structure of the polar focal point of the dendron. Indeed, lateral substituents, such as C_nH_{2n+1} , abruptly reduce the clearing point with increasing length, and influence the stability of mesophase by suppressing it existence.¹⁷ Previously we synthesized mesomorphic aldehydes comprizing a long alkyl residue, which acted as building blocks in the production of iron (III) metallocomplexes which showed spin-crossover properties.^{18,19}

The purpose of the present research is the synthesis of monodendrons with different degrees of branching, derived from 3,4,5-tris(tetradecyloxy)benzoic acid, and determination of the dependence of phase behavior on molecular structure. Thus prepared dendrons are used as precursor to Schiff bases in complexation reaction of spin-cross over metal containing systems.²⁰ Recently, magnetic properties of a new dendrimeric spin crossover Fe(III) complex, $[Fe(L)_2]^+PF_6^-$, where L = 3,5-di[3,4,5-tris(tetradecyloxy)benzoyloxy]benzoyl-4-salicylidene-N-ethyl-N-ethylenediamine, was reported

^{*}For correspondence

for the first time.²⁰ EPR studies show that this compound undergoes a gradual spin transition in the temperature range 70–300 K and has antiferromagnetic ordering below 10 K. Mössbauer spectroscopy at 5 K confirms the presence of magnetic ordering in the dendrimeric iron complex.

2. Experimental

2.1 Materials and Methods

All the reagents and solvents were of chemically pure grade and were used without further purification. Benzyl ester of 3,5-dihydroxybenzoic acid was synthesized by the method in reference.²¹ FT-IR spectra of compounds were recorded on a Bruker Vertex 80V device in the region of $7500-370 \text{ cm}^{-1}$ in KBr pellets. The NMR spectral studies on the nuclei ¹H (500.17 MHz) and ¹³C (125.76 MHz) were recorded on a Bruker Avance-500 spectrometer. Elemental analysis of crystalline compounds was carried out on a FlashEA 1112 analyzer. The standard error of measurement is plus or minus 0.9%. Mass-spectra were obtained using the MALDI-ToF method on a Bruker Daltonics Ultraflex massspectrometer in the positive ion-mode using reflection option; the matrix was 2,5-dihydroxybenzoic acid. Thin layer chromatography was performed on the chromatographic plates PolyGRAM, Sil G/UV 254; the eluent was chloroform. Thermopolarization microscopy was performed on a MIN-8 microscope with a heating plate of a custom design. Differential scanning calorimetry measurements were carried out on a NETZCH DSC 204 F1 device in aluminium capsules, the weight of the sample ≈ 10 mg, the heating rate was 10°C/min in N₂ atmosphere.

2.2 Synthesis of the dendrons

2.2a 3,4,5-Tris(tetradecyloxy)benzoic acid (1): The batches of tetradecyl bromide (20.22 g; 72.92 mmol) and ethyl ester of 3,4,5-trihydroxybenzoic acid (4.89 g; 28.74 mmol) were dissolved in 200 mL acetone. Then 4% NaOH in C₂H₅OH was added, and the mixture was refluxed for 8 h. The reaction was monitored by thinlayer chromatography (TLC). The reaction mixture was poured out into 1 M solution of HCl. After two days the solid residue was filtered off and the solvent was distilled in vacuum. The product was dissolved in diethyl ether and this solution was purified by chromatography on aluminum oxide. The solvent was removed on a rotary evaporator. Yield: 15.00 g (80%). MS MALDI-ToF (m/z): found 781.94, calculated 782.25 (M^++Na) . CHNO analysis (%): Calcd. for $C_{49}H_{90}O_5$: C 77.52; H 11.94; O 10.54. Found: C 76.78; H 12.59; O 10.63. ¹H NMR (CDCl₃, TMS, δ, ppm): 0.81 (t, 9H, CH₃-Alk, J=7.32 Hz); 1.19 (m, 54H, -CH₂-Alk); 1.41 (t, 6H, Alk-<u>CH</u>₂-CH₂-O-, J=6.71 Hz); 1.68 (m, 6H, -CH2-Alk); 1.75 (m, 6H, -CH2-Alk); 3.95 (m, 6H, Alk-CH₂-O); 7.19 (s, 2H, Ph-H); 11.98 (s, 1H, COOH). ¹³C NMR (CDCl₃, TMS, δ , ppm): 14.11 (CH₃-), 22.69 (CH₃-CH₂-), 26.06 (CH₃-CH₂-CH₂-), 29.70 (CH₂-Alk), 31.92 (O-CH₂-CH₂-CH₂-), 69.14 (O-CH₂-Alk), 73.52 (O-CH₂-<u>CH₂-), 108.47</u> (CH_{arom}), 123.58 (C_{arom}), 143.10 (C_{arom}), 152.82 (C_{arom}), 171.87 (C(O)OH). FT-IR (KBr) $v_{\text{max}}/\text{cm}^{-1}$: 4326, 4250 (intermolecular hydrogen bond), 3418 (OH), 3081 (aromatic vibrations of C-H), 2921-2850 (-CH₂-), 2637-2530 (-CH₃-), 1688 (C=O), 1130 (-C-O-C-), 989-969 (flat deformational C-H vibrations of 1,3,4,5-substituted aromatic ring), 936 (-OH), 866 (non-planar deformational C-H vibrations of 1,3,4,5substituted aromatic ring).

2.2b 3,4,5-Tris(tetradecyloxy)benzoyloxy-2-hydroxybenzaldehyde (2): A weighed sample of compound (1) (6.00 g; 7.9 mmol) was dissolved in dichlormethane. 2,4-Dihydroxybenzaldehyde (1.09 g; 7.9 mmol) was added and the mixture was stirred until complete dissolution of the components. Then a sample of dicyclohexylcarbodiimide (2.25 g; 10.9 mmol) was added. The reaction mixture was stirred for 30 min. After that, a catalytic amount of dimethylaminopyridine was added and the mixture was stirred for 12h. Precipitated urea was filtered off on a glass filter. The solvent was removed on a rotary evaporator. The residue was chromatographed on silica gel by chloroform. The product was freeze dried from benzene. Yield: 5.61 g (80.6%). MS MALDI-ToF (m/z): found 902.33, calculated 902.36 (M⁺+Na). CHNO analysis (%): Calcd. for C₅₆H₉₄O₇: C 76.49; H 10.77; O 12.74. Found: C 75.93; H 11.17; O 12.70. ¹H NMR (CDCl₃, TMS, δ , ppm): 0.81 (t, 9H, CH₃-, J=6.10 Hz); 1.28-1.19 (m, 54H, -CH₂-Alk); 1.41 (t, 6H, Alk-CH₂-CH₂-O-, J=6.10 Hz); 1.69 (m, 6H, -CH₂-Alk); 1.76 (m, 6H, -CH₂-Alk); 3.97 (m, 6H, Alk-CH₂-O); 6.83-6.79 (d, 2H, Ph-H, J=7.93 Hz); 7.19 (s, 1H, Ph-H); 7.56-7.54 (d, 2H, Ph-H, J=8.54 Hz); 9.82 (s, 1H, OH-); 11.19 (s, 1H, COH). ¹³C NMR (CDCl₃, TMS, δ , ppm): 14.15 (CH₃-), 22.72 (CH₃-CH₂-), 26.09 (-CH₂-), 29.41 (-CH₂-), 29.72 (-CH₂-), 29.74 (-CH₂-), 30.37 (-CH₂-), 31.96 (CH₃-CH₂-CH₂-), 69.30 (-O-CH₂-Alk), 73.64 (-O-CH₂-Alk), 108.64 (CH_{arom}), 110.98 (CH_{arom}), 114.18 (CH_{arom}), 118.69 (C_{arom}), 123.06 (C_{arom}), 134.97 (CH_{arom}), 143.39 (C_{arom}), 153.04 (C_{arom}), 157.82 (C_{arom}), 163.21 (C_{arom}-OH), 164.06 (C(O)O), 195.52 (CHO). FT-IR (KBr) ν_{max}/cm^{-1} : 4329, 4253 (intermolecular hydrogen bond), 3433 (OH), 3091 (aromatic CH vibrations), 2919-2848 (CH₂-), 1727 (C=O), 1386 – 1274 (Ph-CHO), 1193 (Alk-C-O-C(Ph)), 982 (flat deformational C-H vibrations of 1,3,4,5-substituted aromatic ring), 873 (OH).

2.2c Benzyl ester of 3,5-di[3,4,5-tris(tetradecyloxy) *benzoyloxy benzoic acid* (3): A weighed sample of compound (1) (13.11 g; 17.27 mmol) was dissolved in dichlormethane. Benzyl ester of 3,5-dihydroxybenzoic acid (2.11 g; 8.64 mmol) was added and the mixture was stirred until complete dissolution of the components. Then a sample of dicyclohexylcarbodiimide (3.02 g;14.63 mmol) was added and the reaction mixture was stirred for 30 min. After that, a catalytic amount of dimethylaminopyridine was added and the mixture was stirred for 12 h. Precipitated urea was filtered off on a glass filter. The solvent was removed on a rotary evaporator. The residue was chromatographed on silica gel by chloroform. The product was recrystallized from a 1:1 acetonitrile-chloroform mixture and filtered off. Yield: 13.21 g (88.53%). MS MALDI-ToF (m/z): found 1748.22, calculated 1749.71 (M⁺+Na). CHNO analysis (%): Calcd. for C₁₁₂H₁₈₈O₁₂: C 77.91; H 10.97; O 11.12. Found: C 77.41; H 11.84; O 10.75. ¹H NMR (CDCl₃, TMS δ , ppm): 0.89 (t, 18H, Alk-CH₃, J=5.49 Hz); 1.34-1.26 (m, 108 H, -CH₂-Alk); 1.49 (s, 12H, -CH₂-Alk); 1.76 (m, 12H, -O-CH₂-Alk); 1.83 (m, 12H, -CH₂-Alk); 4.04 (m, 12H, Alk-CH₂-O-); 5.38 (s, 2H, O-CH₂-Ph); 7.32 (s, 2H, Ph-H); 7.36 (s, 2H, Ph-H); 7.39 (m, 4H, Ph-H); 7.44 (s, 2H, Ph-H); 7.83 (s, 2H, Ph-H). ¹³C NMR (CDCl₃, TMS, δ , ppm): 14.14 (CH₃-), 22.71 (CH₃-CH₂-), 26.09 (-O-CH₂-CH₂-CH₂-), 29.41 (CH₃-CH₂-CH₂-CH₂-), 29.66 (-O-CH₂-CH₂-), 30.37 (-CH₂-Alk), 31.95 (CH₃-CH₂-CH₂-), 67.31 (-CH₂-), 69.27 (-O-CH₂-Alk), 73.61 (-O-CH₂-Alk), 108.57 (CH_{arom}), 120.64 (CH_{arom}), 123.16 (CH_{arom}), 128.45 (CH_{arom}), 128.67 (CH_{arom}), 132.34 (CH_{arom}), 135.56 (C_{arom}), 143.26 (C_{arom}), 151.42 (Carom), 153.02 (Carom), 164.51 (C=O), 164.84 (C=O). FT-IR (KBr), ν_{max}/cm^{-1} : 4321, 4253 (intermolecular hydrogen bond), 3414 (OH), 3069 (aromatic vibrations of C-H), 2922-2849 (-CH₂-), 2631 (-CH₃-), 1729 (C=O), 1228-1194 (flat deformational C-H vibrations of 1,3,4,5-substituted aromatic ring), 1115 (-C-O-C-), 890-856 (non-planar deformational C-H vibrations of 1,3,4,5-substituted aromatic ring).

2.2d 3,5-Di[3,4,5-tris(tetradecyloxy)benzoyloxy] benzoic acid (4): The calculated amount of catalyst 5% Pd/C (0.56 g) was mixed with dioxane and activated

with hydrogen in a steel hydrogenation reactor. After that, a solution of 8.46 g of compound (3) in 100 mL of dioxane was added and the reaction mixture was stirred at 50°C under hydrogen (4 atm) until the necessary amount of hydrogen was consumed. The reaction mixture was twice filtered through a glass filter, and solvent was removed on a rotary evaporator. The residue was dissolved in benzene and freeze dried to obtain a white solid product. Yield: 5.01 g (62.5%). MS MALDI-ToF (m/z): found 1657.06, calculated 1659.59 (M⁺+Na). CHNO analysis (%): Calcd. for C₁₀₅H₁₈₂O₁₂: C 77.06; H 11.21; O 11.73. Found: C 76.65; H 12.10; O 11.25. ¹H NMR (CDCl₃, TMS, δ , ppm): 0.80 (m, 18H, Alk-CH₃); 1.18 (m, 54H, -CH₂-Alk); 1.42 (s, 12H, O-CH₂-CH₂-Alk); 1.69 (m, 12H, -CH₂-Alk); 1.77 (m, 12H, -CH₂-Alk); 3.97 (m, 12H, O-CH₂-Alk); 7.33 (s, 4H, Ph-H); 7.35 (s, 1H, Ph-H); 7.81 (d, 2H, Ph-H, J=1.83 Hz). ¹³C NMR (CDCl₃, TMS, δ , ppm): 14.15 (CH₃-), 22.71 (CH₃-CH₂-), 26.11 (-CH₂-Alk), 29.41-29.77 (-CH₂-Alk), 30.37 (-O-CH₂-CH₂-), 31.96 (CH₃-CH₂-CH₂-), 69.29 (-O-CH₂-Alk), 73.63 (-O-CH₂-Alk), 108.57 (CH_{arom}), 123.48 (C_{arom}), 143.29 (C_{arom}), 152.97 (C_{arom}), 164.48 (C(O)OH). FT-IR (KBr), v_{max}/cm⁻¹: 4334, 4249 (intermolecular hydrogen bond), 3414 (OH), 3088 (aromatic vibrations of C-H), 2920-2852 (-CH₂-), 2632 (-CH₃-), 1751 (C=O), 1122 (-C-O-C), 999 (flat deformational C-H vibrations of 1,3,4,5-substituted aromatic ring), 924 (-OH), 856 (non-planar deformational C-H vibrations of 1,3,4,5-substituted aromatic ring).

2.2e 3,5-Di[3,4,5-tris(tetradecyloxy)benzoyloxy]ben*zoyl-4-oxy-2-hydroxybenzaldehyde* (5): Compound (5) was obtained from (4) similar to (2) described earlier. The product was recrystallized from the 1:1 acetonitrile-chloroform mixture and filtered off. Yield: 1.37 g (63.63%). MS MALDI-ToF (m/z): found 1778.19, calculated 1779.69 (M⁺+Na). CHNO analysis (%): Calcd. for C₁₁₂H₁₈₆O₁₄: C 76.58; H 10.67; O 12.75. Found: C 76.48; H 11.15; O 12.37. ¹H NMR (CDCl₃, TMS, δ, ppm): 0.81 (t, 18H, CH₃-Alk, J=6.71 Hz); 1.18-1.29 (m, 108H, -CH₂-Alk); 1.42 (m, 12H, -O-CH₂-CH₂-Alk); 1.69 (m, 12H, -CH₂-Alk); 1.77 (m, 12H, -CH₂-Alk); 3.98 (m, 12H, -O-CH₂-Alk); 6.79 (s, 1H, Ph-H); 6.83 (m, 1H, Ph-H); 7.19 (s, 1H, Ph-H); 7.34 (m, 4H, Ph-H); 7.39 (s, 1H, Ph-H); 7.56 (s, 2H, Ph-H); 7.89 (m, 2H, Ph-H); 7.93 (s, 1H, Ph-H); 9.83 (s, 1H, OH); 11.19 (s, 1H, COH). ¹³C NMR (CDCl₃, TMS, δ, ppm): 14.09 (CH₃-), 22.67 (CH₃-CH₂-), 26.06 (-CH₂-), 29.26-30.33 (-CH₂-), 31.91 (CH₃-CH₂-CH₂-), 69.25 (-O-CH₂-Alk), 73.59 (-O-CH₂-Alk), 108.57 (CH_{arom}), 114.01 (CH_{arom}), 120.92 (C_{arom}), 121.94 (CH_{arom}), 122.91 (CH_{arom}), 130.72 (C_{arom}), 134.92 (CH_{arom}), 143.37 (C_{arom}), 145.63 (C_{arom}), 151.65 (C_{arom}), 152.99 (C_{arom}), 163.17 (C_{arom}-OH), 164.46 (C(O)O), 195.48 (CHO). FT-IR (KBr), ν_{max}/cm^{-1} : 4326, 4253 (intermolecular hydrogen bond), 3420 (-OH), 3103 (aromatic vibrations of CH), 2910-2850 (-CH₂-), 1738 (C=O), 1393–1288 (Ph-CHO), 1196 (Alk-C-O-C(Ph)), 984 (flat deformational C-H vibrations of 1,3,4,5-substituted aromatic ring), 873 (OH).

2.2f Benzyl ester 3,5-di[3,5-bis(3,4,5-tris(tetradecyloxy) benzovloxy)benzovloxy]-benzoic acid (6): Compound (6) was obtained from (4) similar to (3). Yield: 6.38 g (70.58%). MS MALDI-ToF (m/z): found 3494.08/3509.17, calculated 3499.39 (M⁺+NH₄)/ 3504.39 (M⁺+Na). CHNO analysis (%): Calcd. for C₂₂₄H₃₇₂O₂₆: C 77.28; H 10.77; O 11.95. Found: C 76.77; H 11.29; O 11.94. ¹H NMR (CDCl₃, TMS, δ, ppm): 0.80 (m, 36H, CH₃-Alk); 1.18-1.29 (m, 216H, -CH₂-Alk); 1.42 (m, 24H, -O-CH₂-<u>CH₂-Alk</u>); 1.69 (m, 24H, -CH₂-Alk); 1.77 (m, 24H, -CH₂-Alk); 3.98 (m, 24H, -O-CH₂-Alk); 5.31 (s, 2H, -O-CH₂-Ph); 7.19 (s, 1H, Ph-H); 7.27-7.29 (d, 2H, Ph-H, J=7.32 Hz); 7.34 (d, 8H, Ph-H, J=14.04 Hz); 7.37-7.39 (d, 4H, Ph-H, J=8.54 Hz); 7.79 (s, 2H, Ph-H); 7.90 (s, 3H, Ph-H). ¹³C NMR (CDCl₃, TMS, δ, ppm): 14.11 (CH₃-), 22.68 (CH₃-CH₂-), 26.07 (-CH₂-), 29.37 (-CH₂-), 29.69 (-CH₂-), 30.33 (-CH₂-), 31.91 (CH₃-CH₂-CH₂-), 67.36 (-CH₂-Ph), 69.24 (-O-CH₂-Alk), 73.58 (-O-CH₂-Alk), 108.53 (CH_{arom}), 121.14 (CH_{arom}), 122.96 (CH_{arom}), 128.41 (CH_{arom}), 128.65 (CH_{arom}), 130.92 (C_{arom}), 143.28 (Carom), 150.99 (Carom), 151.61 (Carom), 162.99 (C(O)O), 164.44 (C(O)O). FT-IR (KBr), ν_{max}/cm^{-1} : 4335, 4253 (intermolecular hydrogen bond), 3420 (OH), 3094 (aromatic vibrations of C-H), 2929-2850 (-CH₂-), 2666 (CH₃-), 1738 (C=O), 1187 (flat deformational C-H vibrations of 1,3,4,5-substituted aromatic ring), 1127 (-C-O-C-), 892 (non-planar deformational C-H vibrations of 1,3,4,5-substituted aromatic ring).

2.2g 3,5-Di[3,5-bis(3,4,5-tris(tetradecyloxy)benzoyloxy)benzoyloxy]-benzoic acid (7): Compound (7) was obtained from (6) similar to (4). Yield: 3.81 g (70.41%). MS MALDI-ToF (m/z): found 3406.23, calculated 3409.30 (M⁺+NH₄). CHNO analysis (%): Calcd. for C₂₁₇H₃₆₆O₂₆: C 76.86; H 10.88; O 12.27. Found: C 76.27; H 10.99; O 12.74. ¹H NMR (CDCl₃, TMS, δ , ppm): 0.80 (m, 36H, CH₃-Alk); 1.18-1.29 (m, 216H, -CH₂-Alk); 1.42 (m, 24H, -O-CH₂-<u>CH₂-Alk);</u> 1.69 (m, 24H, -CH₂-Alk); 1.76 (m, 24H, -CH₂-Alk); 3.98 (m, 24H, -O-CH₂-Alk); 7.19 (s, 4H, Ph-H); 7.34 (s, 8H, Ph-H); 7.39 (s, 2H, Ph-H); 7.82 (s, 1H, Ph-H); 7.91 (s, 2H, Ph-H). ¹³C NMR (CDCl₃, TMS, δ , ppm): 14.39 (CH₃-), 22.66 (CH₃-<u>CH₂-</u>), 26.02 (-CH₂-), 26.07 (-CH₂-), 29.28 (-CH₂-), 29.35 (-CH₂-), 30.31 (-CH₂-), 31.89 (CH₃-CH₂-<u>CH₂-</u>), 69.24 (-O-CH₂-Alk), 73.58 (-O-CH₂-Alk), 108.55 (CH_{arom}), 120.88 (CH_{arom}), 120.94 (CH_{arom}), 122.97 (CH_{arom}), 130.74 (C_{arom}), 131.19 (C_{arom}), 143.29 (C_{arom}), 149.48 (C_{arom}), 151.61 (C_{arom}), 152.99 (C_{arom}), 164.44 (C(O)O), 167.14 (COOH). FT-IR (KBr), ν_{max} /cm⁻¹: 4326, 4266 (intermolecular hydrogen bond), 3328 (OH), 3094 (aromatic vibrations of CH-), 2929-2850 (-CH₂-), 1738 (C=O), 1117 (-C-O-C-), 1003 (flat deformational C-H vibrations of 1,3,4,5-substituted aromatic ring), 892 (OH).

2.2h 3,5-Di[3,5-bis(3,4,5-tris(tetradecyloxy)benzoyloxy)benzoyloxy]-benzoyloxy-benzaldehyde (8): Compound (8) was obtained from (7) similar to (2). Yield: 2.51 g (68.39%). MS MALDI-ToF (m/z): found 3519.97, calculated 3511.37 (M⁺+NH₄). CHNO analysis (%): Calcd. for C₂₂₄H₃₇₀O₂₈: C 76.62; H 10.62; O 12.76. Found: C 77.13; H 10.63; O 12.24. ¹H NMR (CDCl₃, TMS, δ , ppm): 0.81 (t, 36H, CH₃-Alk, J=3.05 Hz; 1.19-1.29 (m, 216H, -CH₂-Alk); 1.42 (m, 24H, -O-CH₂-CH₂-Alk); 1.69 (m, 24H, -CH₂-Alk); 1.76 (m, 24H, -CH₂-Alk); 3.98 (m, 24H, -O-CH₂-Alk); 7.19 (s, 2H, Ph-H); 7.30 (s, 4H, Ph-H); 7.34 (s, 8H, Ph-H); 7.40 (m, 2H, Ph-H); 7.48 (s, 1H, Ph-H); 7.89 (s, 1H, Ph-H); 7.92 (s, 2H, Ph-H); 9.83 (s, 1H, OH); 11.19 (s, 1H, COH). ¹³C NMR (CDCl₃, TMS, δ, ppm): 14.09 (CH₃-), 22.68 (CH₃-CH₂-), 26.07 (-CH₂-), 29.35-30.68 (-CH₂-), 31.91 (CH₃-CH₂-<u>CH₂-</u>), 69.29 (-O-CH₂-Alk), 73.59 (-O-CH₂-Alk), 108.61 (CH_{arom}), 117.67 (CH_{arom}), 121.13 (Carom), 122.98 (Carom), 143.36 (Carom), 151.63 (Carom), 153.03 (Carom), 164.44 (C(O)O), 199.33 (CHO). FT-IR (KBr), ν_{max}/cm^{-1} : 4326, 4253 (intermolecular hydrogen bond), 3315 (OH), 3103 (aromatic vibrations of CH-), 2951-2859 (-CH₂-), 1738 (C=O), 1393-1279 (Ph-CHO), 1187 (Alk-C-O-C(Ph)), 1003 (flat deformational C-H vibrations of 1,3,4,5-substituted aromatic ring), 883 (OH).

3. Results and Discussion

3,4,5-Tris(tetradecyloxy)benzoic acid (1) was selected as the initial compound, and was synthesized in compliance with a standard method.²² For the regular branching, the method of doubling molecular size was employed, using the benzyl ester of 3,5-dihydroxybenzoic acid^{23,24} (scheme 1). The benzyl ester of 3,5-dihydroxybenzoic acid, employed as a protecting block in the esterification, was prepared by means of alkylation of the carboxyl group of 3,5-dihydroxybenzoic acid with



Scheme 1. Synthesis of compounds (1)–(8).

benzyl bromide in dry DMF.²⁵ The hydroxyl groups location in the structure of the benzyl ester of 3,5dihydroxybenzoic acid are sterically favorable for further molecular growth. The protecting group is easily introduced into the molecule, and selectively removed without any alterations in the structure of the formed compound. Additionally, the protecting group is stable in the presence of a large number of reagents used for further reactions.

The esterification was carried out by interaction between the carboxyl and hydroxyl groups with the aid of dicyclohexylcarbodiimide in dichloromethane. The benzyl group was selectively removed by hydrogenolysis using 5% Pd-C as catalyst in dry 1,4-dioxane²⁶ (scheme 1). The aldehydes (2), (5) and (8) were obtained by means of esterification of the corresponding acid and *para*-hydroxysalicylic aldehyde.

The structure of the compounds was established by FT-IR, NMR, MALDI-ToF mass-spectrometry (matrixassisted laser desorption/ionization) and elemental analysis. To aid identification of the products, reference markers were used. This allowed us to determine the structure and the extent of the reactions.

The results of NMR spectroscopy showed that the integrated intensity of the alkyl fragments of acids (1), (4) and (7) increases with generation number. The R–CH₂–O– fragments in the 3,4,5-position of gallic acid are used as reference signals which characterize the molecular growth, i.e. the ratio of protons in R–CH₂–O– to acids (1)/(4)/(7) is 6/12/24, respectively.

For acids (1), (4) and (7), it was found that the molecular ions are stabilized by sodium and ammonium ions. The data of MALDI-ToF analyses are given in figure 1. The mass of the molecular ions increased exponentially.

For esters (3) and (6), the formation of product after introducing the benzyl fragment was confirmed by the



Figure 1. MS MALDI-ToF spectra of acids (1), (4), and (7).

signal of $-CH_2$ -Ph at 5.38 and 5.31 ppm, respectively. Mass-spectra of compounds (3) and (6) demonstrate doubling of molecular mass from 1748 [M⁺+Na] (3) to 3498 [M⁺+NH₄] (6).

In the NMR spectra of compounds (2), (5), and (8), the signal of the –COH proton is located in the weak field range at 9.8 ppm, and the signal at 11.19 ppm refers to the –OH proton. The mass-spectra of the aldehydes show molecular ions which are stabilized by sodium and ammonium ions. The values are doubled in series from (2) to (5) and from (5) to (8).

The thermal stability and phase behavior of compounds (1)-(8) were studied by differential scanning calorimetry and polarized optical microscopy. Consequently, it was established that liquid crystalline properties are detected with increasing branching degree in a homologous series, summarized in table 1.

Thus, 3,4,5-tris(tetradecyloxy)benzoic acid (1) turns into an isotropic liquid at $T_{iso} = 70-71$ °C in the heating cycle without forming a mesophase. Cooling of the sample initially leads to the growth of needle-shaped crystals. The data of DSC experiments confirm the results of polarized microscopy, table 1. Lengthening of compound (1) to (2) does not promote the formation of a mesophase. For this sample, a "solid-solid" type phase transition at T = 31.96°C (Δ H = 10.02 kJ/mol) and formation of an isotropic liquid at $T_{iso} = 64-65$ °C are characterized in the heating cycle. Cooling of the sample is accompanied by the growth of crystals, starting from $T_{cr} = 34$ °C. Data of DSC experiments confirm the results of microscopy.

In comparison with samples (1) and (2), compound (3) has a more branched structure and does not have terminal polar groups, which leads to the occurrence of enantiotropic mesomorphism (figure 2). After examination of sample (3) by polarized microscopy, it was established that a mesophase appears after reheating, i.e. upon second heating (figure 2c). Sample (3) flows anisotropically by pressing at T = 30-48°C. Upon cooling, the sample becomes too cold, and anisotropy appears at $T = 17^{\circ}C$ as a nongeometric (planar) texture (figure 2a). Data of POM agrees with the differential scanning calorimetry data (figure 2b). As stated above, the feature in these kinds of esters is a protected active functional group which promotes the formation of a mesophase at the expense of microsegregation of the molecules. Upon first heating, the mesophase is difficult to detect because the system is very viscous and the compound is similar to an oligomer. After first heating and cooling, the sample is ordered, and this leads to the occurrence of a mesophase upon reheating (second heating). The exothermic peak in the heating process just before the peak at T = 48.48°C corresponds to

Compound	Thermal cycle	Peak phase-transition temperatures [°C] (transition enthalpies [kJ/mol])
$C_{49}H_{90}O_5(1)$	1 st heating	Cr 72.69 (84.43) → Iso
	1 st cooling	Iso 47.11 (-84.51) → Cr
C ₅₆ H ₉₉ O ₇ (2)	1 st heating	$Cr 31.96^* (10.02)^* \rightarrow Cr 64.51 (99.02) \rightarrow Iso$
	1 st cooling	Iso 34.11 (-80.11) \rightarrow Cr
$C_{112}H_{188}O_{12}$ (3)	2 nd heating	Cr 30.69 (72.18) \rightarrow Mes 48.48 (12.61) \rightarrow Iso
	2 nd cooling	Iso 17.61 (-88.99) \rightarrow Mes 1.67 (-1.21) \rightarrow Cr
C ₁₀₅ H ₁₈₂ O ₁₂ (4)	1 st heating	$Cr 47.61 (33.88) \rightarrow Mes 50.68 (-21.49) \rightarrow Cr 82.34 (102.45) \rightarrow Iso$
	1 st cooling	Iso $30.89 (-67.75) \rightarrow \text{Mes} - 66.14 (-2.41)^{[a]} \rightarrow \text{Cr}^{[a]}$
C ₁₁₂ H ₁₈₂ O ₁₄ (5)	2 nd heating	Cr 31.96 (26.53) \rightarrow Mes 55.49 (20.03) \rightarrow Iso
	2 nd cooling	Iso 40.44 (-8.43) \rightarrow Mes 20.34 (-25.47) \rightarrow Cr
C ₂₂₄ H ₃₇₀ O ₂₈ (6)	2^{nd} heating	Cr 49.51 (218.28)* \rightarrow Mes 59.98 (*) \rightarrow Iso
	2 nd cooling	Iso $34.32 (-107.82) \rightarrow \text{Mes}^{[a]}$
C ₂₁₇ H ₃₆₆ O ₂₆ (7)	1 st heating	$Cr 60.37 (4.07) \rightarrow Iso$
	1 st cooling	Iso 55.35 (-24.76) \rightarrow Mes 14.29 (-51.55) ^[b]
C ₂₂₄ H ₃₇₀ O ₂₈ (8)	1 st heating	$Cr 50.01 (11.24) \rightarrow Iso$
	1 st cooling	Iso $36.52 (-31.53) \rightarrow Mes \ 17.53 (-66.36) \rightarrow Cr \ [a]$

Table 1. The phase transition temperatures of compounds 1–8 according to DSC, during heating and cooling cycles.

Note: * - total area under curve; Cr - crystalline phase; Mes - mesophase; Iso - isotropic liquid. [a] Transition only observed after several day at room temperature. [b] Isotropic liquid at room temperature. No DSC peaks were detected below room temperature

some restructuring process in the development of the mesophase under heating.

Removal of the protective benzene group from compound (3) leads to an increase in the mesophase thermo stability of compound (4), and an extention of the temperature region of its existence (figure 3). Microscopic observations of sample (4) show that the mesophase with an uncharacteristic texture arises at $T_{mes} = 50^{\circ}C$ during the heating cycle (texture is nonrelevant), and it turns into an isotropic liquid at $T_{iso} = 80^{\circ}C$ via a mesophase transition (table 1). This process of crystallization is possible explained by aggregation of (4) which reaches a plateau after $T_{cr} = 50^{\circ}C$ within the investigated range of 49-71°C.²⁷ These aggregates are stable until further warming to T_{iso}. Upon cooling, the sample becomes too cold and anisotropic parts appear at room temperature only after a long time of exposure of the sample. Figure 3a shows an acinous fine domain texture, and against the background are large domains of mesophase which appear as a helical track. In addition, two phase transitions during the heating cycle are registered on the DSC curve (figure 3b). The thermograms of compounds (3) and (4) (by themselves) are not indicative of a mesophase, but the description of microscopic observation gives evidence for enantiotropic mesomorphism. Unfortunately, characteristic textures are not observed upon heating, but a mesophase is revealed by the fluidity of the compound upon pressure and a change of the rotation of crossed polarizers at 45 and 90 degrees. Undoubtedly, investigation of the compounds by X-ray diffraction might to help us to confirm mesomorphism, but under the condition that samples must be orientated. Unfortunately, such investigations are impossible owing to high viscosity. When we obtained the microphotos, we encountered complications owing to the considerable viscosity of the samples and difficulty in obtaining samples with a large domain texture.

Extention of compound (4) on the phenyl ring, and the presence of two polar groups in the ortho-position leads to a small decrease in the mesophase thermal stability (compound (5)). Characteristic texture mesophase of aldehyde (5) was not observed under first heating. A mesophase was observed only upon reheating. Anisotropy appears in the sample after 20–30 min. following cooling cycle.

Further modification of compound (4) to compound (6) leads to a reduction of the mesophase thermal stability, as compared with (4) (figure 4). Transition to an isotropic liquid is observed at $T_{iso} = 59.98^{\circ}C$ (figure 4c). The texture of a mesophase is more characteristic upon reheating. During cooling, anisotropy appears as a non-geometric texture, figure 4a, for the thick sample, and as oily striations to the thin sample, figure 4b. Such behavior can denote a chirality of the mesophase.

Removal of the protective group from compound (6) impairs the conditions for development of mesomorphism in compound (7), which turns into an isotropic liquid upon melting ($T_{iso} = 60^{\circ}$ C). During cooling, a texture with a great number of anisotropic points which lengthen, move, and change simultaneously were observed. The sample shows monotropic mesomorphism.



Figure 2. (a) Nongeometric texture of compound (3), heating cycle, $T = 47^{\circ}C$; (b) DSC curves of compound (3) in heating and cooling cycle. (c) DSC curves of compound (3) at 1st and 2nd heating.

Introduction of a phenyl ring with two polar groups into compound (7) yields compound (8), which vitrifies from the mesophase. Compound (8) melts at $T = 44^{\circ}C$ and turns into an isotropic liquid at $T_{iso} = 50^{\circ}C$. Upon cooling, a mesophase is formed at $T_{mes} = 36^{\circ}C$ with a non-geometric texture (figure 5). Subsequent cooling leads to the appearance of a coloured anisotropic pattern which does not change under shear stress, which characterizes anisotropic glass (Tg = -10.41° C, Δ Cp = 0.45 J/(g*K)).



Figure 3. (a) Fine domain texture of compound (4), cooling cycle, $T = 29^{\circ}C$; (b) DSC curves of compound (4) in heating and cooling cycles.



Figure 4. (a) Nongeometric texture of the thick sample (6) in cooling cycle, $T = 49^{\circ}C$; (b) oily striations texture of the thin sample (6), $T = 20^{\circ}C$, cooling cycle; (c) DSC curves of the sample in heating and cooling cycles.

In conclusion, we have synthesized a new series of compounds derived from the esters of 3,4,5-tris(tetradecyloxy)benzoic acid (2)-(8). It was found that starting from ester (3), mesomorphic properties are revealed, and they depend on the presence of polar terminal groups in compounds (2), (4), (5), (7) and (8) which take part in the formation of hydrogen bonds. For compounds (3) and (6), a mesophase is formed primarily by microsegregation. Increasing the molecular mass in series from (2) to (8) leads to anisotropic vitrification of compound (8).

The IR measurement of all compounds demonstrates the formation of complementary hydrogen bonds between fragments of polar groups in the case of carboxylic acid, aldehydes and esters. The IR absorption of



Figure 5. Texture of mesophase, cooling cycle, $T = 36^{\circ}C$.

acid (1) at 1688 cm^{-1} assigned to the C=O stretching of the carboxylic acid shifted to 1751 cm^{-1} (4) and 1738 cm^{-1} (7), (figure 6), indicating that the carboxylic acids (1), (4) and (7) are quantitatively formed the hydrogen bond by formation of symmetrical and asymmetrical dimers at lengthening of molecules.

This situation is further supported by the fact that the H-stretching peaks in the IR spectrum appears in the



Figure 6. Fragments of FT-IR spectra of acids (1), (4) and (7) in the H-bonded region.

H-bonded region (below 3400 cm^{-1}).²⁸ In particular, compound (1)–(8) have been found to interact in dimers by double intermolecular H-bonds and by intramolecular H-bonds.²⁹

4. Conclusions

A new series of compounds derived from esters of 3,4,5-tris(tetradecyloxy)benzoic acid were synthesized. It was established that liquid-crystalline properties of this series of dendrons arise from of the degree of branching. This behavior can be explained by the formation of hydrogen bonds, as well as processes of microsegregation of the links of the macromolecule.

Supplementary information (SI)

All additional information pertaining to characterization of the compounds using NMR spectra, FT-IR spectra and mass-spectra are given in the supporting information. The electronic supporting information can be seen in www.ias.ac.in/chemsci.

Acknowledgements

This work was supported by the grant of Russian Foundation for Basic Research No. 14-03-31280-mol_a and the grant of the President of the Russian Federation (No. MK-70.2014.3). Dr. Akopova O.B. is thankful for the grant of Ministry of education and science RF (No. 4.106.2014K). EA, NMR, FT-IR spectroscopy and DSC analysis were carried out by the equipments of Interlaboratory scientific center «Verhnevolzhskij region center of physicochemical researching». The authors would like to thank Dr. Simon Dalgleish (Nagoya University) for useful discussion.

References

- Newkome G R, Moorefield C N and Voegtle F 2001 In Dendrimers and dendrons: Concepts, syntheses and applications (Weinheim: Wiley-VCH) p. 636
- Smith D K, Hirst A R, Love C S, Hardy J G, Brignell S V and Huang B 2005 *Prog. Polym. Sci.* 30 220
- 3. Bauer S, Fisher H and Ringsdorf H 1993 Angew. Chem.Int. Ed. **32** 1589
- Pesak D J and Moore J S 1997 Angew. Chem. Int. Ed. 36 1636

- 5. Meier H and Lehmann M 1998 Angew. Chem. Int. Ed. 37 643
- 6. Cameron J H, Facher A, Lattermann G and Diele S 1997 *Adv. Mater.* **9** 398
- 7. Tian Y Q, Kamata K, Yoshita H and Iyoda T 2006 *Chem. Eur. J.* **12** 584
- 8. Frauenrath H 2005 Prog. Polym. Sci. 30 325
- Turrin C-O, Maraval V, Leclaire J, Dantras E, Lacabanne C, Caminade A-M and Majoral J-P 2003 *Tetrahedron* 59 3965
- Ropponen J, Tamminen J, Lahtinen M, Linnanto J, Rissanen K and Kolehmainen E 2005 *Eur. J. Org. Chem.* 2005 73
- Ropponen J, Tuuttila T, Lahtinen M, Nummelin S and Rissanen K 2004 J. Polym. Sci. Part A. 42 5574
- 12. Percec V, Cho W-D, Ungar G and Yeardley D J P 2001 *J. Am. Chem. Soc.* **123** 1302
- Percec V, Won B C, Peterca M and Heiney P A 2007 J. Am. Chem. Soc. 129 11265
- Percec V, Peterca M, Dulcey A E, Imam M R, Hudson S D, Nummelin S, Adelman P and Heiney P A 2008 J. Am. Chem. Soc. 130 13079
- 15. Grebenkin M F and Ivaschenko A V 1989 In *Liquid* crystalline materials (Moscow: Khimiya) p. 228
- 16. Tschierske C 2001 J. Mater. Chem. 11 2647
- 17. Pegenau A, Hegmann T, Tschierske C and Diele S 1999 *Chem. Eur. J.* **5** 1643
- Chervonova U V, Gruzdev M S, Kolker A M, Manin N G and Domracheva N E 2010 *Rus. J. Gen. Chem.* 80 1954
- Chervonova U V, Gruzdev M S and Kolker A M 2011 Rus. J. Gen. Chem. 81 1853
- Vorobeva V E, Domracheva N E, Pyataev A V, Gruzdev M S and Chervonova U V 2015 Low Tem. Phys. 41 15
- 21. Chervonova U V, Gruzdev M S and Kolker A M 2011 *Rus. J. Gen. Chem.* **81** 2288
- 22. Schaz A, Valaityte E and Lattermann G 2005 *Liq. Cryst.* **32** 513
- 23. Tully D C, Wilder K, Fréchet J M J, Trimble A R and Quate C F 1999 *Adv. Mater.* **11** 314
- 24. Saudan C, Balzani V, Gorka M, Lee S-K, Maestri M, Vicinelli V and Vögtle F 2003 J. Am. Chem. Soc. 125 4424
- 25. Denieul M P, Laursen B, Hazell R and Skrydstrup T 2000 J. Org. Chem. 65 6052
- 26. Shreenivasa Murthy H N and Sadashiva B K 2004 *Liq. Cryst.* **31** 1347
- 27. Seeboth Arno, Lotzsch Detlef, Ruhmann Ralf and Muehling Olaf 2014 *Chem. Rev.* **114** 3037
- 28. Ishihara S, Furuki Y and Takeoka S 2008 *Polym. Adv. Technol.* **19** 1097
- 29. Beltrán E., Cavero E., Barberá J, Serrano J L, Elduque A and Giménez R 2009 *Chem. Eur. J.* **15** 9017