

Strong Electronic and Magnetic Coupling in M_4 ($M = \text{Ni}, \text{Cu}$) Clusters via Direct Orbital Interactions between Low-Coordinate Metal Centers

Khetpakorn Chakarawet, Mihail Atanasov, Jonathan Marbey, Philip C. Bunting, Frank Neese, Stephen Hill, and Jeffrey R. Long*



Cite This: <https://dx.doi.org/10.1021/jacs.0c08460>



Read Online

ACCESS |



Metrics & More




Article Recommendations



Supporting Information

ABSTRACT: We present an extensive study of tetranuclear transition-metal cluster compounds $M_4(\text{NP}^t\text{Bu}_3)_4$ and $[M_4(\text{NP}^t\text{Bu}_3)_4][\text{B}(\text{C}_6\text{F}_5)_4]$ ($M = \text{Ni}, \text{Cu}$; $t\text{Bu} = \text{tert-butyl}$), which feature low-coordinate metal centers and direct metal–metal orbital overlap. X-ray diffraction, electrochemical, magnetic, spectroscopic, and computational analysis elucidate the nature of the bonding interactions in these clusters and the impact of these interactions on the electronic and magnetic properties. Direct orbital overlap results in strongly coupled, large-spin ground states in the $[\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4]^{+/0}$ clusters and fully delocalized, spin-correlated electrons. Correlated electronic structure calculations confirm the presence of ferromagnetic ground states that arise from direct exchange between magnetic orbitals, and, in the case of the neutral cluster, itinerant electron magnetism similar to that in metallic ferromagnets. The cationic nickel cluster also possesses large magnetic anisotropy exemplified by a large, positive axial zero-field splitting parameter of $D = +7.95$ or $+9.2 \text{ cm}^{-1}$, as determined by magnetometry or electron paramagnetic resonance spectroscopy, respectively. The $[\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4]^+$ cluster is also the first molecule with easy-plane magnetic anisotropy to exhibit zero-field slow magnetic relaxation, and under a small applied field, it exhibits relaxation exclusively through an Orbach mechanism with a spin relaxation barrier of 16 cm^{-1} . The $S = 1/2$ complex $[\text{Cu}_4(\text{NP}^t\text{Bu}_3)_4]^+$ exhibits slow magnetic relaxation via a Raman process on the millisecond time scale, supporting the presence of slow relaxation via an Orbach process in the nickel analogue. Overall, this work highlights the unique electronic and magnetic properties that can be realized in metal clusters featuring direct metal–metal orbital interactions between low-coordinate metal centers.



INTRODUCTION

Molecular magnetism broadly encompasses the design and study of molecules and molecule-based materials exhibiting magnetic properties and is largely motivated by prospective applications in areas such as magnetic memory, spintronics, quantum computing, and permanent magnetism.^{1,2} Multinuclear transition-metal complexes have attracted considerable interest in this regard, due in large part to the discovery that magnetic exchange interactions in such molecules can give rise to numerous interesting properties, particularly single-molecule magnet behavior.³ Indeed, the field of single-molecule magnetism originated following

additionally give rise to a very large magnetic anisotropy, with $D = -12.34 \text{ cm}^{-1}$, resulting in the largest barrier to magnetic relaxation yet characterized for any transition-metal cluster, $U_{\text{eff}} = 87 \text{ cm}^{-1}$.

More broadly, with the steadily growing number of metal clusters featuring direct metal–metal interactions, the possibility emerges to access unique electronic properties otherwise unattainable in traditional metal clusters, such as high levels of electron delocalization⁹ and meta-atom behavior.⁷ Density functional theory has been widely used to study the magnetic properties of iron–sulfur clusters featuring direct metal–metal interactions.^{13,14} Nonetheless, configuration interactions have been applied only to computational studies of dinuclear complexes due in part to the challenge in the complex electronic structures of these metal clusters.^{15–18} Indeed, such studies are potentially of great significance beyond the elucidation of molecular properties, as magnetic direct exchange through delocalized electrons also governs permanent magnetism in ferromagnets possessing high Curie temperatures, such as metallic iron, cobalt, and nickel.^{19,20} Magnetic studies of polynuclear metal complexes^{1,15,21,22} have previously enabled the refinement of an earlier model for superexchange originally proposed in solid MnO.²³ Likewise, the detailed electronic, magnetic, and theoretical investigation of paramagnetic metal clusters featuring direct metal–metal orbital overlap stands as an important area of fundamental inquiry with the potential to provide new insights into magnetic exchange in metallic clusters and bulk metals.


Here, we report the metal–metal bonded complexes $[\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4]^{+/0}$, which exhibit large magnetic anisotropy and large-spin ground states that are thermally persistent to 300 K. Correlated electronic structure *ab initio* calculations are employed to rationalize the effect of metal–metal interactions on the magnetic properties, and they reveal strong Ni–Ni ferromagnetic coupling arising from a direct exchange mechanism resembling that in ferromagnetic metals. The complex $[\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4]^+$ is also the first easy-plane molecular magnet to exhibit slow magnetic relaxation under zero applied field, while under a small applied field the complex relaxes solely through an Orbach mechanism. In addition, we synthesized the cationic $S = 1/2$ tetranuclear copper analogue $[\text{Cu}_4(\text{NP}^t\text{Bu}_3)_4]^+$, which exhibits spin-vibronic relaxation on the millisecond time scale at low temperatures, suggesting that the observation of an Orbach barrier in the nickel analogue is also a result of slow spin-vibronic relaxation. These findings highlight the unique electronic and magnetic properties accessible with complexes featuring metal–metal bonding interactions.

RESULTS AND DISCUSSION

Synthesis and Characterization. The compound $\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4$ (**1**) was prepared via a modification of a previously reported synthesis.²⁴ In brief, the salt metathesis reaction of LiNP^tBu_3 and NiBr_2 in tetrahydrofuran (THF) and 1,2-dimethoxyethane was followed by *in situ* reduction with KC_8 to yield the desired product, which was separated from the reaction mixture by extraction with hexane. Compound **1** ($n\text{-C}_6\text{H}_{14}$) was isolated as dark-green block-shaped crystals from a concentrated hexane solution stored at -30°C . Single-crystal X-ray diffraction characterization revealed that **1** ($n\text{-C}_6\text{H}_{14}$) crystallizes in the space group $C2/c$, with a crystallographic 2-fold rotational axis passing through two diagonal Ni atoms of the cluster, similar to the previously reported structure of

1·2THF.²⁴ The molecule adopts an idealized D_{2d} symmetry (Figure S1). Each Ni atom is coordinated by the N atoms of two phosphinimide ligands, resulting in an almost linear coordination geometry around each Ni center, with an average N–Ni–N angle of $176.4(6)^\circ$. All Ni atoms lie within the same plane, as dictated by the crystallographic 2-fold symmetry. The average of the four Ni···Ni distances is $2.3631(1) \text{ \AA}$, which is within range of direct metal–metal interactions.²⁵

The oxidation of **1** using $[\text{FeCp}_2][\text{B}(\text{C}_6\text{F}_5)_4]$ ($\text{Cp}^- = \text{cyclopentadienyl anion}$) yielded $[\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4][\text{B}(\text{C}_6\text{F}_5)_4]$ (**2**) as a dark-blue powder that could be crystallized as dark-blue block-shaped crystals from a THF/hexane mixture at -30°C . X-ray diffraction analysis revealed that the compound crystallizes in the space group $P2_12_12_1$ and that the tetranuclear cluster retains its structural integrity upon oxidation (Figure 1,



longer than the Ni...Ni distance of 2.3631(1) Å in 1-*n*-C₆H₁₄ (Table 1), which may be attributed to the population of the extra electron from each copper in metal–metal antibonding orbitals, resulting in a total Cu...Cu bond order of zero (see below).

The oxidation of 3 by [FeCp₂][B(C₆F₅)₄] yielded 4·1.4DFB·0.3*n*-C₆H₁₄ (DFB = 1,2-difluorobenzene) as black rod-shaped crystals after recrystallization from DFB/hexane at −30 °C. Compound 4 crystallizes in the space group *P* $\bar{1}$, and initial structure refinement revealed an intact tetranuclear cluster (Figure S4). In addition, two sites of residual electron density were located in the Fourier difference map above and below the Cu₄ plane. Further analysis revealed that this electron density corresponds to the disordered pentanuclear copper(I) species [Cu₅(NP^tBu₃)₄][B(C₆F₅)₄] (Figure S5), which was further confirmed by mass spectrometry (Figure S7). Refinement of the diffraction data for 4·1.4DFB·0.3*n*-C₆H₁₄ revealed that this compound consists of 81% [Cu₄(NP^tBu₃)₄][B(C₆F₅)₄] cocrystallized with 19% [Cu₅(NP^tBu₃)₄][B(C₆F₅)₄]. A comparison of the metrical parameters of [Cu₄(NP^tBu₃)₄][B(C₆F₅)₄] with the parent neutral compound revealed that the Cu...Cu and Cu–N distances decrease slightly in the cationic cluster (Tables 1 and S3), as expected upon the removal of an electron from an antibonding orbital (see below).

Electrochemistry. The cyclic voltammogram collected for 2 in DFB features the expected one-electron [Ni₄(NP^tBu₃)₄]⁺⁰ redox couple at *E*_{1/2} = −2.02 V versus [FeCp₂]⁺⁰ (Figure 2). Two additional one-electron processes




Figure 2. Cyclic voltammograms for 2 (blue) and 4 (red), obtained in DFB solution containing 1 mM analyte and 0.1 M electrolyte (NP^tBu₃)PF₆. The arrow represents the starting point and the direction of the scan.

occur at *E*_{1/2} = −0.66 and +0.54 V, corresponding to the [Ni₄(NP^tBu₃)₄]^{2+/+} and [Ni₄(NP^tBu₃)₄]^{3+/2+} redox couples, respectively. Comproportionation constants of 1.0 × 10²³ and 2.1 × 10²⁰ were determined for the mixed-valence complexes [Ni₄(NP^tBu₃)₄]⁺ and [Ni₄(NP^tBu₃)₄]²⁺, respectively. These values are much larger than those of typical mixed-valence complexes and are indicative of a delocalized electronic structure arising from direct metal–metal orbital overlap.^{7,10,11}

The cyclic voltammogram for 4 in DFB features three one-electron processes at −0.63, +0.17, and +0.98 V, assigned to

the [Cu₄(NP^tBu₃)₄]⁺⁰, [Cu₄(NP^tBu₃)₄]^{2+/+}, and [Cu₄(NP^tBu₃)₄]^{3+/2+} couples, respectively (Figure 2). Comproportionation constants of 1.9 × 10¹³ and 5

300 K using the van Vleck equation and assuming an $S = 5/2$ ground state and an $S = 3/2$ excited state yielded an energy separation of 221 cm^{-1} (Figure S8). Below $\sim 90\text{ K}$, $\chi_M T$ gradually decreases until a dramatic downturn occurs at $\sim 40\text{ K}$, reaching a value of $3.41\text{ cm}^3\text{ K/mol}$ at 2 K . In contrast, $\chi_M T$ for **1** exhibits much less variation across the examined temperature range. In particular, the data uniformly and gradually decrease from 300 to $\sim 20\text{ K}$ before dropping to a value of $3.00\text{ cm}^3\text{ K/mol}$ at 2 K . The low-temperature drop in the data for compounds **1** and **2** is indicative of significant zero-field splitting.

Low-temperature magnetization measurements were carried out to further quantify the magnetic anisotropy in **1** and **2** and the tetranuclear cluster in **4**. For compound **4**, the reduced magnetization plot features superimposable isofield lines, as expected for an $S = 1/2$ spin system (Figure S9). In contrast, the reduced magnetization plots for **1** and **2** feature nonsuperimposable isofield lines (Figures S10 and S11), indicative of significant zero-field splitting. The magnetization data for **1** and **2** were accordingly fit using the following Hamiltonian

$$\hat{H} = D\hat{S}_z^2 + E(\hat{S}_x^2 - \hat{S}_y^2) + \mu_B H \cdot \mathbf{g} \cdot \hat{\mathbf{S}} \quad (1)$$

where D and E are the axial and transverse zero-field splitting parameters, respectively, $\hat{S}_{x/y/z}$ is the electron spin projection operator onto the $x/y/z$ axis, μ_B is the Bohr magneton, $\mathbf{g}$ is the Landé g tensor, and H is the magnetic field. The fits yielded parameters of $D = -1.93(1)\text{ cm}^{-1}$, $|E| = 0.53(3)\text{ cm}^{-1}$, $g_{\parallel} = 2.180(2)$, and $g_{\perp} = 2.249(1)$ for **1** and $D = +7.95(5)\text{ cm}^{-1}$, $E = 1.17(1)\text{ cm}^{-1}$, $g_{\parallel} = 2.28(1)$, and $g_{\perp} = 2.188(1)$ for **2**.

It is important to note that the vast majority of transition-metal clusters exhibit $|D| < 1\text{ cm}^{-1}$,⁵ for example, $D = -0.46\text{ cm}^{-1}$ for $\text{Mn}_{12}\text{O}_{12}(\text{O}_2\text{CCH}_3)_{16}(\text{OH}_2)_4$ ($S = 10$),²⁷ although smaller spin clusters may exhibit slightly larger $|D|$ values. For instance, the $S = 3$ compound $[\text{Ni}_3\text{L}_3(\text{OH})(\text{Cl})](\text{ClO}_4)$ (HL = 2-[(3-dimethylaminopropylimino)methyl]phenol) exhibits a value of $D = -1.32\text{ cm}^{-1}$, previously the record among Ni clusters.²⁸ The even larger D values measured for **1** and **2** likely arise from the weak ligand field generated by the formally two-coordinate environment, as demonstrated previously for $[\text{Co}_4(\text{NP}^t\text{Bu}_3)_4][\text{B}(\text{C}_6\text{F}_5)_4]$.¹¹ Indeed, a low-coordinate environment is ideal for generating large anisotropy²⁹ because the associated weak ligand field minimizes the energy splitting between states contributing to orbital angular momentum, thus maximizing the zero-field splitting generated through second-order spin–orbit coupling.

Electron Paramagnetic Resonance. High-field, high-frequency EPR spectra were collected to more accurately quantify the magnetic anisotropy in $\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4$ (**1**) and $[\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4][\text{B}(\text{C}_6\text{F}_5)_4]$ (**2**). Data were collected on crystalline powder samples using microwave frequencies in the range 60 – 532 GHz and magnetic fields between 0 and 14.5 T .³⁰ Representative spectra shown in Figure 4 are markedly different for the two compounds. The spectra for **1** exhibit multiple sharp transitions between 64 and 512 GHz (Figure S12a), while the spectra for **2** obtained at frequencies between 65 and 224 GHz are characterized by two

system (Figure 4, lower, red), in agreement with the results from magnetization measurements.

Finally, the X-band EPR spectrum for **4** collected at 2 K in frozen 2-methyltetrahydrofuran (2-MeTHF) features a very broad signal centered around $g = 2.07$ (Figure S16). The broad spectrum is presumed to result from extensive hyperfine interactions involving the four Cu nuclei (^{63}Cu and ^{65}Cu isotopes, both with $I = 3/2$), ligand disorder, and paramagnetic relaxation.

Electronic Structure Analysis. Thermally persistent, large-spin ground states in clusters with direct metal–metal interactions have been rationalized as arising from electrons in molecular orbitals generated from direct orbital overlap.^{6,7,9–11,16,17} However, detailed calculations to support this hypothesis have been performed only on dinuclear complexes.^{16,17} Here, a qualitative molecular orbital analysis (Figure 5) was performed in tandem with density functional theory (DFT) calculations (Figures S17 and S18) to better

understand the nature of the orbital interactions within the $\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4$ cluster and the associated magnetic behavior.

A molecular orbital diagram was first constructed for a hypothetical planar molecule in D_{4h} symmetry as shown on the left side of Figure 5. Here, 20 metal 3d orbitals may engage in bonding interactions according to symmetry considerations. Seven metal group orbitals interact with the 2p group orbitals of the coordinated N atoms, resulting in seven M–L antibonding orbitals (Figure 5, left, red). The remaining 13 orbitals are metal-centered and form 4 M–M bonding, 6 M–M nonbonding, and 3 M–M antibonding molecular orbitals (Figure 5, left; blue, green, and yellow, respectively). Upon lowering the molecular symmetry from D_{4h} to idealized D_{2d} symmetry, the $1b_{1g}$ M–M bonding orbital mixes with a ligand group orbital to form a $3b_2$ orbital (Figure 5, right), as also indicated by DFT calculations (Figure S17). Furthermore, a Walsh analysis reveals that M–L and M–M interactions are of approximately the same order of magnitude, which is the result of the weak ligand field originating from the two-coordinate metal environment. The overall 3d orbital energy splitting determined from DFT calculations is $25\,000\text{ cm}^{-1}$ (Figure S18).

According to the molecular orbital diagram for idealized D_{2d} symmetry, the oxidation of $\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4$ to $[\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4]^+$ is associated with the removal of an electron from the $3a_1^*$ orbital, which has partial metal–metal bonding character (Figure S19, upper). Loss of this electron results in a lengthening of the Ni...Ni distance, as shown by X-ray diffraction analysis (Table 1). In contrast, the oxidation of $\text{Cu}_4(\text{NP}^t\text{Bu}_3)_4$ to $[\text{Cu}_4(\text{NP}^t\text{Bu}_3)_4]^+$ results in the removal of an electron from the $6e^*$ orbital, which has partial M–M antibonding character (Figure S19, lower). This change results in a shortening of the Cu...Cu distances, as observed in a comparison of the solid-state structures of both compounds. It should be noted that, on the basis of this analysis, $\text{Cu}_4(\text{NP}^t\text{Bu}_3)_4$ has a total M–M bond order of zero, which is reflected in its longer M...M distance compared to that in the M_4 clusters in **1**, **2**, and **4**. In both $\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4$ and $\text{Cu}_4(\text{NP}^t\text{Bu}_3)_4$, oxidation leads to shortening of the M–N distances (Table 1), as expected for the removal of an electron from a M–L antibonding orbital.

The spin energy levels of the truncated model complexes $\text{Ni}_4(\text{NPH}_3)_4$ (**1'**) and $[\text{Ni}_4(\text{NPH}_3)_4]^+$ (**2'**) were computed using the complete active space self-consistent field (CASSCF) method³¹ modulated by second-order N -electron valence perturbation theory (NEVPT2),^{32–34} as implemented in the ORCA program.³⁵ Calculations on **1'** were carried out by correlating 4 electrons on 4 localized 3d molecular orbitals [CAS(4,4)] and extended active spaces, correlating 12 electrons on 8 [CAS(12,8)] and 28 electrons on 16 [CAS(28,16)] localized molecular orbitals. All of these calculations yielded a well-isolated $S = 2$ ground state (Table S5). From the CASSCF calculation, an electron-transfer energy of 6.1 eV was found between the lateral pairs of Ni centers, indicating a dominant exchange pathway through adjacent metal centers (Figure 6). Moreover, a calculation with an extended active space, which included the lower-lying, fully occupied orbitals, revealed excited states resulting in two unpaired electrons on a Ni^{2+} site in **1'**, for which parallel spin alignment is governed by Hund's rule (Figure




Figure 6. Localized magnetic orbitals for **1'**, as obtained from CAS(4,4) calculations with computed charge-transfer parameters between the lateral (6.1 eV) and diagonal (0.6 eV) Ni–Ni pairs. Green and blue spheres represent Ni and N atoms, respectively.




Figure 7. Schematic illustration of the excited states in **1'** (right) found from CASSCF calculations using an extended active space. The excited state features a Ni^{2+} center with a parallel alignment of spins according to Hund's rule. The itinerant electron is highlighted in red.

excitation is reminiscent of ferromagnetism in magnetic metals, where a broad *s* conduction band overlaps with a half-filled narrow *d* band, providing a pathway for direct exchange via itinerant electrons, where the ferromagnetic exchange interaction is governed by Hund's rule on each metal atom.²⁰

Calculations performed on **2'** confirmed an $S = 5/2$ ground state and the presence of an $S = 3/2$ excited state that lies 73 cm^{-1} higher in energy (Table S6). This value is smaller than the ground to first excited state splitting determined from fitting the $\chi_{\text{M}}T$ versus *T* data for **2** from 150 to 300 K using the van Vleck equation (221 cm^{-1} , see Figure S8). However, in both cases the separation is such that the population of the $S = 3/2$ excited state is expected at ambient temperature according to Boltzmann statistics, consistent with the temperature dependence of the $\chi_{\text{M}}T$ data for **2** (Figure 3).

Magnetization Relaxation Dynamics. Systems exhibiting large negative values of *D* (easy-axis anisotropy) have long been the primary focus in the pursuit of new single-molecule magnets for two main reasons: $D < 0$ gives rise to a maximal $\pm M_{\text{S}}$ ground state and the suppression of quantum tunneling of the magnetization, and for integer *S*, only systems with $D < 0$ are guaranteed to exhibit the doubly degenerate ground state required for slow magnetic relaxation.³ However, in recent years a number of molecules with easy-plane anisotropy $D > 0$ and half-integer spins have been found to undergo slow magnetic relaxation under an applied field.^{36,37} Spin inversion within the ground state in such systems is prohibited by Kramers' theorem, and thus slow magnetic relaxation occurs via Orbach, Raman, and/or hyperfine-interaction-mediated direct processes.³⁸ Given the presence of a significant easy-

plane anisotropy in **2**, it was therefore of interest to probe the dynamic magnetic properties of this compound.

AC magnetic susceptibility measurements were first carried out on a crystalline sample of **2**. Under zero applied field, compound **2** exhibits no signal in the molar out-of-phase susceptibility (χ_{M}''). However, under a small applied field of 400 Oe, peaks in χ_{M}'' were observed between 1.80 and 2.05 K (Figure S21). Relaxation times (τ) were extracted from these data using a generalized Debye model,³ and a corresponding plot of the logarithm of τ vs inverse *T* is linear (Figure S29), suggesting that the magnetization relaxes via an Orbach process. The temperature-dependent relaxation data were fit using the equation

$$\tau^{-1} = \tau_0^{-1} \exp\left(-\frac{U_{\text{eff}}}{k_{\text{B}}T}\right) \quad (2)$$

to yield an effective spin-reversal barrier of $U_{\text{eff}} = 16.53(6) \text{ cm}^{-1}$ and a pre-exponential factor of $\tau_0 = 4.7(2) \times 10^{-10} \text{ s}$. The value of U_{eff} is in good agreement with the first magnetic excited

a more synthetically accessible system. Finally, the application of a small optimal field of 200 Oe further suppresses fast spin relaxation, enabling full relaxation observed in the out-of-phase susceptibility between 1.8 and 2.1 K (Figure S27). An Arrhenius plot of the corresponding relaxation times versus inverse T was again fit to an Orbach process, yielding $U_{\text{eff}} = 15.7(2) \text{ cm}^{-1}$ and $\tau_0 = 1.4(2) \times 10^{-9} \text{ s}$ (Figures 8 and S29).




Figure 8. Arrhenius plots of relaxation time τ (log scale) versus T (inverse scale) for **2** under $H_{\text{dc}} = 200 \text{ Oe}$ (blue circles) and **4** under $H_{\text{dc}} = 2000 \text{ Oe}$ (red circles). Error bars represent the standard deviations of relaxation times. For **2**, error bars are smaller than the height of the symbols. Solid black lines represent the best fit according to the equations specified in the text. Data were collected on the 10 mM frozen solution samples in 2-MeTHF.

Although compound **1** possesses easy-axis anisotropy (with D values of -1.93 and -1.74 cm^{-1} determined from magnetization and EPR data, respectively), it does not exhibit any signatures of slow magnetic relaxation at temperatures of as low as 2 K and ac frequencies of as high as 1500 Hz. This absence is likely due to the small ground state to first magnetic excited state separation in this compound, calculated to be between 5.1 and 5.7 cm^{-1} from the extracted D parameters.

AC susceptibility data were also collected for **4** to examine the relaxation dynamics of the $S = 1/2$ cluster $[\text{Cu}_4(\text{NP}^t\text{Bu}_3)_4]^+$. A microcrystalline sample of **4** showed no features of slow magnetic relaxation under zero field or applied fields, but a 10 mM frozen solution of **4** in 2-MeTHF exhibited slow magnetic relaxation at as high as 8 K under an optimized field of 2000 Oe (Figure S30). The absence of zero-field relaxation in **4** is consistent with quantum tunneling of the magnetization facilitated by hyperfine interactions with the $I = 3/2$ copper nuclear spin.³⁸ Since there is no magnetic excited state in an $S = 1/2$ system, the observed slow relaxation under an applied field will arise solely due to Raman and/or direct processes according to the following equation

$$\tau^{-1} = CT^n + AH^4T \quad (3)$$

where C and A are coefficients for Raman and direct processes, respectively, and n is the Raman exponent. A least-squares fit to the data yielded $C = 0.43(2) \text{ s}^{-1} \text{ K}^{-4}$, $n = 4$, and $A = 1.95(8) \times 10^4 \text{ s}^{-1} \text{ T}^{-4} \text{ K}^{-1}$ (Figure 8). Interestingly, the Raman relaxation times are on the order of milliseconds for **4**, similar to those previously determined for $[\text{Co}_4(\text{NP}^t\text{Bu}_3)_4]^+$ (Figure S33),¹¹ suggesting that the relaxation behavior may be

characteristic of the spin-vibronic coupling in tetranuclear phosphinimide clusters. In the case of compound **2**, Raman relaxation on this time scale is sufficiently slow to enable exclusive observation of the Orbach barrier.

CONCLUSIONS

The foregoing results demonstrate that direct metal–metal orbital overlap in tetranuclear transition-metal complexes featuring bridging tri-*tert*-butylphosphinimide gives rise to strong electronic and magnetic communication. In $[\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4]^+$, a large $S = 5/2$ ground state results from strong direct exchange via orbital overlap, while large anisotropy is engendered by the weak ligand field. Remarkably, computational results reveal that strong ferromagnetic direct exchange in the cluster is mediated by itinerant electrons, reminiscent of magnetism in ferromagnetic metals. Intriguingly, to our knowledge, $[\text{Ni}_4(\text{NP}^t\text{Bu}_3)_4]^+$ is the first example of a single-molecule magnet with easy-plane

Jonathan Marbey – Department of Physics and National High Magnetic Field Laboratory, Florida State University, Tallahassee, Florida 32310, United States

Philip C. Bunting – Department of Chemistry, University of California, Berkeley, Berkeley, California 94720, United States

Frank Neese – Max-Planck Institut für Kohlenforschung, Mülheim an der Ruhr D-45470, Germany; orcid.org/0000-0003-4691-0547

Stephen Hill – Department of Physics and National High Magnetic Field Laboratory, Florida State University, Tallahassee, Florida 32310, United States; orcid.org/0000-0001-6742-3620

Complete contact information is available at:

<https://pubs.acs.org/10.1021/jacs.0c08460>

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

This work was funded by NSF grant CHE-1800252. Single-crystal X-ray diffraction data were collected at beamlines 11.3.1 and 12.2.1 at the Advanced Light Source, which is a DOE Office of Science User Facility under contract no. DE-AC02-05CH11231. S.H. and J.M. acknowledge support from NSF grant DMR-1610226. Work performed at the National High Magnetic Field Laboratory was supported by NSF grants DMR-1644779 and the State of Florida. We thank the government of Thailand for the support of K.C. through the Development and Promotion of Science and Technology (DPST) scholarship, Dr. Wayne W. Lukens, Jr. at Lawrence Berkeley National Laboratory for X-band EPR measurements, Dr. Miao Zhang at the UC Berkeley Catalysis Center for assistance with mass spectrometry, Kanthen Sivalingam at Max-Planck-Institut für Kohlenforschung for help with CASSCF calculation convergence, Dr. T. David Harris for helpful suggestions, and Dr. Katie R. Meihaus for editorial assistance.

REFERENCES

- (1) Kahn, O. *Molecular Magnetism*; VCH, 1993.
- (2) Benelli, C.; Gatteschi, D. Introduction. In *Introduction to Molecular Magnetism: From Transition Metals to Lanthanides*; Benelli, C., Gatteschi, D., Eds.; Wiley-VCH Verlag GmbH & Co. KGaA: Weinheim, Germany, 2015; pp 1–23.
- (3) Gatteschi, D.; Sessoli, R.; Villain, J. *Molecular Nanomagnets*; Oxford University Press, 2006.
- (4) Sessoli, R.; Gatteschi, D.; Caneschi, A.; Novak, M. A. Magnetic Bistability in a Metal-Ion Cluster. *Nature* **1993**, *365*, 141–143.
- (5) Milios, C. J.; Winpenny, R. E. P. Cluster-Based Single-Molecule Magnets. In *Molecular Nanomagnets and Related Phenomena*; Gao, S., Ed.; Springer: Berlin, 2015; pp 1–109.
- (6) Goddard, C. A.; Long, J. R.; Holm, R. H. Synthesis and Characterization of Four Consecutive Members of the Five-Member $[\text{Fe}_6\text{S}_8(\text{PET}_3)_6]^{n+}$ ($n = 0-4$) Cluster Electron Transfer Series. *Inorg. Chem.* **1996**, *35* (15), 4347–4354.
- (7) Hernández Sánchez, R.; Betley, T. A. Meta-Atom Behavior in Clusters Revealing Large Spin Ground States. *J. Am. Chem. Soc.* **2015**, *137*, 13949–13956.
- (8) Hernández Sánchez, R.; Zheng, S.-L.; Betley, T. A. Ligand Field Strength Mediates Electron Delocalization in Octahedral $[(\text{HL})_2\text{Fe}_6(\text{L}')_6]^{n+}$ Clusters. *J. Am. Chem. Soc.* **2015**, *137*, 11126–11143.
- (9) Hernández Sánchez, R.; Bartholomew, A. K.; Powers, T. M.; Ménard, G.; Betley, T. A. Maximizing Electron Exchange in a $[\text{Fe}_3]$ Cluster. *J. Am. Chem. Soc.* **2016**, *138*, 2235–2243.
- (10) Hernández Sánchez, R.; Betley, T. A. Thermally Persistent High-S

- (29) Layfield, R. A. Organometallic Single-Molecule Magnets. *Organometallics* **2014**, *33*, 1084–1099.
- (30) Hassan, A. K.; Pardi, L. A.; Krzystek, J.; Sienkiewicz, A.; Goy, P.; Rohrer, M.; Brunel, L. C. Ultrawide Band Multifrequency High-Field EMR Technique: A Methodology for Increasing Spectroscopic Information. *J. Magn. Reson.* **2000**, *142* (2), 300–312.
- (31) Malmqvist, P.-Å.; Roos, B. O. The CASSCF State Interaction Method. *Chem. Phys. Lett.* **1989**, *155* (2), 189–194.
- (32) Angeli, C.; Cimiraglia, R.; Evangelisti, S.; Leininger, T.; Malrieu, J.-P. Introduction of n -Electron Valence States for Multi-reference Perturbation Theory. *J. Chem. Phys.* **2001**, *114* (23), 10252–10264.
- (33) Angeli, C.; Cimiraglia, R.; Malrieu, J.-P. N -Electron Valence State Perturbation Theory: A Fast Implementation of the Strongly Contracted Variant. *Chem. Phys. Lett.* **2001**, *350* (3–4), 297–305.
- (34) Angeli, C.; Cimiraglia, R.; Malrieu, J.-P. n -Electron Valence State Perturbation Theory: A Spinless Formulation and an Efficient Implementation of the Strongly Contracted and of the Partially Contracted Variants. *J. Chem. Phys.* **2002**, *117* (20), 9138–9153.
- (35) Neese, F. Software Update: The ORCA Program System, Version 4.0. *Wiley Interdiscip. Rev.: Comput. Mol. Sci.* **2018**, *8* (1), No. e1327.
- (36) Zadrozny, J. M.; Liu, J.; Piro, N. A.; Chang, C. J.; Hill, S.; Long, J. R. Slow Magnetic Relaxation in a Pseudotetrahedral Cobalt(II) Complex with Easy-Plane Anisotropy. *Chem. Commun.* **2012**, *48* (33), 3927.
- (37) Frost, J. M.; Harriman, K. L. M.; Murugesu, M. The Rise of 3-d Single-Ion Magnets in Molecular Magnetism: Towards Materials from Molecules? *Chem. Sci.* **2016**, *7* (4), 2470–2491.
- (38) Gómez-Coca, S.; Urtizberea, A.; Cremades, E.; Alonso, P. J.; Camón, A.; Ruiz, E.; Luis, F. Origin of Slow Magnetic Relaxation in Kramers Ions with Non-Uniaxial Anisotropy. *Nat. Commun.* **2014**, *5*, 4300.