[CONTRIBUTION FROM THE EASTERN REGIONAL RESEARCH LABORATORY, PHILADELPHIA, PENNSYLVANIA]

Preparation of Acrylic and Methacrylic Acids by Pyrolysis of Their Alkyl Esters

BY W. P. RATCHFORD, C. E. REHBERG AND C. H. FISHER

The purpose of this investigation was to effect the synthesis of acrylic and methacrylic acids by thermal decomposition of their ethyl or higher alkyl esters. The analogous pyrolysis of ethyl crotonate into crotonic acid is known² to occur. Since it appeared that such a synthesis might be more practical than the alternative approach by hydrolysis^{3,4,5,6} the present investigation was undertaken.

In this investigation it has now been found (Table I) that both acrylic acid and methacrylic acid can be prepared conveniently and in high yields by passing suitable acrylic or methacrylic esters through a Pyrex glass tube heated at about 500 to 580°. The acids produced in this manner are relatively pure, contain little or no water, and are readily purified by distillation or crystallization.

As would be expected from previous observations⁷ made with acetates of secondary alcohols, *s*-butyl acrylate decomposed more readily than did the esters of primary alcohols. Isobutyl acrylate was more stable than the other esters studied. Possibly this stability is attributable to the presence of only one hydrogen on the β carbon atom of the alkyl group. Ethyl acrylate, ethyl methacrylate, and *n*-butyl methacrylate appeared to have approximately the same thermal stability. Cyanoethyl acrylate was much less stable than ethyl acrylate.

Contact time was relatively unimportant at 570 to 580° , 90 to 94% of the ethyl acrylate being decomposed when the contact time was four to twelve seconds. At lower temperatures, however, the influence of contact time was more marked. Considerable quantities of acrylic acid have been prepared conveniently in this Laboratory by pyrolyzing ethyl acrylate under conditions similar to those of Experiment 3, Table I.

The high yields of acrylic and methacrylic acids and the relative unimportance of contact time at the higher temperatures show that these acids are relatively thermostable. That methyl acrylate is rather stable is demonstrated by its preparation in high yield by the thermal decom-

One of the laboratories of the Bureau of Agricultural and Industrial Chemistry, Agricultural Research Administration, United States Department of Agriculture. Article not copyrighted.
 N. T. M. Wilsmore and A. W. Stewart, Proc. Chem. Soc., 23,

(2) N. T. M. Wilsmore and A. W. Stewart, Proc. Chem. Soc., 23, 309 (1908);
C. D. Hurd, "The Pyrolysis of Organic Compounds," Reinhold Publishing Corp., New York, N. Y., 1929, 807 pp.

(3) D. Pressman and H. J. Lucas, THIS JOURNAL, 64, 1953 (1942).
(4) C. F. Koelsch, *ibid.*, 65, 437 (1943).

(5) O. C. Dermer, W. G. Markham and H. M. Trimble, *ibid.*, 63, 3524 (1941).

(6) H. T. Neher, Ind. Eng. Chem., 28, 267 (1936).

(7) A. J. Van Pelt, Jr., and J. P. Wibaut, Rec. trav. chim., 60, 55 (1941).

TABLE	I
-------	---

Pyrc	LYSIS C	OF ALKYL	Acr	YLATE	S AND N	Летнаси	RYLATES
Expt.	Grams pyro- lyzed	Addition rate, moles of ester per hr.	Temp., °C.	Con- tact time, sec.	Ester decom- posed, %	Gases and losses, %	Yield of un- satu- rated acid, % ^a
		1	Ethyl	Acryla	ate		
1	161.2	0.84	499	6.9	39.7'	13.7	81°
2	203.7	0.57	556	10.7	92.8^{b}	28.2	94°
3	175.8	1.17	568	4.5	89.8°	27.4	90°
4	677.2	1.38	574	3.9	90.9^d	28.7	$92^{\prime\prime}$
		Is	obuty	l Acry	late		
5	76.3	0.83	545	7.3	84.5^{e}	36.8	63″
		5-	Butyl	Acryl	ate		
6	14 0	.77	498	8.4	100°	40.2	97°
		β-Су	anoet	hyl Ac	rylate		
7	98.7	.74	500	7.9	about 92'	17.7	74 ^{c.g}
		Etl	hyl M	ethacr	ylate		
8	149.3	.76	497	7.6	44.1^{d}	11.5	79^d
9	150.0	. 99	550	5.5	83.70	26.2	82 ^d
10	156.1	.74	579	7.1	100^d	30.6	87^d
		n-Br	utyl Ń	1ethac	ryla te		
11	150.1	.49	513	11.6	79.2^{d}	17.7	78ª
12	149.2	. 55	555	9.7	96.8 ^d	34.7	93ª
13	151.6	. 55	586	9.5	98.0^{d}	37.4	91 ^d

^a Yield (per cent. of theoretical) based on unrecovered ester. ^b From distillation data. ^e From titration and distillation data; the yield based on unsaturated acid actually isolated by distillation was usually lower. ^d From titration and saponification data. ^e From titration and saponification of the distilled pyrolysis products; separation by distillation was difficult. ^f About 8% of the products appeared as distillation residue, possibly polymeric material. ^e The yield of acrylonitrile, determined by distillation, was 86.5%.

position of the acetyl derivative of methyl lactate.⁸ The fact that acrylic acid was not obtained in the pyrolysis⁸ of ethyl acetoxypropionate indicates that α -acetoxypropionic acid instead of ethyl acrylate was the principal primary decomposition product.

In a single experiment on the pyrolysis of *n*butyl crotonate at 537° and 7.2 seconds, 88% of the ester was cracked. The yields of crotonic acid and butylene were 84 and 85%, respectively.

Acrylic acid was made also by the acidolysis of methyl acrylate with formic or acetic acid in the presence of a small amount of sulfuric acid and hydroquinone. Formic acid was preferable because it reacted much more rapidly than acetic acid. The highest yield of acrylic acid (80%) was

(8) R. Burns, D. T. Jones and P. D. Ritchie, J. Chem. Soc., 400 (1935).

Nov., 1944

obtained when the acidolysis was carried out with formic acid. The acidolysis method of preparing acrylic acid is similar to the pyrolysis method in that water is not a reactant or product.

Experimental

Acrylic Esters.—Commercial samples of ethyl acrylate, ethyl methacrylate, and *n*-butyl methacrylate were used without purification or the removal of inhibitor. The isobutyl, *s*-butyl, and cyanoethyl esters of acrylic acid were prepared by the alcoholysis of methyl acrylate.⁹

Pyrolysis Experiments.—The equipment and general procedure were essentially similar to those previously described.¹⁰ The esters, which contained a small proportion of hydroquinone, were pumped into the top of the vertical Pyrex glass tube with a constant-feed pump of the type described by Corson and Cerveny.¹¹ The heated portion of the pyrolysis tube was packed with short lengths of Pyrex glass tubing. A small quantity of hydroquinone was placed in the cooled receiver of the pyrolysis unit to inhibit polymerization. Small amounts of water, which distilled azeotropically with ethyl acrylate, were present in the products formed under the more drastic conditions.

Use of a vaporizer to introduce the esters as vapor into the pyrolysis tube seemed beneficial. In an early experiment, for example, a vaporizer was not employed, and the pyrolysis products were brown. In the succeeding experiments a vaporizer was used, and under otherwise similar conditions the products were amber or light yellow.

The yield of acrylonitrile in Experiment 7 was 86.5%. The yields of olefins were sometimes ignored, but the yields of normally gaseous material collected in solid carbon dioxide traps (assumed to be butene) were 83 and 86% in Experiments 12 and 13, respectively.

Isolation of Acrylic Acid from the Pyrolysis Products.— The separation of acrylic acid and isobutyl acrylate by distillation was difficult because of the proximity of their boiling points. The principal difficulty experienced in fractionally distilling the other pyrolysis products arose from the tendency of acrylic acid and its esters to polymerize. For the purpose of preventing or minimizing polymerization, the distillations were carried out below 100-mm. pressure (preferably at about 20 mm.); hydroquinone was always placed in the distilling flask; and carbon dioxide instead of air was led into the distilling flask to prevent bumping. A distilling column filled with copper rings of the Fenske¹² type was used in some of the distillations. The influence of pressure upon the boiling points of acrylic and methacrylic acids is indicated in Figure 1.

The likelihood of polymerization is less when acrylic and methacrylic acids are purified by crystallization (acrylic acid and methacrylic acid melt at approximately 14 and 15°, respectively). In some instances the pyrolysis products were cooled to cause crystallization; the mixture was decanted, and the solid material was allowed to melt. The products of Experiment 4, Table I, were purified by freezing and decanting (three times) and by distillation. The composition of the pyrolysis product as indicated by these methods is given in Table II.

By freezing and decanting, methacrylic acid having a purity of 98.7% (determined by titration) was obtained from some pyrolysis products.¹⁸

Acrylic Acid by Acidolysis of Methyl Acrylate.—Four moles (184 g.) of formic acid, 12 moles (1032 g.) of methyl

(9) C. E. Rehberg and C. H. Fisher, THIS JOURNAL, 66, 1203 (1944).

(10) E. M. Filachione, J. H. Lengel and C. H. Fisher, *ibid.*, 66, 494 (1944).

(11) B. B. Corson and W. J. Cerveny, Ind. Eng. Chem., Anal. Ed., 14, 899 (1942).

(12) M. R. Fenske, C. O. Tongberg and D. Quiggle, Ind. Eng. Chem., 26, 1169 (1934).

(13) In handling the products it is advisable for the operator to wear rubber gloves, since both acrylic and methacrylic acids have a delayed corrosive action on the skin.

TABLE	Π
-------	---

ANALYSIS OF PRODUCTS OF EXPERIMENT 4 Ethyl acrylate %

Method of analysis or separation	Re- covered	Con- verted into acrylic acid	% Acrylic acid yield	Puritya
Freezing and decant-				
ing ^b	9.2	67.1	74.0	96.4
Distillation	8.6	82.8	90.6	97.5
Titration and saponi-				
fication	9.1	84.2	92.4	

^a Content of acrylic acid was determined by titration. ^b Acrylic acid purified in this manner was light amber.

acrylate, 30 g. of hydroquinone and 2 cc. of sulfuric acid were mixed and refluxed in a still having a 3-foot column and a variable take-off head. The still was operated with total reflux until the temperature at the head fell to 32°. Methyl formate was withdrawn, as formed, for eight to twelve hours, when its production ceased. The excess methyl acrylate was then distilled at a pressure of 140 mm., after which acrylic acid of a high degree of purity was distilled at 56° (25 mm.). The yield was 231 g. (80% of the theoretical, based on the formic acid). Over 91% of the methyl acrylate put into the reaction mixture was either recovered or converted into acrylic acid. The acrylic acid (to which had been added 10 g. of hydroquinone) was redistilled and the following constants were determined: b. p., 71° (50 mm.); n^{20} p. 1.4210; d^{20} , 1.0487; MR, calcd., 17.12; found, 17.43 (the calculated value contains no increment for the conjugation)

A similar acidolysis experiment, using acetic instead of formic acid, was much less satisfactory. The rate of reaction was much lower, and the conversion was far from complete even after several days of refluxing. Also, the distillation of the reaction mixture was complicated by the necessity of separating methyl acetate, methyl acrylate, acetic acid, and acrylic acid.



Fig. 1.—Boiling points of acrylic and methacrylic acids at different pressures.

Summary

The principal products obtained in the thermal decomposition of several alkyl acrylates and methacrylates were acrylic or methacrylic acid and olefins corresponding to the alkyl group. Alkyl acrylates were increasingly stable in this order for alkyl groups: s-butyl < 2-cyanoethyl < ethyl and *n*-butyl < isobutyl. The pyrolysis of appropriate acrylic and methacrylic esters constitutes a convenient method for preparing the corresponding unsaturated acids.

The acidolysis of methyl acrylate with formic acid is described.

PHILADELPHIA, PA.

Received July 5, 1944

[CONTRIBUTION FROM THE DEPARTMENT OF CHEMISTRY, UNIVERSITY OF NORTH CAROLINA]

Chemical Constitution and the Tanning Effect. III. The Synthesis and Examination of Fructose Pentagallate, d-Arabinose Tetragallate and α -Methyl-d-glucoside Tetragallate

BY ALFRED RUSSELL AND W. G. TEBBENS

The work already on record¹ describing the preparation, and examination for tanning properties, of the more easily available fully galloylated aldohexoses has now been extended to include a fully galloylated ketohexose (fructose pentagallate I), a fully galloylated aldopentose (d-arabinose tetragallate II) and α -methyl-d-glucoside tetragallate III. Each forms a brittle transparent vitreous mass, is water soluble and, in aqueous solution, gives a typical precipitate with gelatin solution. d-Arabinose tetragallate has very good tanning properties and forms leather strictly comparable with that given by gallotannin. α -Methyl-d-glucoside tetragallate has good leather forming properties—only slightly inferior to those of gallotannin.

Fructose pentagallate is not a tanning material. This result was so surprising that the entire tedi-



(1) Russell, Tebbens and Arey, THIS JOURNAL, 65, 1472 (1943).



ous synthesis of the compound was carried out a second time. However, the second preparation was identical with the first, the final product gave a typical gelatin precipitate in aqueous solution but would not make leather.

It would be idle at the present stage in this investigation to speculate as to why, on the one hand, a fully galloylated aldohexose (pyranose or aldehyde form) or an epimeric form¹ should be a very good tanning material and, on the other, the isomeric fully galloylated ketohexose should have no tanning properties. One minor point is emphasized by the examination of fructose pentagallate—a positive test with gelatin is not always evidence of tanning properties since fructose pentagallate gives the test.

Experimental

Penta-(triacetylgalloyl)-fructose.—7.2 g. (0.04 mole) of anhydrous, finely powdered fructose was suspended in 120 cc. of dry, freshly distilled chloroform and 36 g. of dry, freshly distilled quinoline; 72 g. of freshly distilled triacetylgalloyl chloride was added portionwise with shaking and cooling. After tumbling for three days the pale yellow reaction mixture was completely homogeneous. It was washed three times with 100-cc. portions of water, three times with 100-cc. portions of cold 1% sulfuric acid and four times with 100-cc. portions of cold water (second wash neutral to litmus). The chloroform solution was dried over sodium sulfate and then added slowly with vigorous mechanical stirring over a period of three hours to 800 cc. of anhydrous 90–100° petroleum ether at 0°. The cream-colored amorphous solid so produced was