Synthesis and preliminary physical properties of new neutral tetraalkoxy-substituted nickel bis(1,2-dithiolene) complexes[†]

Thanh-Tuan Bui,^{ab} Bénédicte Garreau-de Bonneval^{ab} and Kathleen I. Moineau-Chane Ching*^{ab}

Received (in Montpellier, France) 29th September 2009, Accepted 30th October 2009 First published as an Advance Article on the web 18th December 2009 DOI: 10.1039/b9nj00519f

Nineteen neutral nickel bisdiphenylethenedithiolene complexes [Ni(dpedt)₂], including seventeen new compounds, were synthesized and characterized by a new short, efficient and multigram-scale synthetic method. Preliminary physical investigations show that these complexes are electronwithdrawing materials exhibiting good thermal stability and high molecular absorption coefficient in the near-infrared spectral region. Electrochemical and optical properties of [Ni(dpedt)₂] depend strongly on the nickel bis(1,2-dithiolene) core and very slightly on the alkyl chain lengths or configurations. These highly soluble coordination compounds are potential candidates as acceptor solution-processable materials for active layers in organic electronic devices, such as field effect transistors or photovoltaic devices.

Introduction

The chemistry of neutral transition-metal (1,2-dithiolene) complexes in the 1960's decade started with the first report on an authentic trisdithiolene complex by Gilbert et al.¹ In 1962, Schrauzer et al.² reported the preparation of an unusual nickel complex, formulated as [NiS₄C₄Ph₄], in the somewhat esoteric reaction between Ni(CO)₄, sulfur and diphenylacetylene. This new nickel complex, quite unlike any other nickel complex known at that time, was intensely colored (green), diamagnetic, and volatile. This was the first authentic neutral nickel bisdiphenylethenedithiolene [Ni(dpedt)₂] reported. Later, they reported the formation of a large number of neutral metal complexes with diaryl and dialkyl "α,β-dithioketones" [MS₄C₄R₄].³ Their methods only give low yields and are not sufficiently general. A little later, they reported a new synthetic method using benzoin.⁴ This method is still generously used nowadays in order to prepare (a)symmetric tetra(hetero)arylsubstituted nickel bis(1,2-dithiolene) complexes.^{5,6} However, it cannot be adopted for long-chain substituted complexes, because one cannot obtain long alkyl/alkoxy chain-substituted benzoins by the benzoin condensation, except for dimethyl-, dimethoxy- and tetramethoxy-benzoins. Ohta et al.⁷⁻¹⁰ overcame this limitation and succeeded in obtaining several series of alkyl- and alkoxy-substituted nickel bis(1,2-bisphenylethene-1,2-dithiolene) complexes by using the corresponding benzils as the precursors. Based on the chemical reactivities and physical properties of the nickel bis(1,2-dithiolene) complexes, many applications were developed such as near infrared (NIR) photodetectors,¹¹ optical switching devices,¹² organic dyes,⁶ non linear optics,¹³ and organic electronics.¹⁴ Results of extensive research on metal bis(1,2-dithiolene) complexes chemistry have been the subject of several reviews.¹⁵ These kinds of complexes are potentially molecular materials for organic electronic applications due to their high molecular absorption coefficients in the NIR spectral region. In this work, our interest is concentrated on synthesizing new neutral nickel bis[1,2-bis(4-alkoxyphenyl)ethene-1,2-dithiolene] complexes in order to obtain room temperature discotic liquid crystals (DLC) for a new conception of multi-layer organic photovoltaic device based on NIR absorbent DLC semiconducting materials. The use of DLC semiconducting molecules would help increasing the efficiency of organic photovoltaic devices due to their high charge mobilities.¹⁶ The first discotic mesogenic neutral nickel bis(1,2-dithiolene) complexes, which contains four n-dodecyloxy chains (Fig. 1), was reported in 1983 by Veber et al.17

Later, Ohta *et al.*⁸ synthesized two new homologous discotic mesospheric complexes with *n*-nonyloxy and *n*-undecyloxy chains (Fig. 1). In 2001, they synthesized a new series of nickel bis(1,2-dithiolene) complexes containing 4-fold linear alkoxy moieties and fully re-studied this family.¹⁰ They claimed that these complexes with $n \geq 9$ exhibit discotic liquid



 $R = R' = n - C_n H_{2n+1} = 1 - 12, 14, 16, 18$

Fig. 1 First discotic mesogenic neutral nickel bis(1,2-dithiolene) complexes reported by Veber *et al.*¹⁷ and then Ohta *et al.*^{8,10}

^a CNRS: LCC (Laboratoire de Chimie de Coordination),

²⁰⁵ Route de Narbonne, F-31077 Toulouse, France.

E-mail: kathleen.chane@lcc-toulouse.fr; Fax: +33561553003; Tel: +33561333152

^b Université de Toulouse (UPS, INPT, LCC), F-31077 Toulouse, France

[†] Electronic supplementary information (ESI) available: ¹H and ¹³C NMR spectra of all nickel complexes. See DOI: 10.1039/b9nj00519f

crystalline properties. Prior to this work, the lowest transition temperatures reported were situated between 50 °C and 60 °C with linear dodecyloxy and linear tetradecyloxy chains.¹⁰

The introduction of branched alkyloxy chains and the synthesis of asymmetric complexes, *i.e.* complexes containing two kinds of alkyloxy (either linear (L) or branched (B)) chains could play an important role on the molecular packing, and thus on the transition temperature.

Results and discussion

Synthesis

Based on the successful benzil method of Ohta et al.,^{8,10} new synthetic pathways were developed to obtain asymmetric compounds or new symmetric complexes. The starting material, *p*-anisil, is a commercially available product. It can be also easily prepared from 4-methoxybenzaldehyde by the method of Wenz.¹⁸ The synthetic pathways are outlined in Scheme 1. The list of all intermediate and final complexes is given in Table 1. As depicted in Scheme 1, the final neutral complexes are achieved from the benzil precursors 3a-3s. The transformation of **3a-3s** into nickel bis(1,2-dithiolene) complexes is well known as a "one-pot" procedure.^{4,19} The thionating reaction of the α -diketone 3 is performed by P_4S_{10} in boiling dioxane leading to thiophosphate ester intermediates.⁴ Recently Arumugam et al.²⁰ demonstrated the preparation and isolation of stable thiophosphate ester consisting in the protected forms of 1,2-dithiolene ligands. According to our synthesis pathway, this thiophosphate ester is not isolated but directly hydrolyzed in the reaction medium. The hydrolysis followed by adding nickel salt in air condition gives neutral products [Ni(dpedt)₂] with quite good yields after purification by repeated processes of precipitation and column chromatography. By convention, all [Ni(dpedt)₂] derivatives in the present work are presented as trans configuration as the exact configuration of nickel complexes are not elucidated. In order to obtain the long alkoxy chain-substituted benzil derivatives 3b-3s, we started from *p*-anisil 3a. By removing one methyl-group of 3a in hydrobromic acid we obtained the phenol derivative 1b. We were then able to graft another linear or branched alkyl chain to get asymmetric benzils 3b-3f. If both methoxy groups are removed, two free phenol functions are available for chemical modification. The introduction of two-fold alkyl chain yielded to symmetric benzils 3g-3m. At this stage, it was possible to graft two different alkyl chains on 1a by successive substitutions. The monoalkoxy-substituted intermediates 2n-2p were systematically purified before the second alkyl chains were introduced. All branched alkyl chains were used as racemic mixtures. The 4,4'-dihydroxybenzil 1a was prepared in big quantities from 3a. The demethylation reaction was performed by a boiling mixture of concentrated hydrobromide acid and glacial acetic acid according to the literature.²¹ In this reaction conditions, the conversion of 4,4'-dimethoxybenzil to α -diketone **1a** strongly depends on the reaction times and the quantity of starting material (the longer the reflux time is, the higher the conversation rate is). We started from 26 g of 3a in 550 ml of acid mixture and the desired product 1a was obtained with nearly quantitative yield

after 50 h of reflux. The complete treatment of reaction mixture after only 17 h gave a mixture of three products: starting 1,2-diketone ($\approx 20\%$ of starting materials), monodemethylation intermediate product 1b, $\approx 30\%$ and 1a, $\approx 30\%$. Example of high yield synthesis of 1b was also reported²² but in the present work the synthesis of 1b was not optimized. Both 1a and 1b were engaged in the next steps for preparing long chain substituted benzils: the precursor of 1,2-dithiolene ligands.



Scheme 1 Synthetic pathways of neutral nickel bis(1,2-dithiolene) complexes. Reagents and conditions: (a) HBr 48%, glacial CH₃COOH, reflux; (b) RBr (0.9 equiv.), K_2CO_3 (0.9 equiv.), DMF, 90 °C, 1 h; (c) RBr (1.2 equiv.), K_2CO_3 (1.5 equiv.), DMF, 90 °C; (d) ROH (1.2 equiv.), DEAD (1.2 equiv.), PPh₃ (1.2 equiv.), THF, 0 °C then 1 h at R.T.; (e) RBr (2.4 equiv.), K_2CO_3 (3.0 equiv.), DMF, 90 °C; (f) ROH (2.4 equiv.), DEAD (2.4 equiv.), PPh₃ (2.4 equiv.), THF, 0 °C then 1 h at R.T.; (g) P₄S₁₀ (2.2 equiv.), dioxane, reflux 5 h then NiCl₂.6H₂O (0.55 equiv.), H₂O, reflux 2 h.

R	R′	1	2	3	Nickel complexes	Yield/color/M _p
Н	Н	1a (96)				
Methyl	Н	1b (28)	_	_	_	
2-Ethylhexyl	Н	_ ` ´	2n (41)	_	_	
n-Decyl	Н		2o (57)		_	
n-Dodecyl	Н		2p (46)		_	
Methyl	Methyl			3a	$[Ni((4-OC_1,4'-OC_1)dpedt)_2]$	18/black/nd
n-Decyl	Methyl			3b (95)	$[Ni((4-OC_1, 4'-OC_{10L})dpedt)_2]$	51/black/147.3
2-Ethylhexyl	Methyl			3c (97)	$[Ni((4-OC_1,4'-OC_{8B})dpedt)_2]$	45/brown/199.1
3,7-Dimethyloctyl	Methyl			3d (84)	$[Ni((4-OC_1, 4'-OC_{10B})dpedt)_2]$	53/black/170.3
2-Butyloctyl	Methyl			3e (77)	$[Ni((4-OC_1,4'-OC_{12B})dpedt)_2]$	49/black/154.8
2-Hexyldecyl	Methyl			3f (96)	$[Ni((4-OC_1, 4'-OC_{16B})dpedt)_2]$	50/black/147.4
2-Ethylhexyl	2-Ethylhexyl			3g (70)	$[Ni((4-OC_{8B}, 4'-OC_{8B})dpedt)_2]$	47/brown/163.7
n-Dodecyl	n-Dodecyl			3h	$[Ni((4-OC_{12L},4'-OC_{12L})dpedt)_2]$	48/brown/168.8
3,7-Dimethyloctyl	3,7-Dimethyloctyl	—	—	3i (78)	$[Ni((4-OC_{10B}, 4'-OC_{10B})dpedt)_2]$	59/black/129.9
2-Butyloctyl	2-Butyloctyl	—	—	3j (90)	$[Ni((4-OC_{12B}, 4'-OC_{12B})dpedt)_2]$	51/black/103.2
2-Hexyldecyl	2-Hexyldecyl	—	—	3k (69)	$[Ni((4-OC_{16B}, 4'-OC_{16B})dpedt)_2]$	49/black/-
2-Octyldodecyl	2-Octyldodecyl	—	—	3l (75)	$[Ni((4-OC_{20B}, 4'-OC_{20B})dpedt)_2]$	43/black/-
2-Decyltetradecyl	2-Decyltetradecyl	—	—	3m (82)	$[Ni((4-OC_{24B}, 4'-OC_{24B})dpedt)_2]$	57/black/-
2-Ethylhexyl	n-Decyl	—	—	3n (69)	$[Ni((4-OC_{10L}, 4'-OC_{8B})dpedt)_2]$	73/black/153.2
n-Decyl	3,7-Dimethyloctyl	—	—	3o (91)	$[Ni((4-OC_{10L}, 4'-OC_{10B})dpedt)_2]$	59/black/158.5
n-Dodecyl	n-Tetradecyl			3p (99)	$[Ni((4-OC_{12L}, 4'-OC_{14L})dpedt)_2]$	52/brown/163.7
n-Dodecyl	<i>n</i> -Undecyl			3q (80)	$[Ni((4-OC_{12L}, 4'-OC_{11L})dpedt)_2]$	68/brown/171.9
n-Dodecyl	2-Butyloctyl			3r (100)	$[Ni((4-OC_{12L}, 4'-OC_{12B})dpedt)_2]$	71/black/99.0
n-Dodecyl	3,7-Dimethyloctyl	—	—	3s (95)	$[Ni((4-OC_{12L}, 4'-OC_{10B})dpedt)_2]$	55/brown/149.7

Table 1 Intermediate and final synthesized compounds. All branched alkyl chains are racemic mixture and yields (%) are listed in bracket. **3h** was isolated from the synthesis of 2p and 3a is a commercial product. Melting points (°C) are determined from DSC diagrams

Synthesis of symmetric 4,4'-dialkoxybenzils (3g-3m)

The symmetric 4,4'-dialkyloxybenzils 3g-3m were synthesized by grafting alkyl chains on the phenol function of 1a. Two different methods were used, depending on the commercial availability of alkyl chains as halogenated alkanes or alcoholic compounds. In the first case, the classical nucleophilic substitution reaction gave 3g in high yield by heating the mixture of 1a and large excess of 2-ethylhexylbromide and a Lewis base (K₂CO₃) in DMF.

In the later case, the Mitsunobu's method²³ was applicable leading to **3i–3m**. The Mitsunobu reaction is very efficient in mild experimental conditions (ambient temperature) and an easy work-up reaction. This allows the conversion of primary and secondary alcohols to esters, phenyl ethers, thioethers and various other compounds with high yields. We are able to graft a large choice of alkyl chains in one step, particularly branched ones that are often available as primary or secondary alcohols.

Synthesis of asymmetric 4,4'-dialkoxybenzils (3b-3f, 3n-3s)

The asymmetric precursors 4,4'-dialkyloxybenzil **3n–3s**, which contain two different alkyl chains (different from methyl), were synthesized from **1a**. For this, the two chains were successively introduced. The reaction of **1a** with a little less than one equivalent of alkyl bromide in short reaction time forms monoalkoxy-substituted benzils **2n–2p** with acceptable yields (41–57%). Usually the symmetric benzils **3** were also isolated as co-products (*e.g.* 4,4'-dodecyloxybenzil **3h** is isolated in the synthesis of **2p** in 30% yield). The quantitative conversion of **1a** to **2o–2p** could be realized by using a large excess of **1a** as described for a similar reaction.²⁴ The introduction of the second alkyl chain was performed either by nucleophilic substitution or the Mitsunobu reaction, as described above,

resulting in **3n–3s**. The dialkoxy-substituted benzils containing one methyl chain **3b–3f** were synthesized from **1b** in similar conditions.

In comparison with other methods of synthesis of asymmetrical long alkoxy-substituted benzils,²⁵ this method presents some advantages. It uses common intermediates such as **1a** and **1b** and allows synthesizing many asymmetric benzils without any difficulty. Moreover, the alkyl chains are introduced in the last steps starting from either halogenated alkanes or alcohols that allow numerous alkyl chains combinations.

All of the synthesized compounds were identified by ¹H and ¹³C NMR spectra. The elemental analyses and mass spectrometry analyses gave complementary confirmations. The analytical data of all [Ni(dpedt)₂] such as visual colors, melting points, elemental analysis results, mass studies are summarized in Table 1 and the experimental section. All attempts to form a suitable crystal for single crystal X-ray diffraction analysis failed. As observed from Table 1, the introduction of long chains generally decreases the melting temperature of the nickel bis(1,2-dithiolene) complexes.

¹H NMR spectra of benzil derivatives and corresponding nickel complexes are similar. Two typical spectra are gathered in Fig. 2: ¹H NMR spectra of 4-decyloxy-4'-methoxybenzil (Fig. 2b) and the corresponding nickel dithiolene complex (Fig. 2a). As observed, the peaks corresponding to protons Hc (triplet) and Hd (singlet) are well distinguishable, both in the case of benzil and dithiolene complex. In the aromatic region, the protons in the metal complex are shifted to higher fields. The metal bis(1,2-dithiolene) core is less electro-attractive than the corresponding 1,2-diketonic group. In addition to the NMR analysis, the good cohesiveness between the theoretical and experimental values of elemental analyses and mass spectroscopy studies confirmed the purity of the



Fig. 2 Partial ¹H NMR spectra of (b) 4-decyloxy-4'-methoxybenzil **3d** and (a) the corresponding nickel complex $[Ni((4-OC_1,4'-OC_{10L})-dpedt)_2]$. The peaks of CD₂Cl₂ solvent have a star.

synthesized products. It is noteworthy that all nickel complexes were obtained from repeated precipitation processes and finally purified by silica-gel column chromatography. Table 1 also summarizes the visual aspects of all [Ni(dpedt)₂]. The colors of some compounds appear to be different. Six of them are brown and thirteen others are black/dark-green.

Preliminary physical investigations

In order to envisage their use as active materials in organic electronic devices, the physical properties of these complexes have to be characterized. Currently, advanced studies are being carried out. Only the preliminary physical properties are given and discussed in this present paper. The typical results on $[Ni((4-OC_{8B},4'-OC_{8B})dpedt)_2]$ are presented.

Thermal behaviors

The highly thermal stability of the targeted compounds is required to envisage their use as active materials in organic electronic devices (*e.g.* OPV, OFET). The thermal analysis studies show that neutral nickel bis(1,2-dithiolene) complexes are thermally stable until 300 °C, as observed in Fig. 3 for compound [Ni((4-OC_{8B},4'-OC_{8B})dpedt)₂]. At higher temperature, the decomposition of the product is observed. This thermal behavior is in good accordance with data reported in the literature.²⁶





Fig. 4 DSC trace of $[Ni((4-OC_{8B},4'-OC_{8B})dpedt)_2]$, scan rate: 10 °C min⁻¹.

The phase transition behaviors of $[Ni(dpedt)_2]$ are studied by differential scanning calorimetry (DSC), polarized optical microscopy (POM) and temperature-dependence powder X-rays diffraction. Fig. 4 shows the phase transition of the $[Ni((4-OC_{8B},4'-OC_{8B})dpedt)_2]$. This complex was obtained as a brown powder. On heating, it melts into an isotropic liquid at 162.8 °C and on cooling down, the crystallization peak appears at 109.3 °C. This phase behavior of $[Ni((4-OC_{8B},4'-OC_{8B})dpedt)_2]$ is much simpler than its analogue's: the tetraoctyloxysubstituted $[Ni(dpedt)_2]$,¹⁰ which contains four linear octyl chains. Its lower melting point is due to the highly steric bulky effect of the 2-ethylhexyl chain.

Optical and electrochemical properties

The electrochemical and optical properties of the synthesized compounds were studied by cyclic voltammetry and UV-VIS-NIR absorption spectroscopy. The cyclic voltammogram of $[Ni((4-OC_{8B},4'-OC_{8B})dpedt)_2]$ in dichloromethane is shown in Fig. 5. Three pairs of redox waves are observed. In reduction, two successive near -0.1 and -0.8 V vs. SCE waves correspond to 1- and 2-electron reduction (respectively, couple 2 and couple 1).²⁷ In oxidation, the first 1-electron oxidation is observed near 1 V vs. SCE (Couple 3).²⁷ The solution absorption spectra in the UV-VIS-NIR region of $[Ni((4-OC_{8B},4'-OC_{8B})dpedt)_2]$ is presented in Table 2. The complex shows a maximum absorption peak in the nearinfrared spectral region, which can be attributed to a π - π^* transition of the nickel bis(1,2-dithiolene) core. All potentials are determined in CH₂Cl₂ solution using a Pt electrode except for [Ni((4-OC12B,4'-OC12B)dpedt)2] and $[Ni((4-OC_{24B},4'-OC_{24B})dpedt)_2]$: for these two compounds, reproducible results are obtained using a glassy carbon electrode.

From this table, it appears that the reduction potentials of these complexes change very slightly depending on the alkoxy chain length and configuration. These experimental values are in good agreement with values reported in the literature.¹⁰ The values, -0.06 to -0.12 V vs. SCE, observed for these complexes are less positive than that of the core complex, the [Ni(dpedt)₂] $(E^{1/2}_{red} = 0.03$ V vs. SCE in CH₂Cl₂).¹⁰ This difference is attributable to the mesomeric electron donating effect of the alkoxy substituents. As observed from Table 2, the values of λ_{max} change only slightly from 924–936 nm. The nature of the alkyl chains does not influence the optical properties of



Fig. 5 Cyclic voltammogram of $[Ni((4-OC_{8B},4'-OC_{8B})dpedt)_2]$ in CH_2Cl_2 containing 0.1 mol L^{-1} (Bu₄N)PF₆ as an electrolyte by using Pt metal working and counter electrodes and a standard SCE reference electrode at 25 °C (scan rate 0.1 V s⁻¹).

Nickel complexes	$E^{1/2}/\mathbf{V}^a$	$\lambda_{\rm max}/{\rm nm}^b$	$\epsilon/L \text{ mol}^{-1} \text{cm}^{-1}$
$[Ni((4-OC_1,4'-OC_1)dpedt)_2]$	-0.09	924	47 000
$[Ni((4-OC_1,4'-OC_{10L})dpedt)_2]$	-0.09	929	50 000
$[Ni((4-OC_1,4'-OC_{8B})dpedt)_2]$	-0.09	931	38 000
$[Ni((4-OC_1, 4'-OC_{10B})dpedt)_2]$	-0.09	928	44 000
$[Ni((4-OC_1,4'-OC_{12B})dpedt)_2]$	-0.10	931	54 000
$[Ni((4-OC_1, 4'-OC_{16B})dpedt)_2]$	-0.08	929	51 000
$[Ni((4-OC_{8B},4'-OC_{8B})dpedt)_2]$	-0.10	934	47 000
$[Ni((4-OC_{12L},4'-OC_{12L})dpedt)_2]$	-0.10	934	49 000
$[Ni((4-OC_{10B}, 4'-OC_{10B})dpedt)_2]$	-0.10	933	50 000
$[Ni((4-OC_{12B}, 4'-OC_{12B})dpedt)_2]$	-0.11	935	43 000
$[Ni((4-OC_{16B}, 4'-OC_{16B})dpedt)_2]$	-0.12	936	54 000
$[Ni((4-OC_{20B}, 4'-OC_{20B})dpedt)_2]$	-0.09	935	51 000
$[Ni((4-OC_{24B},4'-OC_{24B})dpedt)_2]$	-0.11	935	54 000
$[Ni((4-OC_{10L},4'-OC_{8B})dpedt)_2]$	-0.10	934	47 000
$[Ni((4-OC_{10L}, 4'-OC_{10B})dpedt)_2]$	-0.06	933	51 000
$[Ni((4-OC_{12L}, 4'-OC_{14L})dpedt)_2]$	-0.11	933	48 000
$[Ni((4-OC_{12L}, 4'-OC_{11L})dpedt)_2]$	-0.11	933	51 000
$[Ni((4-OC_{12L}, 4'-OC_{12B})dpedt)_2]$	-0.12	934	51 000
$[Ni((4-OC_{12L},4'-OC_{10B})dpedt)_2]$	-0.12	933	52 000

^{*a*} Volts *vs.* SCE in CH₂Cl₂ using platinum metal electrode, except for [Ni((4-OC_{12B},4'-OC_{12B})dpedt)₂] and [Ni((4-OC_{24B},4'-OC_{24B})dpedt)₂] using Glassy carbon electrode. Cyclic voltammogram of [Ni((4-OC_{8B},4'-OC_{8B})dpedt)₂] in CH₂Cl₂ containing 0.1 mol L⁻¹ (Bu₄N)PF₆ as an electrolyte and a standard SCE reference electrode at 25 °C (scan rate 0.1 V s⁻¹). ^{*b*} In CH₂Cl₂ solution.

[Ni(dpedt)₂]. In addition, the high values of molecular absorption coefficient ε range from 38000 to 54000 M⁻¹ cm⁻¹ demonstrating that the [Ni(dpedt)₂] are efficient NIR absorbent materials. The full results of cyclic voltammetry and electronic absorption spectroscopy will be used further to estimate the optical and electrochemical bandgaps, electron affinities (E_a) and ionization potentials (I_p) of all [Ni(dpedt)₂]. From the first results of electrochemical and electronic absorption measurements, one can conclude that the nature of alkyl chains do not influence significantly electrochemical or optical properties in this [Ni(dpedt)₂] series. This could be a very interesting result because the mesomorphic property of the complexes depends on the alkoxy chain length and configuration, whereas the reduction potential and optical absorption do not. That is to say, we can change the peripheral chain length to obtain the mesomorphic properties without changing the electrochemical

or optical properties. The same result and claim were reported for the first time by Ohta *et al.* in 1991⁹ and then in 2001.¹⁰

Conclusion

Nineteen [Ni(dpedt)₂], including seventeen new compounds, were synthesized by new short and efficient synthetic pathways. The synthesis of two common intermediates 4,4'-dihydroxybenzil 1a and 4-hydroxy-4'-methoxybenzil 1b and the introduction of alkyl chains in the later steps allows us to synthesize easily a series of [Ni(dpedt)₂]. The Mitsunobu reaction has proven to be a very efficient method to prepare various alkoxy-substituted aromatic compounds from phenol derivatives. The alternative choice of either the classical nucleophilic substitution reaction or the Mitsunobu reaction gives us a large source of alkyl chains, either from alkyl halides or from primary or secondary alcohols. The complete investigation of mesomorphic properties of this [Ni(dpedt)₂] series and advanced studies by electrochemical and optical methods are being carried out and will be fully discussed in a separate article.

Experimental

General remarks

All used chemicals and solvents were purchased from chemical companies and used as received, unless otherwise mentioned. All reactions were realized under ambient atmosphere unless special indication. ¹H and ¹³C NMR experiments were recorded in the listed deuterated solvents (internal standard) on a 4 Bruker Spectrometers (ARX 250, DPX 300, Avance 300 and Avance 400). Purification of product was performed by column chromatography on silica gel from Merck with a grain size of 0.04-0.063 mm (flash silica gel, Geduran Si 60) with analytically pure solvents. For analytical thin layer chromatography (TLC), silica gel coated substrates "60 F254" from Merck were used and compounds were detected by fluorescence quenching at 254 nm, self-fluorescence at 365 nm. Melting points were determined by DSC thermograms, which were obtained on a DSC 204 NETZSCH system using 2-5 mg samples in 30 µl sample pans and a scan rate of 10 °C min⁻¹. ΔH is calculated in J g⁻¹. Mass analyses were performed at the MS Service at the Paul Sabatier University. Elemental analyses (C. H. S. Ni) were carried out at the CNRS Central Analyses Service in Lyon. UV-VIS-NIR absorption spectra were recorded on two spectrometers Perkin-Elmer Lambda 35 and Perkin-Elmer GX 2000. Voltammetric measurements were carried out with a potentiostat Autolab PGSTAT100 controlled by GPES 4.09 software. Experiments were performed at room temperature in a homemade airtight three-electrode cell connected to a vacuum/argon line. The reference electrode consisted in a saturated calomel electrode (SCE) separated from the solution by a bridge compartment. The counter electrode was a platinum wire of ca. 1 cm² apparent surfaces. The working electrode was a Pt microdisk (0.5 mm diameter) or a glassy carbon (1 mm diameter). The supporting electrolyte (nBu₄N)[PF₆] (Fluka, 99% electrochemical grade) was used as received and simply degassed

under argon. CH_2Cl_2 was freshly distilled over CaH_2 prior to use. The solutions used during the electrochemical studies were typically 10^{-3} mol L^{-1} in complex compound and 0.1 mol L^{-1} in supporting electrolyte. Before each measurement, the solutions were degassed by bubbling Ar and the working electrode was polished with a polishing machine (Presi P230).

4,4'-Dihydroxybenzil (1a). 4,4'-Dimethoxybenzil (26 g, 96.2 mmol) was heated to reflux for 50 h in a mixture of aqueous HBr (48%) and glacial acetic acid (550 mL, 50/50). The reaction mixture was cooled by a bath of ice-water and the yellow precipitate was collected by filtration. The filtrate was then extracted several times with ethyl acetate. The organic phases and the yellow precipitate were combined, washed several times with water, dried with MgSO₄ and the solvent was removed under reduced pressure. The residue was purified by column chromatography (CH₂Cl₂/acetone: 85/15) giving **1a** as pure yellowish solid (22.45 g, 96%). $\delta_{\rm H}$ (250 MHz, CD₃OD) 7.82 (4 H, d, J = 9.0 Hz, aromatic H), 6.91 (4 H, d, J = 9.0 Hz, aromatic H), 4.92 (2 H, br s, phenol H). $\delta_{\rm C}$ (75 MHz, CD₃OD): 194.26, 164.09, 132.17, 124.89, 115.51. HRMS(CI): found 243.0669, [M + H]⁺ requires 243.0657.

4-Hydroxy-4'-methoxybenzil (1b). As described for the synthesis of **1a** but the reflux time was decreased to 17 h. Complete workup gave a mixture of three products: 4,4'-dimethoxybenzil (18% of starting material), **1a** (yellowish solid, 33%) and **1b** (yellow solid, 28%). $\delta_{\rm H}(250 \text{ MHz}, ({\rm CD}_3)_2{\rm CO})$ 9.58 (1 H, s, phenol H), 7.93 (2 H, d, J = 9.0 Hz, aromatic H), 7.87 (2 H, d, J = 9.0 Hz, aromatic H), 7.87 (2 H, d, J = 9.0 Hz, aromatic H), 7.03 (2 H, d, J = 9.0 Hz, aromatic H), 3.94 (3 H, s, $-{\rm OC}H_3$). $\delta_{\rm C}(62.5 \text{ MHz}, ({\rm CD}_3)_2{\rm CO})$ 193.46, 165.04, 163.51, 132.30, 131.94, 126.29, 125.45, 115.95, 114.47, 55.31. HRMS(CI): found 257.0826, $[{\rm M} + {\rm H}]^+$ requires 257.0814.

General procedure for the synthesis of benzils 3b, 3c, 3n, 3p, 3q

A mixture of **1b** (for **3b–3c**) or **2n–2p** (for **3n**, **3o**, **3p**, **3q**) (3.9 mmol), alkyl bromide (5.9 mmol), and powdered potassium carbonate (1.1 g, 7.8 mmol) was stirred in DMF (25 mL) at 90 °C. The reaction was monitored by TLC (hexane/CH₂Cl₂ 50/50). Upon cooling to room temperature, the reaction was quenched by adding water and the resulting mixture was extracted by CH₂Cl₂. The organic phases were combined, rinsed several time by water, dried over anhydrous magnesium sulfate and concentrated under reduced pressure resulting in the crude product which was purified by silica gel column chromatography (hexane/CH₂Cl₂ 50/50).

4-Decyloxy-4'-methoxybenzil (3b). Yellowish solid (1.47 g, 95%). $\delta_{\rm H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.95 (4 H, m, aromatic H), 7.02 (4 H, m, aromatic H), 4.08 (2 H, t, $J = 6.6 \text{ Hz}, -\text{OC}H_2-$), 3.92 (3 H, s, $-\text{OC}H_3$), 1.84 (2 H, m, $-\text{OCH}_2\text{CH}_2-$), 1.49–1.32 (14 H, m), 0.92 (3 H, t, $J = 6.6 \text{ Hz}, -\text{CH}_2\text{CH}_3$). $\delta_{\rm C}(75 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 193.58, 193.51, 164.94, 164.61, 132.18, 126.25, 125.95, 114.69, 114.25, 68.60, 55.68, 31.89, 29.53, 29.30, 28.99, 25.88, 22.67, 13.86.

4-Methoxy-4'-(2-ethylhexyloxy)benzil (3c). Yellowish oil (1.4 g, 97%). $\delta_{\rm H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.96 (4 H, m, aromatic H), 7.03 (4 H, m, aromatic H), 3.98 (2 H, d, $J = 5.7 \text{ Hz}, -\text{OCH}_2-$), 3.92 (3 H, s, $-\text{OCH}_3$), 1.79 (1 H, m, $-\text{CH}_2-\text{CH}-$), 1.53–1.35 (8 H, m), 0.97 (6 H, t, $J = 7.5 \text{ Hz}, -\text{CH}_3$). $\delta_{\rm C}(75 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 193.60, 193.52, 164.94, 164.84, 132.17, 132.10, 126.26, 125.92, 114.72, 114.28, 70.99, 55.68, 39.24, 30.37, 28.99, 23.75, 23.00, 13.81, 10.82.

4-Decyloxy-4'-(2-ethylhexyloxy)benzil (3n). Yellow oil (0.54 g, 69%). $\delta_{\rm H}(250$ MHz, CD₂Cl₂) 7.96 (4 H, dd, J = 1.75-7.0 Hz, aromatic H), 7.02 (4 H, m, aromatic H), 4.09 (2 H, t, J = 6.5 Hz, $-OCH_2CH_2-$), 4.00 (2 H, d, J = 5.75 Hz, $-OCH_2CH-$), 1.87–1.77 (3 H, m), 1.51–1.33 (22 H, m), 1.00–0.90 (9 H, m, $-CH_3$). $\delta_{\rm C}(62.5$ MHz, CD₂Cl₂) 193.60, 164.82, 164.60, 132.17, 126.01, 125.97, 114.70, 71.01, 68.61, 39.27, 31.91, 30.40, 29.55, 29.32, 29.02, 25.90, 23.77, 23.02, 22.69, 13.88, 13.82, 10.84.

4-Dodecyloxy-4'-tetradecyloxybenzil (**3p**). Yellow solid (1.17 g, 99%). $\delta_{\rm H}(250$ MHz, CD₂Cl₂) 7.96 (4 H, m, aromatic H), 7.03 (4 H, m, aromatic H), 4.11 (4 H, t, J = 6.5 Hz, $-\rm OCH_2-$), 1.87–1.32 (44 H, m, $-\rm CH_2-$), 0.95 (6 H, t, J = 6.3 Hz, $-\rm CH_3$). $\delta_{\rm C}(62.5$ MHz, CD₂Cl₂) 193.57, 164.59, 161.06, 132.17, 126.00, 114.68, 68.60, 64.01, 31.92, 29.64, 29.57, 29.54, 29.50, 29.34, 29.31, 29.19, 29.00, 28.53, 25.88, 25.80, 22.68, 13.87.

4-Dodecyloxy-4'-undecyloxybenzil (3q). Yellowish solid (1.1 g, 80%). $\delta_{\rm H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.96 (4 H, dt, J = 9.6-2.7 Hz, aromatic H), 7.03 (4 H, dt, J = 9.6-2.7 Hz, aromatic H), 4.08 (4 H, t, J = 6.6 Hz, $-\text{OC}H_2-$), 1.84 (4 H, m, $-\text{OCH}_2\text{C}H_2-$), 1.51–1.31 (34 H, m), 0.92 (6 H, t, J = 6.3 Hz, $-\text{C}H_3$). $\delta_{\rm C}(75 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 193.57, 164.59, 132.17, 125.99, 114.69, 68.60, 66.75, 31.93, 29.59, 29.55, 29.33, 29.01, 25.90, 22.70, 13.89. HRMS(CI): found 565.4244, [M + H]⁺ requires 565.4257.

General procedure for the synthesis of benzils 3d, 3e, 3f, 3o, 3r, 3s

A THF (50 mL) solution of 4-hydroxy-4'-methoxy benzil (1.5 g, 5.85 mmol), PPh₃ (1.85 g, 7.02 mmol), and alcohol (7.02 mmol) were cooled to 0 °C. To the solution was added diethyl azodicarboxylate in toluene solution (3.2 mL, 7.02 mmol, 40% w/v), the mixture was kept at that temperature for 1 h and then was allowed to warm to room temperature and stirred for 1 h. The reaction mixture was then evaporated. After addition of 300 mL of hexane, the mixture was filtered. The filtrate was evaporated, and the residue was purified by silica gel column chromatography (hexane/CH₂Cl₂ 50/50)

4-(3,7-Dimethyloctyloxy)-4'-methoxybenzil (3d). Yellow oil (1.95 g, 84%). $\delta_{\rm H}(250$ MHz, CD₂Cl₂) 7.96 (4 H, m, aromatic H), 7.03 (4 H, m, aromatic H), 4.13 (2 H, t, J = 6.6 Hz, $-\text{OC}H_2-$), 3.93 (3 H, s, $-\text{OC}H_3$), 1.93–1.20 (10 H, m), 1.00 (3 H, d, J = 6.4 Hz, $-\text{C}H_3$), 0.93 (6 H, d, J = 6.6 Hz, $-\text{C}H_3$). $\delta_{\rm C}(62.5$ MHz, CD₂Cl₂) 193.58, 193.51, 164.95, 164.60, 132.19, 126.27, 125.98, 114.73, 114.27, 66.97, 61.01, 55.70, 39.21, 37.20, 35.90, 29.83, 27.99, 24.64, 22.44, 22.34, 19.36, 13.89.

4-(2-Butyloctyloxy)-4'-methoxybenzil (3e). Yellow oil (1.92 g, 77%). $\delta_{\rm H}(250 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.95 (4 H, m, aromatic H), 7.05

(2 H, d, J = 9.0 Hz, aromatic H), 7.00 (2 H, d, J = 8.8 Hz, aromatic H), 3.99 (2 H, d, J = 5.8 Hz, $-OCH_2$ -), 3.93 (3 H, s, $-OCH_3$), 1.88–0.92 (23 H, m). $\delta_C(62.5$ MHz, CD_2Cl_2) 193.60, 193.53, 164.94, 164.86, 132.18, 126.28, 125.93, 114.74, 114.26, 71.43, 65.46, 55.69, 40.58, 37.81, 31.84, 31.23, 30.93, 29.64, 29.01, 26.75, 23.03, 22.66, 13.87, 13.83.

4-(2-Hexyldecyloxy)-4'-methoxybenzil (3f). Yellow oil (2.71 g, 96%). $\delta_{\rm H}(250$ MHz, CD₂Cl₂) 7.95 (4 H, m, aromatic H), 7.05 (2 H, d, J = 9.0 Hz, aromatic H), 7.00 (2 H, d, J = 8.8 Hz, aromatic H), 3.99 (2 H, d, J = 5.8 Hz, $-\text{OC}H_2$), 3.93 (3 H, s, $-\text{OC}H_3$), 1.88–0.90 (31 H, m). $\delta_{\rm C}(62.5$ MHz, CD₂Cl₂) 193.6, 164.86, 132.17, 126.28, 125.91, 114.74, 114.26, 71.44, 65.47, 55.70, 40.60, 37.82, 31.91, 31.22, 29.96, 29.64, 29.56, 29.31, 26.76, 22.69, 13.88.

4-Decyloxy-4'-(3,7-dimethyloctyloxy)benzil (30). Yellow solid (2.45 g, 91%). $\delta_{\rm H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.96 (4 H, m, aromatic H), 7.03 (4 H, m, aromatic H), 4.15–4.06 (4 H, m, $-\text{OC}H_2$), 1.86–1.19 (26 H, m), 1.00–0.90 (12 H, m, $-\text{C}H_3$). $\delta_{\rm C}$ (75 MHz, CD₂Cl₂) 193.56, 164.58, 164.56, 132.17, 126.00, 114.69, 68.59, 66.95, 39.19, 37.18, 35.88, 31.89, 29.80, 29.54, 29.31, 29.00, 27.97, 25.89, 24.62, 22.68, 22.43, 22.33, 19.35, 13.88.

4-Dodecyloxy-4'-(2-butyloctyloxy)benzil (3r). Yellow solid (1.97 g, 100%). $\delta_{\rm H}(300$ MHz, CD₂Cl₂) 7.96 (4 H, dt, J = 9.6–2.7 Hz, aromatic H), 7.03 (4 H, dt, J = 9.6–2.7 Hz, aromatic H), 4.09 (2 H, t, J = 6.6 Hz, $-\text{OC}H_2\text{CH}_2$ –), 3.98 (2 H, d, J = 6.6 Hz, $-\text{OC}H_2$ –CH), 1.86 (4 H, m), 1.51–1.31 (33 H, m), 0.94 (9 H, m, $-CH_3$). $\delta_{\rm C}$ (75 MHz, CD₂Cl₂): = 193.59, 164.83, 164.59, 132.17, 126.01, 125.95, 114.72, 114.69, 71.41, 68.60, 37.80, 31.93, 31.84, 31.23, 30.92, 29.64, 29.59, 29.55, 29.36, 29.33, 29.01, 26.75, 25.90, 23.03, 22.70, 22.67, 13.87, 13.83. HRMS(CI): found 579.4433, [M + H]⁺ requires 579.4413.

Synthesis of 4,4'-di(2-ethylhexyloxy)benzil (3g)

A mixture of 4,4'-dihydroxybenzil (3) (3.26 g, 13.5 mmol), alkyl bromide (40.5 mmol), potassium iodide (0.68 mmol) and powdered potassium carbonate (54 mmol) was stirred in DMF (80 mL) at 90 °C and the reaction was monitored by TLC. Upon cooling to room temperature, the reaction was quenched by adding water and the resulting mixture was extracted by CH₂Cl₂. The organic phases were combined, rinsed several times with water, dried over anhydrous magnesium sulfate and concentrated under reduced pressure resulting in a crude product which was purified by silica gel column chromatography (hexane/CH₂Cl₂ 50/50). Yellowish oil (4.32 g, 70%). $\delta_{\rm H}(250 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.94 (4 H, d, J =9.0 Hz, aromatic H), 7.02 (4 H, d, J = 9.0 Hz, aromatic H), 3.99 (4 H, d, J = 5.8 Hz, OCH₂CH), 1.83–1.78 (2 H, m, OCH₂CH), 1.52–1.24 (16 H, m, –CH₂–), 1.01–0.93 (12 H, m, $-CH_3$). $\delta_C(75 \text{ MHz}, CD_2Cl_2)$: 193.61, 164.81, 132.15, 125.97, 114.71, 70.98, 39.25, 30.37, 29.00, 23.75, 23.00, 13.81, 10.82

General procedure for the synthesis of benzils 3i-3m

A THF (50 mL) solution of 4,4'-dihydroxy benzil (1.5 g, 6.2 mmol), PPh₃ (3.9 g, 14.9 mmol), and alcohol (14.9 mmol) was cooled to 0 $^{\circ}$ C. To the solution was added diethyl

azodicarboxylate in toluene solution (6.8 mL, 14.9 mmol, 40% w/v), the mixture was kept at that temperature for 1 h and then was allowed to warm to room temperature and stirred for 1 h. The reaction mixture was then evaporated. After addition of 300 ml of hexane, the mixture was filtered. The filtrate was evaporated, and the residue was purified by silica gel column chromatography (hexane/CH₂Cl₂ 50/50)

4,4'-Di(3,7-dimethyloctyloxy)benzil (3i). Yellow oil (2.52 g, 78%). $\delta_{\rm H}(300$ MHz, CD₂Cl₂) 8.13 (4 H, d, J = 9.0 Hz, aromatic H), 7.20 (4 H, d, J = 9.0 Hz, aromatic H), 4.31 (4 H, m, $-\text{OC}H_2$ -), 2.09–1.37 (20 H, m), 1.17 (6 H, d, J = 6.6 Hz, $-CH_3$), 1.10 (12 H, d, J = 6.6 Hz, $-CH_3$). $\delta_{\rm C}(75$ MHz, CD₂Cl₂) 193.75, 164.75, 132.36, 126.18, 114.89, 67.15, 39.39, 37.37, 36.07, 31.78, 30.00, 28.17, 24.82, 22.62, 22.52, 19.54, 14.07.

4,4'-Di(2-butyloctyloxy)benzil (3j). Yellow oil (4.3 g, 90%). $\delta_{\rm H}(250 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.96 (4 H, dd, J = 1.8-8.8 Hz, aromatic H), 7.03 (4 H, d, J = 8.8 Hz, aromatic H), 7.03 (4 H, d, J = 8.8 Hz, aromatic H), 3.99 (4 H, d, J = 5.8 Hz, $-\text{OCH}_2-$), 1.88-1.83 (2 H, m, $-\text{OCH}_2\text{C}H-$), 1.47-1.34 (32 H, m, $-\text{CH}_2-$), 0.95-0.91 (12 H, m, $-\text{CH}_3$). $\delta_{\rm C}(62.5 \text{ MHz}, \text{CD}_2\text{Cl}_2) = 193.62$, 164.83, 132.16, 125.98, 114.73, 71.42, 37.81, 31.84, 31.24, 30.94, 29.65, 29.01, 26.76, 23.03, 22.67, 13.87, 13.84.

4,4'-Di(2-hexyldecyloxy)benzil (3k). Yellow oil (3.94 g, 69%). $\delta_{\rm H}(250$ MHz, CD₂Cl₂) 7.96 (4 H, d, J = 9.0 Hz, aromatic H), 7.04 (4 H, d, J = 9.0 Hz, aromatic H), 3.99 (4 H, d, J = 5.5 Hz, $-\rm OCH_2-$), 1.88–1.81 (2 H, m, $-\rm OCH_2CH-$), 1.46–1.21 (48 H, m, $-\rm CH_2-$), 0.95–0.90 (12 H, m, $-\rm CH_3$). $\delta_{\rm C}(62.5$ MHz, CD₂Cl₂) 193.61, 164.83, 132.16, 125.98, 114.73, 71.44, 37.83, 31.91, 31.85, 31.61, 31.24, 29.97, 29.65, 29.57, 29.32, 26.77, 22.69, 13.88.

4,4'-Di(2-octyldodecyloxy)benzil (31). Yellow oil (5 g, 75%). $\delta_{\rm H}(250 \text{ MHz}, {\rm CD}_2{\rm Cl}_2)$ 7.96 (4 H, d, J = 8.8 Hz, aromatic H), 7.03 (4 H, d, J = 8.8 Hz, aromatic H), 3.99 (4 H, d, J = 5.6 Hz, $-{\rm OCH}_2-$), 1.87–1.83 (2 H, m, $-{\rm OCH}_2{\rm CH}-$), 1.46–1.31 (64 H, m, $-{\rm CH}_2-$), 0.95–0.90 (12 H, t, J = 5.9 Hz, $-{\rm CH}_3$). $\delta_{\rm C}(62.5$ MHz, ${\rm CD}_2{\rm Cl}_2$) 193.60, 164.82, 132.14, 125.96, 114.72, 71.42, 37.80, 31.91, 31.20, 29.95, 29.63, 29.58, 29.55, 29.34, 29.30, 26.75, 22.68, 13.87.

4,4'-Di(2-decyltetradecyloxy)benzil (3m). Yellow oil (6.21g, 82%). $\delta_{\rm H}(250 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.96 (4 H, d, J = 8.8 Hz, aromatic H), 7.04 (4 H, d, J = 8.8 Hz, aromatic H), 7.04 (4 H, d, J = 8.8 Hz, aromatic H), 3.99 (4 H, d, $J = 5.6 \text{ Hz}, -\text{OC}H_2-$), 1.88–1.31 (82 H, m), 1.03–0.90 (12 H, m, $-\text{CH}_3$). $\delta_{\rm C}(62.5 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 193.60, 164.82, 132.14, 125.97, 114.72, 71.43, 37.80, 31.92, 31.20, 29.95, 29.64, 29.59, 29.35, 26.76, 22.69, 13.87.

General procedure for the synthesis of 4-alkoxy-4'-hydroxybenzil 2n-2p and 3h

To a mixture of 4,4'-dihydroxybenzil (3) (1.0 g, 4.13 mmol), powdered potassium carbonate (3.72 mmol) in DMF (40 mL) at 90 °C was added dropwise and slowly (in about 1 h) a solution of alkyl bromide (3.72 mmol) in DMF (40 mL). After 1 h, the reaction was quenched by adding water and the resulting mixture was extracted by ethyl acetate. The organic phases were combined, rinsed several times with water, dried over anhydrous magnesium sulfate and concentrated under reduced pressure resulting in the crude product which was purified by silica gel column chromatography (hexane/CH₃COOC₂H₅: 75/25).

4-(2-Ethylhexyloxy)-4'-hydroxybenzil (2n). Yellow oil (0.54 g, 41%). $\delta_{\rm H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.91 (4 H, m, aromatic H), 7.00 (4 H, m, aromatic H), 6.74 (1 H, br s, phenol H), 3.98 (2 H, d, J = 5.7 Hz, $-\text{OCH}_2-$), 1.79 (1 H, m, $-\text{OCH}_2\text{CH}-$), 1.50–1.28 (8 H, m, $-\text{CH}_2-$), 0.99–0.91 (6 H, m, $-\text{CH}_3$). $\delta_{\rm C}(75 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 193.79, 193.69, 164.98, 162.00, 132.56, 132.27, 126.16, 125.80, 115.89, 114.78, 71.04, 60.55, 39.25, 30.38, 29.00, 23.76, 23.01, 20.85, 13.96, 13.82, 10.83.

4-Decyloxy-4'-hydroxybenzil (20). Yellow solid (4.06 g, 57%). $\delta_{\rm H}(300$ MHz, CD₂Cl₂) 7.96–7.88 (4 H, m, aromatic H), 7.03–6.93 (4 H, m, aromatic H), 6.01 (1 H, br s, phenol H), 4.1 (2 H, t, J = 6.3 Hz, $-\text{OCH}_2$ –), 1.88–1.79 (2 H, m, $-\text{OCH}_2$ CH₂–), 1.51–1.31 (14 H, m, $-\text{CH}_2$ –), 0.94 (3 H, t, J = 6.3 Hz, $-\text{CH}_3$). $\delta_{\rm C}(62.5$ MHz, CD₂Cl₂) 193.72, 193.64, 164.75, 161.86, 132.56, 132.28, 126.25, 125.86, 115.88, 114.76, 68.66, 31.91, 29.55, 29.32, 29.01, 25.90, 22.69, 13.98, 13.88.

4-Dodecyloxy-4'-hydroxybenzil (2p). Yellow solid (3.47g, 46%). $\delta_{\rm H}(250$ MHz, CD₂Cl₂) 8.04 (1 H, br s, phenol H), 7.96 (4 H, m, aromatic H), 7.09 (4 H, m, aromatic H), 4.11 (2 H, t, J = 6.5 Hz, $-\text{OCH}_2$ -), 1.87–1.31 (20 H, m), 0.95 (3 H, t, J = 6.2 Hz, $-\text{CH}_3$). HRMS(CI): found 411.2546, [M + H]⁺ requires 411.2535.

4,4'-Didodecyloxybenzil (3h). Yellowish solid isolated from the synthesis of **2p** (3.59 g, 30%). $\delta_{\rm H}(250 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.96 (4 H, m, aromatic H), 7.03 (4 H, m, aromatic H), 4.11 (4 H, t, $J = 6.5 \text{ Hz}, -\text{OC}H_2-$), 1.87–1.32 (40 H, m, $-\text{C}H_2-$), 0.95 (6 H, t, $J = 6.3 \text{ Hz}, -\text{C}H_3$). $\delta_{\rm C}(62.5 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 193.57, 164.59, 132.17, 126.00, 114.68, 68.60, 45.33, 31.93, 29.64, 29.59, 29.56, 29.36, 29.33, 29.02, 25.90, 22.70, 13.89. HRMS(CI): found 579.4441, [M + H]⁺ requires 579.4413.

General procedure for the synthesis of nickel bis(1,2-dithiolene) complexes (4a–4s)

A mixture of dialkoxybenzil (4.91 mmol) and P_4S_{10} (4.8 g, 10.80 mmol) in 25 mL of dioxane was heated to reflux at 130 °C for 5 h. When the initial yellow suspension became a clear dark brown solution, the hot mixture was filtered to remove an insoluble pale yellow solid. To the filtrate was added a solution of NiCl₂·6H₂O (0.64 g, 2.70 mmol) in 5 mL of water, and the mixture was heated to reflux for 2 h. The mixture was then cooled to room temperature and a small quantity of water was added. The black crystalline precipitate appeared and was collected by filtration. The crude product was purified by repeated precipitation from solution in CH₂Cl₂ by ethanol (3 times) and the final purification was performed by column chromatography (hexane/CH₂Cl₂).

Nickel bis[1,2-di(4-methoxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC₁,4'-OC₁)dpedt)₂])

Black powder (0.87 g, 18%). Elemental analysis: found C, 57.88; H, 4.19; Ni, 8.71; S, 19.58. $C_{32}H_{28}NiO_4S_4$ requires C, 57.93; H, 4.25; Ni, 8.85; S, 19.33%. $\delta_H(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$

7.39 (8 H, d, J = 7.5 Hz, aromatic H), 6.88 (8 H, d, J = 7.5 Hz, aromatic H), 3.86 (12 H, s, $-\text{OC}H_3$). $\delta_{\text{C}}(75$ MHz, CD₂Cl₂) 180.77, 160.48, 134.28, 130.34, 113.81, 55.37. HRMS(CI): found 663.0297, [M + H]⁺ requires 663.0302.

Nickel bis[1-(4-decyloxyphenyl)-2-(4-methoxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC₁,4'-OC_{10L})dpedt)₂])

Black powder (0.86 g, 51%, mp 147.3 °C). Elemental analysis: found C, 65.60; H, 7.10; Ni, 6.25; S, 14.10. $C_{50}H_{64}NiO_4S_4$ requires C, 65.56; H, 7.04; Ni, 6.41; S, 14.00%. $\delta_{H}(400 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.37 (8 H, m, aromatic H), 6.86 (8 H, m, aromatic H), 4.03 (4 H, t, J = 6.4 Hz, $-\text{OC}H_2\text{CH}_2$ -), 3.86 (6 H, s, $-\text{OC}H_3$), 1.85–1.80 (4 H, m, $-\text{OC}H_2\text{CH}_2$ -), 1.56–1.33 (28 H, m, $-\text{C}H_2$ -0.94 (6 H, t, J = 6.8 Hz, $-\text{C}H_3$). δ_{C} (75 MHz, CD₂Cl₂) 183.52, 180.93, 160.47, 160.12, 134.08, 130.35, 114.30, 113.81, 68.22, 55.36, 31.89, 29.56, 29.55, 29.37, 29.31, 29.19, 25.98, 22.67, 13.86. HRMS(CI): found 915.3100, [M + H]⁺ requires 915.3119.

Nickel bis[1-(4-(2-ethylhexyloxy)phenyl)-2-(4-methoxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC₁,4'-OC_{8B})dpedt)₂])

Brown powder (0.64 g, 45%, mp 199.1 °C). Elemental analysis: found C, 64.11; H, 6.44; Ni, 6.61; S, 15.20 C₄₆H₅₆NiO₄S₄ requires C, 64.25; H, 6.56; Ni, 6.83; S, 14.92%. $\delta_{\rm H}$ (400 MHz, CD₂Cl₂) 7.39 (8 H, m, aromatic H), 6.88 (8 H, m, aromatic H), 3.92 (4 H, d, J = 5.6 Hz, $-OCH_2$ CH–), 3.86 (6 H, s, $-OCH_3$), 1.79–1.71 (2 H, m, $-OCH_2$ CH–), 1.57–1.39 (16 H, m, $-CH_2$ –), 1.00 (12 H, t, J = 7.6 Hz, $-CH_3$). $\delta_{\rm C}$ (100 MHz, CD₂Cl₂) 180.75, 180.50, 160.43, 160.32, 134.37, 134.03, 130.35, 130.33, 114.33, 113.80, 70.66, 55.34, 39.39, 30.47, 29.07, 23.83, 23.05, 13.85, 10.88. HRMS(CI): found 859.2512, [M + H]⁺ requires 859.2493.

Nickel bis[1-(4-(3,7-dimethyloctyloxy)phenyl)-2-(4-methoxy-phenyl)ethene-1,2-dithiolene] complex ($[Ni((4-OC_1,4'-OC_{10B})-dpedt)_2]$)

Black powder (1.08 g, 53%, mp 170.3 °C). Elemental analysis: found C, 65.64; H, 6.91; Ni, 6.32; S, 14.63. $C_{50}H_{64}NiO_4S_4$ requires C, 65.56; H, 7.04; Ni, 6.41; S, 14.00%. $\delta_{H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.38 (8 H, m, aromatic H), 6.87 (8 H, m, aromatic H), 4.07 (4 H, m, $-\text{OC}H_2\text{CH}_2$ -), 3.85 (6 H, s, $-\text{OC}H_3$), 1.88–1.20 (20 H, m), 1.00 (6 H, d, $J = 6.3 \text{ Hz}, -CH_3$), 0.93 (12 H, d, $J = 6.6 \text{ Hz}, -CH_3$). $\delta_{C}(75 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 180.72, 180.53, 160.43, 160.07, 134.34, 134.07, 130.35, 114.30, 113.80, 66.55, 55.34, 39.23, 37.25, 36.11, 29.87, 27.98, 24.65, 22.45, 22.35, 19.41. HRMS(CI): found 915.3079 and 943.3484, [M + H]⁺ requires 915.3119 and [M + C_2H_3]⁺ requires 943.3432

Nickel bis[1-(4-(2-butyloctyloxy)phenyl)-2-(4-methoxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC₁,4'-OC_{12B})dpedt)₂])

Black powder (1.06 g, 49%, mp 154.8 °C). Elemental analysis: found C, 66.93; H, 7.36; Ni, 5.86; S, 13.02. $C_{54}H_{72}NiO_4S_4$ requires C, 66.72; H, 7.47; Ni, 6.04; S, 13.19%. δ_H (300 MHz, CD₂Cl₂) 7.40 (8 H, m, aromatic H), 6.89 (8 H, m, aromatic H), 3.91 (4 H, d, J = 5.7 Hz, $-OCH_2CH-$), 3.86 (6 H, s, $-OCH_3$), 1.84 (2 H, m, $-OCH_2CH-$), 1.57–1.32 (32 H, m), 0.97–0.90 (12 H, m, $-CH_3$). δ_C (75 MHz, CD₂Cl₂) 180.93, 180.68, 160.45, 160.34, 134.40, 134.06, 130.32, 130.30, 114.34, 113.80, 71.07, 55.34, 37.90, 31.85, 31.30, 30.99, 29.66, 29.04, 26.78, 23.04, 22.66, 13.86, 13.84. HRMS(CI): found 971.3742, $[M + H]^+$ requires 971.3745.

Nickel bis[1-(4-(2-hexyldecyloxy)phenyl)-2-(4-methoxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC₁,4'-OC_{16B})dpedt)₂])

Black powder (1.47 g, 50%, mp 147.4 °C). Elemental analysis: found C, 68.43; H, 8.18; Ni, 5.17; S, 12.08. $C_{62}H_{88}NiO_4S_4$ requires C, 68.68; H, 8.18; Ni, 5.41; S, 11.83. $\delta_{H}(400 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.39 (8 H, m, aromatic H), 6.87 (8 H, m, aromatic H), 3.90 (4 H, d, J = 5.2 Hz, $-OCH_2CH-$), 3.86 (6 H, s, $-OCH_3$), 1.84 (2 H, m, $-OCH_2CH-$), 1.50–1.35 (48 H, m), 0.94 (12 H, m, $-CH_3$). $\delta_C(100 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 180.66, 180.40, 160.42, 160.31, 134.40, 134.04, 130.38, 130.35, 114.34, 113.80, 71.10, 55.33, 37.96, 31.93, 31.88, 31.33, 30.03, 29.70, 29.61, 29.35, 26.84, 26.82, 22.70, 13.91. HRMS(CI): found 1083.5101, [M + H]⁺ requires 1083.4997.

Nickel bis[1,2-di(4-(2-ethylhexyloxy)phenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC_{8B},4'- OC_{8B})dpedt)₂])

Brown powder (2 g, 47%, mp 163.7 °C). Elemental analysis: found C, 68.55; H, 8.07; Ni, 5.42; S, 12.10. $C_{60}H_{84}NiO_4S_4$ requires C, 68.23; H, 8.02; Ni, 5.56; S, 12.14. $\delta_{H}(400 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.38 (8 H, d, J = 8.4 Hz, aromatic H), 6.88 (8 H, d, J = 8.4 Hz, aromatic H), 3.92 (8 H, d, J = 5.6 Hz, $-OCH_2CH-$), 1.80 (4 H, m, $-OCH_2CH-$), 1.57–1.37 (32 H, m, $-CH_2-$), 0.99–0.95 (24 H, m, $-CH_3$). $\delta_{C}(100 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 180.78, 160.34, 134.07, 130.33, 114.33, 70.67, 39.38, 30.46, 29.06, 23.82, 23.04, 13.83, 10.87. HRMS(CI): found 1055.4709, [M + H]⁺ requires 1055.4684.

Nickel bis[1,2-di(4-dodecyloxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC_{12L},4'- OC_{12L})dpedt)₂])

Brown powder (1.6 g, 48%, mp 168.8 °C). Elemental analysis: found C, 71.62; H, 9.08; Ni, 4.46; S, 9.32. $C_{76}H_{116}NiO_4S_4$ requires C, 71.28; H, 9.13; Ni, 4.58; S, 10.01%. $\delta_{\rm H}(300$ MHz, CD₂Cl₂) 7.37 (8 H, dd, J = 2.0-9.0 Hz, aromatic H), 6.86 (8 H, dd, J = 2.0-9.0 Hz, aromatic H), 4.00 (8 H, t, J = 6.6 Hz, $-OCH_2CH_2-$), 1.86–1.77 (8 H, m, $-OCH_2CH_2-$), 1.51–1.42 (72 H, m), 0.92 (12 H, t, J = 6.3 Hz, $-CH_3$). $\delta_{\rm C}(75$ MHz, CD₂Cl₂) 180.73, 160.09, 134.11, 130.33, 114.29, 68.21, 31.94, 29.65, 29.61, 29.40, 29.36, 29.30, 29.21, 26.01, 22.71, 13.89. HRMS(CI): found 1279.7148, [M + H]⁺ requires 1279.7188.

Nickel bis[1,2-di(4-(3,7-dimethyloctyloxy)phenyl)ethene-1,2dithiolene] complex ([Ni((4-OC_{10B},4'-OC_{10B})dpedt)₂])

Black powder (1.44 g, 59%, mp 129.9 °C). Elemental analysis: found C, 69.85; H, 8.74; Ni, 4.78; S, 11.25. $C_{68}H_{100}NiO_4S_4$ requires C, 69.90; H, 8.63; Ni, 5.02; S, 10.98%. $\delta_{\rm H}(400 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.37 (8 H, d, J = 8.4 Hz, aromatic H), 6.86 (8 H, d, J = 8.4 Hz, aromatic H), 4.07 (8 H, m, $-\text{OC}H_2\text{CH}_2-$), 1.90–1.84 (8 H, m, $-\text{OC}H_2\text{C}H_2-$), 1.73–1.21 (32 H, m), 1.01 (12 H, d, J = 6.4 Hz, $-\text{C}H_3$), 0.94 (24 H, d, J = 6.4 Hz, $-\text{C}H_3$). $\delta_{\rm C}(100 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 180.58, 160.05, 134.14, 130.35, 114.30, 66.55, 39.24, 37.27, 36.14, 29.88, 28.00, 24.66, 22.47, 22.37, 19.43. HRMS(CI): found 1167.5953, [M + H]⁺ requires 1167.5936.

Nickel bis[1,2-di(4-(2-butyloctyloxy)phenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC_{12B}, 4'-OC_{12B})dpedt)₂])

Black powder (2.36 g, 51%, mp 103.2 °C). Elemental analysis: found C, 71.57; H, 9.14; Ni, 4.32; S, 10.06. $C_{76}H_{116}NiO_4S_4$ requires C, 71.28; H, 9.13; Ni, 4.58; S, 10.01%. $\delta_{H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.39 (8 H, m, aromatic H), 6.88 (8 H, m, aromatic H), 3.91 (8 H, d, J = 5.7 Hz, $-\text{OC}H_2\text{CH}$ -), 1.85–1.79 (4 H, m, $-\text{OC}H_2CH$ -), 1.54–1.34 (64 H, m, $-CH_2$ -), 0.97–0.91 (24 H, m, $-CH_3$), $\delta_C(75$ MHz, CD₂Cl₂) 180.71, 160.32, 134.07, 130.29, 114.33, 71.05, 37.91, 31.85, 31.30, 31.00, 29.67, 29.05, 26.78, 23.05, 22.67, 13.87, 13.85. HRMS(CI): found 1279.7188, [M + H]⁺ requires 1279.7188.

Nickel bis[1,2-bis(4-(2-hexyldecyloxy)phenyl)ethene-1,2-dithiolene] complex ([Ni(4-OC_{16B},4-OC_{16B})dpedt)₂])

Black pasty powder (2.03 g, 49%). Elemental analysis: found C, 73.75; H, 9.96; Ni, 3.58; S, 8.18. C₉₂H₁₄₈NiO₄S₄ requires C, 73.42; H, 9.91; Ni, 3.90; S, 8.52%. $\delta_{\rm H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.38 (8 H, d, J = 8.7 Hz, aromatic H), 6.87 (8 H, d, J = 8.7 Hz, aromatic H), 3.91 (8 H, d, J = 5.7 Hz, $-\text{OCH}_2\text{CH}$ -), 1.83–1.80 (4 H, m, $-\text{OCH}_2\text{CH}$ -), 1.56–1.34 (96 H, m, $-\text{CH}_2$ -), 0.93–0.91 (24 H, m, $-\text{CH}_3$), $\delta_{\rm C}(75 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 180.69, 160.32, 134.07, 130.29, 114.65, 114.33, 71.06, 37.94, 31.91, 31.86, 31.30, 30.00, 29.67, 29.58, 29.32, 26.81, 26.79, 22.68, 13.88. HRMS(CI): found 1503.9624, [M + H]⁺ requires 1503.9692.

Nickel bis[1,2-bis(4-(2-octyldodecyloxy)phenyl)ethene-1,2dithiolene] complex ([Ni((4-OC_{20B},4'-OC_{20B})dpedt)₂])

Black pasty powder (2.28 g, 43%). Elemental analysis: found C, 75.19; H, 10.64; Ni, 3.16; S, 6.72. $C_{108}H_{180}NiO_4S_4$ requires C, 75.00; H, 10.49; Ni, 3.39; S, 7.42%. $\delta_{\rm H}(400 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.38 (8 H, d, J = 8.8 Hz, aromatic H), 6.87 (8 H, d, J = 8.8 Hz, aromatic H), 3.91 (8 H, d, J = 5.2 Hz, $-\text{OC}H_2\text{CH}-1.84$ (4 H, m, $-\text{OC}H_2\text{C}H-$), 1.50–1.34 (128 H, m, $-\text{C}H_2-$), 0.95 (24 H, m, $-\text{C}H_3$). $\delta_{\rm C}(100 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 180.60, 160.31, 134.11, 130.32, 114.33, 71.09, 37.97, 31.95, 31.32, 30.03, 29.70, 29.67, 29.66, 29.61, 29.38, 29.36, 26.85, 22.71, 13.92. MS(CI): found 1729.10, [M + H]⁺ requires 1729.21.

Nickel bis[1,2-bis(4-(2-decylyltetradecyloxy)phenyl)ethene-1,2dithiolene] complex ([Ni((4-OC_{24B},4'-OC_{24B})dpedt)₂])

Black pasty powder (3.74 g, 57%). Elemental analysis: found C, 76.79; H, 11.11; Ni, 2.86; S, 6.91. $C_{124}H_{212}NiO_4S_4$ requires C, 76.22; H, 10.94; Ni, 3.00; S, 6.56. $\delta_{H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.38 (8 H, d, J = 8.7 Hz, aromatic H), 6.87 (8 H, d, J = 8.7 Hz, aromatic H), 3.90 (8 H, d, J = 5.7 Hz, $-\text{OC}H_2\text{CH}$ -), 1.82 (4 H, m, $-\text{OC}H_2\text{C}H$ -) 1.56–1.30 (160 H, m, $-\text{C}H_2$ -), 0.94–0.85 (24 H, m, $-\text{C}H_3$), $\delta_{C}(75 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 180.72, 160.32, 134.07, 130.28, 114.33, 71.07, 37.91, 31.92, 31.27, 29.99, 29.66, 29.62, 29.35, 26.80, 22.69, 13.88. MS (CI): found 1953.57, [M + H]⁺ requires 1953.47.

Nickel bis[1-(4-(2-ethylhexyloxy)phenyl)-2-(4-decyloxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC_{10L},4'-OC_{8B})dpedt)₂])

Black powder (1.24 g, 73%, mp 153.2 °C). Elemental analysis: found C, 68.80; H, 8.23; Ni, 5.06; S, 11.57. $C_{64}H_{92}NiO_4S_4$ requires C, 69.10; H, 8.34; Ni, 5.28; S, 11.53%. $\delta_{H}(400 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.37 (8 H, d, J = 8.4 Hz, aromatic H), 6.86 (8 H, m,

aromatic H), 4.02 (4 H, t, J = 6.4 Hz, $-OCH_2CH_2-$), 3.92 (4 H, d, J = 5.2 Hz, $-OCH_2CH-$), 1.84–1.75 (6 H, m), 1.57–1.34 (44 H, m), 1.00–0.92 (18 H, m, $-CH_3$). $\delta_C(100$ MHz, CD_2Cl_2) 180.59, 180.55, 160.29, 160.05, 134.16, 134.10, 130.35, 114.32, 114.28, 70.65, 68.20, 39.40, 31.92, 30.48, 29.60, 29.58, 29.41, 29.34, 29.23, 29.08, 26.02, 23.84, 23.06, 22.70, 13.89, 13.87, 10.90. HRMS(CI): found 1111.5359, [M + H]⁺ requires 1111.5310.

Nickel bis[1-(4-(3,7-dimethyloctyloxy)phenyl)-2-(4-decyloxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC_{10L},4'-OC_{10B})dpedt)₂])

Black powder (1.7 g, 59%, mp 158.5 °C). Elemental analysis: found C, 70.04; H, 8.68; Ni, 4.94; S, 11.11. $C_{68}H_{100}NiO_4S_4$ requires C, 69.90; H, 8.63; Ni, 5.02; S, 10.98%. $\delta_H(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.37 (8 H, m, aromatic H), 6.86 (8 H, m, aromatic H), 4.04 (8 H, m, $-OCH_2\text{CH}_2$ -), 1.90–1.20 (52 H, m), 1.00–0.90 (24 H, m, $-CH_3$). $\delta_C(75 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 180.61, 160.05, 134.12, 130.34, 114.28, 68.20, 66.54, 39.23, 37.25, 36.12, 31.91, 29.87, 29.59, 29.57, 29.39, 29.33, 29.21, 27.99, 26.01, 24.65, 22.69, 22.45, 22.35, 19.41, 13.89. HRMS(CI): found 1167.5985, $[M + H]^+$ requires 1167.5936.

Nickel bis[1-(4-dodecyloxyphenyl)-2-(4-tetradecyloxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4- OC_{12L} ,4'- OC_{14L})dpedt)₂])

Brown powder (0.67 g, 52%, Mp 163.7 °C). Elemental analysis: found C, 71.82; H, 9.42; Ni, 4.21; S, 8.68. $C_{80}H_{124}NiO_4S_4$ requires C, 71.88; H, 9.35; Ni, 4.39; S, 9.59%. $\delta_{\rm H}(300$ MHz, CD₂Cl₂) 7.37 (8 H, dd, J = 2.0–9.0 Hz, aromatic H), 6.86 (8 H, dd, J = 2.0–9.0 Hz, aromatic H), 6.86 (8 H, dd, J = 2.0–9.0 Hz, aromatic H), 4.00 (8 H, t, J = 6.6 Hz, $-OCH_2CH_2$ –), 1.88–1.75 (8 H, m, $-OCH_2CH_2$ –), 1.54–1.31 (80 H, m), 0.92 (12 H, t, J = 6.3 Hz, $-CH_3$). $\delta_{\rm C}(75$ MHz, CD₂Cl₂) 180.98, 160.08, 134.10, 130.31, 114.28, 68.20, 31.92, 29.65, 29.59, 29.57, 29.37, 29.34, 29.19, 25.98, 22.68, 13.86. HRMS(CI): found 1335.7930, [M + H]⁺ requires 1335.7814.

Nickel bis[1-(4-dodecyloxyphenyl)-2-(4-undecyloxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC_{12L},4'-OC_{11L})dpedt])₂])

Brown powder (0.79 g, 68%, mp 171.9 °C). Elemental analysis: found C, 70.68; H, 9.12; Ni, 4.52; S, 9.06. $C_{74}H_{112}NiO_4S_4$ requires C, 70.95; H, 9.01; Ni, 4.69; S, 10.24%. $\delta_{\rm H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.38 (8 H, dd, J = 2.0–9.0 Hz, aromatic H), 6.86 (8 H, dd, J = 2.0–9.0 Hz, aromatic H), 4.00 (8 H, t, J = 6.6 Hz, $-OCH_2CH_2$ –), 1.84–1.77 (8 H, m, $-OCH_2CH_2$ –), 1.56–1.32 (68 H, m), 0.92 (12 H, t, J = 6.6 Hz, $-CH_3$). $\delta_{\rm C}(75$ MHz, CD₂Cl₂) 180.72, 160.08, 134.10, 130.31, 114.28, 68.20, 31.91, 29.65, 29.63, 29.60, 29.57, 29.38, 29.34, 29.19, 25.99, 22.68, 13.87. HRMS(CI): found 1251.6968, [M + H]⁺ requires 1251.6875.

Nickel bis[1-(4-(2-butyloctyloxy)phenyl)-2-(4-dodecyloxyphenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC_{12L},4'-OC_{12B})dpedt)₂])

Black powder (1.48 g, 71%, mp 99.0 °C). Elemental analysis: found C, 70.98; H, 9.17; Ni, 4.33; S, 9.59. $C_{76}H_{116}NiO_4S_4$ requires C, 71.28; H, 9.13; Ni, 4.58; S, 10.01%. $\delta_{H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.38 (8 H, d, J = 8.7 Hz, aromatic H), 6.87 (8 H, dd, J = 1.5-8.7 Hz, aromatic H), 4.00 (4 H, t, J = 6.6 Hz, $-\text{OC}H_2\text{CH}_2$ -), 3.90 (4 H, d, J = 5.7 Hz, $-\text{OC}H_2\text{CH}$ -), 1.87–1.78 (6 H, m), 1.57–1.32 (68 H, m), 0.97–0.90 (18 H, m, –*CH*₃). $\delta_{\rm C}$ (75 MHz, CD₂Cl₂) 180.71, 180.65, 160.31, 160.07, 134.13, 134.05, 130.32, 130.30, 114.32, 114.28, 71.05, 68.20, 37.91, 31.92, 31.86, 31.30, 31.00, 29.67, 29.64, 29.60, 29.58, 29.39, 29.35, 29.21, 29.05, 26.79, 26.00, 23.05, 22.69, 22.67, 13.88, 13.86. HRMS(CI): found 1279.7188, [M + H]⁺ requires 1279.7188.

Nickel bis[1-(4-(3,7-dimethyloctyloxy)phenyl)-2-(4-dodecyloxy-phenyl)ethene-1,2-dithiolene] complex ([Ni((4-OC_{12L},4'-OC_{10B})-dpedt)₂])

Brown powder (1.13 g, 55%, mp 149.7 °C). Elemental analysis: found C, 70.80; H, 8.88; Ni, 4.64; S, 10.20. $C_{72}H_{108}NiO_4S_4$ requires C, 70.62; H, 8.89; Ni, 4.79; S, 10.47%. $\delta_{\rm H}(300 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 7.38 (8 H, d, J = 9.0 Hz, aromatic H), 6.87 (8 H, dd, J = 1.5–9.0 Hz, aromatic H), 4.08–3.99 (8 H, m, –OC H_2 –), 1.85–1.20 (60 H, m), 1.00–0.90 (24 H, m, –CH₃). $\delta_{\rm C}(75 \text{ MHz}, \text{CD}_2\text{Cl}_2)$ 180.71, 160.07, 134.10, 130.31, 114.29, 68.20, 66.54, 39.22, 37.23, 36.10, 31.92, 29.86, 29.65, 29.63, 29.59, 29.57, 29.38, 29.34, 29.19, 27.98, 25.99, 24.64, 22.68, 22.43, 22.34, 19.39, 13.89. HRMS(CI): found 1223.6636, [M + H]⁺ requires 1223.6562.

Acknowledgements

Authors thank the French National Research Agency for financial support as part of ANR CPA-FALOIR 2007–2010 Project. Authors also thank A. Sournia-Saquet for the preliminary electrochemical investigation.

References

- 1 T. W. J. Gilbert and E. B. Sandell, J. Am. Chem. Soc., 1960, 82, 1087.
- 2 G. N. Schrauzer and V. Mayweg, J. Am. Chem. Soc., 1962, 84, 3221–3221.
- 3 G. N. Schrauzer, V. Mayweg, H. W. Finck, U. Müller-Westerhoff and W. Heinrich, Angew. Chem., Int. Ed. Engl., 1964, 3, 381; G. N. Schrauzer and V. Mayweg, Z. Naturforsch., B: Anorg. Chem., Org. Chem., Biochem., Biophys., Biol., 1964, 19, 192; G. N. Schrauzer and H. W. Finck, Angew. Chem., Int. Ed. Engl., 1964, 3, 133.
- 4 G. N. Schrauzer and V. P. Mayweg, J. Am. Chem. Soc., 1965, 87, 1483–1489.
- 5 P. Y. Bie, H. Wang, C. L. Zhang, X. F. Pan and T. K. Yang, *Chin. Chem. Lett.*, 2002, **13**, 167–170.
- 6 N. Kuramoto and K. Asao, Dyes Pigm., 1990, 12, 65-76.
- 7 K. Ohta, A. Takagi, H. Muroki, I. Yamamoto, K. Matsuzaki, T. Inable and Y. Maruyama, J. Chem. Soc., Chem. Commun., 1986, 883–885; K. Ohta, H. Hasebe, H. Ema, T. Fujimoto and I. Yamamoto, J. Chem. Soc., Chem. Commun., 1989, 1610–1611; K. Ohta, H. Hasebe, H. Ema, M. Moriya, T. Fujimoto and I. Yamamoto, Mol. Cryst. Liq. Cryst., 1991, 208, 21–32; K. Ohta, Y. Inagaki-Oka, H. Hasebe and I. Yamamoto, Polyhedron, 2000, 19, 267–274.
- 8 K. Ohta, A. Takagi, H. Muroki, I. Yamamoto, K. Matsuzaki, T. Inabe and Y. Maruyama, *Mol. Cryst. Liq. Cryst.*, 1987, 147, 15–24.
- 9 K. Ohta, H. Hasebe, M. Moriya, T. Fujimoto and I. Yamamoto, Mol. Cryst. Liq. Cryst., 1991, 208, 33-41.
- 10 H. Horie, A. Takagi, H. Hasebe, T. Ozawa and K. Ohta, J. Mater. Chem., 2001, 11, 1063–1071.
- 11 M. C. Aragoni, M. Arca, F. A. Devillanova, F. Isaia, V. Lippolis, A. Mancini, L. Pala, G. Verani, T. Agostinelli, M. Caironi, D. Natali and M. Sampietro, *Inorg. Chem. Commun.*, 2007, 10, 191–194.

- S. Oliver and C. Winter, Adv. Mater., 1992, 4, 119–121;
 C. S. Winter, S. N. Oliver, J. D. Rush, C. A. S. Hill and
 A. E. Underhill, Mol. Cryst. Liq. Cryst., 1993, 235, 181–189.
- 13 J.-Y. Cho, S. Barlow, S. R. Marder, J. Fu, L. A. Padilha, E. W. Van Stryland, D. J. Hagan and M. Bishop, *Opt. Lett.*, 2007, **32**, 671–673.
- G. C. Anyfantis, G. C. Papavassiliou, N. Assimomytis, A. Terzis, V. Psycharis, C. P. Raptopoulou, P. Kyritsis, V. Thoma and I. B. Koutselas, *Solid State Sci.*, 2008, 10, 1729–1733; T. D. Anthopoulos, G. C. Anyfantis, G. C. Papavassiliou and D. M. de Leeuw, *Appl. Phys. Lett.*, 2007, 90, 122105; T. D. Anthopoulos, S. Setayesh, E. Smits, M. Cölle, E. Cantatore, B. de Boer, P. W. M. Blom and D. M. de Leeuw, *Adv. Mater.*, 2006, 18, 1900–1904; T. Taguchi, H. Wada, T. Kambayashi, B. Noda, M. Goto, T. Mori, K. Ishikawa and H. Takezoe, *Chem. Phys. Lett.*, 2006, 421, 395–398.
- 15 N. Robertson and L. Cronin, Coord. Chem. Rev., 2002, 227, 93–127; P. Deplano, M. L. Mercuri, A. Serpe and L. Pilia, in *The chemistry of metal enolates*, ed. J. Zabicky, John Wiley & Sons, Ltd., 2009, pp. 879–928; B. Garreau-de Bonneval, K. Moineau-Chane Ching, T.-T. Bui and L. Valade, Coord. Chem. Rev., 2009 (to be submitted); E. I. Stiefel, in *Prog. Inorg. Chem.*, ed. K. D. Karlin, John Wiley and Sons, Hoboken, New Jersey, 2004, vol. 52.

- 16 A. M. Van de Craats, J. M. Warman, A. Fechtenkötter, J. D. Brand, M. A. Harbison and K. Müllen, *Adv. Mater.*, 1999, 11, 1469–1472.
- 17 M. Veber, R. Fugnitto and H. Strzelecka, Mol. Cryst. Liq. Cryst., 1983, 96, 221–227.
- 18 G. Wenz, Macromol. Rapid Commun., 1985, 6, 577.
- 19 K. Ohta, A. Takagi, H. Muroki, I. Yamamoto, K. Matsuzaki, T. Inable and Y. Maruyama, J. Chem. Soc., Chem. Commun., 1986, 883–885.
- 20 K. Arumugam, J. E. Bollinger, M. Fink and J. P. Donahue, *Inorg. Chem.*, 2007, 46, 3283–3288.
- 21 C. Giansante, P. Ceroni, V. Balzani, M. Maestri, S.-K. Lee and F. Vogtle, *New J. Chem.*, 2007, **31**, 1250–1258.
- 22 H. Sakurai, K. Tanabe and K. Narasaka, Chem. Lett., 2000, 168-169.
- 23 O. Mitsunobu, M. Yamada and T. Mukaiyama, Bull. Chem. Soc.
- Jpn., 1967, 40, 935–939; O. Mitsunobu and M. Yamada, Bull. Chem. Soc. Jpn., 1967, 40, 2380–2382.
 24 P. Secondo and F. Fages, Org. Lett., 2006, 8, 1311–1314.
- 25 E. J. Foster, J. Babuin, N. Nguyen and V. E. Williams, Chem. Commun., 2004, 2052–2053.
- 26 C.-T. Chou, Y.-F. Pai, C.-C. Lin, T. K. Misra and C.-Y. Liu, J. Chromatogr., A, 2004, 1043, 255–263.
- 27 A. Sournia-Saquet, B. Garreau-de Bonneval, K. I. Chane-Ching and L. Valade, J. Electroanal. Chem., 2008, 624, 84–90.