Surface modification of nylon 6,6 using a carbene insertion approach

Anton Blencowe,^a Kevin Cosstick^b and Wayne Hayes^{*a}

Received (in Cambridge, UK) 6th October 2005, Accepted 2nd November 2005 First published as an Advance Article on the web 17th November 2005 DOI: 10.1039/b514205a

The diazirine functionalised fluorenone, 3-[3-(trifluoromethyl)diazirin-3-yl]phenyl-9-oxo-9*H*fluorene-2-carboxylate was synthesised to act as a model compound capable of modifying a wide variety of polymeric substrates. Photochemical activation of the diazirine moiety of the fluorenone derivative was utilised to afford highly reactive carbenes capable of insertion into or addition to a wide variety of functionalities. In this paper the photoinduced attachment of a fluorenone derivative to nylon 6,6 has been studied using UV-visible spectroscopic analysis. Incorporation of the fluorenone chromophore onto the backbone of nylon at different loading levels and after different coating cycles has been investigated and is detailed in this paper.

1. Introduction

The development of compounds capable of functionalising multiple substrates has been the subject of intense research. An area that has attached considerable interest is the modification of polymeric substrates with multifunctional dyes and reactants. Included amongst these types of reagents are 'universal dyes' which possess high affinities for multiple substrate types. A notable example is the vinyl sulfone azo dye developed¹ by Lee *et al.*, which possesses the ability to act as a disperse dye and a reactive dye. When applied to polyester-cotton blends the vinyl sulfone moiety reacts with the nucleophilic groups present in the cotton whilst the dye is also dispersed efficiently into the hydrophobic polyester fibres. Freeman and Sokolowska-Gajda have developed naphtholazo dyes that can act as disperse or ionic dyes if they are converted into their cationic form.² More recently, Freeman and co-workers have developed a pyrazoline based reactive-disperse dye that has high affinities for polyester, nylon and wool fibres.³ Although such universal dyes have shown significant promise these reagents are still limited to use with particular polymeric substrates as a result of their chemical reactivity and selectivity.

An alternative class of reactants that is capable of reacting with almost all organic functionalities are carbenes. The ability of carbenes to react rapidly with any groups within their vicinity, including C–H, O–H, N–H and S–H bonds and C–C double bonds, render these reagents ideal for functionalising organic substrates. As a result of the highly reactive and indiscriminate nature of carbenes they have been applied widely for the modification of substrates to afford biofunctional materials.⁴ In addition, carbene insertion approaches have also been adopted for the general modification of polymeric materials to afford functionalised substrates with enhanced physical and chemical characteristics.⁵ Braybrook *et al.* have developed tosylhydrazone and diazirine functionalised azobenzene dyes,⁶ which, under photolytic conditions

decompose with extrusion of nitrogen to afford carbenes. In preliminary experiments the tosylhydrazone-dye was converted to its sodium salt and then photolysed in methanol and 2,2,2-trifluoroethanol. The reaction in methanol afforded the desired O-H insertion product only in low yield, whereas exclusive formation of the desired ether occurred with 2,2,2trifluoroethanol. Photolysis of the diazirine-dye in cyclohexane and methanol resulted in low yields of the desired C-H and O-H insertion products, respectively. More recently, Moloney and co-workers have employed carbenes derived from the thermal treatment of diaryldiazomethanes to introduce electron-rich aromatic systems onto the surface of various polymeric substrates, including polystyrene, polythene, nylon, silica, controlled pore glass and poly(tetrafluoroethylene).⁷ Reaction of the electron-rich aromatic systems introduced onto the substrate surface with diazonium salts resulted in intense coloration which was found to be consistent with initial modification of the polymeric substrate via the carbene insertion approach employed.

In the light of these developments our studies have focused on the development of a functionalised carbene that is capable of reacting in a single step with any substrate type upon exposure to suitable stimuli (for example light). The carbene derivative has been designed so that it can be mixed with the substrate in an inert form as a diazirine. The carbene is then liberated from the diazirine⁸ upon irradiation. In the present study, the ability of a photoinduced carbene containing fluorenone to react with nylon 6,6 was investigated. The diazirine functionalised dye was mixed initially with nylon 6,6 in different weight to weight ratios and irradiated using a 125 W high pressure mercury vapour lamp. After exhaustive washing, the amount of chromophore incorporated on to the nylon substrate was assessed using UV-visible spectroscopic analysis.

2. Results and discussion

2.1 Synthesis of diazirine functionalised fluorenone 1

The diazirine functionalised fluorenone **1** was synthesised efficiently (87%) from 3-(3-hydroxylphenyl)-3-(trifluoromethyl)

^a The School of Chemistry, The University of Reading, Whiteknights, Reading, UK RG6 6AD. E-mail: w.c.hayes@reading.ac.uk

^b DuPont, P.O. Box 401, Wilton Site, Middlesbrough, Cleveland, UK TS6 8JJ



Scheme 1 Synthesis of diazirine functionalised fluorenone derivative 1, (a) *n*-BuLi, Et₂NCOCF₃ (b) NH₂OH \cdot HCl (c) TsCl, NEt₃, DMAP (d) NH₃, -78 °C (e) Ag₂O (f) BBr₃ (g) fluorenone-2-carboxylic acid, DCC, DMAP.

diazirine **2** and fluorenone-2-carboxylic acid (Scheme 1) using the coupling reagent N,N'-dicyclohexylcarbodiimide (DCC) and a catalytic amount of 4-(N,N-dimethylamino)pyridine (DMAP).

The hydroxyl diazirine 2 was constructed in 6-steps (overall yield of 78%) from commercially available 3-bromophenol (Scheme 1) using a method based upon the synthesis of trifluoromethyl aryl diazirines first reported by Brunner et al.9 3-Bromophenol was protected initially as the methyl ether 3 using sodium hydroxide in the presence of iodomethane. Reaction of the methyl ether 3 with *n*-butyllithium and N,N-diethyltrifluoroacetamide¹⁰ afforded the respective trifluoromethyl ketone, 2,2,2-trifluoro-1-(3-methoxyphenyl) ethanone, which was then converted to the corresponding oxime 4 via reaction with hydroxylamine hydrochloride. Formation of the diaziridine 5 was achieved by converting the oxime 4 to its O-tosyl derivative, O-tosyl-2,2,2-trifluoro-1-(3-methoxyphenyl)ethanone oxime, which was then reacted with liquid ammonia to yield the diaziridine 5. Oxidation of 5 using Ag₂O afforded 3-(trifluoromethyl)-3-(3-methoxyphenyl)diazirine, which was then deprotected with boron tribromide to afford the hydroxyl diazirine 2.

The fluorenone derivative **1** was a bright yellow crystalline solid similar in appearance to that of fluorenone-2-carboxylic acid. UV-visible spectroscopic analysis of **1** in 2,2,2-trichloroethanol revealed a strong absorption band ($\lambda_{max} = 277$ nm) with a pronounced shoulder at $\lambda = 304$ nm resulting from the conjugated aromatic system of the fluorenone moiety. The adsorption resulting from the π - π * transition of the diazo moiety of the diazirine could be observed as a weak adsorption band centred at $\lambda = 369$ nm. The molar absorptivity coefficient of **1** in 2,2,2-trichloroethanol was determined to be 62 407 m² mol⁻¹ at $\lambda = 277$ nm.

2.2 Photochemisty of diazirine functionalised fluorenone 1

In order to simulate the reaction between the carbene generated from **1** and nylon 6,6, model reactions were conducted involving representative substrates. Irradiation (using a 125 W high pressure mercury lamp) of the fluorenone **1** in acetic acid, *n*-butylamine and *N*-butylbutyramide¹¹ (0.03 M) for a period of 12 hours resulted in high yields (>95%) of the desired insertion products. Photochemical reaction of **1** with acetic acid resulted in exclusive formation of the ester **6** (Scheme 2) as



Scheme 2 Insertion products generated *via* photochemical reaction of **1** with acetic acid, *n*-butylamine and *N*-butylbutyramide.

shown by ¹H NMR spectroscopic analysis.¹² Photolysis of **1** in *n*-butylamine afforded secondary amines (such as 7, Scheme 2) arising from insertion of carbenes into the amine N-H bonds and C-H insertion products (such as 8, Scheme 2) as revealed by ¹H and ¹⁹F NMR spectroscopic analysis.^{13–15 19}F NMR spectroscopic analysis of the product obtained upon photolysis of 1 in N-butylbutyramide revealed an extensive number of resonances corresponding to the trifluoromethyl group of a complex mixture of products arising from insertion of the carbene into N-H and C-H bonds. In addition, the carbonyl oxygen could have acted as an election donor, reacting with a carbene to initially form an ylide which could react further to afford secondary products.^{15,16} UV-visible spectroscopic analysis of the crude product mixtures obtained from photochemical reaction of the fluorenone 1 with acetic acid, nbutylamine and N-butylbutyramide exhibited strong adsorption maxima at 277 nm (in 2,2,2-trichloroethanol) corresponding to the fluorenone moiety.

The ability of the carbene generated from 1 to insert into the X–H (X = C, O or N) bonds of acetic acid, *n*-butylamine and *N*-butylbutyramide demonstrated that, upon photochemical activation, the carbene would be capable of inserting into the chain ends and polymer backbone of nylon 6,6. In such circumstances it would be possible to attach several fluorenone molecules to a single polymer chain.

Photolysis of benzophenone derivatives such as 9-fluorenone can also generate diradical species that are capable of reacting with nylon. To determine if the fluorenone moiety of 1 would react with nylon in this manner, 9-fluorenone was dissolved in cyclohexane and acetic acid (0.15 M) and irradiated for a period of 12 hours. Subsequent removal of the solvent and analysis of the residue via ¹H NMR spectroscopic analysis revealed that ca. 10% of 9-fluorenone reacted with cyclohexane via hydrogen abstraction (Scheme 3),¹⁷ whereas no reaction occurred when acetic acid was used. These results imply that, upon irradiation, the fluorenone carbonyl of 1 could become photo-excited leading to hydrogen abstraction from the alkyl backbone of nylon and the formation of a 9-hydroxyfluorenyl radical (see 9, Scheme 3).¹⁸ The radicals produced in this process could then react further to afford a variety of products including alcohols, alkanes, ketones and carboxylic acids or undergo radical-radical coupling.¹⁷

2.3 Dyeing of nylon 6,6

As a result of the poor solubility of nylon 6,6 in common organic solvents, attachment of the model fluorenone



Scheme 3 Photochemical reaction of 9-fluorenone with cyclohexane.

derivative via photochemical means was conducted in the solid phase. Anhydrous diethyl ether solutions of 1 were added to nylon 6,6 powder (with dimensions varying from 44 to 440 μm) in a 5 mL vial, vortexed and then sonicated under argon. To produce thin layers of the nylon powder suitable for irradiation the solvent was removed from the mixture under reduced pressure (0.1 mbar) at 50 °C, whilst being spun at ca. 400 rpm. The vials were flushed with argon, sealed and placed 3 cm away from a 125 watt high pressure mercury vapour lamp and irradiated for 12 hours. The resultant nylon powder was then washed with chloroform, tetrahydrofuran (THF) and methanol, dried (0.1 mbar) at 40 °C and analysed using UVvisible spectroscopic analysis. To eliminate chemisorption as a possible mechanism of dyeing, blanks were run in parallel using the same procedure without irradiation. In order to eliminate nylon photolytic degradation as a possible source of contaminates that could absorb within the UV-visible region under investigation, nylon powder was irradiated for 72 hours under argon. Samples of nylon powder were removed every 12 hours and analysed via UV-visible spectroscopic analysis. Changes were not observed in the UV-visible spectrum of the nylon powder after each 12 hour period of irradiation and thus it was concluded that the nylon used was stable under the photolytic conditions employed.

UV-visible spectroscopic analysis of the modified nylon obtained using different ratios of diazirine to nylon indicated that the fluorenone derivative **1** was incorporated successfully at each of the mixing ratios employed (diazirine:nylon, 1:1, 1:2, 1:5, 1:10, 1:20, 1:100, 1:1000). A graph of absorbance at 277 nm *versus* the mixing ratio (diazirine/nylon) employed revealed an exponential relationship in which the absorbance was found to increase as the mixing ratio increased (Fig. 1, \blacktriangle). At mixing ratios of <0.1 (diazirine:nylon 1:10) the absorbance of the modified nylon was found to increase in the mixing ratio. However, at higher mixing ratios (>0.1) the absorbance of the modified nylon



Fig. 1 \blacktriangle = Absorbance of functionalised nylon at 277 nm *vs.* mixing ratio (diazirine/nylon). \bullet = Percentage incorporation of chromophore *vs.* mixing ratio of diazirine and nylon (diazirine/nylon).

only increased slightly with an increase in the mixing ratio, reaching a plateau at a diazirine : nylon mixing ratio of 1 : 2. These results indicate that there is a limit to the loading of the diazirine derivative at which additional chromophore is not incorporated onto the substrate regardless of the amount of diazirine employed. At higher loadings (diazirine : nylon 1 : 1) it is proposed that the carbenes produced from the fluorenone derivative 1 are in close enough proximity to react with other molecules of 1, thus limiting the reaction of the carbene with the nylon substrate.

The percentage of chromophore incorporated into the nylon compared to the amount of fluorenone derivative 1 employed initially is shown in Fig. 1 (\bullet). At high mixing ratios the amount of chromophore incorporated is <1% and was found to increase exponentially as the mixing ratio decreased resulting in ca. 9% incorporation of the chromophore at a diazirine: nylon mixing ratio of 1: 1000. The results confirm that at high mixing ratios more of the fluorenone derivative 1 is in contact with itself as opposed to the substrate. Thus, at high loadings only a small proportion of the applied fluorenone derivative 1 is in close enough proximity to react with the nylon polymer chains upon photoactivation of the diazirine moiety. In addition, the adsorption of radiation by the fluorenone derivative 1 at the surface of the solid mixture may hinder the activation of the diazirine moiety of other molecules of 1 just below the surface. UV-visible and NMR spectroscopic analyses of the washings obtained when high mixing ratios (e.g. diazirine: nylon, 1:1) were employed provided evidence for unreacted diazirine. In addition, a singlet resonance at $\delta_{\rm F}$ –68.5 ppm in the ¹⁹F NMR spectrum¹⁹ of the washings revealed the presence of the azine derivative²⁰ (see 10, Fig. 2) of the fluorenone 1. The formation of azine derivatives in the solution phase chemistry of diazirine functionalised azobenzene dyes has also been reported by Braybrook *et al.*⁶ At lower diazirine : nylon mixing ratios (<1:10) the diazirine **1** was not detected *via* either UV-visible or 19 F NMR spectroscopic analysis of the washings, implying complete decomposition of the diazirine moiety of 1.

To determine if the amount of chromophore incorporated after additional dyeing cycles followed a linear relationship the nylon was mixed with the fluorenone derivative **1**, irradiated, washed and then the procedure was repeated a total of six times. The modified nylon was analysed *via* UV-visible



Fig. 2 Structure of azine 10.



Fig. 3 Absorbance of functionalised nylon at 277 nm vs. the coating cycle for the diazirine : nylon mixing ratios of 1:1, 1:10, 1:100 and 1:1000, respectively.

spectroscopic analysis after each coating cycle. A graph of absorbance at 277 nm against the coating cycle at four different diazirine: nylon mixing ratios (1:1, 1:10, 1:100) and 1:1000) revealed a linear relationship for each mixing ratio employed, in which the absorbance increased with each coating cycle (Fig. 3). In addition to the UV-visible spectroscopic results obtained it was possible to observe a difference in the depth of colour after each coating cycle. For example, after six coating cycles (at a 1:1 diazirine: nylon mixing ratio) the colour of the nylon powder had changed from a bright white to a light yellow.

3. Conclusions

A diazirine functionalised fluorenone has been synthesised efficiently and employed as a model compound to demonstrate the applicability of carbene insertion processes for the modification of polymeric substrates such as nylon 6,6. Photochemical reaction of the fluorenone derivative with substrates representative of the functional groups present in nylon afforded high yields of carbene insertion products. Solid state photochemical reactions of the fluorenone derivative with nylon were conducted at different diazirine:nylon mixing ratios and UV-visible spectroscopic analysis of the modified nylon revealed that the fluorenone moiety was incorporated successfully into the nylon and enabled quantification of the amount of chromophore present. In addition, repeating the photo-induced modification cycle resulted in a linear increase in the amount of chromophore incorporated.

4. Experimental

Materials

Reagents were purchased from either Lancaster, Acros Chimica or the Aldrich Chemical Company and were used without further purification, unless stated. Diethyl ether and tetrahydrofuran (THF) were distilled from benzophenone and sodium. Dichloromethane was distilled from CaH₂. Samples of nylon 6,6 (stabilised with copper halide) were supplied by DuPont. GC grade 2,2,2-trichloroethanol (99.9 + %) was used for UV-visible spectroscopic analysis.

Instrumentation

Thin-layer chromatography (TLC) was performed on aluminium sheets coated with Merck silica gel 60 F₂₅₄. Developed TLC plates were stained with potassium permanganate solution or scrutinised under 254 nm UV light. Column chromatography was performed using SI60 Sorbent silica (40-63 µm) supplied from VWR international. Melting points were determined using a Mettler FP61 melting point apparatus and are uncorrected. ¹H Nuclear magnetic resonance (NMR) spectroscopy was performed on either a Bruker DPX250 (250 MHz) or a Bruker AMX400 (400 MHz) spectrometer (using TMS and the deuterated solvent as lock and residual solvent). ¹³C NMR spectroscopy was performed on Bruker AC250 (62.8 MHz) or Bruker AMX400 (100 MHz) spectrometers. ¹⁹F NMR spectroscopy was performed on a Bruker DPX250 (235 MHz) spectrometer (using CFCl₃ as internal reference). Infrared spectroscopy was performed using a Perkin Elmer 1720-X spectrometer with the samples analysed as thin films. UV-visible analysis was performed on a Perkin Elmer Lambda 25 UV/Vis spectrometer using methanol or 2,2,2-trichloroethanol as the solvent. Mass spectra (MS) were obtained either using a Fisons VG Autospec instrument or Finnigan MAT 95 instrument operating in chemical ionisation mode, using ammonia as the impact gas.

Preparation of fluorenone derivative 1

3-[3-(Trifluoromethyl)diazirin-3-yl]phenyl-9-oxo-9H-fluorene-2-carboxylate 1. Fluorenone-2-carboxylic acid (510 mg, 2.27 mmol) was dissolved in anhydrous dichloromethane (35 mL) under argon and DCC (692 mg, 3.41 mmol) and DMAP (2 mol%, 5 mg, 0.04 mmol) were added. After a period of 10 minutes, the diazirine 2 (361 mg, 1.78 mmol) was added and the reaction was stirred at room temperature in the dark for 20 hours. The insoluble N, N'-dicyclohexylurea was removed by filtration and the filtrate was concentrated in vacuo to afford a yellow solid. Purification via column chromatography on silica (1:1 hexane: dichloromethane) afforded the fluorenone derivative 1 as a bright yellow solid, 638 mg (87%); T_d 113.2 °C; UV-visible (MeOH): $\lambda = 372$ nm (N=N); IR ν_{max}/cm^{-1} (thin film) 739, 1056, 1151, 1188, 1241, 1605, 1713, 1719 and 3070; ¹H NMR (250 MHz, CDCl₃, TMS) $\delta_{\rm H}$ 7.07–7.08 (m, 1H, ArH), 7.12 (dquin, J = 1.8, 7.9 Hz, 1H, ArH), 7.33 (ddd, J = 1.0, 2.3, 8.2 Hz, 1H, ArH), 7.42 (td, J = 1.1, 7.4 Hz, 1H, ArH), 7.49 (t, J = 7.9 Hz, 1H, ArH), 7.58 (td, J = 1.2, 7.5 Hz, 1H, ArH), 7.65 (dt, J = 1.0, 7.5 Hz, 1H, ArH), 7.68 (dd, J = 0.6, 7.8 Hz, 1H, ArH), 7.75 (dt, J = 1.0, 7.4 Hz, 1H, ArH), 8.35 (dd, J = 1.6, 7.8 Hz, 1H, ArH), 8.45 (dd, J = 0.6, 1.6 Hz, 1H)ArH) ppm; ¹³C NMR (62.8 MHz, CDCl₃) $\delta_{\rm C}$ 28.7 (q, J = 40.3Hz, CN₂), 119.9 (ArCH), 120.4 (ArCH), 121.4 (ArCH), 121.5 $(q, J = 271.5 \text{ Hz}, CF_3), 123.2 (ArCH), 124.1 (ArCH), 124.8$ (ArCH), 125.8 (ArCH), 130.1 (ArCH), 130.2 (ArCC), 130.5 (ArCH), 131.3 (ArCC), 134.8 (ArCC), 135.1 (ArCC), 135.1 (ArCH), 137.0 (ArCH), 143.5 (ArCC), 149.7 (ArCC), 151.4 (CO₂), 164.2 (ArCO), 192.8 (CO) ppm; ¹⁹F NMR (235 MHz, CDCl₃, CFCl₃) $\delta_{\rm F}$ -65.5 (s, CF₃) ppm; CI-MS ([M]⁺ - N₂) calculated for C₂₂H₁₁F₃O₃: 380.0660, found: 380.0651.

3-(Trifluoromethyl)-3-(3-hydroxylphenyl)diazirine 2. 3-(Trifluoromethyl)-3-(3-methoxyphenyl)diazirine (11.43 g, 52.9 mmol) was dissolved in anhydrous dichloromethane (180 mL). Boron tribromide (7.55 mL, 79.4 mmol) was added dropwise over a period of 30 minutes and the mixture was stirred in the dark under argon for 24 hours. Water (30 mL) was added carefully followed by dichloromethane (100 mL) and water (200 mL). After 1 hour the organic phase was removed and the aqueous phase was extracted with dichloromethane $(3 \times 150 \text{ mL})$. The combined organic extracts were dried (MgSO₄), filtered and concentrated *in vacuo* at 40 °C to afford an orange oil. Purification via column chromatography on silica (3:2 hexane: dichloromethane), afforded the diazirine 2 as a very pale yellow oil, 10.36 g (97%); UV-visible (MeOH): $\lambda = 361 \text{ nm}$ (N=N); IR $\nu_{\text{max}}/\text{cm}^{-1}$ (thin film) 1154, 1204, 1272, 1355, 1454, 1500, 1588, 1612 and 3334; ¹H NMR (250 MHz, CDCl₃, TMS) $\delta_{\rm H}$ 5.00 (s, 1H, OH), 6.67 (m, 1H, ArH), 6.71-6.75 (m, 1H, ArH), 6.85-6.90 (m, 1H, ArH), 7.27 $(t, J = 7.9 \text{ Hz}, 1\text{H}, \text{Ar}H) \text{ ppm}; {}^{13}\text{C NMR} (62.8 \text{ MHz}, \text{CDCl}_3)$ $\delta_{\rm C}$ 28.7 (q, J = 40.5 Hz, CN_2), 113.9 (ArCH), 117.2 (ArCH), 119.2 (ArCH), 122.4 (q, J = 274.6 Hz, CF_3), 130.6 (ArCH), 131.2 (ArCC), 156.2 (ArCO) ppm; ¹⁹F NMR (235 MHz, CDCl₃, CFCl₃) $\delta_{\rm F}$ -65.6 (s, CF₃) ppm; CI-MS ([MH]⁺ – N₂) calculated for C₈H₅F₃O: 175.0371, found: 175.0365.

1-Bromo-3-methoxybenzene 3. 3-Bromophenol (10.02 g, 58 mmol) was dissolved in THF (150 mL) and KOH pellets (6.50 g, 116 mmol) were added. The mixture was stirred for a period of 30 minutes under argon and then MeI (5.4 mL, 87 mmol) was added. After 16 hours water (300 mL) and diethyl ether (100 mL) were added and the mixture was stirred for a further 30 minutes. The organic phase was removed and the aqueous phase was extracted with diethyl ether (3 \times 150 mL). The combined organic extracts were dried (MgSO₄), filtered and concentrated in vacuo to afford 3 as a pale yellow oil, 10.70 g (99%); IR $\nu_{\rm max}/{\rm cm}^{-1}$ (thin film) 766, 838, 1039, 1230, 1246, 1284, 1429, 1477, 1575, 1590 and 2937; ¹H NMR (250 MHz, $CDCl_3$, TMS) $\delta_H 3.79$ (s, 3H, OCH_3), 6.81–6.85 (m, 1H, ArH), 7.05–7.06 (m, 1H, ArH), 7.08–7.17 (m, 2H, 2ArH) ppm; ¹³C NMR (62.8 MHz, CDCl₃) δ_C 55.8 (CH₃), 113.5 (ArCH), 117.5 (ArCH), 123.2 (ArCBr), 124.2 (ArCH), 130.9 (ArCH), 160.8 (ArCO) ppm; CI-MS ($[M]^+$) calculated for C₇H₇OBr: 185.9, found: 185.9.

2.2.2-Trifluoro-1-(3-methoxyphenyl)ethanone. 1-Bromo-3methoxybenzene 3 (5.00 g, 26.9 mmol) was dissolved in anhydrous THF (100 mL) and cooled to -78 °C under argon. 1.6 M n-BuLi in hexanes (16.8 mL, 26.9 mmol) was added over a period of 5 minutes and the mixture was stirred for a further 5 minutes. N,N-Diethyltrifluoroacetamide (5.01 g, 29.9 mmol) was added over a period of 5 minutes and the mixture was stirred for 2 hours. The mixture was poured into a saturated NH₄Cl (300 mL) solution and stirred rapidly for an hour before extraction with diethyl ether (3 \times 100 mL). The combined organic extracts were dried (MgSO₄), filtered and concentrated in vacuo to afford a pale yellow oil. Purification via column chromatography on silica (3:2 hexane: dichloromethane) afforded the ketone, 2,2,2-trifluoro-1-(3-methoxyphenyl)ethanone, as a pale yellow oil, 4.83 g (88%); IR $\nu_{\rm max}$

cm⁻¹ (thin film) 1154, 1202, 1256, 1343, 1466, 1492, 1584, 1600 and 1718; ¹H NMR (250 MHz, CDCl₃, TMS) $\delta_{\rm H}$ 3.88 (s, 3H, OCH₃), 7.23–7.28 (m, 1H, Ar*H*), 7.46 (t, *J* = 16.1 Hz, 1H, Ar*H*), 7.57 (s, 1H, Ar*H*), 7.65–7.68 (m, 1H, Ar*H*) ppm; ¹³C NMR (62.8 MHz, CDCl₃) $\delta_{\rm C}$ 55.9 (CH₃), 114.3 (ArCH), 117.0 (q, *J* = 291.3 Hz, CF₃), 122.7 (ArCH), 123.2 (ArCH), 130.5 (ArCH), 131.5 (ArCC), 160.4 (ArCO), 180.8 (q, *J* = 35.1 Hz, CO) ppm; ¹⁹F NMR (235 MHz, CDCl₃, CFCl₃) $\delta_{\rm F}$ –71.6 (s, CF₃) ppm; CI-MS ([M]⁺) calculated for C₉H₇F₃O₂: 204.0398, found: 204.0400.

2,2,2-Trifluoro-1-(3-methoxyphenyl)ethanone oxime 4. 2,2,2-Trifluoro-1-(3-methoxyphenyl)ethanone (7.92 g, 30.0 mmol) and hydroxylamine hydrochloride (5.56 g, 80.0 mmol) were dissolved in ethanol (150 mL) and maintained under reflux for 2 hours before the mixture was neutralised with 4 M NaOH. After a further 2 hours under reflux, the mixture was neutralised again and the solution was concentrated in vacuo. The resulting residue was dissolved in water (200 mL) and extracted with diethyl ether (4×150 mL). The combined organic extracts were washed with 0.25 M HCl (200 mL), water (200 mL), dried (MgSO₄), filtered and concentrated in vacuo to afford the oxime 4 as a clear viscous oil, 8.07 g (97%); IR $\nu_{\rm max}$ cm⁻¹ (thin film) 1137, 1197, 1251, 1343, 1430, 1489, 1582, 1602, 1702 and 3346; ¹H NMR (250 MHz, CDCl₃, TMS) $\delta_{\rm H}$ 3.84 (s, 3H, OCH₃), 7.00-7.09 (m, 3H, 3ArH), 7.37-7.44 (m, 1H, ArH), 8.81 (br s, 1H, OH) ppm; ¹³C NMR (62.8 MHz, CDCl₃) $\delta_{\rm C}$ 55.8 (OCH₃), 114.7 (ArCH), 116.7 (ArCH), 121.0 $(q, J = 274.8 \text{ Hz}, CF_3), 121.2 (ArCH), 127.5 (ArCC), 130.2$ (ArCH), 147.8 (q, J = 32.4 Hz, CN), 159.8 (ArCO) ppm; ¹⁹F NMR (235 MHz, CDCl₃, CFCl₃) $\delta_{\rm F}$ -67.3 (s, CF₃) ppm; CI-MS ($[M]^+$) calculated for C₉H₈F₃O₂N: 219.0507, found: 219.0508.

O-Tosyl-2,2,2-trifluoro-1-(3-methoxyphenyl)ethanone oxime. Oxime 4 (12.18 g, 55.6 mmol), triethylamine (11.7 mL, 83.4 mmol), DMAP (50 mg) and p-toluenesulfonyl chloride (10.60 g, 55.6 mmol) were dissolved in dichloromethane (200 mL) under argon and stirred at room temperature for 36 hours in the dark. The resulting mixture was washed with water (2 \times 150 mL) and 0.25 M HCl (2 \times 150 mL). The combined aqueous washings were washed with dichloromethane (2 \times 100 mL) and the organic extracts were collected together, washed with saturated NaHCO₃ (150 mL), dried (MgSO₄), filtered and concentrated in vacuo to afford the O-tosyl oxime. O-tosyl-2,2,2-trifluoro-1-(3-methoxyphenyl)ethanone oxime as a white solid, 20.43 g (98%); mp 111.0–111.6 °C; IR ν_{max} cm⁻¹ (thin film) 1154, 1178 1194, 1255, 1291, 1390, 1487, 1578 and 1606; ¹H NMR (250 MHz, CDCl₃, TMS) $\delta_{\rm H}$ 2.48 (s, 3H, CH₃), 3.82 (s, 3H, OCH₃), 6.88-6.89 (m, 1H, ArH), 6.93-6.96 (m, 1H, ArH), 7.03-7.07 (m, 1H, ArH), 7.35-7.41 (m, 3H, 3ArH), 7.89 (AA'XX' system, 2H, 2ArH) ppm; ¹³C NMR (62.8 MHz, CDCl₃) δ_C 22.2 (CH₃), 55.8 (OCH₃), 114.3 (ArCH), 117.6 (ArCH), 119.9 (q, J = 277.6 Hz, CF_3), 120.9 (ArCH), 126.3 (ArCC), 129.6 (2ArCH), 130.3 (2ArCH), 130.4 (ArCH), 131.6 (ArCC), 146.6 (ArCC), 154.4 (q, J = 33.7 Hz, CN), 159.9 (ArCO) ppm; ¹⁹F NMR (235 MHz, CDCl₃, CFCl₃) $\delta_{\rm F}$ –67.4 (s, CF₃) ppm; CI-MS ([M]⁺) calculated for C₁₆H₁₄O₄F₃NS: 373.0596, found: 373.0599.

3-(Trifluoromethyl)-3-(3-methoxyphenyl)diaziridine 5. O-Tosyl-2,2,2-trifluoro-1-(3-methoxyphenyl)ethanone oxime (20.01 g, 53.6 mmol) was dissolved in dichloromethane (80 mL) and added dropwise over a period of 30 minutes to liquid ammonia (200 mL) at -78 °C under argon. After 12 hours the mixture was gradually warmed to room temperature. Water (200 mL) and dichloromethane (100 mL) were added and the mixture was stirred for 1 hour before removal of the organic phase and further extraction of the aqueous phase with dichloromethane $(3 \times 100 \text{ mL})$. The combined organic extracts were dried (MgSO₄), filtered and concentrated in vacuo to afford the diaziridine 5 as a crystalline solid, 11.60 g (99%); mp 40.1-40.6 °C; IR ν_{max} /cm⁻¹ (thin film) 1164, 1217, 1247, 1370, 1461, 1586, 1604 and 3256; $^1\mathrm{H}$ NMR (250 MHz, CDCl_3, TMS) δ_H 2.22 (d, J = 8.8 Hz, 1H, NH), 2.76 (d, J = 8.8 Hz, 1H, NH), 3.83 (s, 3H, OCH₃), 6.96-7.00 (m, 1H, ArH), 7.15-7.16 (m, 1H, ArH), 7.19–7.22 (m, 1H, ArH), 7.31 (t, J = 8.0 Hz, 1H, ArH) ppm; ¹³C NMR (62.8 MHz, CDCl₃) $\delta_{\rm C}$ 55.7 (OCH₃), 58.4 (q, J = 35.8 Hz, CN_2), 114.0 (ArCH), 116.2 (ArCH), 120.7 (ArCH), 123.9 (q, J = 278.3 Hz, CF_3), 130.3 (ArCH), 133.4 (ArCC), 160.1 (ArCO) ppm; ¹⁹F NMR (235 MHz, CDCl₃, CFCl₃) $\delta_{\rm F}$ -75.9 (s, CF₃) ppm; CI-MS ([MH]⁺) calculated for C₉H₉F₃N₂O: 219.0745, found: 219.0748.

3-(Trifluoromethyl)-3-(3-methoxyphenyl)diazirine. Diaziridine 5 (11.40 g, 52.3 mmol) was dissolved in diethyl ether (120 mL) and Ag₂O (14.81 g, 63.8 mmol) was added. The mixture was stirred vigorously in the dark under argon for 20 hours. The insoluble silver residues were removed by filtration though a MgSO₄-Celite[®] layered sinter bed and the filtrate was concentrated in vacuo to afford 3-(trifluoromethyl)-3-(3methoxyphenyl)diazirine as a very pale yellow oil, 11.01 g (98%); UV-visible (MeOH): $\lambda = 363$ nm (N=N); IR ν_{max} / cm⁻¹ (thin film) 1154, 1214, 1267, 1355, 1467, 1496, 1584, 1607 and 2962; ¹H NMR (250 MHz, CDCl₃, TMS) $\delta_{\rm H}$ 3.73 (s, 3H, OCH₃), 6.61 (s, 1H, ArH), 6.68-6.72 (m, 1H, ArH), 6.84-6.89 (m, 1H, Ar*H*), 7.23 (t, J = 8.1 Hz, 1H, Ar*H*) ppm; ¹³C NMR (62.8 MHz, CDCl₃) $\delta_{\rm C}$ 28.8 (q, J = 40.2 Hz, CN_2), 55.7 (OCH₃), 112.6 (ArCH), 115.6 (ArCH), 119.1 (ArCH), 122.5 $(q, J = 274.7 \text{ Hz}, CF_3), 130.0 (ArCC), 130.4 (ArCH), 160.2$ (ArCO) ppm; ¹⁹F NMR (235 MHz, CDCl₃, CFCl₃) $\delta_{\rm F}$ –65.6 (s, CF₃) ppm; CI-MS ($[M]^+$ – N₂) calculated for C₉H₇F₃O: 188.0449, found: 188.0442.

General procedure for dyeing of nylon 6,6 using the fluorenone dye 1

Nylon 6,6 powder was washed prior to modification with hexane, chloroform, THF and methanol (10 mL of each) and dried under vacuum (0.1 mbar). Nylon powder was weighed into a 5 mL vial and a solution of **1** in anhydrous diethyl ether (1 mL) was added to afford weight to weight diazirine : nylon mixing ratios of 1:1, 1:2, 1:5, 1:10, 1:20, 1:100 and 1:1000, respectively. The vial was spun at 400 rpm and the solvent removed under reduced pressure (0.1 mbar) at 50 °C for 2 hours. The vial was flushed with argon, sealed and irradiated using a 125 W high pressure mercury lamp for 12 hours. The modified nylon was washed three times with chloroform, THF and methanol (3 × 10 mL of each) and dried under vacuum (0.1 mbar) at 40 °C. Blanks were prepared

in an identical manner and washed in an identical manner, however, they were stored in the dark for 12 hours as opposed to being irradiated.

Acknowledgements

AB would like to thank DuPont Fellows Forum for funding.

References

- 1 J. J. Lee, N. K. Han, W. J. Lee, J. H. Choi and J. P. Kim, *Color. Technol.*, 2003, **119**, 134.
- 2 J. Sokolowska-Gajda and H. S. Freeman, Dyes Pigm., 1990, 14, 35.
- 3 P. Suwanruji, H. S. Freeman and D. Zhao, *Color. Technol.*, 2004, **120**, 220.
- 4 A. Blencowe and W. Hayes, Soft Matter, 2005, 1, 178.
- 5 (a) U. G. Kang, J. W. Raksis, C. L. Kehr and C. A. Ferrin, in Polymer Surface Modification using Aqueous Stable Diazo Solution, US Patent 5,075,427, 1991; (b) R. Reiner and H. Kaiser, in Process and Compounds for Surface Modification of Macromolecular Substances, US Patent 4,309,453, 1982; (c) D. A. Olsen and A. J. Osterras, in Carbene Modified Organic Surfaces, Canadian Patent 812,736, 1969; (d) A. W. Morgan and J. S. Swenson, in Process for the Chemical Modification of the Solid Surface of a Polymer, US Patent 3,376,278, 1968; (e) P. J. Pullan, in Dyeing Textile Fibres, Br. Patent 1,395,885, 1975; (f) P. J. Pullan, in A Method of Colouring a Fabric or Film, Br. Patent 1,412,963, 1975; (g) C. Holstead, R. A. Jeffreys, L. Shuttleworth and R. S. Wickham. in Photographic Materials, Br. Patent 1,344,993, 1974; (h) C. Holstead, L. Shuttleworth, J. Griffiths and P. J. Pullan, in Dveing or Treating Films and Fibres, Br. Patent 1,344,991, 1974; (i) M. G. Moloney, W. Ebenezer and K. Awenat, in Process for the Surface Functionalisation of Polymeric Substrates using Diarylcarbenes as Reactive Intermediates, US Patent 6,699,527, 2004; (i) K. Awenat, W. Ebenezer and M. G. Moloney, in A Method for the Functionalisation of Polymeric Substrates, Br. Patent PCT/GB99/03629, 1999
- 6 D. R. Braybrook, M. G. Moloney, H. M. I. Osborn and W. J. Norris, J. Photochem. Photobiol., A, 1993, 70, 171.
- 7 K. M. Awenat, P. J. Davis, M. G. Moloney and W. Ebenezer, *Chem. Commun.*, 2005, 990.
- 8 Chemistry of Diazirines, ed. M. T. H. Liu, CRC Press, Boca Raton, 1987, vol. 1.
- 9 (a) J. Brunner, H. Senn and F. M. Richards, J. Biol. Chem., 1980, 255, 3313; (b) J. Brunner and G. Semenza, *Biochemistry*, 1981, 20, 7174.
- 10 J. H. Robson and J. Reinhart, J. Am. Chem. Soc., 1955, 77, 498.
- 11 C. Aubert, C. Huard-Perrio and M.-C. Lasne, J. Chem. Soc., Perkin Trans. 1, 1997, 2837.
- 12 (a) A. D. Allen, I. C. Ambridge, C. Che, H. Micheal, R. J. Muir and T. T. Tidwell, J. Am. Chem. Soc., 1983, 105, 2343; (b) J. Gaspar and A. Guerrero, *Tetrahedron: Asymmetry*, 1995, 6, 231.
- (a) J. P. Richard, J. Am. Chem. Soc., 1989, 111, 6735; (b) F. Levrat,
 H. Stoeckli-Evans and N. Engel, *Tetrahedron: Asymmetry*, 2002,
 13, 2335; (c) Y. Gong, K. Kato and H. Kimoto, *Bull. Chem. Soc. Jpn.*, 2002, 75, 2637.
- 14 T. Okano, H. Sugiura, M. Fumoto, H. Matsubara, T. Kusukawa and M. Fujita, J. Fluorine Chem., 2002, 114, 91.
- 15 A. Admasu, A. D. Gudmundsdóttir, M. S. Platz, D. S. Watt, S. Kwiatkowski and P. J. Crocker, J. Chem. Soc., Perkin Trans. 2, 1998, 1093.
- 16 M. S. Platz, W. R. White and D. A. Modarelli, *Res. Chem. Intermed.*, 1994, 20, 175.
- 17 J.-F. Rontani, Trends Photochem. Photobiol., 1997, 4, 125.
- 18 (a) R. S. Davidson, P. F. Lambeth, F. A. Younis and R. Wilson, J. Chem. Soc. C, 1969, 2203; (b) R. S. Davidson and R. Wilson, J. Chem. Soc. B, 1970, 71.
- 19 S. Benomar, B. Patel and A. E. Tipping, J. Fluorine Chem., 1990, 50, 207.
- 20 (a) M. T. H. Liu and K. Ramakrishnan, J. Org. Chem., 1977, 42, 3450; (b) M. P. Doyle, A. H. Devia, K. E. Bassett, J. W. Terpstra and S. N. Mahapatro, J. Org. Chem., 1987, 52, 1619.