

View Article Online View Journal

RSC Advances

This article can be cited before page numbers have been issued, to do this please use: M. Zarghani and B. Akhlaghinia, *RSC Adv.*, 2016, DOI: 10.1039/C6RA07252F.



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. This Accepted Manuscript will be replaced by the edited, formatted and paginated article as soon as this is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/advances

Published on 24 March 2016. Downloaded by Gazi Universitesi on 26/03/2016 13:20:09

View Article Online DOI: 10.1039/C6RA07252F

ROYAL SOCIETY OF CHEMISTRY

Journal Name

ARTICLE

Received 00th January 20xx, Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

Magnetically separable Fe₃O₄@chitin as an eco-friendly nanocatalyst with high efficiency for green synthesis of 5-substituted-1*H*-tetrazoles under solvent-free conditions

Monireh Zarghani^a and Batool Akhlaghinia*^a

The present study describes an efficient, eco-friendly and simple method for the synthesis of 5-substituted-1*H*-tetrazoles catalyzed by magnetite-chitin ($Fe_3O_4@$ chitin) as a green and recyclable catalyst. $Fe_3O_4@$ chitin was initially prepared using hydrothermal synthesis. Subsequently, the structure, morphology, and magnetic properties of the prepared nanocatalyst were studied with some different spectroscopic, microscopic and thermogravimetric techniques such as FT-IR, XRD, SEM, TEM, VSM and TGA. Obtained results showed that $Fe_3O_4@$ chitin nanoparticles exhibited uniform cubic shape and were well monodispersed. Also, magnetic measurement revealed that the synthesized nanocatalyst had superparamagnetic feature. The application of this new nanocatalyst allows the synthesis of a variety of tetrazoles through the reaction of nitriles with 1-butyl-3-methylimidazolium azide ([Ibmim][N₃]) under solvent-free condition. This synthetic pathway is a green protocol offering significant advantages, such as excellent yield of products in short reaction times, mild reaction conditions, minimizing chemical waste, easy preparation of the catalyst and its recyclability up to six cycles without any considerable loss of efficiency.

1. Introduction

During recent decades, there has been a considerable research interest in the area of green chemistry using environmentally benign reagents and clean synthetic procedures. In this context, nanotechnology as one of the most fascinating developments can be applied to produce safer and more sustainable nanostructure material and more efficient chemical processes.¹⁻⁵ Among the various nanomaterial, magnetic nanoparticles as an eco-friendly metal oxide, have received considerable attention because of their potential applications, including magnetic fluids,⁶ magnetic resonance imaging,⁷ biotechnology/biomedicine⁸ and data storage.⁹ Moreover, recent search has been shown that magnetic nanoparticles could be efficient and promising supports for catalysts.¹⁰⁻¹⁵ From the viewpoint of green chemistry, it is useful to develop new catalyst recycling methods to replace conventional procedures such as centrifugation and filtration.¹⁶ Thus, magnetite nanoparticles became the strong candidate due to unique paramagnetic properties which allow them to be efficiently separated from the reaction mixtures by an external magnet.¹⁷⁻²⁰ Additionally, other important features of these nanoparticles are high degree of chemical stability in various solvents, easy synthesis and modification, high surface area, low toxicity, cost-effective and benign character.²¹

On the other hand, the recent scientific reports indicate that natural polymers with many significant biological (biodegradable, biocompatible and bioactive) and chemical properties (polycationic, hydrogel, reactive groups such as OH and NH₂) can be used as heterogeneous catalytic systems.²²⁻²⁵ Chitin as a linear aminopolysaccharide to be found as skeletal scaffold in broad variety of fungi, protists, diatoms and invertebrates species, ²⁶ is one of the most abundant biopolymer on earth after cellulose. This biopolymer has been proven to be an extremely promising material because of its many advantageous characteristics such as biodegradability, biocompatibility, excellent chelation behavior, and the least toxicity.²⁷ Chitin composed of 2-acetamide-2-deoxy-Dglucopyranose, has highly crystalline structure due to strong hydrogen bonding of two hydroxyl and an acetamide groups in its linear structure. In addition, it has been found that hydroxyl groups and N-acetyl amide group in the glucose ring of chitin have the excellent chelation capacity with metal ions.²⁸

Other important feature of this biopolymer is high thermal stability up to 360 °C. Literature survey shows that chitin is a stable biopolymer under common hydrothermal conditions and could be effectively used as a scaffold for hydrothermal mineral deposition.

^{a.} Department of Chemistry, Faculty of Sciences, Ferdowsi University of Mashhad, Mashhad 9177948974, Iran.

^{*} E-mail: akhlaghinia@um.ac.ir, Tel.: +98-51-3880-5527.

⁺ Footnotes relating to the title and/or authors should appear here.

Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x

DOI: 10.1039/C6RA07252F

In this regard, there have been a variety of reports describing the use of chitin as a template for the hydrothermal synthesis of nanocrystals such as ZnO, ZrO_2 , SiO₂, and Fe₂O₃ (hematite), GeO₂.²⁹⁻³³

Recently, the chemistry of heterocycles has acquired immense importance. Among this, 5-substituted-1*H*-tetrazoles which represent an important class of heterocyclic compounds have attracted great attention in recent years due to their wide range of applications. Most important applications of these compounds include their use in pharmaceuticals, material sciences, coordination chemistry and recognized as a useful intermediate in synthetic organic chemistry.³⁴⁻³⁸ Up to now, numerous methods have been reported for the preparation of 5-substituted-1*H*tetrazoles in the presence of various reactants and catalysts,³⁹⁻⁴³ but each has its own disadvantage, such as the use of strong Lewis acids, expensive reagents, longer reaction times, tedious separation procedures and use of large amount of toxic solvents. Therefore, it is of great practical importance to develop a more efficient and environmentally benign method that avoids these drawbacks.

Consequently, due to our interest towards the extension of environmentally friendly methods for the synthesis of tetrazoles⁴⁴⁻⁴⁷ and based on our previous experience in this respect (that hydrogen bonding of chitin could be catalyzed this cycloaddition reaction),⁴⁶ we decided to prepare and characterize magnetitechitin nanocatalyst as a novel, green and recyclable heterogeneous catalyst (Scheme 1). Then synthesis of tetrazoles *via* reaction between nitriles and azide ion was examined in solvent free condition. 1-Butyl-3-methylimidazolium azide [bmim][N₃] was used as the azide ion source in the present study. The results showed that magnetite-chitin nanocatalyst is highly efficient in this cycloaddition reaction, and it can be easily separated from the reaction mixture.

2. Experimental

Published on 24 March 2016. Downloaded by Gazi Universitesi on 26/03/2016 13:20:09

2.1. Chemicals and instruments

All chemical reagents and solvents were purchased from Merck and Sigma-Aldrich chemical companies and were used as received without further purification. Chitin was extracted from cuttlebone which was taken out from cuttlefish (*Sepia esculenta*).⁴⁶ It is commonly found in saltwater beaches like Persian Gulf in Iran.

The purity determinations of the products were accomplished by TLC on silica gel polygram STL G/UV 254 plates. The melting points of products were determined with an Electrothermal Type 9100 melting point apparatus. The FTIR spectra were provided on pressed KBr pellets using an AVATAR 370 FT-IR spectrometer (Therma Nicolet spectrometer, USA) at room temperature in the range between 4000 and 400 cm⁻¹. The NMR spectra were obtained in Brucker Avance 100, 300 and 400 MHz instruments in CDCl₃,



DMSO-d₆ and CD₃CN. Elemental analysis was performed using a Thermo Finnigan Flash EA 1112 Series instrument. Mass spectra were recorded with a CH7A Varianmat Bremem instrument at 70 eV electron impact ionization, in m/z (rel %). TGA analysis was carried out on a Shimadzu Thermogavimetric Analyzer (TG-50) in the temperature range of 25-900 °C at a heating rate of 10 °C /min under air atmosphere. Transmission electron microscopy (TEM) was performed with a Leo 912 AB microscope (Zeiss, Germany) with an accelerating voltage of 120 kV. SEM images were also recorded using Leo 1450 VP scanning electron microscope operating at an acceleration voltage 20 kV. The crystal structure of catalyst was analyzed by XRD using a D8 ADVANCE-Bruker diffractometer operated at 40 kV and 30 mA utilizing CuKa radiation (λ = 0.154 A°). The magnetic property of catalyst was measured using a vibrating sample magnetometer (VSM, 7400 Lake Shore). Inductively-coupled plasma mass spectrometry (ICP-MS) was carried out on a Varian Australia. All of the products were known compounds and they were characterized by the FT-IR spectroscopy, ¹H NMR, ¹³C NMR spectroscopy, and mass spectrometry and comparison of their melting points with known compounds.

2.2. Extraction of ß-chitin from cuttlebone

Published on 24 March 2016. Downloaded by Gazi Universitesi on 26/03/2016 13:20:09

A cuttlebone (\approx 15 g) was cut into 1 × 1 cm pieces and soaked for 12 h in 500 mL of 2 M HCl under low vacuum. A low vacuum was used to exclude CO₂ bubbles, which formed during dissolution of the aragonite component, from the internal chambers of the organic matrix. The procedure was repeated overnight in fresh aqueous 2 M HCl. The pieces were then washed with distilled water until neutral pH and added to 500 mL of 1 M NaOH at a boiling temperature for 4 h to remove associated proteins. The samples were filtered, washed with copious amounts of water, and added to 95% ethanol for 3 h, followed by further washing with distilled water. The organic matrix was stored in water at 4 °C.^{27a}

2.3. Hydrothermal synthesis of the Fe_3O_4 @chitin

Into a three-necked 500 mL round-bottom flask equipped with argon gas inlet tube and dropping funnel, 2 g of chitin was dispersed in 150 mL of deionized water. Then, $FeCl_3.6H_2O$ (46 mmol, 12.4 g) and $FeSO_4.7H_2O$ (23 mmol, 6.3 g) were added to the white suspension. The resulting mixture was mechanically stirred for 3 min at room temperature under Ar atmosphere. Consequently, 20 mL ammonium hydroxide (25%) was dropped very slowly into the mixture under vigorous stirring. The resulting black mixture was continuously stirred for 5 h at 75 °C under Ar atmosphere. Finally, the mixture was permitted to cool at room temperature and Fe₃O₄@chitin nanoparticles were separated by an external magnet and washed with deionized water several times before being dried under vacuo at 50 °C overnight.

2.4. Synthesis of 1-butyl-3-methylimidazolium chloride

1-Chlorobutane (10.8 g, 0.8 mol) was added to 1-methyimidizole (8.2 g, 0.1 mol), in a round bottomed fask equipped with a reflux condenser. The mixture was stirred at 70 °C for 48 h. After formation of two phases, the top layer which contains unreacted starting material was decanted. Then ethyl acetate (30 mL) was added with entire mixing followed by its decantation and this step was repeated three times. After the third decanting of ethyl acetate, remaining solvent was removed by heating at 70 °C. The obtained pale yellow liquid was vacuum distilled and the resulting 1-butyl-3-methylimidazolium chloride was placed for vacuum drying at 80 °C in a vacuum drying oven.⁴⁸

2.5. Synthesis of 1-butyl-3-methylimidazolium azide

Freshly prepared 1-butyl-3-methylimidazolium chloride (3.49 g, 20 mmol) and NaN₃ (1.30 g, 20 mmol) were added into 25 mL deionized water, and the mixture was stirred for 24 h at room temperature. The solvent was removed under reduced pressure at 50°C. To separate 1-butyl-3 methylimidazolium azide from the crude product (which contains azide ionic liquid and NaCl), the resulting mixture was washed with acetonitrile (3 ×10 mL).

The remaining acetonitrile was removed under high vacuum to yield yellow transparent liquid that became more viscous upon extensive drying. Isolated yield was 92% (3.33 g).⁴⁹

2.6. Typical procedure for synthesis of 5-phenyl-1H-tetrazole in the presence of the $Fe_3O_4@chitin$



DOI: 10.1039/C6RA07252F

ARTICLE

Fig. 1 FT-IR spectra of (a) Chitin and (b) Fe₃O₄@chitin.

A mixture of benzonitrile (0.103 g, 1 mmol) and [bmim][N₃] (0.216 g, 1.2 mmol) in the presence of 0.03 g of Fe₃O₄@chitin was stirred at 110 $^{\circ}$ C. The progress of the reaction was monitored by TLC. When the reaction was completed, the catalyst was removed magnetically and then 10 mL HCl (4 N) was added to the resulting solution. Finally, the obtained aqueous solution was extracted with ethyl acetate (2 × 10 mL) and the combined organic phase was washed with distilled water (2 × 20 mL), dried over anhydrous sodium sulfate and concentrated to obtain the the white precipitate. The crude 5-phenyl-1*H*-tetrazole was recrystallized from *n*-hexane / ethylacetate (1 : 1) obtaining 0.1386 g of colourless crystals (95% yield).

3. Results and Discussion

3.1. Characterization of catalyst

The Fe₃O₄@chitin as a magnetically heterogeneous nanocatalyst was prepared by hydrothermal method which consists of the reaction between Fe²⁺ and Fe³⁺ ions and NH₄OH in the presence of chitin (see Scheme 1). The composition of the synthesized nanocatalyst was analyzed by some technical methods such as Fourier transform infrared (FT-IR) spectroscopy, X-ray diffraction (XRD), transmission electron microscopy (TEM), scanning electron microscopy (SEM), energy-dispersive X-ray spectroscopy (EDX), thermogravimetric analysis (TGA) and vibrating sample magnetometry (VSM).

FT-IR spectroscopy is an appropriate technique to identify surface chemical structure of nanocatalyst. The FT-IR spectra of chitin as well as the magnetite-chitin nanocatalyst in the range of 4000–400 cm⁻¹ have been depicted in Fig. 1a and 1b respectively. The FT-IR spectrum of chitin was established by the following absorption bands: O–H and N–H stretching vibrations around 3460-3250 cm⁻¹, C–H stretching vibrations at 2977 and 2870 cm⁻¹, N–H bending vibrations at 1680 cm⁻¹. Furthermore, the specific amide bonds were detected at 1662 cm⁻¹ (amide I), 1550 cm⁻¹ (amide II) and 1315 cm⁻¹ (amide III). The intense band located at 1475 cm⁻¹ (C–N stretching vibrations) and the broad bands ranging from 1160 to 1010 cm⁻¹ (C–O–C and C–O stretching vibrations) are indicative of chitin. In addition, the other strong chitin band at 860 cm⁻¹

ARTICLE

(related to $-\text{CH}_3$ in acetylamide groups) can be clearly observed in Fig. 1a. 50

The FT-IR spectrum of Fe₃O₄@chitin was shown as Fig. 1b. As can be seen, the presence of Fe_3O_4 nanoparticles was confirmed by detecting absorption band at around 603 cm⁻¹ which corresponding to the Fe-O stretching bond of magnetite nanoparticles.⁵¹ On the other hand, although the all characteristic bands of chitin were present in the FT-IR spectrum of nanocatalyst but some of them exhibited noticeable changes.⁵² For instance, after incorporation of magnetite in the chitin matrix, hydroxyl and acetyl groups frequencies (which related to absorption bands appearing around 3460 and 3250 cm^{-1} in chitin) shifted to 3420 and 3260 cm^{-1} in Fe₃O₄@chitin, respectively. Its occurrence may indicate an interaction between the ${\sf Fe_3O_4}$ nanoparticles and the –OH and –NH stretching vibration of chitin. Splitting of the absorption bands at 1620 (amide I) and 1550 cm $^{-1}$ (amide II) (due to -NH bending vibrations) and 857-876 cm⁻¹ (-CH₃ in acetylamide groups) also confirmed these interactions. Thus, overall the observation revealed that Fe₃O₄@chitin as a green nanocatalyst was successfully synthesized *via* an environmentally friendly process.

Also, XRD analysis was applied to detect the crystallinity of the synthesized nanocatalyst (Fig. 2). As shown in Fig. 2a, the characteristic peaks with strong intensities appeared at angles corresponding to (2, 2, 0), (3, 1, 1), (4, 0, 0), (4, 2, 2), (5, 1, 1) and (4, 4, 0) reflections were in good agreement with the standard pattern for crystalline magnetite with cubic structure (JCPDS 19-0629).⁵³ Moreover, in comparison with the standard pattern of pure Fe₃O₄ MNPs, two additional small and weak peaks (at 9.6 and 19.6 angles) were found in the XRD pattern of Fe₃O₄@chitin which could be attributed to the characteristic peaks of chitin (Fig. 2b).⁵⁴



Fig. 2 The XRD patterns of (a) Chitin and (b) Fe₃O₄@chitin.

This fact suggested that the coating process did not result in the phase change of Fe_3O_4 nanoparticles.

To elucidate the morphology and size of the synthesized nanocatalyst, Fe_3O_4 @chitin was analyzed by SEM and TEM (Fig. 3). It is evident from SEM image (Fig. 3a) that the shape of Fe_3O_4 @chitin nanocatalyst is not clearly defined, however, synthesized nanocatalyst is well dispersed. The TEM micrograph of the Fe_3O_4 @chitin shown in Fig. 3b revealed that the synthesized nanoparticles existed as cubicles with a mean edge length of 25 nm and were nearly monodisperse.⁵⁵ Obtained results indicated that the presence of chitin during the synthesis of Fe_3O_4 nanoparticles, leads to improvement of the nanoparticles size and distribution. Energy-dispersive X-ray analysis (EDX), indicated the presence of C, O and Fe elements (Fig. 4), which further supported the conclusion that Fe_3O_4 nanoparticles have been synthesized successfully in the presence of chitin.

Thermogravimetric analysis (TGA) of the Fe₃O₄@chitin was also used to determine the content of organic materials of the nanocatalyst, as shown in Fig. 5. Upon heating, Fe₃O₄@chitin showed a weight loss of about 6.24 % at temperatures ranging from 50 to 140 °C, mainly due to the loss of water, because polysaccharides usually have a strong affinity for water and therefore may be easily hydrated. The second weight loss (3.02 % in the range of 160–340 °C) was attributed to the partial decomposition of chitin chain. After that, there was a significant weight loss (about 9.01 %) from 350 °C to 650 °C corresponding to the complete decomposition of biopolymer backbone. In comparison with literature,^{27b, 29-33} it can be concluded that chitin has somehow greater stability due to interaction with Fe₃O₄ nanoparticles.

The magnetic property of Fe₃O₄@chitin, which was critical to ensure its application, was measured using VSM. The hysteresis loop of synthesized nanocatalyst is shown in Fig. 6. The results of VSM showed that the magnetic saturation value of Fe₃O₄@chitin was 32.5 em μ ·g⁻¹, which was lower than the reference value for pure Fe₃O₄ MNPs.⁵³ It may be ascribed to the cover of chitin polymeric matrix on the surface of magnetic Fe₃O₄ MNPs. Moreover, it is clearly seen from this figure that no remanence and coercivity was observed, which indicated that the nanoparticles obtained in this study are superparamagnetic. These magnetic properties allow easily and quickly separation of the nanocatalyst from the reaction mixture with the help of an external magnet. Published on 24 March 2016. Downloaded by Gazi Universitesi on 26/03/2016 13:20:09.

S RSC Advances (Sin

Journal Name

ARTICLE

Fig. 3 (a) SEM image of $Fe_3O_4@$ chitin, (b) TEM image of $Fe_3O_4@$ chitin.







Fig. 5 TGA thermogram of Fe₃O₄@chitin.



Fig. 6 (a) Magnetization curve of Fe_3O_4 @chitin (b) Separation of nanocatalyst using an external magnet.

3.2. Catalytic synthesis of 5-substituted-1H-tetrazoles

Recently, we reported an efficient and green synthesis of 5substituted-1H-tetrazoles from organic nitriles and azide ion using highly porous expanded perlite as a natural heterogeneous catalyst in high yields.⁴⁷ Accordingly, 1-butyl-3-methylimidazolium azide ([bmim][N₃]) ionic liquid was used as an azide ion source instead of the highly toxic reagents such as NaN₃ or TMSN₃. Also, the cycloaddition reaction was performed in solvent free condition that in comparison with the most reported literature, it was very ecofriendly procedure. These advantages become even more attractive if such reactions can be catalyzed by using easily recyclable catalyst such as magnetic nanoparticles. Hence, according to our previous experience and in order to extend the range of high efficient heterogeneous catalyst, we now report a new method for the preparation of 5-substituted-1H-tetrazoles via reaction between a wide variety of nitriles and [bmim][N₃] as an azide source in solvent free condition by using Fe_3O_4 @chitin as a simple, green, and recyclable catalyst (Scheme 2).

To obtain the best conditions for the synthesis of 5-substituted-1*H*-tetrazoles, initial studies were performed upon the reaction of benzonitrile with 1-butyl-3-methylimidazolium azide as a model reaction and the effects of different conditions were investigated for this reaction (Table 1). According to Table 1, when the model reaction was performed under catalyst-free conditions at 100 °C, the desired product was obtained in low yield (Table 1, entry 1), whereas, using 0.03 g of Fe₃O₄@chitin in [3 + 2] cycloaddition reaction as a nanocatalyst afforded high yield of the product (90%) in short reaction time (20 min) (Table 1, entry 2). To study the effect of different molar ratios of reactants, [3 + 2] cycloaddition reaction was performed with different molar ratios of benzontrile / [bmim][N₃] (Table 1, entries 2, 3 and 4). As shown, increasing the Published on 24 March 2016. Downloaded by Gazi Universitesi on 26/03/2016 13:20:09.

DOI: 10.1039/C6RA07252F Journal Name



Scheme 2 Synthesis of 5-substituted-1*H*-tetrazoles in the presence of Fe_3O_4 @chitin under solvent-free conditions.

amount of $[bmim][N_3]$ was found to have no effect on the yield (90%) of [3 + 2] cycloaddition reaction. In contrast, decreasing the amount of $[bmim][N_3]$ dropped down the yield reaction a lot. The effect of temperature on the reaction was also evaluated (Table 1, entries 5, 6). The best result was achieved by carrying out the reaction at 110 $^{\circ}\text{C},$ affording 95 % of 5-phenyl 1H- tetrazole in 20 min. Different amount of the catalyst (0.035, 0.03 and 0.02 g) was also optimized and it was found that 0.03 g of catalyst gave the maximum yield of the product (Table 1, entries 7, 8). An increase in the amount of catalyst did not improve the results to any great extent. However using 0.02 g of catalyst could not provide satisfactory yield. Comprehensively, the optimum reaction conditions for synthesis of 5-phenyl-H-tetrazole were as follows: 1 : 1.2 molar ratio of reactants at 110 °C in the presence of 0.03 g of Fe₃O₄@chitin as catalyst, under solvent free conditions. Consequently, we checked the effect of Fe₃O₄ nanoparticles and chitin on the [3 + 2] cycloaddition reaction, by carrying out the reaction under the optimized reaction conditions, separately (Table 1, entries 9 and 10). It was observed that, by using 0.03 g of Fe_3O_4 nanoparticles as catalyst, the desired product was obtained in low yield and in long reaction time (50 %, 1h), while, the same reaction in the presence of 0.03 g chitin gave admirable yield (70 %) in short reaction time (30 min) (Table 1, entry 10). In comparison with catalytic performance of Fe₃O₄@chitin (95% yield in 20 min vs 70 % in 30 min), it could be concluded that Lewis acidity of Fe₃O₄ nanoparticles may promote the [3 + 2] cycloaddition reaction.⁵⁶ However, it should be mentioned that the aim of supporting chitin on the surface of magnetic nanoparticles was its easy magnetically separation, its recovery and its reusability.

To assess the efficiency and scope of the present methodology, various 5-substituted-1-H-tetrazoles were synthesized by the [3 + 2] cycloaddition reaction between a wide range of structurally divergent nitriles and [bmim][N₃] in presence of Fe₃O₄@chitin under the optimized reaction conditions. The representative results are summarized in Table 2. Generally, the aromatic nitriles containing electron withdrawing and electron-donating substituent were well tolerated under the reaction conditions and gave the corresponding tetrazoles in good to excellent yields. However, as it is shown in Table 2, reactions of electron poor nitrile compounds were completed within a short reaction time, whereas electron rich nitriles required more reaction time to proceed properly (compare entries 1-5 with entries 6-11). So, it can be concluded that the electronic character of substituents on the aromatic rings of the nitriles had a noteworthy effect on the efficiency of the reaction which demonstrated that electron donating substituents on aromatic rings decrease the electrophilic character of nitrile. In the same way, the reaction was examined using phenanthrene-9carbonitrile in which the desired product was obtained in good yield, although longer reaction time was required which may be due to the steric hindrance (Table 2 entry 12).

Table 1 Optimization of various reaction parameters for the synthesis of 5-phenyl-1H-tetrazole

Entry	Molarratio (Benzontrile/[bmim][N ₃])	Catalyst (g)	Temperature (°C)	Time (min)	Isolated yield (%)
1	1:1.2	-	100	1(h)	10
2	1:1.5	0.03	100	20	90
3	1:1.2	0.03	100	20	90
4	1:1	0.03	100	20	70
5	1:1.2	0.03	120	20	95
6	1:1.2	0.03	110	20	95
7	1:1.2	0.02	110	20	85
8	1:1.2	0.035	110	20	95
9 ^{<i>a</i>}	1:1.2	0.03	110	1(h)	50
10^{b}	1:1.2	0.03	110	30	70

^{*a*} The reaction was performed in the presence of Fe_3O_4 NPs. ^{*b*} The reaction was performed in the presence of chitin.

Published on 24 March 2016. Downloaded by Gazi Universitesi on 26/03/2016 13:20:09.

Journal Name

ARTICLE

Furthermore, when heteroaromatic nitriles such as thiophene-2carbonitrile, 4-pyridinecarbonitrile and 2-pyridinecarbonitrile were used as substrate, due to the strong electron withdrawing effect of the heteroatoms, excellent yields of the corresponding 5substituted-1-*H*-tetrazoles were obtained in a short reaction time (Table 2 entries 13, 14 and 15). It is noteworthy that not only aromatic nitriles but also aliphatic ones could also be employed to afford the desired products in admirable yields (Table 2 entries 16, 17 and 18). These results demonstrated the superior properties of Fe₃O₄@chitin as an eco-friendly and effective heterogeneous catalysts for the synthesis of 5-substituted-1-*H*-tetrazoles by [3 + 2] cycloaddition from nitriles and [bmim][N₃].

Table 2 Synthesis of different structurally 5-substituted-1*H*-tetrazoles in the presence of Fe₃O₄@chitin under solvent-free condition.



Entry	R	Product	Time (min)	lsolated Yield (%)
1	C ₆ H ₅	N N N N N N N N N N N N N N N N N N N	20	95
2	4-BrC ₆ H ₄		30	90
3	4-CIC ₆ H ₄		20	95
4	4-NO ₂ C ₆ H ₄		15	98
5	4-CNC ₆ H ₄		15	95

ARTICLE

Page 8 of 13

DOI: 10.1039/C6RA07252F Journal Name

w Article O



RSC Advances Accepted Manuscript

8 | J. Name., 2012, 00, 1-3

This journal is © The Royal Society of Chemistry 20xx



In order to establish the structure of synthesized tetrazoles, their melting points were initially compared with the known compounds. The data were found to be in good agreement with expected values. Then to further elucidate the structure of these compounds, spectroscopic methods such as FT-IR spectroscopy, mass spectrometry, ¹H NMR and ¹³C NMR spectroscopy were recorded. Key features in the FT-IR spectra of the products include the absorption bands at: $3485-3329 \text{ cm}^{-1}$ (related to the N–H stretching vibration), $1469-1430 \text{ cm}^{-1}$ (due to scissoring bending C–H), $1293-1233 \text{ cm}^{-1}$ (due to N–N=N–), 1189-1110 and $1106-1041 \text{ cm}^{-1}$ (due to tetrazole ring). Also, in ¹HNMR and ¹³C NMR spectra, a signal at 10.98-7.80 and 164-151 ppm which correspond to the NH and quaternary carbon NH–C=N, respectively, can be beneficial for further confirming the structure of desired products.

The catalytic activity of Fe_3O_4 @chitin in [3 + 2] cycloaddition reaction was proved by the fact that a long reaction time and comparatively lower yield of product was observed when the model reaction was carried out in absence of Fe_3O_4 @chitin which do not afford formation of desired product (Table 2, entry 1). Based on the literature, as well as our findings, plausible reaction pathway is shown in Scheme 3.^{46, 57} Initially, we assume that nitrile functionality is activated through hydrogen bond formation between nanocatalyst hydroxyls and nitrogen atom of nitrile group, so facilitate the attack of azide ion which leads to the formation of intermediate I. In the next step, the intermediate II is afforded from the [3 + 2] cycloaddition reaction between activated nitrile and azide ion. At last, protonolysis of the intermediate II by HCI (4 N) causes to produce III and IV. However, the more stable tautomer IV is achieved due to the equilibrium (5-substituted 1*H*-tetrazole). The

Published on 24 March 2016. Downloaded by Gazi Universitesi on 26/03/2016 13:20:09.

RSC Advances

Page 10 of 13

DOI: 10.1039/C6RA07252F Journal Name

nanocatalyst re-enters to the catalytic cycle by making the active sites for further turnovers.

ARTICLE

One of the main advantages associated with supporting a catalyst onto Fe₃O₄ MNPs is the possibility of recovery by simple magnetic decantation and reuse without loss of activity. So, in relevance with this, the activity of the recycled catalyst was examined using the reaction of benzonitrile and [bmim][N₃] under the optimized conditions. In order to regenerate the nanocatalyst, upon completion of reaction, it was separated magnetically and washed several times with deionized water and ethyl acetate to remove residual compounds. The resultant nanocatalyst was dried at 50 °C under vacuum, and reused for subsequent runs. As shown in Fig. 7, the recycled catalyst could be reused up to six runs without any noteworthy loss of activity, which demonstrates the practical recyclability of the synthesized nanocatalyst. Moreover, in order to investigate the amount of Fe leaching in these reactions, after magnetically separation of the nanocatalyst, the resulting mixture was analyzed by ICP-MS before and after the six cycles. The results showed the absence of Fe in the first run, while a very small amount of Fe (0.0021 mmol) was detected after six runs. It indicates that 95 % of the nanocatalyst could be recovered in this method.

In addition, a comparative study of the reported methods in the literature on [3 + 2] cycloaddition reaction was compiled in Table 3 to highlight the advantages of this nanocatalyst. Table 3 clearly demonstrates that lower temperature and shorter reaction time were required for this cycloaddition reaction, while, several of the previously reported procedures did not provide these conditions.⁵⁸⁻⁶² However, recently, we have been succeeded to perform this [3 + 2] cycloaddition reaction in a very short time by applying new natural heterogeneous catalyst.^{46, 47} Similarly, the catalytic system

natural heterogeneous catalyst.^{4b, 47} Similarly, the catalytic system presented in the present study offers excellent yields in short reaction times with the difference that the Fe₃O₄@chitin can be easily separated from the reaction mixture by using an external magnet.



Scheme 3 Plausible mechanism for the formation of 5-substituted-1*H*-tetrazoles in presence of Fe_3O_4 @chitin.





Additionally, this nanocatalyst promoted the synthesis of 5-substituted-1*H*-tetrazole in solvent-free conditions instead of toxic solvents, which follows along the line of green chemistry.

4. Conclusions

In summary, with the aim of have a good contribution in innovation of green chemistry, we have reported an operationally simple, clean and highly efficient procedure for the synthesis of 5-substituted-1Htetrazoles using Fe₃O₄@chitin nanocatalyst in a green media. As a novel and eco-friendly heterogeneous catalyst, Fe₃O₄@chitin was easily prepared and characterized by spectroscopic, magnetic and thermal techniques (TEM, SEM, FT-IR, XRD, VSM and TGA). The ultimate material was found to be Fe₃O₄@chitin nanocatalyst with a mean edge length of 25 nm, cubic shape, and strong magnetic property. Then synthesized nanocatalyst has been used as an efficient catalyst for the preparation of various 5-substituted-1-Htetrazoles via reaction between nitriles and [bmim][N₃] as the azide ion source under solvent-free condition. Excellent results were obtained in each case affording the corresponding tetrazoles in short reaction times and high yields. Furthermore, this process avoids problems associated with organic solvent and toxic reagent use, which makes it a useful and attractive protocol in view of the economic and environmental advantages. Apart from this, simplicity of product separation and effortless reusability of nanocatalyst are the important features of this method.

Acknowledgements

The authors gratefully acknowledge the partial support of this study by Ferdowsi University of Mashhad Research Council (Grant no. p/3/29760).

10 | J. Name., 2012, 00, 1-3

Journal Name

Table 3 Comparison between efficiency of Fe₃O₄@chitin and some other catalysts for the synthesis of 5-phenyl-1H-tetrazole.

Entry	Catalyst	Solvent	Temperature (°C)	Time (h)	Yield (%)
1	Fe₃O₄@SiO₂/Salen Cu(II) ⁵⁸	DMF	120	7	90
2	CuFe ₂ O ₄ ⁵⁹	DMF	120	12	82
3	Ag NPs ⁶⁰	DMF	120	8	92
4	Cyanuric chloride 61	DMF	120	2	90
5	CAN/HY-Zeolite ⁶²	DMF	110	4	93
6	CuSO ₄ .5H ₂ O ⁴⁴	DMSO	140	1	98
7	CAES 45	DMSO	130	1	95
8	Cuttlebone 46	DMSO	120	20 (min)	98
9	Expanded Perlite 47	Solvent-free	110	10 (min)	95
10	Fe ₃ O ₄ @chitin	Solvent-free	110	20 (min)	95

Notes and references

- 1 A. Benhammou, A. Yaacoubi, L. Nibou and B. Tanouti, J. Colloid. Interf. Sci., 2005, **282**, 320.
- 2 M. Prasad and S. Saxena, Ind. Eng. Chem. Res., 2004, 43, 1512.
- 3 C. C. Liu, M. K. Wang and Y. S. Li, *Ind. Eng. Chem. Res.*, 2005, **44**, 1438.
- 4 A. Özcan, A. S. Özcan, S. Tunali, T. Akar and I. Kiran, J. Hazard. Mater., 2005, **124**, 200.
- 5 G. F. Goya, T. S. Berquo and F. C. Fonseca, *J. Appl. Phys.*, 2003, **94**, 3520.
- S. Chikazumi, S. Taketomi, M. Ukita, M. Mizukami, H. Miyajima, M. Setogawa and Y. Kurihara, J. Magn. Magn. Mater., 1987, 65, 245.
- 7 Y. M. Huh, Y. W. Jun, H. T. Song, S. Kim, J. S. Choi, J. H. Lee, S. Yoon, K. S. Kim, J. S Shin, J. S. Suh and J. Cheon, *J. Am. Chem. Soc.*, 2005, **127**, 12387.
- 8 (a) Q. A. Pankhurst, *BT Technol. J.*, 2006, **24**, 33; (b) Z. P. Xu, Q. H. Zeng, G. Q. Lu and A. B. Yu, *Chem. Eng. Sci.*, 2006, **61**, 1027.
 9 D. L. Huber, *Small*, 2005, **1**, 482.
- 10 M. Ma, Q. Zhang, D. Yin, J. Dou, H. Zhang and H. Xu, *Catal. Commun.*, 2012, **17**, 168.
- 11 F. Zamani and S. M. Hosseini, Catal. Commun., 2014, 43, 164.
- 12 Y. Q. Zhang, X. W. Wei and R. Yu, *Catal Lett.*, 2010, **135**, 256.
- 13 M. B. Gawande, P. S. Brancoa and R. S. Varma, *Chem. Soc. Rev.*, 2013, **42**, 3371.
- 14 Z. Wang, P. Xiao, B. Shen and N. He, *Colloids Surf.*, A: *Physicochem. Eng. Aspects*, 2006, **276**, 116.
- 15 V. Polshettiwar, B. Baruwati and R. S. Varma, *Green Chem.*, 2009, **11**, 127.
- W. Zhang, X. Chen, T. Tang and E. Mijowska, Nanoscale, 2014, 6, 12884.
- 17 Y. Liu, M. Chen and Y. Hao, Chem. Eng. J., 2013, 218, 46.
- 18 R. Hudson, Y. Feng, R. S. Varmab and A. Moores, *Green Chem.*, 2014, **16**, 4493.
- 19 C. Amatore, S. Bensalen, S. Ghalem and A. Jutand, J. Organomet. Chem., 2004, 689, 4642.

- 20 C. Amatore and A. Jutand, J. Organomet. Chem., 1999, **576**, 254.
- 21 A. Schatz, M. Hager and O. Reiser, *Adv. Funct. Mater.*, 2009, **19**, 2109.
- 22 Z. Zarnegar and J. Safari, RSC Adv., 2014, 4, 20932.
- 23 G. Li, Y. Jiang, K. Huang, P. Ding, J. Chen, J. Alloys Compd., 2008, 466, 451.
- 24 M. R. Shushizadeh, E. Moghimi Pour, A. Zare and Z. Lashkari, *Bioactive Carbohydrates and Dietary Fibre*, 2015, **6**, 133.
- 25 B. Duan, F. Liu, M. He and L. Zhang, Green Chem., 2014, 16, 2835.
- (a) S. Hajji, I. Younes, O. Ghorbel-Bellaaj, R. Hajji, M. Rinaudo, M. Nasri and K. Jellouli, *Int. J. Biol. Macromol.*, 2014, 65, 298.
 (b) E. Brunner, P. Richthammer, H. Ehrlich, S. Paasch, P. Simon, S. Ueberlein, and K. H. Pe'e, *Angew. Chem. Int. Ed.*, 2009, 48, 9724.
 (c) H. Ehrlich, P. Simon, W. Carrillo-Cabrera, V. V. Bazhenov, J. P. Botting, M. Ilan, A. V. Ereskovsky, G. Muricy, H. Worch, A. Mensch, R. Born, A. Springer, K. Kummer, D. V. Vyalikh, S. L. Molodtsov, D. Kurek, M. Kammer, S. Paasch and E. Brunner, *Chem. Mater.*, 2010, 22, 1462; (d) H. Ehrlich, *Int. Geol. Rev.*, 2010, 52, 661.
- 27 (a) W. Ogasawara, W. Shenton, S. A. Davis and S. Mann, *Chem. Mater.*, 2000, **12**, 2835; (b) F. A. Al Sagheer, M. A. Al-Sughayer, S. Muslim and M. Z. Elsabee, *Carbohydr. Polym.*, 2009, **77**, 410.
- 28 (a) A. M. tsuoka, T. Isogawa, Y. Morioka, B. R. Knappett, A. E. H. Wheatley, S. Saito and H. Naka, *RSC Adv.*, 2015, **5**, 12152; (b) V. Q. Nguyen, M. Ishihara, S. Nakamura, H. Hattori, T. Ono, Y. Miyahira and T. Matsui, *J. Nanomater.*, 2013, **2013**, 1.
- 29 H. Ehrlich, P. Simon, M. Motylenko, M. Wysokowski, V. V. Bazhenov, R. Galli, A. L. Stelling, D. Stawski, M. Ilan, H. Stocker, B. Abendroth, R. Born, T. Jesionowski, K. J. Kurzydłowskii and D. C. Meyer, *J. Mater. Chem. B.*, 2013, 1, 5092.
- 30 M. Wysokowski, I. Petrenko, A. L. Stelling, D. Stawski, T. Jesionowski and H. Ehrlich, *Polymers*, 2015, 7, 235.
- M. Wysokowski, M. Motylenko, J. Walter, G. Lota, J. Wojciechowski, H. Stöcker, R. Galli, A. L. Stelling, C. Himcinschi, E. Niederschlag, E. Langer, V. V. Bazhenov, T. Szatkowski, J. Zdarta, I. Pertenko, Z. Kljajić, T. Leisegang, S. L. Molodtsov, D.

RSC Advances Accepted Manuscript

DOI: 10.1039/C6RA07252F

Journal Name

C. Meyer, T. Jesionowski, and H. Ehrlich, RSC Adv., 2014, 4, 61743

- 32 M. Wysokowski, M. Motylenko, J. Beyer, A. Makarova, H. Stöcker, J. Walter, R. Galli, S. Kaiser, D. Vyalikh, V. V. Bazhenov, I. Petrenko, A. L. Stelling, S. L. Molodtsov, D. Stawski, K. J. Kurzydłowski, E. Langer, M. V. Tsurkan, T. Jesionowski, J. Heitmann, D. C. Meyer, H. Ehrlich, Nano Res., 2015, 8, 2288.
- 33 M. Wysokowski, M. Motylenko, V. V. Bazhenov, D. Stawski, I. Petrenko, A. Ehrlich, T. Behm, Z. Kljajic, A. L. Stelling, T. Jesionowski, and H. Ehrlich, Front. Mater. Sci., 2013, 7, 248
- (a) A. R. Katritzky, B. V. Rogovoy and K. V. Kovalenko, J. Org. 34 Chem., 2003, 68, 4941; (b) M. L. Kantam, K. B. S. Kumar and K. P. Raja, J. Mol. Catal. A: Chem., 2006, 247, 186.
- 35 (a) S. J. Wittenberger, Recent development in tetrazole chemistry: A review. Org. Prep. Proced. Int. 1994, 26, 499; (b) N. P. Gaponik, S. V.Voitekhovich and O. A. Ivashkevich, Russ. Chem. Rev. 2006, 75, 507.
- (a) R. J. Herr, Bioorg. Med. Chem. 2002, 10, 3379; (b) L. V. 36 Myznikov, A. Hrabalek and G. I. Koldobskii, Chem. Heterocycl. Compd. 2007, 43, 1; (c) J. Roh, K. Vávrová and A. Hrabálek, Eur. J. Org. Chem., 2012, 2012, 6101; (d) G. I. Koldobskii, Russ. J. Org. Chem., 2006, 42, 487.
- (a) R. N. Butler, in Comprehensive Heterocyclic Chemistry II, ed. 37 A. R. Katritzky, C. W. Rees and E. F. V. Scriven, Pergamon Press, Oxford, 1996, 4, p. 674; (b) R. N. Butler, in Comprehensive Heterocyclic Chemistry II, ed. A. R. Katritzky and C. W. Rees, Pergamon Press, Oxford, 1984, 5, p. 791.
- 38 D. Cantillo, B. Gutmann, and C. O. Kappe, J. Org. Chem., 2012, 77. 10882.
- 39 A. Teimouri and A. Najafi Chermahini, Polyhedron, 2011, 30, 2606.
- 40 D. Kong, Y. Liu, J. Zhang, H. Li, X. Wang, G. Liu, B. Li and Z. Xu, NJC, DOI: 10.1039/c4nj00034j.
- 41 M. Rahman, A. Roy, M. Ghosh, S. Mitra, A. Majee and A. Hajra, RSC Adv., 2014, 4, 6116.
- D. Habibi, M. Nasrollahzadeha and T. A. Kamali, Green Chem., 42 2011. 13. 3499
- 43 U. Yapuri, S. Palle, O. Gudaparthi, S. R. Narahari, D. K. Rawat, K. Mukkanti and J. Vantikommu, Tetrahedron Lett., 2013, 54, 4732.
- 44 B. Akhlaghinia and S. Rezazadeh, J. Braz. Chem. Soc., 2012, 23, 2197.
- 45 N. Razavi and B. Akhlaghinia, RSC Adv., 2015, 5, 12372.
- S. S. E. Ghodsinia and B. Akhlaghinia, RSC Adv., 2015, 5, 49849. 46
- 47 R. Jahanshahi and B. Akhlaghinia, RSC Adv., 2015, 5, 104087.
- P. N. Tshibangu, S. N. Ndwandwe and E. D. Dikio, Int. J. 48 Electrochem. Sci., 2011, 6, 2201.
- 49 H. Valizadeh, M. Amiri and E. Khalili, Mol. Diversity, 2012, 16, 319.
- (a) K. Skołucka-Szary, A. Ramięga, W. Piaskowska, B. Janicki, M, 50 Grala, P. Rieske, Z. Bartczak and S. Piaskowski, Mater. Sci. Eng., C, 2016, 60, 489; (b) H. Ehrlich, M. Krautter, T. Hanke, P. Simon, C. Knieb, S. Heinemann and H. Worch, J. Exp. Zool. (Mol. Dev. Evol.), 2007, 308B, 347.
- 51 J. Zhou, Z. Dong, H. Yang, Z. Shi, X. Zhou and Rong Li, Appl. Surf. Sci., 2013, 279, 360.
- 52 H. Tang, W. Zhou, A. Lu, and L. Zhang, J. Mater. Sci., 2014, 49, 123.
- 53 M. Zarghani and B. Akhlaghinia, Appl. Organomet. Chem., 2015, 29, 683.
- M. Wysokowski, M. Motylenko, H. Stocker, V. V. Bazhenov, E. 54 Langer, A. Dobrowolska, K. Czaczyk, R. Galli, A. L. Stelling, T. Behm, Ł. Klapiszewski, D. A. zewicz, M. Nowacka, S. L. Molodtsov, B. Abendroth, D. C. Meyer, K. J. Kurzydłowski, T. Jesionowskia and H. Ehrlich, J. Mater. Chem. B, 2013, 1, 6469.
- 55 (a) G. Marcelo, A. Muñoz-Bonilla, J. Rodríguez-Hernández and M. Fernández-García, Polym. Chem., 2013, 4, 558; (b) Z. Xu, C. Shen, Y. Tian, X. Shi and H. J. Gao, Nanoscale, 2010, 2, 1027.

- A. O. Dhokte, M. A. Sakhare, M. K. Lande, and B. R. Arbad, J. 56 Korean Chem. Soc., 2013, 57, 73.
- D. R. Patila, Y. B. Wagha, P. G. Ingoleb, K. Singhb and D. S. 57 Dalal, NJC, DOI: 10.1039/C3NJ00569K.
- 58 F. Dehghani, A. R. Sardarian and M. Esmaeilpour, J. Organomet. Chem. 2013, 743, 87.
- 59 M. Abd El Aleem Ali Ali El-Remaily, A. M. Abu-Dief, Tetrahedron, 2015, 71, 2579.
- P. Mani, C. Sharma, S. Kumar and S. K. Awasthi, J. Mol. Catal. A: 60 Chem., 2014, 392, 150.
- P. Sivaguru, P. Theerthagiri and A. Lalitha, Tetrahedron Lett., 61 2015, 56, 2203.
- P. Sivaguru, K. Bhuvaneswari, R. Ramkumar, A. Lalitha, 62 Tetrahedron Lett., 2014, 55, 5683.

Graphical Abstract

Magnetically separable Fe_3O_4 (chitin as an eco-friendly nanocatalyst with high efficiency for

green synthesis of 5-substituted-1*H*-tetrazoles under solvent-free conditions



Monireh Zarghani, Batool Akhlaghinia *

1. Eco-friendly Fe_3O_4 @chitin nanocatalyst was prepared, characterized and applied for synthesis of 5-substituted-1*H*-tetrazoles in a green media.