View Article Online View Journal

# Chemical Science

## Accepted Manuscript

CrossMark

This article can be cited before page numbers have been issued, to do this please use: Y. J. Kim, S. M. Kim, E. J. Cho, H. Hosono, J. W. Yang and S. W. Kim, *Chem. Sci.*, 2015, DOI: 10.1039/C5SC00933B.



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/chemicalscience

## Journal Name

# ARTICLE

Received 00th January 20xx, Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/



Ye Ji Kim, <sup>a,b‡</sup> Sun Min Kim,<sup>a‡</sup> Eun Jin Cho,<sup>c</sup> Hideo Hosono,<sup>d</sup> Jung Woon Yang,<sup>a\*</sup> and Sung Wng Kim<sup>a,b\*</sup>

A simple and highly efficient transfer hydrogenation of alkynes and alkenes by using a two-dimensional electride, dicalcium nitride ( $[Ca_2N]^*e^-$ ), as an electron transfer agent is disclosed. Excellent yields in the transformation are attributed to the remarkable electron transfer efficiency in the electride-mediated reactions. It is clarified that an effective discharge of electrons from the  $[Ca_2N]^*e^-$  electride in alcoholic solvents is achieved by the decomposition of the electride via alcoholysis and the generating ammonia and  $Ca(O'Pr)_2$ . We found that the choice of solvent was crucial for enhancing the electron transfer efficiency of 80% was achieved by using a DMF mixed isopropanol cosolvent system. This is the highest value reported to date among single electron transfer agents in the reduction of C-C multiple bonds. The observed reactivity and efficiency establish that electrides with a high density of anionic electrons can readily participate in the reduction of organic functional groups.

#### Introduction

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.

Access Article. Published on 13 April 2015. Downloaded on 24/04/2015 03:54:21

The development of simple and efficient chemical transformation routes with maximal yields has been a continuously pursued challenge in synthetic chemistry as such protocols can provide important benefits in the field of organic synthesis such as saving starting materials, reagents, and energy, thereby lowering production cost and environmental impacts.<sup>1</sup> Among fundamental reactions in synthetic organic chemistry, the reduction of organic functional groups with carbon-carbon (C-C) multiple bonds is one of the most universally applied and crucial synthetic processes in academic and in industrial circles.<sup>2</sup> The reduction of C-C multiple bonds has been widely used in the synthesis of natural products and pharmaceutical compounds as well as in the petroleum chemistry.<sup>3</sup> The established methods for this are 1) hydrogenation, where hydrogen gases are activated on a transition metal catalysts such as Pt, Ru, Pd, Rh or Ni; and 2) transfer hydrogenation, where hydrogen from source materials is added to a substrate.<sup>4,5</sup> Transfer hydrogenation can be further classified into three kinds of methods based on

<sup>d</sup> Materials and Structure Laboratory, Tokyo Institute of Technology, Yokohama 226-8503, Japan the initiation mode: 1) electron transfer, 2) hydride transfer, and 3) hydrogen atom transfer.<sup>6</sup> Among these reactions, the electron transfer method using an electron donating agent is currently the most classical and general reaction in synthetic chemistry.

For efficient electron transfer hydrogenation, it is essential to use an agent with a high reduction potential to facilitate the electron transfer. In this regard, many types of materials, such as simple metals (Mg and Yb), stabilized alkali metal systems (Na in silica-gel and in ammonia liquid), and lanthanide iodides (Sml<sub>2</sub> and Tml<sub>2</sub>), have been employed in electron transfer hydrogenation.<sup>7</sup> Despite of their effectiveness in the reported transfer hydrogenations, there are several drawbacks in the methodology. Major disadvantages are the toxicity and the cost of agents and rigorous reaction conditions. Furthermore, the separation of products from the resultants is laborious and inefficient, yielding pollutants. Above all these drawbacks, the low electron transfer efficiency of the reaction is the most critical issue to be addressed for efficient transfer hydrogenation. For example, the simple metals show the limited efficiency of 30%. Although moderate electron transfer efficiency in Sml<sub>2</sub>-mediated reactions has been achieved, the use of toxic and rare lanthanide element, and the requirement of additives such as amines are drawbacks to be solved.

In order to achieve simple and efficient electron transfer hydrogenation for C-C multiple bonds, it is necessary to use a strong electron transfer agent and to simplify the reaction process, satisfying the following characteristics. First, the material must have a sufficient reduction potential to effectively transfer the electrons to the C-C multiple bonds. Second, the material must consist of abundant elements to replace the high cost of lanthanides and circumvent the

<sup>&</sup>lt;sup>a</sup> Department of Energy Science, Sungkyunkwan University, Suwon 440-746, Korea. <sup>b</sup> Center for Integrated Nanostructure Physics, Institute for Basic Science,

Sungkyunkwan University, Suwon 440-746, Korea. <sup>c.</sup> Department of Chemistry, Chung-Ang University, Seoul 156-756, Korea.

<sup>&</sup>lt;sup>+</sup> Electronic Supplementary Information (ESI) available: [Experimental details and characterization]. See DOI: 10.1039/x0xx00000x

<sup>&</sup>lt;sup>\*</sup>These authors contributed equally to this work

<sup>\*</sup> Kimsungwng@skku.edu (S. W. K), \* jwyang@skku.edu (J. W. Y)

Table 1. C	ptimization o	f transfer h	ydrogenation	for alkyne	utilizing	$[Ca_2N]^+ \cdot e$

View Article Online

		[Ca <sub>2</sub> N] <sup>*</sup>	re <sup>-</sup> 125 M) ie 1a'	2a +	20		
#	$[Ca_2N]^+ e^-$ (equiv.)	Time	Solvent	Conversion <sup>b</sup>	<b>1a' : 2a : 2b</b> ratio <sup>b</sup>	Efficiency(%) <sup>e</sup>	
1	2	6 h	MeOH	24%	70 : trace : 30	41	T
2	2	2 h	THF:MeOH(1:1)	40%	78:4:18	71	
3	3	2 h	THF:MeOH(1:1)	54%	82:2:16	66	
4	4	2 h	THF:MeOH(1:1)	70%	88 : trace : 11	66	
5	5	2.5 h	THF:MeOH(1:1)	84%	97 : trace : 3	66	
6	5	14 h	THF:EtOH(1:1)	93%	85 : trace :14	69	
7	5	24 h	THF: <i>i</i> PrOH(1:1)	>99%	79:9:12	72	
8	5	15 h	Toluene: iPrOH(1:1)	85%	74 : trace : 26	59	9
9	5	15 h	DMF: <i>i</i> PrOH(1:1)	>99%(96%) <sup>c</sup>	100 : trace : trace	80	
$10^d$	5	15 h	DMF: <i>i</i> PrOH(1:1)	N.D	N.D		

<sup>*a*</sup> Conditions: Diphenylacethylene (0.5 mmol, 0.125 M),  $[Ca_2N]^+ e^- [1 \text{ mmol} \sim 2.5 \text{ mmol} (2 \sim 5 \text{ equiv.})]$ , r.t. <sup>*b*</sup> Determined by gas chromatography. <sup>*c*</sup> Isolated yield. <sup>*d*</sup>  $[Ca_{24}Al_{28}O_{64}]^{4+} \cdot 4e^-$  electride was used instead of  $[Ca_2N]^+ \cdot e^-$ . <sup>*e*</sup> The electron transfer efficiency was calculated from the ratio of the participated electrons in reactions to provided electrons from electride.

further purification process. Third, the reaction process must be simple to directly transfer the electrons from source agents to substrates. Fourth, the reaction must occur under very mild conditions without forming side products, which consume the electrons of the agents in the transferring process. In this regard, the use of electrides in alcoholic solvents meets the four requirements with respect to their potential for electron transfer based on low work functions and mild alcoholysis. Herein, we report a simple and highly efficient transfer hydrogenation of alkenes and alkynes by using an inorganic electride [Ca<sub>2</sub>N]<sup>+</sup>·e<sup>-</sup>, as an efficient electron transfer agent in alcoholic solvents. This protocol provided up to 80% of electron transfer efficiency, which is the highest value among the electron transfer agents in the reductive reactions of C-C multiple bonds. From the reactivity control of electride in alcoholic solvents, we demonstrated that the choice of solvent in terms of both acidity and polarity was crucial for maximizing the electron transfer efficiency. It is also suggested from the working model based on the mechanistic studies through X-ray diffraction and ion chromatography that the alcoholysis played a key role in transferring the anionic electrons of electride. Electrides are ionic crystals in which loosely trapped interstitial electrons in crystallographic empty space such as cavities, channels or interlayers behave as anions.<sup>8</sup> The degree of interaction between trapped anionic electrons, i.e., localization or delocalization, largely determines the chemical and physical properties of the system.<sup>9</sup> The most characteristic feature of the electrides is their low work function based on the loosely trapped anionic electrons.<sup>10</sup> The first crystalline electride, Cs<sup>+</sup>(18-crown-6)<sub>2</sub>·e<sup>-</sup>, was synthesized by using solvated electrons as precursors.<sup>8c</sup> The solvated electrons in an alkali metal-amine solution were successfully separated from the cations of alkali metals with the addition of crown ethers and occupied the structural cavities in the grown crystals of the electride. In synthetic chemistry, while solvated electrons as a potent reducing agent were applied to the classical Birch

and Bouveault-Blanc reductions, organic electrides have not been used as functional materials due to their fatal drawback of thermal and chemical instability at room temperature.<sup>11</sup>

In contrast, the room temperature stable inorganic electride [Ca<sub>24</sub>Al<sub>28</sub>O<sub>64</sub>]<sup>4+</sup>·4e<sup>-</sup> (C12A7:e<sup>-</sup>) mitigates the drawback of organic electrides, providing access to a new frontier in synthetic chemistry. Because the inherent electrons in electride can be directly participated in the chemical reactions, the use of electride in synthetic chemical reactions would be favourable in energetically compared to the electrochemical reactions, which use an additional electrical energy with a low electron transfer rate, and indispensable noble metal electrodes and electrolytes. Moreover, as already demonstrated, this electride-mediated methodology is feasible for scalable reactions such as pinacol coupling reaction using [Ca<sub>2</sub>N]<sup>+</sup>·e<sup>−</sup> electride.<sup>12</sup>

The C12A7:e<sup>-</sup> electride was verified as an effective electron donor in chemical reactions such as ammonia synthesis and decomposition, N<sub>2</sub> dissociation, and CO<sub>2</sub> splitting.<sup>13</sup> Recently, a two-dimensional (2D) electride,  $[Ca_2N]^+ e^-$ , which has anionic electron layers between cationic framework layers ([Ca<sub>2</sub>N]<sup>+</sup>) was discovered.<sup>14</sup> This 2D electride also showed very promising characteristics as a strong electron donor for synthetic chemistry in terms of its small work function (2.6 eV) and high electron concentration ( $\sim 1.37 \times 10^{22}$  cm<sup>-3</sup>) similar to those of typical alkali metals. Because the opened layer structured  $[Ca_2N]^+ e^-$  electride provides better accessibility to anionic electrons when compared to the closed cage structured C12A7:e electride, we conducted direct electron transfer from a C12A7:e<sup>-</sup> electride to various organic substrates bearing C-C multiple bonds and demonstrated highly efficient electron transfer hydrogenation of alkynes and alkenes in alcoholic solvents.<sup>12,15</sup>

This article is licensed under a Creative Commons Attribution 3.0 Unported Licence

Access Article. Published on 13 April 2015. Downloaded on 24/04/2015 03:54:21

## Results and discussion

**Journal Name** 

 Table 2. Optimization of transfer hydrogenation for alkene utilizing  $[Ca_2N]^+$ .

  $e^{-a}$ 



#	Time	Solvent	Conversion <sup>b</sup>
1	1 h	MeOH	62%
2	1 h	Toluene:MeOH(1:1)	75%
3	1 h	DMF:MeOH(1:1)	>99%
$4^c$	2 h	DMF:EtOH(1:1)	79%
$5^c$	14 h	DMF: <i>i</i> PrOH(1:1)	35%

<sup>*a*</sup> Conditions: *trans*-Stilbene (0.5 mmol, 0.125 M),  $[Ca_2N]^+ \cdot e^-$  (1.5 mmol, 3 equiv.), r.t., solvent. <sup>*b*</sup> Determined by gas chromatography. <sup>*c*</sup>  $[Ca_2N]^+ \cdot e^-$  was remained after reaction.

Initially, we examined the effects of the solvent as an electride activator and proton donor, and optimized the reaction conditions (Table 1). The use of a methanol solvent showed a low conversion of 1a (Table 1, entry 1). The reaction rapidly proceeded with the sudden decomposition of the  $[Ca_2N]^+ e^$ electride, forming a gel-type suspension and degrading the homogeneity of the reaction mixture. Since the methanol solvent reduces the reaction rate and the solubility of the starting materials, we applied a THF:MeOH co-solvent for a gentler reaction that can increase the solubility of the starting material and improve the homogeneity of the reaction mixture, leading to an increased conversion rate (Table 1, entry 2). Further optimizations were investigated by increasing the equivalents of the electride (Table 1, entries 2-5). Whereas the yield of 1a' increased as the equivalents of the electride increased, the electron transfer efficiency was moderate. We also postulated that both the acidity and the polarity of the solvent may influence the reactivity of the electride. Indeed, a significant enhancement in the yield of 1a' was observed by switching the solvent from methanol to isopropanol (Table 1, entries 5-7). The electron transfer efficiency was improved with decreasing acidity of alcohols  $[pK_a;$  methanol (15.54), ethanol (15.9), isopropanol (17.1)], although the reaction times were prolonged. This phenomenon is ascribed to the hydrogen evolution consuming electrons by reacting with the alcohols. A relatively acidic alcohol readily reacts with electrons to liberate hydrogen gas, consuming electrons and then reducing efficiency. Thus, employing less acidic alcohols such as isopropanol is essential to achieve the high yield of 1a' owing to the enhanced electron transfer efficiency.

Finally, we used a polar solvent as a co-solvent to maximize the yield of **1a'** and the electron transfer efficiency (Table 1, entry 9). The use of the polar solvent DMF with *i*PrOH led to significant enhancement in both the yield (>99%) and the electron transfer efficiency (~80%). These results suggest that a more polar environment might enhance the solvation effect of anionic electrons from the electride in the co-solvent or the dissociation of ionic bonds between the cationic layers and the anionic electrons of the electride, leading to the high electron transfer efficiency. Indeed, a transient solvated electron in the water of the highest polar solvent is well-known phenomenon in radiation chemistry, implying a possible existence of transient solvated electrons in DMF:/PrOH solvent. In addition, no reaction occurred when the C12A7:e<sup>-</sup> electride was employed under the optimized reaction conditions. This also supports the gentle alcoholysis of layer structured  $[Ca_2N]^+ \cdot e^-$  electride in DMF:/PrOH solvent that allows the efficient transfer of anionic electrons to substrates. However, we could not achieve a selective hydrogenation during the reaction due to the thermodynamic favour. The relative reactivity of aromatic substrates increases in the following order: *diphenylacethylene << cis-stilbene*  $\approx$  trans-stilbene, indicating the difficulty of selective hydrogenation for *cis*- and *trans*-stilbene from diphenylacethylene.<sup>16</sup>

Table 3. Scope of transfer hydrogenation for alkyne and alkene utilizing  $[Ca_2N]^+e^{-,a}$ 

$\begin{array}{c} R_1 \xrightarrow{\qquad R_2 \text{ or } R_3} \xrightarrow{\qquad R_5} \\ R_1 \xrightarrow{\qquad H_2} \\ 1 \end{array}$	[Ca <sub>2</sub> N] <sup>+</sup> ·e <sup>−</sup> (3 or 5 equiv.) DMF:/PrOH (or MeOH) (1:1) (0.125 M), r.t.	$\begin{array}{c c} R_1 & H \\ H & H \\ H & R_2 \\ 1 \end{array}$	or $H \xrightarrow{R_3}_{H}$	
# Sub:	strate	Product	Time	Yield <sup>b</sup>
$1    R_1 = C_6 H_5, R$	$\mathbf{R}_2 = \mathbf{C}_6 \mathbf{H}_5 \left( \mathbf{1a} \right)$	1a′	15 h	96%
2 $R_1 = 2$ -Me-C <sub>6</sub> H.	$_{4}, R_{2} = C_{6}H_{5}(\mathbf{1b})$	1b'	21 h	89%
3 $R_1 = 3$ -OMe-C <sub>6</sub> H	$\mathbf{H}_{4}\mathbf{R}_{2}=\mathbf{C}_{6}\mathbf{H}_{5}(\mathbf{1c})$	1c′	21 h	95%
4 $R_1 = 4$ -OMe-C <sub>6</sub> H	$H_4, R_2 = C_6 H_5 (\mathbf{1d})$	1d′	10 h	98%
$5^c$ $R_1 = R_2 = 4-1$	$Me-C_6H_4$ (1e)	1e'	24 h	97%
6 $R_1 = 4 - F - C_6 H_4$	$R_{2} = C_{6}H_{5}(\mathbf{1f})$	1f'	12 h	96%
7 $R_1 = 2,4-F-C_6H_2$	$_{4}, \mathbf{R}_{2} = \mathbf{C}_{6}\mathbf{H}_{5}\left(\mathbf{1g}\right)$	1g′	14 h	93%
8 $R_1 = 4 - F - C_6 H_4$ , R	$L_2 = 4 - F - C_6 H_4 (\mathbf{1h})$	1h′	24 h	94%
9 $R_1 = 4 - Ph - C_6 I$	$\mathbf{H}_{4},\mathbf{R}_{2}=\mathbf{H}\left(\mathbf{1i}\right)$	1i′	42 h	92%
$10^d$ R <sub>3</sub> = C <sub>6</sub> H <sub>5</sub> , R <sub>4</sub> = 0	$C_6H_5, R_5 = H(2a)$	1a′	1 h	99%
$11^d$ R <sub>3</sub> = C <sub>6</sub> H <sub>5</sub> , R <sub>4</sub> = 1	$\mathbf{H},\mathbf{R}_5=\mathbf{C}_6\mathbf{H}_5(\mathbf{2b})$	1a'	1 h	97%
$12^d$ $R_3 = R_4 = C_6 H_5$	$R_5 = C_6 H_5 (2c)$	1c'	1 h	92%
$13^d$ R <sub>3</sub> = 3,5-OMe-C <sub>6</sub> H (2)	$_{3}, R_{4} = C_{6}H_{5}, R_{5} = H$ 2d)	2d′	1 h	87%
$14^d$ R <sub>3</sub> = 4-Me-C <sub>6</sub> H <sub>4</sub> , R H	$_{4} = 4$ -Me-C <sub>6</sub> H <sub>4</sub> , R <sub>5</sub> = (2e)	1e′	1 h	85%
15 $R_1 = C_{10}H_{20}$	$\mathbf{R}_{2}=\mathbf{H}\left(\mathbf{1j}\right)$	1j′	N.D.	N.D.
$16^d   R_3 = C_{10}H_{20}, R_4$	= H, R <sub>5</sub> $=$ H ( <b>2f</b> )	1j′	N.D.	N.D.

<sup>*a*</sup> Conditions: Alkyne derivatives (0.5 mmol, 0.125 M),  $[Ca_2N]^+ \cdot e^-$  (2.5 mmol, 5 equiv.), r.t. <sup>*b*</sup> Isolated yield. <sup>*c*</sup> HMPA:*i*PrOH (v/v=1:1) was used instead of DMF:*i*PrOH (v/v=1:1). <sup>*d*</sup> Conditions: Alkene derivatives (0.5 mmol, 0.125 M),  $[Ca_2N]^+ \cdot e^-$  (1.5 mmol), DMF:MeOH (v/v =1:1), r.t.

We also examined the electron transfer hydrogenation of alkenes in this protocol using *trans*-stilbene **2a** as a model compound. Similar to the results of alkyne, the use of a cosolvent improved the conversion of **2a** (Table 2, entry entries 1-3). In addition, the relationship between the acidity of the solvents and the electron transfer efficiency was identical (Table 2, entries 3-5), strongly suggesting that the rate of the protonation step is an important parameter for enhancing the electron transfer efficiency. It is notable that the reaction with DMF:MeOH was completed in one hour, providing a quantitative yield of **1a'**.

With optimized conditions in hand, the substrate scope of alkynes and alkenes was examined under the optimized reaction conditions (Table 3). Both electron-rich and electrondeficient aromatic alkynes were well converted into the corresponding alkanes with excellent yield (Table 3, entries 1-

#### ARTICLE

8). Terminal alkyne **1i** was also a suitable substrate for electron transfer hydrogenation, showing an excellent yield (Table 3, entry 9). Reactions of stilbene derivatives also proceeded well, providing excellent yields of the corresponding alkanes, indicating a possibility for much broader application of the present protocol (Table 3, entries 10-14).

Journal Name



Fig 1. (a) Schematic illustration of electron transfer mechanism, (b) Proposed mechanism of transfer hydrogenation utilizing electride as electron transfer agent.

It was found that no reaction occurred in the use of aliphatic substrates such as 1-dodecyne 1j and 1-dodecene 2f (Table 3, entries 15-16). To clarify the different reactivity between aromatic and aliphatic substrates in thermodynamic consideration, we measured reduction potentials by using cyclic voltammetry (CV), in which the potentials of diphenylacetylene 1a and 1-dodecyne 1j were measured by employing a glassy carbon electrode, an Ag/AgCl reference, and a platinum wire auxiliary electrode in 0.5 M sulphuric acid solution. It was revealed that the reduction potential (-1.54 V vs Ag/AgCl electrode) of 1a was higher than that (-1.70 V vs Ag/AgCl electrode) of 1j, indicating that 1a is a better electron acceptor than 1j. This result implies that the reduction potential of electrons participating in the reduction of substrates is ranged between -1.54 and -1.70 V. This thermodynamic consideration gives an important insight that an appropriate choice of electron transfer media is a critical factor to provoke the electride-mediated reactions via the control of reduction potential since the electrons released from  $[Ca_2N]^+ \cdot e^-$  electride are transferred to substrates through transfer media.

Next, we conducted additional experiments to verify the validity of direct electron transfer via the alcoholysis of  $[Ca_2N]^+ e^-$ . The decomposition of the electride was confirmed by X-ray diffraction (XRD) measurements and ion-chromatography (IC) that revealed the formation of  $Ca(O^iPr)_2$  and ammonia, respectively (Supporting Information). The reaction of diphenylacethylene was conducted in the presence

of radical scavengers under optimized conditions to clarify the radical reaction that occurs by donation of electrons from the electride via the single electron transfer (SET) process. The employment of various radical scavengers, such as TEMPO, 1,4-dinitrobenzene and galvinoxyl, decreased the yields of **1a'** to a level corresponding to the amount of scavengers (See Supporting Information). On the basis of these results, we proposed a plausible mechanism that involves the SET process (Fig 1). In this process, the use of isopropanol eliminated the need for an additional hydrogen source.



Fig 2. Comparison of electron transfer efficiency in the reduction of alkyne (red) and alkene (blue) using typical electron transfer agent and  $[Ca_2N]^+$ .e<sup>-</sup>electride. The Na-SG is the sodium metal in silica gel.

Finally, we compared the electron transfer efficiency of electride-mediated reactions to the efficiency of reactions using various electron transfer agents (Fig 2). The present reaction using  $[Ca_2N]^+ e^-$  electrides showed a higher electron transfer efficiency than that of other agents [Yb, Mg, Na-SG,  $SmI_2(H_2O)_n$ , indicating that this protocol is simple and efficient for the reduction of C-C multiple bonds. In comparison with other agents, the electron transfer efficiency for the  $[Ca_2N]^+e^{-1}$ electride was significantly higher than that for Yb, Mg, and Na-SG, and similar to the costly compound Sml<sub>2</sub>(H<sub>2</sub>O)<sub>n</sub>. Furthermore, we estimated the electron transfer efficiency of all electride-mediated organic syntheses (Supporting information). The present transfer hydrogenation showed better performance than the other reactions using  $[Ca_2N]^+ e^{-1}$ and C12A7:e<sup>-</sup> electrides such as pinacol coupling<sup>12</sup> and hydrotrifluoromethylations<sup>14</sup>, supporting the simplicity and effectiveness of the reaction protocol.

#### Conclusions

We have developed a simple and highly efficient transfer hydrogenation process utilizing  $[Ca_2N]^+ e^-$  electride as an electron donor in an alcoholic solvent as a hydrogen atom donor. This methodology provides a new class of materials as a promising alternative for reducing the processes of C-C multiple bonds in terms of high electron transfer efficiency using an electride composed of naturally abundant elements.

Chemical Science Accepted Manuscri

#### View Article Online DOI: 10.1039/C5SC00933B

### Journal Name

#### Acknowledgements

This work was supported by the IBS-R011-D1, the National Research Foundation (2013R1A1A1008025 and 2012M3A7B4049652) of Korea and the Japan Science and Technology Agency ACCEL program.

#### Notes and references

- (a) B. M. Trost, Angew. Chem., 1995, **107**, 285; Angew.Chem. Int. Ed. Engl., 1995, **34**, 259; (b) B. M. Trost, Science, 1991, **254**, 1471.
- 2 A. Molná, A. Sárkány and M. J. Varga, J. Mol. Cat. A, 2001, 173, 185.
- 3 M. Hudlicky, *Reductions in Organic Chemistry*, Wiley-VCH, New York, 1984.
- 4 J. G. de Vries and C. J. Elsevier, *The Handbook of Homogenous Hydrogenation*, Wiley-VCH, Weinheim, 1984.
- 5 G. Brieger and T. J. Nerstric, Chem. Rev., 1974, 74, 567.
- 6 R. A. W. Johnstone and A. H. Wilby, Chem. Rev., 1985, 85, 129.
- 7 (a) R. O. Hutchins and Suchismia, *Tetrahedron Lett.*, 1989, **30**, 129; (b)
  Z. Hou, H. Taniguchi and Y. Fujiwara, *Chem. Lett.*, 1987, **16**, 305; (c)
  M. J. Costanzo, M. N. Patel, K. A. Petersen and P. F. Vogt, *Tertrahedron Lett.*, 2009, **50**, 5463; (d) A. Dahlen and G. Hilmersson, *Tertahedron Lett.*, 2003, **44**, 2661; (e) M. Szostak, M. Spain and D. J. Procter, *Angew. Chem.*, 2013, **125**, 7378; *Angew. Chem. Int. Ed.*, 2013, **52**, 7237.
- 8 (a) J. L. Dye, *Inorg. Chem.*, 1997, 36, 3816; (b) J. L. Dye, *Acc. Chem. Res.*, 2009, 42, 1564; (c) J. L. Dye, *Science*, 1990, 247, 663.
- 9 (a) S. W. Kim, S. Matsuishi, T. Nomura, Y. Kubota, M. Takana, K. Hayashi, T. Kamiya, M. Hirano and H. Hosono, *Nano Lett.*, 2007, 7, 1138; (b) M. Miyakawa, S. W. Kim, M. Hirano, Y. Kohama, H. Kawaji, T. Atake, H. Ikegami, K. Kono and H. Hosono, *J. Am. Chem. Soc.*, 2007, 129, 7270.
- Y. Toda, H. Yanagi, E. Ikenaga, J. J. Kim, M. Kobata, S. Ueda, T. Kamiya, M. Hirano, K. Kobayashi and H. Hosono, *Adv. Mater.*, 2007, **19**, 3564.
- 11 (a) A. J. Birch, Pure Appl. Chem., 1996, 68, 553; (b) L. Bouveault, G. Blanc, Bull. Soc. Chim. Fr., 1904, 31, 666; (c) L. Bouveault, G. Blanc, Compt. Rend., 1903, 136, 1676.
- 12 Y. J. Kim, S. M. Kim, H. Hosono, J. W. Yang and S. W. Kim, Chem. Commun., 2014, 50, 4791
- (a) M. Kitano, Y. Inoue, Y. Yamazaki, F. Hayashi, S. Kanbara, S. Matsuichi, T. Yokoyama, S.W. Kim, M. Hara and H. Hosono, *Nat. Chem.*, 2012, 4, 934; (b) F. Hayashi, Y. Toda, Y. Kanie, M. Kitano, Y. Inoue, T. Yokoyama, M. Hara and H. Hosono, *Chem. Sci.*, 2013, 4, 3124; (c) N. Kuganathan, H. Hosono, A. L. Shluger and P. V. Sushko, *J. Am. Chem. Soc.*, 2014, 136, 2216; (d) Y. Toda, H. Hirayama, N. Kuganathan, A. Torrisi, P.V. Sushko and H. Hosono, *Nat. Commun.*, 2013, 4, 2378.
- 14 K. Lee, S. W. Kim, Y. Toda and H. Hosono, Nature, 2013, 494, 336.
- 15 S. Choi, Y. J. Kim, S. M. Kim, J. W. Yang, S.W. Kim and E. J. Cho, *Nat. Commun.*, 2014, **5**, 4481.
- 16 M. Szostak, M. Spain and D. J. Procter, J. Org. Chem., 2014, 79, 2252.

This journal is C The Royal Society of Chemistry 20xx