Synthesis and characterisation of new oligoacetylenic silanes

Wai-Yeung Wong,* Albert W.-M Lee,* Chun-Kin Wong, Guo-Liang Lu, Hongkui Zhang, Tian Mo and Kwun-Ting Lam

Department of Chemistry, Hong Kong Baptist University, Waterloo Road, Kowloon Tong, Hong Kong, P.R. China. E-mail: rwywong@hkbu.edu.hk

Received (in Montpellier, France) 21st August 2001, Accepted 20th November 2001 First published as an Advance Article on the web 19th February 2002

Synthetic routes to a series of novel oligoacetylenic silanes with or without (hetero)aromatic bridges have been developed. The compound Me₃SiC=CSi(Ph)₂C=CSiMe₃ was first prepared, which was selectively desilylated with CaCO₃ in methanol at room temperature to afford the mono-protected bis(alkynyl) silane Me₃SiC=CSi(Ph)₂C=CH in moderate yield. Treatment of this mono-protected species with "BuLi, followed by silylation with Ph₂SiCl₂, gives a good yield of Me₃SiC=CSi(Ph)₂C=CSi(Ph)₂C=CSi(Ph)₂C=CSi(Ph)₂C=CSiMe₃, with alternating silicon and acetylene units. A range of linear silicon-linked oligoalkynes containing phenylene, bithienylene and anthrylene rings, HC=CRC=CSi(Ph)₂C=CRC=CH and HC=CRC=CSi(Ph)₂C=CRC=CSi(Ph)₂C=CRC=CH (R = 1,4-phenylene, 5,5'-bithienylene or 9,10-anthrylene), were synthesised by condensation reactions of Ph₂SiCl₂ with the components obtained *in situ* from a HC=CRC=CH-ⁿBuLi mixture in THF and the products were isolated by chromatography on silica. All these new compounds have been characterised by IR, ¹H and ¹³C NMR and UV/VIS spectroscopies and mass spectrometry. The single-crystal X-ray structure of HC=C(*p*-C₆H₄)C=CSi(Ph)₂C=C(*p*-C₆H₄)C=CSi(Ph)₂C=C (*p*-C₆H₄)C=CH has been determined, showing that two silicon atoms and six acetylene units constitute the backbone of the molecule.

The molecular design and synthesis of linear, cyclic or dendritic systems composed of silicon atoms and acetylene units has aroused considerable interest.¹⁻⁵ These carbon-rich acetylenebased scaffolds have been demonstrated to exhibit intriguing electrical, electronic, optical and structural properties.¹⁻⁵ The lower ionisation energy of the silicon atom compared with carbon is expected to enhance the through-bond interaction of ethynyl units along the backbone.^{6,7} In this context, the chemistry of linear inorganic polymers containing alternating arrangements of silvlene and π -electron moieties represents an important area of current active research because they possess good potential as functional materials such as semiconductors,⁸ hole-transporting^{9–11} and heat-resistant materials,^{12–14} photoresists^{15,16} and ceramic precursors.^{1,17} The unusual electrical and optical properties associated with these materials are generally attributed to the delocalisation of electrons through the silvlene linkages via π -d_{si} interactions^{18,19} or σ - π conjugation.^{6,20} Among these, π -conjugated systems incorporating phenylene, anthrylene or oligothienylene bridges along with Si residues in the main chain have been extensively investigated regarding their applications to electro- and optical devices.²¹⁻²⁸

However, to our knowledge, reports on the synthesis of linear oligoacetylenic silanes have been scarce and related problems in this area remain relatively unexplored.^{5,29,30} Alkynylsilane-based short-chain oligomers are not only key intermediates in the preparation of their polymeric or cyclic compounds but also useful alternative materials with potentially enhanced performance by limiting the conjugation length of the polymer.^{31,32} In this respect, oligo(phenylene vinylene)s represent one of the best examples that have recently drawn considerable attention.^{31–33} Investigation of well-defined π -conjugated oligomers can provide an insight into the electronic, emissive and structural properties of the related polymeric materials.³¹ These oligoacetylenic silanes are also attractive building blocks for molecular architectures, but their

syntheses have been largely hampered by the limited availability of suitable difunctionalised silyl compounds by the ready polymerisation of the starting silylacetylene precursors.^{34–37} We have recently described a systematic approach to the synthesis of some oligoacetylenic sulfides,^{38,39} and the fruitful results prompted us to prepare a new series of linear oligoacetylenic silanes containing Ph₂SiC=C units. Based on our experience in the preparation of oligoacetylenic sulfides and related compounds in organic synthesis,⁴⁰ we report here the first synthesis of a novel class of well-defined oligo(alkynylsilane)s, with or without (hetero)aromatic groups, and a description of their spectroscopic, optical and structural properties is also presented.

Results and discussion

Syntheses

The preparation of the silvlacetylene oligomer 3 starts with the synthesis of a mono-protected bis(alkynyl) silane 2. Treatment of trimethylsilylacetylene with "BuLi at -78°C yielded the corresponding lithium salt, which reacted in situ with Ph2SiCl2 to provide a white solid, Me3SiC=C-Si(Ph)₂C≡CSiMe₃, 1, in 72% yield based on Me₃SiC≡CH (Scheme 1). The desired mono-protected bis(acetylene) silane 2 was obtained as a colourless liquid in moderate yield when 1 was desilylated with CaCO₃ in MeOH at room temperature. 2 was found to be slightly unstable in air, especially when concentrated, which precluded satisfactory elemental analysis. It is noteworthy that mono-desilylation of 1 to produce 2 did not occur under commonly used desilylation conditions (e.g., K_2CO_3 -MeOH or KF-MeOH).^{38,39,41-43} Careful mono-desilylation of 1 with a CaCO₃-MeOH mixture should be conducted under anhydrous condition and



Scheme 1 (i) "BuLi, -20°C, Ph₂SiCl₂, THF; (ii) CaCO₃-MeOH, r.t.

close monitoring with TLC. When HC=CSi(Ph)₂C=CH started to appear, the reaction was quenched by water. Work-up and flash column chromatography gave 2 in 42% yield. Although the yield of 2 was not very high, the recovered 1 could be reused to prepare 2. Freshly prepared 2 was then treated with "BuLi followed by silylation with Ph₂SiCl₂ in THF to furnish, on chromatography, 3 as a colourless oily substance with a yield of 65%. The chain length was doubled in this synthetic procedure. Attempts have also been made to extend the chain length through further mono-desilylation of 3 followed by silylation with Ph₂SiCl₂. Unfortunately, only a complicated mixture was obtained in this way.

In the pursuit of more stable oligoacetylenic silanes with tunable physical and optical properties, it seemed an attractive goal to us to synthesise new silylacetylene compounds containing a range of aromatic and heteroaromatic moieties along the backbone. The synthetic route leading to the target molecules is outlined in Scheme 2. When HC≡CRC≡CH was treated with 1 equiv. of "BuLi or freshly prepared (Me₃Si)₂NLi (as a base) in THF followed by 0.5 equiv. of Ph₂SiCl₂ at -78°C, a mixture of HC=CRC=CSi(Ph)₂C=CRC=CH and $HC \equiv CRC \equiv CSi(Ph)_2C \equiv CRC \equiv CSi(Ph)_2C \equiv CRC \equiv CH$ (R = 1,4phenylene, 5,5'-bithienylene or 9,10-anthrylene) was formed along with small amounts of their higher oligomers and the recovered starting diethynyl compounds. Purification of 4-6 was effected by preparative TLC on silica, leading to the isolation of the products as white (4a and 4b), pale yellow (5a and 5b) and orange-yellow (6a and 6b) solids in moderate to good yields. Compounds 4-6 are generally stable as solids in air at room temperature and dissolve readily in common organic solvents such as CH₂Cl₂ and CHCl₃. However, 5 and 6 decompose slightly when kept in solution for a prolonged period of time or under light and do not melt below their decomposition temperatures. All the new compounds in this



Scheme 2 (i) ⁿBuLi, -20 °C, Ph₂SiCl₂, THF.

study were satisfactorily characterised by common spectroscopic methods (IR, MS, ¹H and ¹³C NMR).

Spectroscopic properties

All the spectroscopic data of compounds 1-6 are consistent with their structures (Experimental section). The IR spectra of these oligoacetylenic species display strong $v_{C=C}$ absorption bands in the range 2040–2159 cm⁻¹.^{28,38,43} The terminal acetylenic C–H signal also appears around 3275-3305 cm⁻¹ for 2, 4, 5 and 6. In all cases, ¹H NMR resonances arising from the protons of the organic fragments were observed, and all the phenyl, phenylene, bithienylene and anthrylene carbon atoms were clearly identified in the aromatic region of the $^{13}\text{C-}\{^1\text{H}\}$ NMR spectra. Notably, there are four and six distinct¹³C NMR signals for all the individual sp carbons in 4a-6a and 4b-6b, respectively, in accordance with their formulations. Assignment of these ¹³C resonances was made on the basis of peak intensities and by analogy with results of other similar acetylide compounds.^{28,38,43,44} For **4–6**, the ¹³C chemical shifts remain relatively unshifted for the outermost acetylene carbons as compared to the free ligand HC=CRC=CH whereas the innermost acetylene carbons in close proximity to Si appear at more downfield positions. For comparison, while the sp carbons of 5,5'-diethynyl-2,2'-bithiophene resonate at δ 76.66 (C=CH) and 82.68 (C=CH),⁴³ those for 5a appear at δ 76.58 and 82.77 for the outermost carbons and at δ 93.46 and 101.03 for the innermost C=C units close to the SiPh₂ group. The ¹³C NMR spectrum of 5b shows six resonances of sp carbon atoms. The nearly unaltered chemical shift values at δ 76.58 and 82.76 in 5b correspond to the two outer carbons, while the lower field signals at δ 93.46, 93.62, 101.00 and 101.05 are ascribed to the middle and innermost acetylene carbons. The ²⁹Si NMR chemical shifts of 4 and 6 do not differ significantly from those for the longer chain homologues,45 in line with the UV/VIS spectral data (vide infra). These results indicate that there is a diminishing effect on the degree of electronic conjugation with increasing number of Si residues in the backbone. The formulae of these oligoacetylenic silanes were successfully confirmed by EI and positive FAB mass spectrometry and the respective molecular ion peaks were detected in each case.

The optical properties of our new compounds have been investigated in CH₂Cl₂ solutions. The electronic absorption and emission data are given in the Experimental section. Trimethylsilyl-capped Si-containing tetrayne 3 shows ca. 50 nm red-shifted absorption bands in comparison with 1, probably due to the extended conjugation through Si as the chain length is doubled. The absorption spectra of 4a and 4b are dominated by $\pi - \pi^*$ transitions of the bridging units in the near-UV region, and a notable bathochromic shift in λ_{max} with increased extinction coefficients is observed upon going from 1,4-diethynylbenzene (260, 273 nm) to 4a (274, 290 nm) and 4b (274, 289, 303 nm). Both **5a** and **5b** exhibit strong $\pi - \pi^*$ transitions in the near-UV range with a similar absorption pattern, attributable to the bithienyl moiety.⁴³ The lowest energy band red-shifts from 353 (5,5'-diethynyl-2,2'-bithiophene)⁴³ to 365 (5a) and 370 nm (5b). The polymeric analogue of 5 with a single thiophene group $[-C \equiv CSi(Ph)_2C \equiv C(2,5-C_4H_2S)C \equiv C-]_n$ shows its lowest energy absorption at 304 nm in the same solvent.⁴⁵ The UV/VIS spectra of **6a** and **6b** are characterised by intense absorption bands with fine structure most likely arising from transitions similar to those for anthracene.⁴⁶ With reference to the bands in anthracene (326, 342, 359, 378 nm), those for **6a** and **6b** are red-shifted by *ca*. 50-80 nm, the bathochromic shift being greater than for 9,10-diethynylanthracene (λ_{max} 361, 380, 402, 426 nm).²⁸ The corresponding absorption peaks in 6b with a longer chain length are further red-shifted with respect to those in 6a. These properties are suggestive of the presence of through-Si conjugation along the backbone in these oligomeric organosilicon systems. However, the extent of bathochromic shifts induced by the increase online chain length is less pronounced with increasing number of repeat units. The fact that the polymeric homologues of **4** and **6**, $[-C \equiv CSi(Ph)_2C \equiv CRC \equiv C-]_n$, display very similar lowest energy peaks at 303 (R = 1,4-phenylene) and 450 (R = 1,10-anthrylene) nm as those of **4b** and **6b**, respectively, suggest that there would probably be little benefit in increasing the number of repeating units above three in the control of spectral properties of these diphenylsilylene materials.^{36,45}

In the solution state, compounds 4-6 are luminescent at room temperature and the emission peaks range from 339 to 484 nm. There is a slight bathochromic shift in the emission wavelength upon going from compounds **a** to **b** within each series incorporating a particular R group. We also note that the position of the absorption maximum depends on the nature of the aromatic unit R. For the series **4a–6a**, the λ_{max} of the low-energy band increases from 290 nm for 4a to 365 nm for 5a and a significant red-shift of the absorption maximum is observed for 6a (438 nm) when a more electron-rich unit such as anthracene is introduced. A similar trend was also encountered for the group 4b-6b. It has been suggested for some conjugated aromatic copolymers that the position of the absorption maximum is related to the degree of destabilisation of the HOMO and stabilisation of the LUMO.47 The presence of the electron-rich anthracene residue in 6a and 6b tends to reduce the energy gap between these frontier levels, and gives rise to a bathochromic shift of the absorption and emission compared to the other two groups of molecules having phenylene and bithienylene moieties.

Crystal structure analysis

The crystallographically determined structure of 4b by an X-ray diffraction experiment serves to identify the oligomeric nature of the product unequivocally. A perspective drawing of compound 4b is shown in Fig. 1, which includes the atom numbering scheme. The principal bond lengths and angles are listed in Table 1. There is a crystallographic centrosymmetry at the central phenylene ring such that two halves of the molecule are related by an inversion centre at the centroid of the C(25)-C(26)-C(27A)-C(25A)-C(26A)-C(27) plane. In the solid state, **4b** possesses three $-C \equiv C(p-C_6H_4)C \equiv C$ moieties alternately connected by two SiPh₂ units in a linear fashion. There are a total of six C=C units in the entire molecule. The C=C bond lengths lie within the narrow range of 1.197(2)–1.206(3) Å and the C=CH bond shows a slight shortening of bond length [1.164(4) Å] due to the libration effect.⁴⁸ The Si–C(sp) single bond lengths are 1.810(2)-1.822(2) Å [ave. 1.816(2) Å], which are slightly shorter than those observed in related silylacetylene compounds such as the two silapericyclyne conformers [1.83(2)-1.836(3) Å],⁴⁹ the *cis-trans* and all-*trans* isomers of 1,2,5,6-tetramethyl-1,2,5,6-tetraphenyl-1,2,5,6-tetrasilacycloocta-3,7-diyne [1.841(5)-1.843(5), 1.828(6)-1.836(6) Å, respectively]³⁵ and the 1G-dendrimer with 10 silicon atoms and 9 acetylene units [1.827(5)-1.851(5) Å].⁵ These data, together with the slightly shorter \equiv C–C(ring) bond [ca. 1.427(3)– 1.436(2) Å], are consistent with a partial conjugation effect along the molecular backbone. The linearity of the acetylene units is evident from the bond angles of Si-C(sp)-C(sp) and $C(sp)-C(sp)-C(sp^2)$, and the unusually small Si(1)-C(10)-C(9) bond angle $[172.7(2)^{\circ}]$ is presumably caused by the solid-state packing effect in the crystal lattice. All the aromatic rings are nearly planar with normal bond parameters.

Concluding remarks

The present work provides a convenient entry to a new series of oligoacetylenic silanes. The results here indicate through-Si conjugation along the backbone of these molecules and



Fig. 1 A perspective drawing of 4b with the atom numbering scheme.

Table 1 Selected bond lengths (Å) and angles (°) for compound 4b

C(1)–C(2)	1.164(4)	C(2)–C(3)	1.433(3)
C(6)–C(9)	1.427(3)	C(9)–C(10)	1.206(3)
Si(1)-C(10)	1.810(2)	Si(1)-C(11)	1.822(2)
Si(1) - C(13)	1.855(2)	Si(1)-C(19)	1.855(2)
C(11)-C(12)	1.197(2)	C(12)-C(25)	1.436(2)
C(1)–C(2)–C(3)	177.3(3)	C(6)-C(9)-C(10)	176.7(2)
Si(1)-C(10)-C(9)	172.7(2)	Si(1)-C(11)-C(12)	178.0(2)
C(10)–Si(1)–C(11)	109.44(9)	C(11)-C(12)-C(25)	178.1(2)

attempts have been made to evaluate how the nature of the linking unit R and the chain length of this type of oligomers would influence their optical and spectroscopic properties. We are currently extending these studies to higher generations and further investigations of other properties (such as conducting properties) of these π -electronic systems are now in progress.

Experimental

General

All reactions were conducted under an atmosphere of dry nitrogen with the use of standard Schlenk techniques. Solvents for preparative work were dried and distilled before use. IR spectra were recorded on a Nicolet FTIR-550 spectrometer. NMR spectra were recorded in CDCl₃ on a JEOL JNM-EX 270, Varian Inova 400 MHz or Bruker 600 MHz FT-NMR spectrometer. Electron impact (EI) and fast atom bombardment (FAB) mass spectra were recorded on a Finnigan-SSQ 710 spectrometer. Electronic absorption and luminescence spectra were measured in appropriate solvents with a Varian Cary 100 UV/VIS spectrophotometer and a Perkin-Elmer LS50B luminescence spectrometer, respectively. Unless otherwise stated, all reagents were from commercial sources and used as received. The starting diethynyl compounds HC=CRC=CH (R = 1,4-phenylene, 5,5'-bithienylene or 9,10anthrylene) were prepared according to the reported procedures.^{41,43,44,50} Separation of products was accomplished by column chromatography on silica or preparative silica TLC plates (Merck, Kieselgel 60).

Synthetic procedures

Me₃SiC=CSi(Ph)₂C=CSiMe₃, 1. ^{*n*}BuLi (13 cm³, 20.8 mmol, 1.6 M solution in hexane) was added dropwise to a solution of trimethylsilylacetylene (1.96 g, 20.0 mmol) in dry diethyl ether (40 cm³) at -78 °C under a nitrogen atmosphere. After the mixture was stirred at -78 °C for 1 h, Ph₂SiCl₂ (2.53 g, 10.0

mmol) was added in one portion and the reaction mixture was stirred for 2 h at this temperature. The solution was then allowed to warm up to room temperature and stirred for an additional 3 h. The crude material was partitioned between NH₄Cl solution and diethyl ether. The aqueous layer was extracted with ether and the organic phase was dried over Na_2SO_4 , filtered and concentrated. The title product was purified by column chromatography on silica, eluting with petroleum ether- CH_2Cl_2 (4 : 1, v/v). The product was obtained as a white solid in 72% yield (3.76 g). m.p.: 65-67 °C. IR (KBr): 2109 cm⁻¹ ($v_{C=C}$). ¹H NMR (CDCl₃): δ 0.22 (s, 18H, Me), 7.36–7.39 (m, 6H, Ph) and 7.70–7.73 (m, 4H, Ph). ¹³C-{¹H} NMR (CDCl₃): δ -0.16 (Me), 106.10, 118.90 (C=C), 127.86, 129.99, 134.69 (aromatic CH) and 132.73 (aromatic quaternary C). ²⁹Si NMR (CDCl₃): δ –17.58 and 0.00. EI MS: m/z 376 (M⁺). UV/VIS (cyclohexane): λ_{max}/nm ($\varepsilon \times 10^4$ dm² mol⁻¹ cm⁻¹) 211 (3.0) and 224 (2.8). Calcd for C₂₂H₂₈Si₃: C, 70.14; H, 7.49. Found: C, 69.89; H, 7.20%.

Me₃SiC=CSi(Ph)₂C=CH, 2. To a solution of 1 (132 mg, 0.35 mmol) in MeOH (10 cm³) was added CaCO₃ (35 mg). The reaction mixture was stirred at room temperature for 5 h and the course of the reaction was monitored closely by spot TLC. When HC=CSi(Ph)₂C=CH started to appear, the reaction was subsequently quenched by water and the mixture extracted with CH₂Cl₂. The resulting organic extract was dried over Na₂SO₄, filtered and concentrated. The concentrate was then subjected to flash column chromatography on silica using petroleum ether-CH₂Cl₂ (6 : 1, v/v) as eluent to give 2 as a colourless liquid (45 mg, 42%). This compound can be used for the following preparation without further purification. IR (CH₂Cl₂): 3283 ($v_{=CH}$) and 2040 cm⁻¹($v_{C=C}$). ¹H NMR (CDCl₃): δ 0.22 (s, 9H, Me), 2.70 (s, 1H, C≡CH), 7.38–7.41 (m, 6H, Ph) and 7.72–7.74 (m, 4H, Ph). $^{13}C-{^{1}H}$ NMR (CDCl₃): δ -0.33 (Me), 83.91, 105.24 and 119.52 (C≡C), 96.96 (C≡CH), 128.07, 130.36, 134.76 (aromatic CH) and 131.99 (aromatic guaternary C). ²⁹Si NMR (CDCl₃): δ –49.77 and –17.27. EI MS: m/z 304 (M⁺). A satisfactory elemental analysis was not obtained, probably due to contamination by a trace amount of HC≡CSi(Ph)₂C≡CH.

Me₃SiC≡CSi(Ph)₂C≡CSi(Ph)₂C≡CSi(Ph)₂C≡CSiMe₃, 3. Compound 2 (48 mg, 0.16 mmol) was dissolved in dry THF (10 cm³) in a Schlenk flask. After cooling the flask to $-78 \,^{\circ}$ C, ⁿBuLi was added dropwise to the stirred solution. After stirring for 1 h at $-78 \,^{\circ}$ C, Ph₂SiCl₂ (20 mg, 0.08 mmol) was added dropwise. The resulting mixture was stirred at $-78 \,^{\circ}$ C for 2 h and then warmed at room temperature for another 0.5 h. The crude material was extracted between NH₄Cl solution and CH₂Cl₂. The organic layer was dried over Na₂SO₄ and filtered. Concentration of the filtrate followed by silica column chromatography using petroleum ether–CH₂Cl₂ (6 : 1, v/v) as eluent

Published on 19 February 2002. Downloaded by NORTHERN ARIZONA UNIVERSITY on 29/07/2013 09:45:59.

afforded **3** as a colourless oil in 65% yield (41 mg). IR (KBr): 2040 cm⁻¹ ($v_{C=C}$). ¹H NMR (CDCl₃): δ 0.22 (s, 18H, Me), 7.34–7.43 (m, 18H, Ph) and 7.75–7.79 (m, 12H, Ph). ¹³C-{¹H} NMR (CDCl₃): δ –0.33 (Me), 105.31, 110.39, 111.97, 119.69 (C=C), 128.06, 128.07, 130.29, 130.44, 134.87, 134.98 (aromatic CH), 132.08 and 134.76 (aromatic quaternary C). ²⁹Si NMR (CDCl₃): δ –50.48, –27.31 and –17.28. EI MS: m/z 788 (M⁺). UV/VIS (cyclohexane): λ_{max}/nm ($\varepsilon \times 10^4$ dm³ mol⁻¹ cm⁻¹) 256 (1.9), 262 (2.4), 266 (2.5) and 273 (2.0). A satisfactory analytical analysis was not obtained due to contamination by a trace amount of HC=CSi(Ph)₂C=CH that was present in the previous step.

HC=CRC=CSi(Ph)₂C=CRC=CH, 4a, and HC=CRC=C- $Si(Ph)_2C \equiv CRC \equiv CSi(Ph)_2C \equiv CRC \equiv CH$, 4b (R = 1,4-phenylene). To a chilled solution of 1,4-diethynylbenzene (200 mg, 1.59 mmol) in dried THF (20 cm³) at -20 °C, (Me₃Si)₂NLi (266 mg, 1.59 mmol) freshly prepared from (Me₃Si)₂NH and ⁿBuLi in THF (20 cm³) or ⁿBuLi (1.0 cm³, 1.60 mmol, 1.6 M in hexane) was added dropwise under a nitrogen purge. The mixture was stirred for 30 min at this temperature and then 2 h at room temperature. The resulting solution was again cooled to -20 °C and a solution of Ph₂SiCl₂ (201 mg, 0.80 mmol) in THF (10 cm³) was added dropwise over 30 min. The reaction mixture was stirred for a further 30 min at -20 °C prior to stirring at room temperature for 3 h. The volatile components were evaporated and the residue was extracted with CH₂Cl₂. The organic extract was dried over Na₂SO₄ and filtered. The filtrate was concentrated and subjected to preparative TLC isolation using silica plates and hexane- CH_2Cl_2 (3 : 1, v/v) as eluent. From the second $(R_f = 0.55)$ and third $(R_f = 0.45)$ bands, compounds 4a and 4b were obtained as white solids with yields of 52 (179 mg) and 17% (67 mg), respectively, based on 1,4-diethynylbenzene. The starting 1,4-diethynylbenzene was also recovered in a pure form from the top band (40 mg, 20%), which can be employed as a precursor for the synthesis of more 4a and 4b. 4a: m.p.: 96–98 °C. IR (KBr): 3276 ($v_{=CH}$) and 2157 cm⁻¹($v_{C=C}$). ¹H NMR (CDCl₃): δ 3.24 (s, 2H, C=CH), 7.47-7.52 (m, 10H, Ph), 7.58-7.60 (m, 4H, C₆H₄) and 7.89-7.94 (m, 4H, C₆H₄) ¹³C-{¹H} NMR (CDCl₃): δ 79.43 (C≡CH), 83.02, 89.62, 107.98 (C≡C), 128.17, 130.42, 131.97, 132.00, 134.89 (aromatic CH), 122.69, 122.95 and 132.44 (aromatic quaternary C). ²⁹Si NMR (CDCl₃): δ –47.88. FAB MS: m/z 432 (M⁺). UV/VIS (CH₂Cl₂): λ_{max}/nm ($\varepsilon \times 10^4$ dm³ mol^{-1} cm⁻¹) 228 (3.1), 274 (9.0) and 290 (1.1). Emission (CH₂Cl₂, $\lambda_{\text{excitation}} = 290$ nm): 339 nm. Calcd for C₃₂H₂₀Si: C, 88.85; H, 4.66. Found: C, 88.59; H, 4.40%. 4b: m.p.: 180-182 °C. IR (KBr): 3287 ($v_{=CH}$) and 2159 cm⁻¹ ($v_{C=C}$). ¹H NMR (CDCl₃): δ 3.19 (s, 2H, C≡CH), 7.43–7.47 (m, 16H, aromatic), 7.52-7.54 (m, 8H, aromatic) and 7.83-7.85 (m, 8H, aromatic).¹³ C-{¹H} NMR (CDCl₃): δ 79.44 (C=CH), 83.01, 89.56, 90.00, 107.95, 108.00 (C≡C), 128.17, 130.43, 131.96, 132.17, 132.20, 134.89 (aromatic CH), 122.67, 122.93, 123.08 and 132.38 (aromatic quaternary C). ²⁹Si NMR (CDCl₃): δ -47.89. FAB MS: m/z 738 (M⁺). UV/VIS (CH₂Cl₂): λ_{max}/nm $(\varepsilon \times 10^4 \text{ dm}^3 \text{ mol}^{-1} \text{ cm}^{-1})$ 228 (4.7), 274 (14.1), 289 (14.8) and 303 (11.3). Emission (CH₂Cl₂, $\lambda_{\text{excitation}} = 289$ nm): 329, 399sh nm. Calcd for $C_{54}H_{34}Si_2$: C, 87.76; H, 4.64. Found: C, 87.52; H, 4.31%.

HC=CRC=CSi(Ph)₂C=CRC=CH, 5a, and HC=CRC=C-Si(Ph)₂C=CRC=CSi(Ph)₂C=CRC=CH, 5b (R = 5,5'-bithienylene). These compounds were prepared using the conditions described above for 4a and 4b but 5,5'-diethynyl-2,2'-bithiophene (118 mg, 0.55 mmol) was used instead of 1,4-diethynylbenzene. Elution using a 2 : 1 hexane–CH₂Cl₂ mixture gave three yellow bands, from which three compounds were separated. In order of elution, these compounds were 5,5'-diethynyl-2,2'-bithiophene (R_f =0.68, 20 mg, 17%), 5a (R_f =0.50, 42 mg, 25%) and **5b** ($R_f = 0.27$, 18 mg, 10%), all as viale Average Av solids. 5a: m.p.: 90-92 °C (dec.). IR (KBr): 3284 (v_{=CH}), 2139 and 2098 cm⁻¹($v_{C=C}$). ¹H NMR (CDCl₃): δ 3.42 (s, 2H, C=CH), 7.04 (d, ${}^{3}J_{H-H} = 1.6$ Hz, 2H, thienyl), 7.05 (d, ${}^{3}J_{H-H} =$ 1.6 Hz, 2H, thienyl), 7.17 (d, ${}^{3}J_{H-H} = 4.0$ Hz, 2H, thienyl), 7.27 (d, ${}^{3}J_{H-H} = 4.0$ Hz, 2H, thienyl), 7.43–7.48 (m, 6H, Ph) and 7.81–7.84 (m, 4H, Ph). ${}^{13}C{-}{}^{1}H$ NMR (CDCl₃): δ 82.77 (C≡CH), 76.58, 93.46, 101.03 (C≡C), 123.97, 124.04, 128.21, 130.52, 133.99, 134.88, 134.94 (aromatic CH), 121.53, 121.56, 132.01, 137.97 and 138.92 (aromatic quaternary C). ²⁹Si NMR (CDCl₃): δ -47.78. FAB MS: m/z 608 (M⁺). UV/VIS (CH₂Cl₂): λ_{max}/nm ($\epsilon \times 10^4$ dm³ mol⁻¹ cm⁻¹) 229 (2.5), 259 (1.4) and 365 (5.3). Emission (CH₂Cl₂, $\lambda_{\text{excitation}} = 365$ nm): 409 nm. Calcd for C₃₆H₂₀SiS₄: C, 71.01; H, 3.31. Found: C. 70.81; H, 3.42%. 5b: m.p.: 53-54°C (dec.). IR (KBr): 3285 $(v_{\equiv CH})$, 2142 and 2100 cm⁻¹ $(v_{C\equiv C})$. ¹H NMR (CDCl₃): δ 3.42 (s, 2H, C=CH), 7.04 (d, ${}^{3}J_{H-H}$ = 1.6 Hz, 2H, thienyl), 7.05 (d, ${}^{3}J_{H-H}$ = 1.6 Hz, 2H, thienyl), 7.06 (d, ${}^{3}J_{H-H}$ = 3.6 Hz, 2H, thienyl), 7.17 (d, ${}^{3}J_{H-H} = 3.6$ Hz, 2H, thienyl), 7.26 (t, ${}^{3}J_{H-H} =$ 4.0 Hz, 4H, thienyl), 7.42-7.48 (m, 12H, Ph) and 7.81-7.83 (m, 8H, Ph). ¹³C-{¹H} NMR (CDCl₃): δ 82.76 (C=CH), 76.58, 93.46, 93.62, 101.00, 101.05 (C=C), 123.98, 124.05, 124.14, 128.21, 130.52, 133.99, 134.89, 134.91, 134.95 (aromatic CH), 121.55, 121.56, 121.74, 132.00, 137.98, 138.85 and 138.93 (aromatic quaternary C). ²⁹Si NMR (CDCl₃): δ –47.79. FAB MS: $m/z \ 1002 \ (M^+)$. UV/VIS (CH₂Cl₂): $\lambda_{max}/nm \ (\varepsilon \times 10^4 \ dm^3)$ mol⁻¹ cm⁻¹) 230 (2.9), 260 (1.5) and 370 (7.2). Emission (CH₂Cl₂, $\lambda_{\text{excitation}} = 370 \text{ nm}$): 412 nm. Calcd for $C_{60}H_{34}Si_2S_6$: C, 71.82; H, 3.42. Found: C, 71.45; H, 3.21%.

HC=CRC=CSi(Ph)₂C=CRC=CH, 6a, and HC=CRC=C- $Si(Ph)_2C \equiv CRC \equiv CSi(Ph)_2C \equiv CRC \equiv CH$, 6b (R = 9,10-anthrylene). These anthryl-substituted oligoalkynes were similarly synthesised as described for 4a and 4b from 9,10-diethynylanthracene (288 mg, 1.27 mmol). The resulting brown-yellow suspension was then purified by silica TLC separation, eluting with hexane-CH₂Cl₂ (3 : 1, v/v) to give three major yellow bands identified as 9,10-diethynylanthracene ($R_{\rm f} = 0.73, 72 \text{ mg}$, 25%), **6a** ($R_{\rm f} = 0.54$) and **6b** ($R_{\rm f} = 0.44$). Further purification of the desired products 6a and 6b was accomplished by another TLC separation using the same solvent mixture, followed by recrystallisation to afford orange-yellow solids of 6a and 6b in 27 (109 mg) and 10% (44 mg) yield, respectively. 6a: m.p.: 155–156 °C (dec.). IR (KBr): 3303 ($v_{\equiv CH}$) and 2131 cm⁻¹($v_{C\equiv C}$). ¹H NMR (CDCl₃): δ 4.10 (s, 2H, C=CH), 7.50–7.56 (m, 4H, anthryl), 7.57-7.67 (m, 10H, Ph), 8.09-8.20 (m, 4H, anthryl), 8.57-8.67 (m, 4H, anthryl) and 8.69-8.79 (m, 4H, anthryl). ¹³C-{¹H} NMR (CDCl₃): δ 90.24 (C=CH), 80.18, 101.26, 105.60 (C=C), 126.98, 127.02, 127.08, 127.30, 128.32, 130.50, 135.01 (aromatic CH), 117.74, 118.34, 127.66, 132.35 and 132.62 (aromatic quaternary C). ²⁹Si NMR (CDCl₃): δ –47.40. FAB MS: m/z 632 (M⁺). UV/VIS (CH₂Cl₂): λ_{max}/nm ($\varepsilon \times 10^4$ dm³ mol⁻¹ cm⁻¹) 228 (3.1), 270 (11.7), 390 (1.3), 412 (2.6) and 438 (3.4). Emission (CH₂Cl₂, $\lambda_{\text{excitation}} = 390$ nm): 436 and 480 nm. Calcd for C48H28Si: C, 91.10; H, 4.46. Found: C, 90.84; H, 4.28%. **6b**: m.p.: 96–98 °C (dec.). IR (KBr): 3290 ($v_{\equiv CH}$) and 2130 cm⁻¹($v_{C=C}$). ¹H NMR (CDCl₃): δ 4.09 (s, 2H, C=CH), 7.47-7.55 (m, 4H, anthryl), 7.56-7.72 (m, 20H, Ph), 8.06-8.23 (m, 8H, anthryl), 8.57–8.65 (m, 4H, anthryl) and 8.69–8.83 (m, 8H, anthryl). $^{13}C-{^{1}H}$ NMR (CDCl₃): δ 90.24 (C=CH), 80.17, 101.20, 101.74, 105.55, 105.65 (C=C), 126.98, 127.02, 127.07, 127.30, 127.38, 128.32, 130.52, 135.01, 135.16 (aromatic CH), 117.70, 118.34, 127.16, 130.78, 132.34, 132.63 and 132.65 (aromatic quaternary C). ²⁹Si NMR (CDCl₃): δ –47.41. FAB MS: m/z 1040 (M⁺). UV/VIS (CH₂Cl₂): λ_{max}/nm ($\varepsilon \times 10^4$ dm⁴ mol⁻¹ cm⁻¹) 228 (6.4), 270 (16.7), 391 (1.6), 413 (3.1), 423 (2.9), 438 (3.6) and 450 (3.6). Emission (CH₂Cl₂, $\lambda_{\text{excitation}} = 413$ nm): 454 and 484 nm. Calcd for C₇₈H₄₆Si₂: C, 90.14; H, 4.46. Found: C, 89.85; H, 4.14%.

Table 2 Summary of crystal structure data for compound 4b

Empirical formula	C54H34Si2
M	738.99
Crystal system	Triclinic
Space group	$P\overline{1}$
a/Å	8.0001(7)
b/Å	9.4959(9)
c/Å	14.769(1)
$a/^{\circ}$	80.960(2)
$\beta/^{\circ}$	74.773(2)
γ/°	82.454(2)
U/A^3	1064.4(2)
Z	1
$\mu (Mo-K\alpha)/mm^{-1}$	0.119
No. reflections collected	6216
Unique reflections	4519
R _{int}	0.0188
Observed reflections $[I > 2\sigma(I)]$	4519
R_1	0.0583
$wR_2 \left[I > 2\sigma(I) \right]$	0.1741
R_1	0.0695
wR_2 (all data)	0.1890
$R_1 = \sum F_o - F_c / \sum F_o , wR_2 = [\sum w(F_o^2 - F_c^2)^2 / \sum w(F_o^2 - F_o^2)^2 / \sum w$	$\sum w F_{\rm o}^2 ^2]^{1/2}.$

Crystallography

Colourless crystals of 4b suitable for X-ray diffraction analysis were grown by evaporation of its solution in a hexane-CH₂Cl₂ mixture. Geometric and intensity data were collected using graphite-monochromated Mo-K α radiation ($\lambda = 0.71073$ Å) on a Bruker AXS SMART CCD area detector. The collected frames were processed with the software SAINT⁵¹ and an absorption correction was applied (SADABS⁵²) to the collected reflections. The structure was solved by direct methods (SHELXTL⁵³) in conjunction with standard difference Fourier techniques and subsequently refined by full-matrix leastsquares analyses. All non-hydrogen atoms were assigned with anisotropic displacement parameters. Hydrogen atoms were generated in their idealised positions and allowed to ride on the respective carbon atoms. Crystallographic and other experimental details are collected in Table 2.

177961. CCDC reference number See http:// www.rsc.org/suppdata/nj/b1/b108510g for crystallographic data in CIF or other electronic format.

Acknowledgements

We thank the Hong Kong Research Grants Council (HKBU 2048/97P) and the Hong Kong Baptist University (FRG/98-99/II-77) for financial support.

References

- 1 R. J. P. Corriu, Angew. Chem., Int. Ed., 2000, 39, 1376, and references cited therein.
- K. Tamao, M. Uchida, T. Izumizawa, K. Furukawa and 2 S. Yamaguchi, J. Am. Chem. Soc., 1996, 118, 11974.
- S. Yamaguchi, K. Iimura and K. Tamao, Chem. Lett., 1998, 89. 3
- F. Diederich, Chem. Commun., 2001, 219. 4
- T. Matsuo, K. Uchida and A. Sekiguchi, Chem. Commun., 1999, 5 1799
- 6 R. Gleiter, W. Schäfer and H. Sakurai, J. Am. Chem. Soc., 1985, 107, 3046, and references cited therein.
- 7 U. Salzner, J. B. Lagowski, P. G. Pickup and R. A. Poirier, Synth. Met., 1998, 96, 177
- M. Ishikawa and J. Ohshita, in Handbook of Organic Conductive 8 Molecules and Polymers, ed. H. S. Nalwa, Wiley, New York, 1997, vol. 2, ch. 15, p. 685.
- 9 A. Adachi, S. A. Manhart, K. Okita, J. Kido, J. Ohshita and A. Kunai, Synth. Met., 1997, 91, 333.

- 10 A. Adachi, J. Ohshita, T. Ohno, A. Kunai, SView Mtalhalphline K. Okita and J. Kido, Appl. Organomet. Chem., 1999, 13, 859
- 11 S. A. Manhart, A. Adachi, K. Sakamaki, K. Okita, J. Ohshita, T. Ohno, T. Hamaguchi, A. Kunai and J. Kido, J. Organomet. Chem., 1999, 592, 52.
- S. Ijadi-Maghsoodi and T. J. Barton, Macromolecules, 1990, 23, 12 4485
- 13 M. Itoh, M. Mitsuzaka, K. Iwata and K. Inoue, Macromolecules, 1997, 30, 694.
- 14 J. Ohshita, A. Shinpo and A. Kunai, Macromolecules, 1999, 38, 5998
- 15 M. Ishikawa and K. Nate, in Inorganic and Organometallic Polymers, eds. M. Zeldin, K. J. Wynne and H. R. Allcock, ACS Symposium Series 360, ACS, Washington, DC, 1988, ch. 16.
- 16 J. Ohshita and M. Ishikawa, in *Polymeric Materials Encyclopedia*, ed. J. C. Salamone, CRC Press, New York, 1996, pp. 892 and references therein.
- M. Birot, J.-P. Pillot and J. Dunoguès, Chem. Rev., 1995, 95, 1443, and references therein.
- 18 H. Sakurai, H. Sugiyama and M. Kira, J. Phys. Chem., 1990, 94, 1837
- 19 H. Sakurai, J. Organomet. Chem., 1980, 200, 261.
- J. Yao and D. Y. Son, Organometallics, 1999, 18, 1736. 20
- M. Kira and S. Tokura, Organometallics, 1997, 16, 1100. 21
- F. Garten, A. Hilberer, F. Cacialli, Y. van Dam, B. Schlatmann, 22 R. H. Friend, T. M. Krapwijk and G. Hadziioannou, Adv. Mater., 1997, 9, 127
- 23 E. R. Silcoff and T. Sheradsky, Macromolecules, 1998, 31, 9116.
- K. Yoshino, A. Fujii, H. Nakayama, S. Lee, A. Naka and 24 M. Ishikawa, J. Appl. Phys., 1999, 85, 414.
- 25 M. Kakimoto, H. Kashihara, T. Kashiwagi, T. Takiguchi, J. Ohshita and M. Ishikawa, Macromolecules, 1997, 30, 7816.
- A. Kunai, T. Ueda, K. Horata, E. Toyoda, I. Nagamoto, 26 J. Ohshita and M. Ishikawa, Organometallics, 1996, 15, 2000.
- 27 K. Boyer-Elma, F. H. Carré, R. J.-P. Corriu and W. E. Douglas, J. Chem. Soc., Chem. Commun., 1995, 1, 725.
- 28 W. E. Douglas, D. M. H. Guy, A. K. Kar and C. Wang, Chem. Commun., 1998, 2125.
- 29 U. Krüerke, J. Organomet. Chem., 1970, 21, 83.
- H. Li, D. R. Powell, T. K. Firman and R. West, Macromolecules, 30 1998, 31, 1093.
- K. Müllen and G. Wegner, Electronic Materials: The Oligomer 31 Approach, Wiley-VCH, Weinheim, 1998.
- 32 P. F. van Hutten, V. V. Krasnikov and G. Hadziioannou, Acc. Chem. Res., 1999, 32, 257.
- S. Wang, W. J. Oldham, Jr., R. A. Hudack, Jr. and G. C. Bazan, 33 J. Am. Chem. Soc., 2000, 122, 5695 and references cited therein.
- J. Ohshita, A. Takata, A. Kunai, M. Kakimoto, Y. Harima, 34 Y. Kunugi and K. Yamashita, J. Organomet. Chem., 2000, 611, 537.
- 35 M. Ishikawa, T. Hatano, Y. Hasegawa, T. Horio, A. Kunai, A. Miyai, T. Ishida, T. Tsukihara, T. Yamanaka, T. Koike and J. Shioya, Organometallics, 1992, 11, 1604.
- 36 R. J. P. Corriu, W. E. Douglas, Z.-X. Yang, F. Garnier and A. Yassar, J. Organomet. Chem., 1991, 417, C50.
- 37 M. Ishikawa, Y. Hasegawa, A. Kunai and T. Yamanaka, J. Organomet. Chem., 1990, **381**, C51. A. W. M. Lee, A. B. W. Yeung, M. S. M. Yuen, H. Zhang,
- 38 X. Zhao and W. Y. Wong, Chem. Commun., 2000, 75.
- H. Zhang, A. W. M. Lee, W.-Y. Wong and M. S. M. Yuen, 39 J. Chem. Soc., Dalton Trans., 2000, 3675.
- 40 A. W. M. Lee and W. H. Chan, Top. Curr. Chem., 1997, 190, 103.
- 41 S. Takahashi, Y. Kuroyama, K. Sonogashira and N. Hagihara, Synthesis, 1980, 627.
- W.-Y. Wong, K.-H. Choi, G.-L. Lu and J.-X. Shi, Macromol. 42 Rapid Commun., 2001, 22, 461.
- J. Lewis, N. J. Long, P. R. Raithby, G. P. Shields, W.-Y. Wong 43 and M. Younus, J. Chem. Soc., Dalton Trans., 1997, 4283.
- 44 M. S. Khan, A. K. Kakkar, N. J. Long, J. Lewis, P. Raithby, P. Nguyen, T. B. Marder, F. Wittmann and R. H. Friend, J. Mater. Chem., 1994, 4, 1227.
- R. J. P. Corriu, W. E. Douglas, Z.-X. Yang, Y. Karakus, G. H. 45 Cross and D. Bloor, J. Organomet. Chem., 1993, 455, 69.
- J. B. Birks, Photophysics of Aromatic Molecules, Wiley, London, 46 1970
- 47 A. P. Davey, S. Elliott, O. O'Connor and W. Blau, J. Chem. Soc., Chem. Commun., 1995, 1433.

- 48 J. P. Glusker, M. Lewis and M. Rossi, in Crystal Structure Analysis for Chemists and Biologists, VCH Publishers, New York, 1994, ch. 13, p. 548.M. Unno, T. Saito and H. Matsumoto, *Chem. Lett.*, 1999,
- 49 1235.
- 50 M. Younus, Ph.D. Thesis, University of Cambridge, 1996.
- SAINT, Reference Manual, Siemens Energy and WawohttitionOnline Madison, WI, 1994–1996.
 G. M. Sheldrick, SADABS, Empirical Absorption Correction Pro-gram, University of Göttingen, Germany, 1997.
 G. M. Sheldrick, SHELXTLTM, Reference Manual, version 5.1, Siemens, Madison, WI, 1997.