View Article Online View Journal

# Journal of Materials Chemistry A

## Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: B. Saglio, M. Mura, M. Massetti, F. Scuratti, D. Beretta, X. Jiao, C. R. McNeill, M. Sommer, A. Famulari, G. lanzani, M. Caironi and C. BERTARELLI, *J. Mater. Chem. A*, 2018, DOI: 10.1039/C8TA04901G.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the **author guidelines**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the ethical guidelines, outlined in our <u>author and reviewer resource centre</u>, still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/materials-a

### ARTICLE

Received 00th January 20xx, Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/



B. Saglio<sup>ab</sup>, M. Mura<sup>a</sup>, M. Massetti<sup>bc</sup>, F. Scuratti<sup>bd</sup>, D. Beretta<sup>b</sup>, X. Jiao<sup>e</sup>, C. R. McNeill<sup>e</sup>, M. Sommer<sup>f</sup>, A. Famulari<sup>a</sup>, G. Lanzani<sup>bc</sup>, M. Caironi<sup>b\*</sup> and C. Bertarelli<sup>ab\*</sup>

Doped polymer semiconductors are actively studied for opto- and micro-electronic applications including thermoelectric generators, where a high electrical conductivity is a key factor. In general, n-type doping is more challenging to achieve than p-type doping. Here we study n-type doping of a commonly used electron transporting naphthalene-diimide bithiophene copolymer with a series of air-stable and solution-processable benzimidazole dopants. To understand the role of dopant structure on miscibility and the resulting conductivity, benzimidazoles with different linear and branched alkyl substituents were synthesized, and their doping efficacy compared through combined morphological, electrical and thermoelectric characterization. We observe a clear dependence of the nature of the alkyl substituent on dopant intercalation into the semicrystalline morphology. By increasing the length or the steric hindrance of the alkyl substituents, the miscibility between dopant and copolymer is enhanced leading to optimized electrical conductivity.

#### Introduction

Published on 19 July 2018. Downloaded by University of Reading on 7/19/2018 1:08:55 PM

Conjugated polymers have found application in various electronic devices, including transistors and circuits,<sup>1–3</sup> solar cells<sup>4,5</sup> and light emitting diodes.<sup>6,7</sup> Charge transport in polymer films is largely governed by the polymer chemical structure and solid-state packing of interacting conjugated segments<sup>8</sup>. Research in this field has led to a rationalization of the molecular design and a better understanding of the charge transport mechanism. Through the establishment of structure-property relationships,<sup>9–11</sup> tailored structures and optimized processing have led to enhanced electronic performance.

For most electronic and opto-electronic devices, it is desirable to tune the electrical conductivity ( $\sigma$ ) through doping in order to enable optimized devices. More recently, the increased interest in polymer thermoelectrics<sup>12,13</sup> as cost-effective waste heat energy converters has re-activated research in molecular doping to achieve high and controllable values of  $\sigma$ . Doping of conjugated polymers is typically achieved by the addition of molecular dopants which produce an increase in the number of free charge carriers and hence of  $\sigma$ .



N-type doping of polyacetylene was first performed under inert atmosphere using metal complexes, such as sodium and potassium naphthalene,19 with elemental dopants such as Na, K, Li and Cs,<sup>20-23</sup> or alternatively, inorganic salts as Li<sub>2</sub>CO<sub>3</sub>, Na<sub>2</sub>CO<sub>3</sub>, K<sub>2</sub>CO<sub>3</sub>, Cs<sub>2</sub>CO<sub>3</sub>, and LiNH<sub>2</sub><sup>24-28</sup> have also been proposed. However, such doping could only be carried out by evaporation at high temperatures, which is less attractive than solutionbased techniques; moreover, inorganic ions often affect the device operation lifetime since they diffuse through the organic layer. Aromatic donor compounds, e.g. TTF<sup>29,30</sup> or BEDT-TTF,<sup>31</sup> form charge transfer complexes and can be processed from solution, while being unstable in air. This last issue can be overcome by stable precursors, which can be in situ converted into the dopant upon thermal or light activation, e.g. 1Hbenzimidazole derivatives such as DMBI-POH<sup>32</sup> or the organic salt o-MeO-DMBI-I<sup>33</sup>. The latter can only be processed by evaporation.

TA04901C

<sup>&</sup>lt;sup>a.</sup> Dipartimento di Chimica, Materiali e Ing. Chimica "G. Natta , Politecnico di Milano, Piazza L. Da Vinci 32, 20133 Milano, Italy

<sup>&</sup>lt;sup>b.</sup> Center for Nano Science and Technology @PoliMi, Istituto Italiano di Tecnologia, Via Pascoli 70/3, 20133 Milano, Italy \*Email - chiara.bertarelli@polimi.it

C Dipartimento di Fisica, Politecnico di Milano, Piazza L. Da Vinci 32, 20133 Milano, Italy

<sup>&</sup>lt;sup>d</sup> Dipartimento di Elettronica, Informazione e Bioingegneria, Politecnico di Milano, Piazza L. Da Vinci 32, 20133 Milano, Italy

e- Department of Materials Science and Engineering, Monash University Wellington Road, Clayton, Victoria, 3800, Australia.

<sup>&</sup>lt;sup>f.</sup> Chemnitz University of Technology, Chemistry Department, Strasse der Nationen 62, 09111 Chemnitz, Germany.

In 2010, Bao et al. first reported n-type dopant 1,3-dimethyl-2-2-phenyl-2,3-dihydro-1*H*-benzoimidazole (DMBI) – which had been previously reported as a reagent for the reduction of organic compounds<sup>34</sup> – as an effective, solution processable and air-stable dopant to significantly increase the conductivity of phenyl-C<sub>61</sub>-butyric acid methyl ester (PCBM).<sup>35</sup> Later, Schlitz et al.<sup>36</sup> used the same compound to dope poly(N,N'-bis-2octyldodecylnaphthalene-1,4,5,8-bis-dicarboximide-2,6-diyl-

alt-5,5'-2,2'-bithiophene) P(NDI2OD-T2), obtaining an increase of the electrical conductivity of about five orders of magnitude, reaching  $5 \times 10^{-4}$  S/cm. In the same study a poor miscibility of the dopant and P(NDI2OD-T2) was reported, *i.e.* phase segregation occurred at high dopant concentration, limiting the effectiveness of the doping and the maximum conductivity that could be achieved. Another limitation relates to the strong charge localization in the polymer, as evidenced by Fabiano et al.<sup>37</sup>

Here we address the miscibility issue by studying the effect of the benzimidazole alkyl substituents on the doping efficiency. With electronic effects of the alkyl substituents on electron transfer being negligible, we have designed and synthesized a series of 1-H benzimidazoles in which the N-alkyl substituents have been systematically varied (Fig. 1). This strategy is aimed at increasing dopant solubility and miscibility with P(NDI2OD-T2) through an enhanced interaction with its alkyl side chains. In contrast to recent work that has focused on dopant/

copolymer miscibility by controlling backbone backbone curvature<sup>38</sup> or varying chain length or chain branching,<sup>39,40</sup> we show here that a tailored modification of the dopant structure towards longer and bulkier alkyl substituents has a strong effect miscibility and doping efficiency.

#### Experimental

Published on 19 July 2018. Downloaded by University of Reading on 7/19/2018 1:08:55 PM

ARTICLE

#### Dopant synthesis

Unless otherwise stated, all chemicals and solvents were purchased from Sigma Aldrich and used as received. Reactions of air- and water-sensitive reagents and intermediates were carried out in dried glassware under argon. Thin layer chromatography was performed by using silica gel on aluminum foil. NMR spectra were acquired on a Bruker ARX400. Mass spectroscopy was carried out with a Bruker Esquire 3000 plus.



Fig. 1 Molecular structure of N-alkyl substituted 1H- benzimidazoles.

**4-Bromo-N,N-dipropylaniline (2d):** N,N-Dipropylaniline (1, g, 5,64 mmol, 1 eq.) was dissolved in 17 ml dry DMF, and the solution was stirred at -18°C under argon. NBS (1.05 g, 5.92 mmol, 1.05 eq.), dissolved in 5 ml dry DMF, was dropwise added over a period of 1.5 hours. Then the reaction mixture was stirred at -18 °C for 3.5 hours and at room temperature overnight. The reaction mixture was separated between dichloromethane (DCM)/water, the water phase extracted with DCM, the DCM layers combined, dried over Na<sub>2</sub>SO<sub>4</sub> and concentrated under reduced pressure. A suspension of the residue in Et<sub>2</sub>O was filtered, and the filtrate was washed with 3M NaOH aqueous solution and water, dried over Na<sub>2</sub>SO<sub>4</sub>, and concentrated under reduced pressure. The crude product was purified by flash chromatography with silica gel and hexane:ethyl acetate (9:1) to give the product as an orange oil in 83% yield.

<sup>1</sup>H NMR (d6-benzene, 400MHz): ppm 7.29 (dt, J=9.17 Hz, J=3.42 Hz, J=2.26 Hz, 2H H-Ph), 6.27 (dt, J=9.17 Hz, J=3.42 Hz, J=2.26, 2H, H-Ph), 2.79 (t, J=7.58, 4H, N-CH<sub>2</sub>), 1.29 (m, J=7.58, J=7.40, 4H, -CH<sub>2</sub>-), 0.65 (t, J=7.40, 6H, CH<sub>3</sub>).

**4-Bromo-N,N-diisopropylaniline (2e):** N,N-Diisopropylaniline (546 mg, 3.08 mmol, 1 eq.) was dissolved in 3 ml anhydrous acetonitrile under argon. NBS (548mg, 3.08 mmol, 1 eq.), dissolved in 3ml anhydrous acetonitrile, was added dropwise at 0 °C over 30 minutes. The reaction mixture was stirred at 0 °C for 1 hour and then at room temperature overnight. Water was added, the reaction mixture was extracted with hexane, the organic phase dried over Na<sub>2</sub>SO<sub>4</sub> and the solvent removed under reduced pressure. The crude product was purified by flash chromatography with hexane:ethyl acetate (8:2) as eluent, obtaining the pure product as an orange oil with 48% yield. <sup>1</sup>H NMR (d<sub>6</sub>-benzene, 400MHz): ppm 7.25 (dt, J=9.17 Hz, J=3.42 Hz, J=2.26, 2H *H*-Ph), 6.52 (dt, J=9.17 Hz, J=3.42 Hz, J=2.26Hz, 2H, *H*-Ph), 3.33 (sestet, J=6.72 Hz, 2H, N-*CH*), 0.89 (d, J=6.72 Hz, 12H, *-CH*<sub>3</sub>).

**4-Bromo-***N*,*N*-**diisobutylaniline (2f):** The reaction was carried out according to the procedure of **2e**. The crude product was purified by flash chromatography using hexane:chloroform 9:1 as eluent to give 2f as an orange oil in 21% yield. <sup>1</sup>H NMR (d<sub>6</sub>-benzene, 400MHz): ppm 7.28 (m, J=9.17 Hz, J=3.42 Hz, J=2.26, 2H *H*-Ph), 6.32 (m, J=9.17 Hz, J=3.42 Hz, J=2.26, 2H, *H*-Ph), 2.79 (d, J=7.34 Hz, 4H, N-*CH*<sub>2</sub>), 1.84 (m, J=6.72 Hz, 2H, -*CH*), 0.68 (d, J=6.72 Hz, 12H, -*CH*<sub>3</sub>).

**4-(Dipropylamino)benzaldehyde (3d):** Compound 2d (1.20 g, 4.68 mmol, 1 eq.) was dissolved in 9 ml anhydrous THF and the solution was cooled to -78° C under an argon atmosphere. 2.5M n-BuLi (in n-hexane, 4.77 mmol, 1.02 eq.) was added dropwise and the reaction mixture was stirred for 30 minutes at the same temperature. Anhydrous DMF (9.4 ml) was added and the solution was kept stirring at -78° C for 30 minutes. Then the mixture was warmed up to room temperature, quenched with 70 ml of water and extracted with DCM (3x). The combined organic layers were dried with Na<sub>2</sub>SO<sub>4</sub>. After solvent removal, the crude product was purified by flash chromatography with

#### ARTICLE

View Article Online



Fig. 2 Synthetic routes for the realization of N-alkyl substituted 1H- benzimidazoles.

hexane:ethylacetate (8:2) to give a yellow oil in 54% yield.  $^1\mathrm{H}$ NMR (d<sub>6</sub>-benzene, 400MHz): ppm 9.85 (s, 1H, CHO) 7.70 (d, J=8.92 Hz 2H H-Ph), 6.35 (d, J=8.92 Hz, 2H, H-Ph), 2.77 (t, J=7.64 Hz, 4H, N-CH<sub>2</sub>), 1.24 (m, J=7.46 Hz, J=7.70 Hz, 4H, CH<sub>2</sub>-CH<sub>3</sub>), 0.60 (t, J=7.40 Hz 6H, CH<sub>2</sub>-CH<sub>3</sub>).

4-(Diisopropylamino)benzaldehyde (3e): The reaction was carried out according to the procedure of 3d. <sup>1</sup>H NMR (d<sub>6</sub>benzene, 400MHz): ppm 9.60 (s, 1H, CHO) 7.56 (d, J=8.07 Hz, 2H H-Ph), 6.73 (d, J=8.07 Hz, 2H, H-Ph), 3.89 (m, J=6.48, J=6.66 Hz, J=6.91 Hz 2H, N-CH), 1.23 (d, J=6.72 Hz, 12H, CH<sub>2</sub>-CH<sub>3</sub>). (Yield: 50%).

4-(Isobutyl(isopropyl)amino)benzaldehyde (3f): The reaction was carried out according to the procedure of 3d. <sup>1</sup>H NMR (d<sub>6</sub>benzene, 400MHz): ppm 9.60 (s, 1H, CHO) 7.59 (d, J=8.92 Hz 2H H-Ph), 6.59 (d, J=8.92 Hz, 2H, H-Ph), 3.14 (d, J=7.34 Hz, 4H, N-*CH*<sub>2</sub>), 2.00 (m, J=6.85 Hz, J=6.78 Hz, 2H, CH<sub>2</sub>-*CH*), 0.81 (d, J=6.60 Hz, 12H, CH-CH<sub>3</sub>). (Yield: 67%).

#### 4-(1,3-Dimethyl-2,3-dihydro-1H-benzo[d]imidazol-2-yl)-N,N-

dimethylaniline (DMBI): The synthetic procedure of this compound was previously reported by Naab.41 N,N'-dimethylo-phenylenediamine (1.00 mmol, 1 eq.), N,N'-dimethyl-1,2phenylenediamine (1.00 mmol, 1 eq.) and a drop of glacial acetic acid were dissolved in 2 ml of methanol. The mixture was sonicated for 5 hours, followed by storage in the fridge overnight. The precipitate was filtered and washed with methanol to obtain DMBI as white powder in 26% yield. <sup>1</sup>H NMR (d6-DMSO, 400MHz): ppm 7.33 (d, J=8.74 Hz, 2H, H-Ph), 5.25 (d, J=8.74 Hz, 2H, H-Ph), 6.58 (m, J=3.18 Hz, J=2.01 Hz, 2H, H-Ph), 6.39 (m, J=3.18, J=2.20, 2H, H-Ph), 4.73 (s, 1H, N-H-N), 2.93 (s, 6H, N-CH3), 2.44 (s, 6H, N-CH3).

#### 4-(1,3-Dimethyl-2,3-dihydro-1H-benzo[d]imidazol-2-yl)-N,Ndiethylaniline (DEtBI): The reaction was carried out according to the procedure of DMBI. <sup>1</sup>H NMR (d<sub>6</sub>-DMSO, 400MHz): ppm 7.29 (d, J=8.74 Hz, 2H, H-Ph), 6.69 (d, J=8.74 Hz, 2H, H-Ph), 6.58

(m, J=3.18 Hz, J=2.01 Hz, 2H, H-Ph), 6.39 (m, J=3.18 Hz, J=2.01 Hz, 2H, H-Ph), 4.71 (s, 1H, N-H-N), 3.35 (m, J=7.27 Hz, J=7.95 Hz, 4H, N-CH<sub>2</sub>), 2.45 (s, 6H, N-CH<sub>3</sub>), 1.11 (t, J=6.85 Hz, 6H, CH<sub>2</sub>-CH<sub>3</sub>). (Yield: 42%).

#### 4-(1,3-Dimethyl-2,3-dihydro-1H-benzo[d]imidazol-2-yl)-N,N-

dipropylaniline (DPrBI): The reaction was carried out according to the procedure of DMBI. <sup>1</sup>H NMR (d<sub>6</sub>-DMSO, 400MHz): ppm 7.27 (d, J=8.74 Hz, 2H, H-Ph), 6.65 (d, J=8.74 Hz, 2H, H-Ph), 6.58 (m, J=3.18 Hz, J=2.01 Hz, 2H, H-Ph), 6.39 (m, J=3.18 Hz, J=2.01 Hz, 2H, H-Ph), 4.67 (s, 1H, N-H-N), 3.24 (m, J=7.46 Hz, J=7,58, 4H, N-CH<sub>2</sub>), 2.44 (s, 6H, N-CH<sub>3</sub>), 1.54 (m, J=7.58 Hz, 4H, CH<sub>2</sub>-CH<sub>2</sub>-CH<sub>3</sub>), 0.89 (m, J=9.00 Hz, J=7.40 Hz, 6H, CH<sub>2</sub>-*CH*<sub>3</sub>). (Yield: 17%).

#### N,N-Dibutyl-4-(1,3-dimethyl-2,3-dihydro-1H-

benzo[d]imidazol-2-yl)aniline (DBuBI): The reaction was carried out according to the procedure of DMBI. <sup>1</sup>H NMR (d<sub>6</sub>-DMSO, 400MHz): ppm 7.28 (d, J=8.74 Hz, 2H, H-Ph) 6.66 (d, J=8.74 Hz, 2H, H-Ph), 6.58 (m, 3.18 Hz, J=2.01 Hz, 2H, H-Ph), 6.39 (m, J=3.18Hz, J=2.01 Hz, 2H, H-Ph), 4.70 (s, 1H, N-H-N), 3.27 (q, J=7.24 Hz, 4H, N-CH2), 2.45 (s, 6H, N-CH3), 1.52 (m, J=8.07 Hz, J=6.91 Hz, 4H, CH<sub>2</sub>-CH<sub>2</sub>-CH<sub>2</sub>), 1.34 (m, J=7.58 Hz, J=7.35 Hz, 4H, CH<sub>2</sub>-CH<sub>2</sub>-CH<sub>2</sub>), 0.93 (t, J=7.34 Hz, 6H, CH<sub>2</sub>-CH<sub>3</sub>). (Yield: 31%).

#### 4-(1,3-Dimethyl-2,3-dihydro-1H-benzo[d]imidazol-2-yl)-N,N-

diisopropylaniline (DiPrBI): The reaction was carried out according to the procedure of DMBI. <sup>1</sup>H NMR (d<sub>6</sub>-DMSO, 400MHz): ppm 7.27 (d, J=8.74 Hz, 2H, H-Ph), 6.84 (d, J=8.74 Hz, 2H, H-Ph), 6.59 (m, J=3.18 Hz, J=2.01 Hz, 2H, H-Ph), 6.40 (m, J=3.18 Hz, J=2.01 Hz, 2H, H-Ph), 4.69 (s, 1H, N-H-N), 3.84 (m, J=6.78 Hz, J=6.85, 2H, N-CH), 2.45 (s, 6H, N-CH<sub>3</sub>), 1.21 (d, J=6.85 Hz, 12H, CH-CH<sub>3</sub>). (Yield: 31%).

#### 4-(1,3-Dimethyl-2,3-dihydro-1H-benzo[d]imidazol-2-yl)-N,Ndiisobutylaniline (DiBuBI): The reaction was carried out according to the procedure of DMBI. <sup>1</sup>H NMR (d<sub>6</sub>-DMSO, 400MHz): ppm 7.26 (d, J=8.74 Hz, 2H, H-Ph), 6.67 (d, J=8.74 Hz, 2H, H-Ph), 6.58 (m, J=3.18 Hz, J=2.01 Hz, 2H, H-Ph), 6.39 (m,

#### ARTICLE

J=3.18 Hz, J=2.01 Hz, 2H, *H*-Ph), 4.67 (s, 1H, N-*H*-N), 3.16 (d, J=7.09 Hz, 4H, N-*CH*<sub>2</sub>), 2.44 (s, 6H, N-*CH*<sub>3</sub>), 1.99 (m, J=6.72 Hz, J=6.97 Hz, 2H, N-CH<sub>2</sub>-*CH*) 0.87 (d, J=6.60 Hz, 12H, CH-*CH*<sub>3</sub>). (Yield: 55%).

Sample preparation and doping procedure. The samples were prepared starting from a solution of P(NDI2OD-T2) (Polyera ActivInk N2200,  $M_n$  = 29 kDa, purchased from Flexterra Inc.), in 1,2-dichlorobenzene (DCB) that was heated to 80 °C and stirred for 1 hour. The concentration of the solutions used for films for variable temperature electrical conductivity, room temperature conductivity and Seebeck coefficient measurements were 5 mg/ml, 10 mg/ml and 20 mg/ml, respectively. The solution was filtered with a 0.45 µm pore size polytetrafluoroethylene (PTFE) filter. The dopant was dissolved in DCB at a concentration of 10 mg/ml. Aliquots of dopant were added to 100 µl polymer solution and mixed at room temperature. Dopant concentrations between 10 % to 50 % were tested. Except for Seebeck coefficient measurements (see below), films were spin coated in an  $N_2$  glovebox at 1000 rpm for 90 s and then at 3000 rpm for 10 s onto glass substrates, previously cleaned with acetone and iso-propanol and treated with an oxygen plasma for 10 minutes. Films were annealed on a hot plate at ≈150 °C for six hours in N<sub>2</sub> glovebox.

Electrical conductivity measurements. Two 50 nm thick gold contacts were evaporated (MB-ProVap-3) on the films leading to devices with an inter-electrode distance of 7 mm and width of 12 mm. Prior to measurement, samples were annealed at  $\approx$ 80 °C for 10 minutes under N<sub>2</sub>. Measurements were taken under N<sub>2</sub> atmosphere and at ambient temperature with a 2-point method with a Keysight Technologies semiconductor parameter analyzer (SPA).

#### Seebeck coefficient measurements

The polymer/dopant solutions were deposited by spin coating (1000 rpm for 60 s) onto 2 cm x 1 cm glass substrates and then annealed at 120 °C for 30 minutes in a nitrogen glovebox. The Seebeck measurements were carried out in vacuum at 90 °C, after an overnight annealing treatment at 130 °C in order to avoid any thermal effect during the measurement, using the system described in *Beretta et al.*<sup>42</sup>

Temperature-dependentelectricalconductivitymeasurements.Four 50 nm thick gold contacts wereevaporated on the films leading to devices with an inter-electrodes distance of 3 mm and width of 5 mm. Prior to four-point conductivity measurement, samples were annealed at~150 °C overnight in vacuum. The four-point probesmeasurements were taken in vacuum in the temperature rangebetween 200 K and 300 K, with a  $\Delta T$  of 10 K between each step.Downward and upward scans were performed in order to checkthe absence of hysteresis during the measurements.

**Atomic force microscopy.** Sample preparation was identical as for the electrical characterization. Topographies were

measured with Agilent 5500 Atomic Force Microscope, working in Acoustic Mode. All images are presented W社代码 33种名 colour scale.

**Grazing incidence wide angle X-ray scattering.** GIWAXS measurements were performed at the SAXS/WAXS beamline at the Australian Synchrotron<sup>43</sup>. 11 keV photons were used with scattering patterns recorded on a Dectris Pilatus 1M detector. Images shown were acquired at an incident angle close to the critical angle. Such images were chosen from a series of images taken with incident X-ray angle varying from 0.05° to 0.25° in steps of 0.01° with the chosen image showing the highest scattering intensity. The X-ray exposure time was 3 s such that no film damage was identified. The sample-to-detector distance was calibrated using a silver behenate sample. The results were analyzed by an altered version of the NIKA 2D<sup>44</sup> based in IgorPro.

Differential scanning calorimetry. Pristine dopants were measured on a Perkin-Elmer DSC 8500 instrument equipped with a liquid nitrogen cooling system (Perkin-Elmer CLN2) under N<sub>2</sub> at 10 K/min. Blend samples were prepared from *o*-DCB solution, thoroughly dried and placed into the heating pans. Measurements were acquired on a NETZSCH DSC 204 *F1 Phoenix*<sup>®</sup> under N<sub>2</sub> at 10 K/min.

**Thermogravimetry**. TGA was performed on a Perkin Elmer TGA 4000 between 50–650  $^{\circ}$ C under N<sub>2</sub> at 10 K min<sup>-1</sup>.

#### **Results and discussion**

The six dopant molecules synthesised are shown in Fig. 1. DMBI has been studied before and features methyl substituents. 4-(1,3-Dimethyl-2,3-dihydro-1*H*-benzo[*d*]imidazol-2-yl)-*N*,*N*-diethylaniline (DEtBI) has ethyl substituents, **4**-(1,3-dimethyl-

2,3-dihydro-1*H*-benzo[*d*]imidazol-2-yl)-*N*,*N*-dipropylaniline (DPrBI) has *n*-propyl substituents and N,N-dibutyl-4-(1,3dimethyl-2,3-dihydro-1*H*benzo[*d*]imidazol-2-yl)aniline (DBuBI) has *n*-butyl substituents. DMBI, DEtBI DMPrBI and DBuBI thus have linear chains of increasing length. In contrast, 4-(1,3dimethyl-2,3-dihydro-1*H*-benzo[*d*]imidazol-2-yl)-*N*,*N*-

diisopropylaniline (DiPrBI) and 4-(1,3-dimethyl-2,3-dihydro-1Hbenzo[d]imidazol-2-yl)-N,N-diisobutylaniline (DiBuBI) have branched alkyl substituents of different size. The general synthetic scheme consists of the ultrasound-assisted coupling between the N,N'-dimethyl-1,2-benzendiamine and the N-alkyl substituted p-aminobenzaldehyde (Fig. 2). For the synthesis of DMBI, DEtBI and DBuBI the procedure previously reported for DMBI<sup>41</sup> was followed, starting from the commercially available N,N-dialkyl aminobenzaldehydes. The products were precipitated in the reaction mixture at low temperature, separated by filtration and washed with small portions of methanol. For the synthesis of the other dopants (DPrBI, DiPrBI, DiBuBI), the starting compound was the N,N-dialkyl substituted aniline, which was first brominated in p-position with Nbromosuccinimide (NBS), lithiated with n-butyllithium and

Published on 19 July 2018. Downloaded by University of Reading on 7/19/2018 1:08:55 PM.

#### Journal Name



Fig. 3 Electrical conductivity  $\sigma$  vs. dopant concentration (from 10 to 50 %) of all N-alkyl substituted 1H- benzimidazoles synthetized.

quenching with DMF afforded the N,Ndialkylaminobenzaldehyde (Fig. 2). The resulting compound was finally coupled with N,N'-dimethyl-1,2-phenylenediamine and products (2d-f) were precipitated and separated by filtration. We have also tried to synthesize 1H-benzimidazoles with longer alkyl chains (i.e. hexyl), but we could not isolate the pure product by precipitation according to the procedure described for all the other compounds.

The temperature stability and phase transitions of the dopants were investigated using thermogravimetry (TGA) and differential scanning calorimetry (DSC). From TGA, onset temperatures for degradation under N<sub>2</sub> of ~ 200 °C can be extracted (Figure SI 1). Melting points  $T_m$  between 60 °C and 120 °C were observed for all dopants, with longer alkyl substituents leading to lower  $T_m$  values (Figures SI 2-7).

As a general procedure to test the n-doping ability of these new N-alkyl substituted 1H-benzimidazoles, aliquots of each dopant dissolved in anhydrous DCB were separately added to P(NDI2OD-T2) solutions with a dopant concentration varying from 10 to 50 wt.-%. The room temperature conductivity of thin films spin-coated as a function of dopant concentration is shown in Fig. 3. Conductivity is found to increase by orders of magnitude with respect to undoped P(NDI2OD-T2) (4.6×10<sup>-7</sup>  $\pm$ 1.7×10<sup>-7</sup> S/cm), thus indicating that all N-alkyl substituted 1Hbenzimidazoles are effective dopants. Conductivity as a function of dopant concentration follows the general trend previously observed for the case of DMBI and is similar for all dopants:  $\boldsymbol{\sigma}$  first increases with concentration, reaching a maximum in between 15 % and 30 % dopant concentration, and then decreases for higher concentrations. This decrease at high concentration was ascribed to phase segregation in the case of DMBI<sup>36</sup>. For films doped with dopants with linear alkyl chains,  $\sigma$ increases with increasing chain length. The maximum  $\sigma$  values are 1.8  $\times 10^{\text{-3}} \pm 1.9 \times 10^{\text{-4}}$  S/cm, 3.4  $\times 10^{\text{-3}} \pm 9.7 \times 10^{\text{-4}}$  S/cm, 4.0  $\times 10^{\text{-3}}$  $^3$   $\pm$  1.6×10^{\text{-4}} S/cm and 4.1×10^{\text{-3}} \pm 6.6×10^{\text{-4}} S/cm, for DMeBI, DEtBI, DPrBI and DBuBI, respectively. The maximum  $\sigma$  values for samples doped with the propyl and butyl derivatives are very close, thus suggesting that the effect of increasing the alkyl chain length is approaching a plateau. When doping P(NDI2OD-T2) with e N-alkyl-1H-benzimidazoles bearing branched chains, the highest conductivity value of  $7.2 \times 10^{-3} \pm 1.4 \times 10^{-4}$  S/cm was achieved with DiPrBI at 25 % doping, which is almost one order of magnitude higher than that obtained with DMBI. The DiBuBI



Fig. 4 Temperature dependence of electrical conductivity between 200 and 300 K for the polymer doped with three representative dopants at 20% concentration.

showed a conductivity in the same range of the dopant with *n*-butyl substituents.

We also performed measurements to determine the Seebeck coefficients ( $\alpha$ ) of three representative polymer/dopant blends, namely the reference 1H-benzimidazole with methyl (DMBI), the dopant with linear chains giving the most effecting doping (DBuBI) and the dopant with branched chains giving the most effective doping (DiPrBI). The measured values of  $\alpha$  at 363 K are always negative, as expected for a Seebeck effect dominated by electrons, with values of -44 µV/K for the DMBI-doped sample, -35 µV/K for the DBuBi-doped sample and -32 µV/K for the DiPrBi-doped sample. These values are extracted with an error bar of ± 15 µV/K, owing to the high sample electrical resistance. For the DiPrBi-doped sample which achieved the highest electrical conductivity, we also estimated the power factor (*PF*) at 363 K to be ~1.1 × 10<sup>-3</sup> µW/mK.

The temperature dependence of the electrical conductivity was measured for the same samples in order to characterize the activation energy ( $E_a$ ) of  $\sigma$  (Fig. 4). In all cases,  $\sigma$  decreases with



Fig. 5 Atomic Force Microscopy images of: a) undoped P(NDI2OD-T2) film, b) P(NDI2OD-T2) film doped with DMBI, c) P(NDI2OD-T2) film doped with DBuBI, d) P(NDI2OD-T2) film doped with DiPrBI. Dopant concentration is 20 % for all samples.

ARTICLE

#### ARTICLE

Published on 19 July 2018. Downloaded by University of Reading on 7/19/2018 1:08:55 PM

decreasing temperature, with the best fit achieved with a temperature dependence of  $\ln \sigma(T) \propto T^{-1/2}$  (see SI for details), indicating a variable range hopping (VRH) transport regime with dimensionality of d = 1 as already reported previously. <sup>37</sup> Values for  $E_a$  of ~330meV were determined for each system. Therefore, the differences in  $\sigma$  cannot be ascribed to a modification of the transport properties, *i.e.* a difference in the energetic barriers experienced by charge carriers, but rather to the number of molecules effectively active in the doping process. This evidence suggests that the different alkyl chains play a role in the polymer/dopant interaction and on the doping efficiency.

The microstructure of the different films was investigated first by acquiring the topography of the respective surfaces with AFM. Four types of exemplary samples were chosen: undoped P(NDI2OD-T2), P(NDI2OD-T2):DMBI, P(NDI2OD-T2):DBuBI and P(NDI2OD-T2):DiPrBI; in other words the blend with the lowest  $\sigma$ , the blend with the dopant with the longest linear alkyl chains and the blend with the highest  $\sigma$ , respectively. The undoped P(NDI2OD-T2) film surface shows a typical fiber-like morphology (Fig. 5). In all other cases, round features of varying number and size appear as well. In particular, the surface of P(NDI2OD-T2):DiPrBI film is similar to the undoped film, and it shows also a similar r.m.s. roughness (R<sub>rms P(NDI2OD-T2)</sub> = 0.76 nm; R<sub>rms</sub> P(NDI2OD-T2):DiPrBI = 0.86 nm). The doped sample with the lowest  $\sigma$ , instead, showed the highest surface roughness ( $R_{rms P(NDI2OD-}$ T2):DMBI = 2.55 nm), whereas the sample with longest linear alkyl chains, characterized by an intermediate  $\sigma$ , has a roughness in between the above mentioned cases.

To obtain further insights into the aggregation/crystallization behaviour of P(NDI2OD-T2) in the presence of the various ntype dopants, synchrotron-based grazing-incidence wide-angle scattering (GIWAXS)<sup>45</sup> measurements were conducted. Two of the representative 2D GIWAXS patterns are displayed in Fig. 6 a) and b). As seen from Fig. 6 a), the simultaneous appearance of in-plane (IP) (h00) and (001) peaks, along with out-of-plane (OOP) (010) peak indicates that in undoped films P(NDI2OD-T2) crystallites adopt preferentially a face-on orientation with respect to the substrate<sup>46</sup>. Interestingly, well-defined OOP P(NDI2OD-T2) (h00)' diffraction peaks occur with the incorporation of the dopants. Since these out-of-plane P(NDI2OD-T2) (h00)' lamellar peaks are absent in the undoped P(NDI2OD-T2) thin films, incorporation of the dopant molecules induces an edge-on orientation of the crystallites. The 2D GIWAXS patterns of the remaining P(NDI2OD-T2):dopant films show a similar behaviour of varying extent (Fig. SI 11). In addition, the absence of IP  $\pi$ - $\pi$  stacking (0k0)' with respect to OOP lamellar (h00)' suggests that the dopant molecules may be disrupting the  $\pi$ - $\pi$  stacking of the edge-on oriented P(NDI2OD-T2) chains. Diffraction peaks related to a dopant phase are absent, indicating either good intermixing of the dopant within the polymer matrix, or that the dopant molecules are unable to crystallize in the blend.

## 

respectively<sup>47</sup>. The OOP profiles from Figure 6 c) clearly show higher order (h00)' diffraction peaks from all P(NDI2OD-T2):dopant blends, suggesting that all dopants, regardless of the nature of the alkyl side chain, are capable of inducing edge-on P(NDI2OD-T2) crystallites in the blends. Intriguingly, the incorporation of dopant molecules has a distinct effect on P(NDI2OD-T2) crystallites along different crystallographic axis. As shown in Figure 6 d), the IP P(NDI2OD-T2) (h00) lamellar stacking peaks of residual face-on crystallites in the blends shift toward higher values of q (magnitude of the scattering vector) after the blending with dopants, while the P(NDI2OD-T2) (00l) backbone stacking peaks retain a constant q value. This observation implies that the dopants reduce the lamellar spacing of P(NDI2OD-T2) the face-on crystallites, without disrupting the originally well-ordered backbone arrangement. Although IP lamellar stacking direction does not contribute to charge transport, the obvious changes of lamellar spacing with the addition of dopants unambiguously point out that strong molecular interaction between P(NDI2OD-T2) and dopants exists. Further details can be obtained from the 1D GIWAXS profiles around the OOP (200)' peaks and IP (004) peaks, which are chosen for closer investigation since they do not show overlap with other diffraction peaks. As plotted in Figure 6 e), different dopants induce different populations of edge-on P(NDI2OD-T2) crystallites, evidenced by the varying OOP (200)' diffraction intensity in thin films with similar film thickness. The dopant-induced edge-on P(NDI2OD-T2) crystallites may be one of the contributors for the enhanced  $\sigma$  compared to the undoped P(NDI2OD-T2) thin film. However, the fact that the best performing P(NDI2OD-T2):DiPrBI thin film only exhibits an intermediate level of edge-on crystallinity as indicated by the plots around OOP (200)' region, implies that other factors are contributing to the improvement of  $\sigma$ . In addition, the impact of the dopants on the P(NDI2OD-T2) backbone stacking has been investigated by examining the IP P(NDI2OD-T2) (004) peaks as shown in Figure 6 f). It is apparent that the incorporation of all dopants, except for DMBI, slightly reduces the crystallinity of P(NDI2OD-T2) backbone stacking, evidenced by the moderate reduction of the IP P(NDI2OD-T2) (004) peak intensity. The DMBI, on the other hand, almost eliminates the IP P(NDI2OD-T2) (004) peak, suggesting that the DMBI dopant molecules tend to disrupt the ordered arrangement of P(NDI2OD-T2) molecules along the backbone direction. This observation matches well with the AFM images where the largest surface roughness and the lowest  $\sigma$  is observed for P(NDI2OD-T2):DMBI. Lastly, the crystallite orientation distribution (COD) profiles of the dopant-induced edge-on P(NDI2OD-T2) crystallites have also been examined. Although no linear correlation between COD and conductivity was found (see Figure SI 12), the different COD extracted from the P(NDI2OD-T2) thin films with various dopants provides direct evidence that different molecular structures of dopants impact the preferential orientation of P(NDI2OD-T2) crvstallites distinctively. Notably the P(NDI2OD-T2):DMBI has the broadest

COD supporting the higher degree of disorder in this blend which may contribute to its low  $\sigma$ .

to contraction in (h00)' direction. Also, the less prevalent កាក stacking peak can be rationalized by dopant intereal atom 4901G



Fig. 6 2D grazing-incidence wide-angle X-ray scattering (GIWAXS) patterns for a) pure P(NDI2OD-T2) and b) P(NDI2OD-T2): DiBuBI, plotted with identical intensity scale. The sector-averaged 1D profiles along out-of-plane (OOP) and in-plane are plotted in c) and d), respectively. Note the sharp peaks around 0.6 Å<sup>-1</sup><q<0.7 Å<sup>-1</sup> in P(NDI2OD-T2):DiPrBI along OOP is parasitic scattering from upstream beamline. The close-up profiles for dopant induced P(NDI2OD-T2) (200)' diffraction along OOP and P(NDI2OD-T2) (004) along IP are also demonstrated in e) and f), respectively.

We interpret these observations by intercalation of dopants in between P(NDI2OD-T2) backbones. Such a picture is in agreement with the higher q values of the (h00)' reflections in the blend. Due to intercalation, the average distance between two P(NDI2OD-T2) backbones increases generating additional space for the amorphous alkyl chain layers, which finally leads

These results are finally corroborated by differential scanning calorimetry measurements on blends, where a new endotherm is observed at 30-40 K higher than  $T_{m,dopant}$ , that neither arises from the pristine dopant nor from P(NDI2OD-T2) (Figure SI 8). Although a reliable quantification of the corresponding melting

ournal of Materials Chemistry A Accepted Manusc

#### ARTICLE

enthalpy  $\Delta H_m$  is not possible, on a qualitative basis  $\Delta H_m$  increases with increasing doping concentration (Fig. S9).

A chemical reaction of the dopant and the copolymer matrix as an alternative origin for the new endotherm can be excluded as samples were fully soluble after the DSC measurements and the corresponding NMR spectra did not show other signals than those of dopant and copolymer (data not shown).

The observation of intercalation of DMBI and its derivatives is different compared to the findings of Schlitz et al.<sup>36</sup> and also to the miscibility behaviour of P(NDI2OD-T2) and DPBI, which is the phenyl-derivative of DMBI. Shin et al. reported segregation and crystallization of DPBI in P(NDI2OD-T2):DPBI blends processed from chlorobenzene, leading to dopant melting in asprepared blends.<sup>38</sup> While the different structure of DPBI compared to DMBI may be one of the reasons for the different behaviour, it is also possible that the solvent has a prominent effect. Dichlorobenzene, as used here, is a better solvent for P(NDI2OD-T2) compared to chlorobenzene, which was used by Shin et al.<sup>48</sup> Thus, the presence of a larger amount of P(NDI2OD-T2) aggregates may promote the segregation of dopant already in chlorobenzene solution, while dopant intercalation may be favoured for processing from dichlorobenzene where less aggregated, *i.e.* more molecularly dissolved chains, are present. Hence, solvent quality may be important for controlling intercalation, which will be the subject of further investigations.

#### Conclusions

We have designed, synthesized and characterized a series of new air-stable 1H-benzimidazole-based dopants to study the effect of the dopant alkyl substituents on morphology and electrical properties of blends with the copolymer P(NDI2OD-T2). It was demonstrated that dopants with increasingly longer linear alkyl chains give rise to higher  $\sigma$  values. Up to four times higher conductivities (4.1  $\times$  10  $^{-3}$  S/cm) were obtained for nbutyl-substituted dopants compared to the reference having methyl groups (DMBI). Dopants with branched alkyl chains were also studied. The highest  $\sigma$  was obtained from blends with isopropyl-substituted dopants (7  $\times$  10<sup>-3</sup> S/cm). Conductivity measurements as function of the temperature highlighted that charge transport follows а thermally activated. monodimensional variable range hopping (VRH) regime. Moreover, the activation energies were found to be very similar for all the doped samples irrespective of dopant, specifically ~330 meV, indicating similar energetic barriers for transport. Structural analysis showed that the dopant molecules induce an edge-on orientation of polymer crystallites, a decrease in the lamellar stacking distance, and a disruption of backbone and  $\pi$ stacking order compared to pristine P(NDI2OD-T2) films. These observations, along with presence of a new endotherm in the blend, provide evidence for the intercalation of the dopant molecules between P(NDI2OD-T2) chains.

Overall, our work demonstrates that, besides tailoring of the conjugated backbone, the engineering of the solubilizing chains in small molecular dopants is an effective strategy to control and improve the miscibility of dopants and polymers. This strategy allows to maintain the electron transfer process, while optimizing the conductivity thanks to an improved Adoping efficiency. Such a result, which is particularly relevant for n-type doping, is important for the development of advanced optoelectronic organic devices and efficient organic thermoelectric generators.

#### Acknowledgements

The authors are greateful to C. Müller, Chalmers University of Technology, Göteborg, for fruitful discussions, to A. Warmbold and F. Nübling for TGA and DSC measurements on dopants and blends. This work was performed in part at the SAXS/WAXS beamline at the Australian Synchrotron, part of ANSTO. C.R.M. acknowledges support from the Australian Research Council (DP170102145).

#### References

- (1) Kola, S.; Sinha, J.; Katz, H. E. *J. Polym. Sci. Part B Polym. Phys.* **2012**, *50*, 1090–1120.
- (2) Natali, D.; Caironi, M. Adv. Mater. 2012, 24, 1357–1387.
- (3) Lin, P.; Yan, F. *Adv. Mater.* **2012**, *24*, 34–51.
- (4) Walzer, K.; Männig, B.; Pfeiffer, M.; Leo, K. *Chem. Rev.* **2007**, *107*.
- (5) Che, G.; Li, L.; Liu, C.; Su, B.; Wang, Q. Chem. Bull. / Huaxue Tongbao 2013, 76.
- Pfeiffer, M.; Leo, K.; Zhou, X.; Huang, J. S.; Hofmann, M.; Werner, A.; Blochwitz-Nimoth, J. Org. Electron. physics, Mater. Appl. 2003, 4.
- (7) Opitz, A. J. Phys. Condens. Matter 2017, 29.
- (8) Chang, M.; Lim, G.; Park, B.; Reichmanis, E. *Polymers* (*Basel*). **2017**, *9*, 212.
- Noriega, R.; Rivnay, J.; Vandewal, K.; Koch, F. P. V; Stingelin,
  N.; Smith, P.; Toney, M. F.; Salleo, A. *Nat. Mater.* 2013, 12, 1038–1044.
- (10) Chua, L.-L.; Zaumseil, J.; Chang, J.-F.; Ou, E. C.-W.; Ho, P. K.-H.; Sirringhaus, H.; Friend, R. H. *Nature* 2005, 434, 194–199.
- (11) Fazzi, D.; Caironi, M. Phys. Chem. Chem. Phys. 2015, 17, 8573–8590.
- (12) Chen, Y.; Zhao, Y.; Liang, Z. Energy Environ. Sci. 2015, 8, 401–422.
- (13) Bubnova, O.; Crispin, X. Energy Environ. Sci. 2012, 5, 9345.
- (14) Fabretto, M. V.; Evans, D. R.; Mueller, M.; Zuber, K.; Hojati-Talemi, P.; Short, R. D.; Wallace, G. G.; Murphy, P. J. Chem. Mater. 2012, 24, 3998–4003.
- Kim, N.; Kee, S.; Lee, S. H.; Lee, B. H.; Kahng, Y. H.; Jo, Y. R.;
  Kim, B. J.; Lee, K. Adv. Mater. 2014, 26, 2268–2272.
- Bubnova, O.; Khan, Z. U.; Wang, H.; Braun, S.; Evans, D. R.; Fabretto, M.; Hojati-Talemi, P.; Dagnelund, D.; Arlin, J.-B.; Geerts, Y. H.; Desbief, S.; Breiby, D. W.; Andreasen, J. W.; Lazzaroni, R.; Chen, W. M.; Zozoulenko, I.; Fahlman, M.; Murphy, P. J.; Berggren, M.; Crispin, X. Nat. Mater. 2013, 13, 190–194.
- (17) de Leeuw, D. M.; Simenon, M. M. J.; Brown, a. R.; Einerhand, R. E. F. Synth. Met. **1997**, 87, 53–59.
- (18) Jones, B. A.; Facchetti, A.; Wasielewski, M. R.; Marks, T. J. J. Am. Chem. Soc. 2007, 129, 15259–15278.

Published on 19 July 2018. Downloaded by University of Reading on 7/19/2018 1:08:55 PM

- Journal Name
- (19) Chiang, C. K.; Gau, S. C.; Jr., C. R. F.; Park, Y. W.; MacDiarmid, A. G.; Heeger, A. J. *Appl. Phys. Lett.* **1978**, *33*, 18.
- (20) D. M. Ivory; Miller, G. G.; Sowa, J. M.; Shacklette, L. W.; Chance, R. R.; Baughman, R. H. J. Chem. Phys. 1979, 71, 1506–1507.
- (21) Ali Benamara, A.; Galtier, M.; Montaner, A. *Synth. Met.* **1991**, *41*.
- (22) Parthasarathy, G.; Shen, C.; Kahn, A.; Forrest, S. R. J. Appl. *Phys.* **2001**, *89*.
- (23) Chang, C.-C.; Hsieh, M.-T.; Chen, J.-F.; Hwang, S.-W.; Chen, C. H. Appl. Phys. Lett. **2006**, *89*.
- (24) Kao, P.-C.; Wang, J.-Y.; Lin, J.-H.; Yang, C.-H. *Thin Solid Films* **2013**, *527*.
- (25) Kao, P.-C.; Lin, J.-H.; Wang, J.-Y.; Yang, C.-H.; Chen, S.-H. J. Appl. Phys. **2011**, 109.
- (26) Barbot, A.; Lucas, B.; Di Bin, C.; Ratier, B. Org. Electron. physics, Mater. Appl. **2014**, 15.
- (27) Kao, P.-C.; Chang, C.-C.; Lin, S.-Y. Surf. Coatings Technol.
  2013, 231, 135–139.
- (28) Zhou, D.-Y.; Zu, F.-S.; Zhang, Y.-J.; Shi, X.-B.; Aziz, H.; Liao, L.-S. Appl. Phys. Lett. 2014, 105, 83301.
- (29) Grant, P. M.; Greene, R. L.; Wrighton, G. C.; Castro, G. *Phys. Rev. Lett.* **1973**, *31*.
- (30) Goetz, K. P.; Vermeulen, D.; Payne, M. E.; Kloc, C.; McNeil, L. E.; Jurchescu, O. D. *J. Mater. Chem. C* **2014**, *2*.
- (31) Nollau, A.; Pfeiffer, M.; Fritz, T.; Leo, K. J. Appl. Phys. **2000**, 87, 4340–4343.
- Menke, T.; Wei, P.; Ray, D.; Kleemann, H.; Naab, B. D.; Bao,
  Z.; Leo, K.; Riede, M. Org. Electron. physics, Mater. Appl.
  2012, 13.
- (33) Wei, P.; Menke, T.; Naab, B. D.; Leo, K.; Riede, M.; Bao, Z. J. Am. Chem. Soc. 2012, 134.
- (34) Zhu, X.-Q.; Zhang, M.-T.; Yu, A.; Wang, C.-H.; Cheng, J.-P. J. Am. Chem. Soc. **2008**, 130, 2501–2516.
- (35) Wei, P.; Oh, J. H.; Dong, G.; Bao, Z. J. Am. Chem. Soc. 2010, 132, 8852–8853.
- (36) Schlitz, R.; Brunetti, F. G.; Glaudell, A. M.; Miller, P. L.;
  Brady, M. a; Takacs, C. J.; Hawker, C. J.; Chabinyc, M. L.
  Adv. Mater. 2014, 26, 2825–2830.
- (37) Wang, S.; Sun, H.; Ail, U.; Vagin, M.; Persson, P. O. Å.;
  Andreasen, J. W.; Thiel, W.; Berggren, M.; Crispin, X.; Fazzi,
  D.; Fabiano, S. Adv. Mater. 2016, 28, 10764–10771.
- (38) Shin, Y.; Massetti, M.; Komber, H.; Biskup, T.; Nava, D.; Lanzani, G.; Caironi, M.; Sommer, M. *Adv. Electron. Mater.* **2018**, *1700581*, 1700581.
- (39) Wang, Y.; Nakano, M.; Michinobu, T.; Kiyota, Y.; Mori, T.; Takimiya, K. *Macromolecules* **2017**, *50*.
- Liu, J.; Qiu, L.; Portale, G.; Koopmans, M.; ten Brink, G.;
  Hummelen, J. C.; Koster, L. J. A. Adv. Mater. 2017, 1701641.
- Naab, B. D.; Guo, S.; Olthof, S.; Evans, E. G. B.; Wei, P.;
  Millhauser, G. L.; Kahn, A.; Barlow, S.; Marder, S. R.; Bao, Z.
  J. Am. Chem. Soc. 2013, 135, 15018–15025.
- (42) Beretta, D.; Bruno, P.; Lanzani, G.; Caironi, M. *Rev. Sci. Instrum.* **2015**, *86*, 75104.
- (43) Kirby, N. M.; Mudie, S. T.; Hawley, A. M.; Cookson, D. J.; Mertens, H. D. T.; Cowieson, N.; Samardzic-Boban, V. J. Appl. Crystallogr. 2013, 46, 1670–1680.
- (44) Ilavsky, J. J. Appl. Crystallogr. 2012, 45, 324–328.
- Schaffer, C. J.; Wang, C.; Hexemer, A.; Müller-Buschbaum,
  P. Polymer (Guildf). 2016, 105, 1–11.

- (46) Rivnay, J.; Steyrleuthner, R.; Jimison, L. H.; Caşadei, A; Online Chen, Z.; Toney, M. F.; Facchetti, A. DNeher, D. Salleo, A01G Macromolecules 2011, 44, 5246–5255.
- (47) Min, J.; Jiao, X.; Ata, I.; Osvet, A.; Ameri, T.; Bäuerle, P.;
  Ade, H.; Brabec, C. J. Adv. Energy Mater. 2016, 6, 1–9.
- Steyrleuthner, R.; Schubert, M.; Howard, I.; Klaumünzer, B.;
  Schilling, K.; Chen, Z.; Saalfrank, P.; Laquai, F.; Facchetti, A.;
  Neher, D. J. Am. Chem. Soc. 2012, 134, 18303–18317.

## N-alkyl substituted 1H-benzimidazoles as improved n-type dopants of a naphthalene-diimide based copolymer

B. Saglio<sup>ab</sup>, M. Mura<sup>a</sup>, M. Massetti<sup>bc</sup>, F. Scuratti<sup>bd</sup>, X. Jiao<sup>e</sup>, C. R. McNeill<sup>e</sup>, M. Sommer<sup>f</sup>, A. Famulari<sup>a</sup>, G. Lanzani<sup>bc</sup>, M. Caironi<sup>b\*</sup> and C. Bertarelli<sup>ab\*</sup>

Alkyls in 1H-benzimidazoles influence their intercalation within the naphthalene diimide-based copolymer, thus affecting the electrical conductivity.

