

View Article Online View Journal

RSC Advances

This article can be cited before page numbers have been issued, to do this please use: Q. Lu, C. Wei, L. Sun, Z. A. ALOthman, V. Malgras, Y. Yamauchi, H. Wang and L. Wang, *RSC Adv.*, 2016, DOI: 10.1039/C5RA24709H.



This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. This Accepted Manuscript will be replaced by the edited, formatted and paginated article as soon as this is available.

You can find more information about *Accepted Manuscripts* in the **Information for Authors**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the <u>Ethical guidelines</u> still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.



www.rsc.org/advances

Page 1 of 18

Smart design of hollow AuPt nanospheres with porous shell as DOI: 10.1039/C5RA24709H superior electrocatalysts for ethylene glycol oxidation

Qingqing Lu,^{a,b} Changting Wei,^{a,b} Litai Sun,^{a,b} Zeid A. ALOthman,^c Victor Malgras,^d

Yusuke Yamauchi,^{c,d} Hongjing Wang,*^e Liang Wang*^{a,e}

- a State Key Laboratory of Electroanalytical Chemistry, Changchun Institute of Applied Chemistry, Chinese Academy of Sciences, Changchun, Jilin 130022, P. R. China.
- b University of Chinese Academy of Sciences, Beijing 100039, P. R. China.
- c Department of Chemistry, College of Science, King Saud University, Riyadh 11451, Saudi Arabia
- d International Center for Materials Nanoarchitectonics (MANA), National Institute for Materials Science (NIMS), 1-1 Namiki, Tsukuba, Ibaraki 305-0044, Japan.
- e College of Chemical Engineering, Zhejiang University of Technology, Hangzhou, Zhejiang 310014, P.R. China.

*Corresponding authors' e-mails: hjw@zjut.edu.cn and wangliang@zjut.edu.cn

SC Advances Accepted Manuscript

Abstract

View Article Online DOI: 10.1039/C5RA24709H

Hollow bimetallic electrocatalysts have recently stimulated an increasing attention due to their accessible interior surface and bimetallic synergy effect. Herein, for the first time, we successfully anchor a porous AuPt shell on modified silica spheres with the assistance of Pluronic F127. The whole process consists in a simple ultrasonic mixing for 30 min at room temperature without any organic solvent. After metal deposition silica etching, well-defined hollow structures are obtained in high yield. The hollow spheres are further characterized by scanning electron microscopy and transmission electron microscopy. The electrochemical analysis reveals that the as-prepared samples demonstrate an electrocatalytic activity and durability superior to the commercial Pt/C catalyst, showing the potential of these AuPt hollow spheres as electrocatalysts for the ethylene glycol oxidation in alkaline medium.

1. Introduction

View Article Online DOI: 10.1039/C5RA24709H

RSC Advances Accepted Manuscript

Inorganic nanostructures with hollow interiors have emerged as intriguing materials over the past decades, owing to their performance in diverse applications such as surface plasmonic resonance (SPR), drug release, sensors, electrode materials and catalysis.¹⁻⁴ In comparison with their bulk counterparts, hollow architectures exhibit unique features such as lower density and cost along with higher specific surface area and utilization efficiency.

On the other hand, the development of direct fuel cells (DFCs) led to promising future candidates cleaner energy sources. Further research related to nanostructured Pt-based electrocatalysts with superior activity and durability, such as porous hollow structures, is highly desirable.⁵⁻⁷ So far, various strategies have been proposed to construct hollow Pt-based electrocatalysts, including galvanic displacement reaction,^{3,4,8-10} Kirkendall effect,¹¹ dealloying,^{12,13} and so on.^{14,15} Xia and co-workers reported a controllable synthesis of hollow Pt nanospheres, nanocages and nanotubes by reacting Ag nanospheres, nanocubes and nanowires with the appropriate salt precursors. However, AgCl precipitates inevitably, thus complicating the procedure and severely hindering the yield.¹⁶ Hollow Pt-based nanospheres were also obtained by employing Co or Ni nanoparticles as sacrificial templates. This approach, however, requires nitrogen to protect the material from oxidation during the whole process.^{3,4,9} Recently the hollow PtCuCo nanoparticles were synthesized by acetic acid-assisted chemical dealloying process. The initial template was obtained by mixing oleylamine, oleic acid and 1-octadecene at 230 °C for 30 min.¹² In all of the aforementioned systems, the required expensive and unstable sacrificial matrices sometimes produce undesirable by-products, making them unsuitable for commercial production at a large scale.

Silica templates can be used for the preparation of hollow structures. The production of

RSC Advances Accepted Manuscript

monodispersed SiO₂ spheres can be easily scaled up by a classical Stöber method.¹⁷ Silica materials_{nine} DOI: 10.1039/C5RA24709H are environmentally friendly and economically viable.¹⁸ Moreover, the hollow cavity can be precisely tuned by simply changing the size and the shape of the silica templates.¹⁹⁻²¹

It is noteworthy that the tolerance and activity for Pt catalysts is limited by the formation of carbon monoxide (CO)-like intermediates. This hindrance can be efficiently overcome by partially substituting Pt with a secondary metal to benefit from an improved bimetallic electronic landscape. As a typical example, Zhang *et al.* revealed that Au clusters can protect the Pt electrocatalysts against dissolution during oxygen reduction reaction.²² Besides, adjacent Au can effectively oxidize CO species into CO_2 and regenerate the poisoned surfaces during methanol oxidation reaction.²³

Here we propose an efficient route to obtain uniformly sized AuPt hollow nanospheres (AuPt-HNSs) with porous shell via silica-templated process, using F127 as surfactant and pore-directing agent, and ascorbic acid as soft reducing agent. Through the porous shells, the guest species are allowed to access the inner active sites, and consequently enhance their catalytic performance.²⁴ Our synthetic process does not contain any organic solvent and can be successfully achieved through a one-step bimetallic decoration of porous AuPt shell on the surface of silica spheres at room temperature. After removing the template, the as-prepared AuPt-HNSs demonstrate superior electrocatalytic activity and durability compared to the state-of-the-art in terms of commercial Pt/C catalyst toward ethylene glycol oxidation in alkaline medium.

2. Experimental section

2.1. Materials and Chemicals

HAuCl₄·4H₂O, K₂PtCl₄, hydrofluoric acid (HF), NH₃·H₂O, isopropanol, ethylene glycol, sodium hydroxide (NaOH), tetraethyl orthosilicate (TEOS) and ascorbic acid (AA) were obtained from Sinopharm Chemical Reagent Co, Ltd (Shanghai, China). 3-Aminopropyltrimethoxysilane

(APTMS) and Pluronic F127 (PEO₁₀₀PPO₆₅PEO₁₀₀) were purchased from Sigma. Commercial Ptt/C_{nline} DOI: 10.1039/C5RA24709F

2.2. Synthesis of SiO₂ spheres

Typically, 200 mL of ethanol was mixed with 15.2 mL of H_2O and 6.4 mL of $NH_3 \cdot H_2O$, and the solution was stirred vigorously for 1 h at room temperature. Then, 12 mL of TEOS was injected into the above mixture. After 3 hours, the milky product was collected by centrifugation at 10,000 rpm for 10 min, followed by washing with ethanol and water. The product was finally dried at 50 °C.

2.3. Synthesis of AuPt-HNSs

Firstly, the surface of silica spheres was modified with an amino group. 150 mg of silica particles was dissolved in a mixture of 45 mL of isopropanol and 900 µl of APTMS. Then the suspension was refluxed at 353 K for 10 h. The functionalized SiO₂ spheres were collected by centrifugation and washed thoroughly with ethanol and water, and then dried at 323 K. Secondly, 2.0 mg silica spheres was dispersed in a solution of K₂PtCl₄ (1.5 mL, 20 mM) and HAuCl₄·4H₂O (0.5 mL, 20 mM). After dissolving 20 mg F127, AA (2.0 mL, 0.1 M) was added and the mixture was sonicated for 30 min at room temperature. Finally, the obtained product was washed with water and dispersed in 10 wt% HF (20 mL) overnight. The as-prepared AuPt-HNSs were dried at 323 K before the electrochemical tests.

RSC Advances Accepted Manuscript

2.4. Characterizations

The morphology and surface structure were examined by a XL30 ESEM FEG scanning electron microscope (SEM) with an accelerating voltage of 20 kV. The transmission electron microscopy and element analysis mapping were recorded on a JEM-2100F high-resolution transmission electron microscope operating at 200 kV. Nitrogen adsorption-desorption isotherms were obtained by using an automatic N₂ adsorption-desorption instrument (Quantachrome Autosorb Automated Gas

RSC Advances Accepted Manuscript

Sorption System) and the samples were degassed in vacuum at 323 K for 24 h. X-ray photoelectron DOI: 10.1039/C5RA24709H spectroscopy (XPS) measurements were performed on an ESCALAB-MKII spectrometer (VG Co, United Kingdom) with Al Kα X-ray radiation as the X-ray source for excitation. Electrochemical experiments were carried out with a CHI 842c electrochemical analyzer (Chenhua Co., Shanghai, China).

2.5. Electrochemical measurements

A conventional three electrode cell was used, including a platinum wire as counter electrode, a Ag/AgCl (3 M KCl) electrode as reference electrode and a modified glassy carbon electrode (GCE, 3 mm in diameter) as working electrode. The glassy carbon electrode was first polished with Al₂O₃ powder, washed with water and ethanol, and coated with the samples (2 mg·mL⁻¹, 3 μ L) and Nafion (0.05 wt%, 3 μ L). The Pt loading amount was 56.6 μ g cm⁻². Before electrochemical experiments, the catalyst surfaces were cleaned by cycling between -0.2 V to 1.2 V (*vs.* Ag/AgCl) in N₂ saturated 0.5 M H₂SO₄ solution. The electrochemically active surface areas (ECSAs) of Pt were estimated by integrating the charges involved in hydrogen desorption (*Q*_H), assuming 210 μ C cm⁻² as the monolayer desorption of hydrogen (*q*_H) at a scan rate of 50 mV s⁻¹, following:²⁵

$$ECSA = \frac{Q_H}{\mathbf{m} \times q_H}$$

where m is the mass of Pt. Ethylene glycol oxidation measurements were performed in a mixture of 0.5 M NaOH and 0.5 M CH₂OHCH₂OH between -0.8 V and 0.4 V at a sweeping rate of 50 mV s⁻¹. The chronoamperometric curves were obtained at -0.1 V (*vs.* Ag/AgCl) for 3600 s. The current densities were acquired by normalizing with respect to the ECSA and the mass of Pt.

3. Results and Discussion

As shown in **Scheme 1**, AuPt-HNSs are obtained by etching the SiO_2 spheres decorated with a porous AuPt shell. In this work, the hard-template (SiO_2) is synthesized through a Stöber method.

RSC Advances

The well-dispersed SiO₂ spheres have an average diameter of around 120 nm (**Fig. S1**). Theyriarentine DOI: 10.1039/C5RA24709H subsequently functionalized with the amino groups of APTMS. Due to the electrostatic interaction between -NH₂⁺ and AuCl₄⁻/PtCl₄²⁻, the addition of reducing agent (AA) initiates the formation of Au-riched nuclei on the silica surface, thereby promoting the subsequent deposition of porous shells with the assistance of F127.

The surface morphology and structure of the obtained AuPt-HNSs (after the removal of the SiO₂ spheres) were investigated by scanning electron microscopy (SEM) and transmission electron microscopy (TEM). As revealed in **Fig. 1A**, monodispersed three-dimensional spheres are successfully obtained without any by-products. There are not serious cracks or collapses after the etching treatment, which confirms the effectiveness of this approach to obtain hollow structures.

The rough and dendritic surfaces indicate the existence of the porous shells, because Pluronic F127 is a versatile structural directing agent use for the formation of nanoporous carbon and nanoporous/dendritic metals.^{13,19,20,24,26} A previous report has also demonstrated that AA is not only a common reducing agent but also favors the growth of branches.²⁷ Guo *et al.* reported high-density Au/Pt hybrid nanoparticles supported on silica nanospheres by mixing pre-synthesized Au nanoparticles and amino-functionalized silica spheres. Then, the obtained composites were further mixed with platinum precursors in a boiling solution for 30 min.²⁸ Compared to the previous approach, our synthetic approach does not require any pre-synthesized Au seed or high-temperature operation. We can successfully achieve a one-step bimetallic coverage of silica support in a short time at room temperature.

After the removal of the silica templates, clear cavities and a uniform particle size (160 nm \pm 10 nm) can be confirmed (**Fig. 1B**). The average wall thickness is about 20 nm. The high-resolution TEM image of an individual particle shows the presence of well-defined dendritic shells (**Fig. 2A**)

RSC Advances Accepted Manuscript

consisting of nanoparticles with a diameter of around 3 nm. Random assembly of such and DOI: 10.1039/C5RA24709+ nanoparticles form interconnected branches in all directions, showing the porous shells. The porous shell can allow the smooth diffusion of guest species and sufficient contact with inner reactive sites. **Fig. 2B** shows a high resolution TEM image of the rectangular area marked in **Fig. 2A**. The lattice distance is 0.23 nm, which corresponds to the (111) plane of a face-centered cubic (*fcc*) AuPt crystal. Selected area electron diffraction (ED) patterns confirm that the structure is polycrystalline, and the rings can be assigned to the (111), (200), (220), and (311) (**Fig. S2**).

The N₂ adsorption-desorption isotherm shows a hysteresis loop at a relative pressure between 0.4 and 0.9, which is characteristic of a porous structure (**Fig. S3**). The Brunauer-Emmett-Teller (BET) surface area of the AuPt-HNSs is calculated to be around 28.6 m²·g⁻¹. This value is comparable with those of hyperbranched Pt nanostructure (15 m²·g⁻¹),²⁷ PdPd alloy nanosponges (19.04 m²·g⁻¹)²⁹ and porous Pt nanoballs (23 m²·g⁻¹).³⁰

High-angle annular dark field scanning transmission electron microscopy (HAADF-STEM) was further used to characterize this unique architecture. The inner cavities are distinguished by the sharp contrast between the shells and hollow interiors (**Fig. 3A**). Elemental mapping (**Fig. 3B-D**) reveals the presence of element Au and Pt. Considering the reduction potentials of Pt and Au species, it is expected that the outer surface is predominantly occupied by Pt atoms. However, the resolution of the system cannot reveal such spatial distribution on the elemental mapping. The atomic ratio of Au and Pt is close to 1:3, which is also confirmed by ICP analysis.

X-Ray photoelectron spectroscopy (XPS) was also adopted to measure the elemental composition and the surface chemical states. **Fig. 4** shows the Au 4*f* and Pt 4*f* doublets. The peaks of Au $4f_{7/2}$ and $4f_{5/2}$ at 83.25 and 87.10 eV basically are an indicatation of the zerovalent state of Au. Similarly, the two peaks of Pt $4f_{7/2}$ (70.50 eV) and Pt $4f_{5/2}$ (73.75 eV) basically indicate the

zerovalent state of Pt. No other visible peaks are present, which confirms the complete reduction of DOI: 10.1039/C5RA24709Hthe metal species.^{8,31}The binding energies of Pt 4*f*_{7/2} and Pt 4*f*_{5/2} of AuPt-HNSs (**Fig. 4**) are shifted to lower values than those in commercial Pt/C catalyst (**Fig. S4**), which is consistent with other reports.^{23,31}This shift of binding energy implies the change in Pt electronic structure due to the formation of Au-Pt bonds, which is partly responsible the enhanced electrocatalytic performance.

It is well-known that XPS can provide the composition of the surface, while ICP results refer to the bulk composition. The Pt:Au atomic ratio determined by XPS analysis is 91.6:8.4 which is much higher than the above ICP result. Since the reduction potential of Au(III) (+ 1.00 V *vs*. SHE) is much higher than Pt (II) (+ 0.76 V *vs*. SHE), it is anticipated that Au will form on the silica surface prior to Pt, leaving a Pt-rich outer surface.²⁴

RSC Advances Accepted Manuscript

To evaluate the catalytic properties of the as-prepared sample, ethylene glycol (EG) oxidation was selected. For comparison, commercial Pt/C (3-5 nm Pt nanoparticles (20 wt%) loaded on XC-72 carbon black) was also measured as a benchmark (**Fig. S5**). Compared with methanol, direct ethylene glycol fuel cells (DEGFCs) exhibits notable advantages, such as a higher boiling point, a lower tendency to crossover from anode to cathode.^{9,32-34} It has been previously testified that the kinetic rate of EG oxidation and the corrosion of materials can be greatly improved in alkaline medium, but the transfer efficiency remains an challenging limitation to overcome.³⁵ Thus it is still desirable to prepare efficient electrocatalysts for EG oxidation reaction. The specific electrochemically surface area (ECSA) of AuPt-HNSs is determined to be 20.1 m² g⁻¹ (**Fig. S6**), which is higher than those of mesoporous Pt nanospheres (16.34 m² g⁻¹),³⁶ PtAg nanotubes (18.2 m² g⁻¹),³³ graphene-based porous Pt catalysts (11.86 m² g⁻¹),³⁷ and Pt nanowire-Sn@CNT (17.2 m² g⁻¹)³⁸.

The surface specific activity (Fig. 5A) represents the intrinsic property of a certain catalyst,

RSC Advances Accepted Manuscript

whereas the mass specific activity (**Fig. 5C**) indicates the utilization efficiency during the catalytic_{num} DOI: 10.1039/C5R424709F reaction.³⁹ In both cases, the typical EG oxidation cyclic voltammogram (CV) curves can be observed. The forward peak characteristic of the total oxidation for EG shows a higher current density (9.91 mA cm⁻²), which is 3.38 times higher than for Pt/C (2.93 mA cm⁻²). The mass activity of AuPt-HNSs is also higher than those of previously reported catalysts, as summarized in **Table S1**. Although our AuPt-HNSs show lower surface area compared to Pt/C (57.9 m² g⁻¹), the catalytic behavior of our sample toward EG oxidation exhibit obvious advantage over commercial Pt/C catalyst.

In addition, the $I_f:I_b$ ratio (I_f and I_b are forward and backward current densities, **Fig. 5C**) is a strong indicator to evaluate the tolerance of a catalyst. The AuPt-HNSs have a higher ratio (2.97) than the hollow $Pt_{54}Cu_{23}Co_{14}(2.5)$ ⁹ or the Pt nanotubes (2.1).³³ The current-time curves describe the tolerance of Pt-based catalysts to adsorbed carbonaceous intermediates during EG oxidation, as shown in **Fig. 5B** and **D**. At the early stage, all the current densities decay rapidly due to the accumulation of generated CO-like poisonous species. Both the starting and final current densities of AuPt-HNSs are superior to those of Pt/C, demonstrating an excellent tolerance over long periods of time.

After 3600 s, the catalysts were measured in the same electrolyte. The AuPt-HNSs maintain 93.4 % of its initial current (**Fig. S7A** and **Fig. S7C**) and the commercial Pt/C lost in 29 % of its initial current (**Fig. S7B** and **Fig. S7D**). Due to the smaller size of the Pt nanoparticle (3-5 nm), the Pt/C exhibits a higher ECSA than that of the AuPt-HNSs. But, small Pt nanoparticles in Pt/C are easily poisoned by the intermediate species adsorbed at the surface. From the above electrochemical results, it is concluded that the AuPt-HNSs showed promising potentials for future application in DEGFCs.

The improved electrocatalytic performance of the AuPt-HNSs possibly benefits from the DOI: 10.1039/C5R424709H following factors: (1) the porous shells are favorable for the diffusion of guest molecules, improving transport kinetics, (2) the hollow configuration can make the full use of the interior active sites and significantly increase the electrochemically active surface area, and (3) the synergistic effect between Au and Pt can contribute to high catalytic activity and good durability due to a better adsorption of hydroxyl groups and activation of poisoned surfaces.^{22,23}

4. Conclusion

Here we present an effective and facile method to synthesize AuPt-HNSs with porous shells in high yield, based on a one-step bimetallic decoration of functionalized SiO₂ nano-spheres with the assistance of F127 and AA. The whole process does not involve any organic solvent or high temperatures. The AuPt-HNSs demonstrate superior catalytic activity and durability toward EG oxidation compared to the commercial Pt/C in alkaline media. We strongly believe that our synthetic approach can be extended to prepare other Pt-based hollow electrocatalysts in the future.

Acknowledgements

This work was supported by the National Natural Science Foundation of China (no. 21273218). Zeid A. ALOthman, Victor Malgras, and Yusuke Yamauchi extend their sincere appreciation to the Deanship of Scientific Research at King Saud University for funding this Prolific Research Group.

Reference

- 1 L. Au, X. Lu and Y. Xia, Adv. Mater., 2008, 20, 2517-2522.
- 2 E. Yan, Y. Ding, C. Chen, R. Li, Y. Hu and X. Jiang, Chem. Commun., 2009, 19, 2718-2720.
- 3 N. Liu, H. Han, Z. Yuan and Z. Ma, *RSC Adv.*, 2015, 5, 1867-1872.
- 4 (a) J. Liu, Y. Wen, P. A. Aken, J. Maier and Y. Yu, *Nano Lett.*, 2014, 14, 6387-6392; (b) J. Liu,
 Z. Yang, J. Wang, L. Gu, J. Maier and Y. Yu, *Nano Energy*, 2015, 16, 389-398; (c) J. Liu, P.
 Kopold, C. Wu, P. A. Aken, J. Maier and Y. Yu, *Energy Environ. Sci.*, 2015, 8, 3531-3538.
- 5 (a) K. Eid, H. Wang, V. Malgras, Z. Alothman, Y. Yamauchi and L. Wang, J. Phys. Chem. C, 2015, 119, 19947-19953; (b) H. Wang, H. Jeong, M. Imura, L. Wang, L. Radhakrishnan, N. Fujita, T. Castle, O. Terasaki and Y. Yamauchi, J. Am. Chem. Soc., 2011, 133, 14526-14529.
- K. Huang, Z. Zhao, L. Cao, Y. Chen, E. Zhu, Z. Lin, M. Li, A. Yan, A. Zettl, Y. M. Wang, X. Duan, T. Mueller and Y. Huang, *Science*, 2015, **348**, 1230-1234.
- (a) S. Park, D. Yoon, H. Baik and K. Lee, *CrystEngComm*, 2015, **17**, 6852-6856; (b) H. Wang,
 S. Ishihara, K. Ariga and Y. Yamauchi, *J. Am. Chem. Soc.*, 2012, **134**, 10819-10821; (c) H.
 Wang, L. Wang, T. Sato, Y. Sakamoto, S. Tominaka, K. Miyasaka, N. Miyamoto, Y. Nemoto, O.
 Terasaki and Yusuke Yamauchi, *Chem. Mater.*, 2012, **24**, 1591-1598.
- 8 H. M. Song, D. H. Anjum, R. Sougrat, M. N. Hedhili and N. M. Khashab, J. Mater. Chem., 2012, 22, 25003-25010.
- 9 W. Hong, C. Shang, J. Wang and E. Wang, *Nanoscale*, 2015, 7, 9985-9989.
- 10 S. Guo, Y. Fang, S. Dong and E. Wang, J. Phys. Chem. C, 2007,111, 17104-17109.
- L. Dubau, J. Durst, F. Maillard, L. Guétaz, M. Chatenet, J. André and E. Rossinot, *Electrochim. Acta*, 2011, 56, 10658-10667.
- 12 X-J. Liu, C-H. Cui, H-H. Li, Y. Lei, T-T. Zhuang, M. Sun, M. N. Arshad, H. A. Albar, T. R.

RSC Advances

Sobahi and S-H. Yu, Chem. Sci., 2015, 6, 3038-3043.

- 13 L. Wang and Y. Yamauchi, J. Am. Chem. Soc., 2013, 135, 16762-16765.
- 14 F. Bai, Z. Sun, H. Wu, R. E. Haddad, X. Xiao and H. Fan, Nano Lett., 2011, 11, 3759-3762.
- 15 N. Fan, Y. Yang, W. Wang, L. Zhang, W. Chen, C. Zou and S. Huang, ACS Nano, 2012, 6, 4072-4082.
- 16 (a) Y. Sun, B. T. Mayers and Y. Xia, *Nano Lett.*, 2002, 2, 481-485; (b) W. Zhang, J. Yang and X. Lu, *ACS Nano*, 2012, 6, 7397-7405.
- M. Yang, Q. Cai, C. Liu, R. Wu, D. Sun, Y. Chen, Y. Tang and T. Lu, J. Mater. Chem. A, 2014, 2, 13738-13743.
- P. Kundu, H. Heidari, S. Bals, N. Ravishankar and G. V. Tendeloo, Angew. Chem., Int. Ed., 2014, 53, 3970-3974.
- 19 H. Ataee-Esfahani, Y. Nemoto, L. Wang and Y. Yamauchi, *Chem. Commun.*, 2011, **47**, 3885-3887.
- 20 H. Ataee-Esfahani, J. Liu, M. Hu, N. Miyamoto, S. Tominaka, K. C. W. Wu and Y. Yamauchi, Small, 2013, 9, 1047-1051.
- 21 A. A. Melvin, V. S. Joshi, D. C. Poudyal, D. Khushalani and S. K. Haram, ACS Appl. Mater. Interfaces, 2015, 7, 6590-6595.
- 22 J. Zhang, K. Sasaki, E. Sutter, and R. R. Adzic, Science, 2007, 315, 220-222.
- (a) H.-P. Liang, T. G. J. Jones, N. S. Lawrence, L. Jiang and J. S. Barnard, *J. Phys. Chem. C*, 2008, **112**, 4327-4332; (b) J. Zeng, J. Yang, J. Y. Lee and W. Zhou, *J. Phys. Chem. B*, 2006, **110**, 24606-24611.
- 24 H. Ataee-Esfahani, L. Wang, Y. Nemoto and Y. Yamauchi, Chem. Mater., 2010, 22, 6310-6318.
- 25 W. Li and A. M. Lane, *Electrochem. Commun.*, 2011, **13**, 913-916.

- 26 Y. Fang, D. Gu, Y. Zou, Z. Wu, F. Li, R. Che, Y. Deng, B. Tu and D. Zhao, Angew. Chem. And Mathematical Doi: 10.1039/C5RA24709H Ed., 2010, 49, 7987-7991.
- 27 L. Wang, C. Hu, Y. Nemoto, Y. Tateyama and Y. Yamauchi, *Cryst. Growth Des.*, 2010, 10, 3454-3460.
- 28 S. Guo, J. Zhai, Y. Fang, S. Dong and E. Wang, Chem.-Asian J., 2008, 3, 1156-1162.
- 29 C. Zhu, S. Guo and S. Dong, Chem.-Eur. J., 2013, 19, 1104-1111.
- 30 G. Surendran, L. Ramos, B. Pansu, E. Prouzet, P. Beaunier, F. Audonnet and H. Remita, *Chem. Mater.*, 2007, **19**, 5045-5048.
- 31 C. Li, H. Wang and Y. Yamauchi, Chem.-Eur. J., 2013, 19, 2242-2246.
- 32 A. Serov and C. Kwak, Appl. Catal., B, 2010, 97, 1-12.

- 33 Y. Kim, H. Kim and W. B. Kim, *Electrochem. Commun.*, 2014, 46, 36-39.
- 34 W. Hong, C. Shang, J. Wang and E. Wang, *Energy Environ. Sci.*, 2015, **8**, 2910-2915.
- 35 C. Jin, Y. Song and Z. Chen, *Electrochim. Acta*, 2009, **54**, 4136-4140.
- 36 Y. Li, B. P. Bastakoti, V. Malgras, C. Li, J. Tang, J. H. Kim and Y. Yamauchi, Angew. Chem., Int. Ed., 2015, 54, 11073-11077.
- 37 L. Zhang, J.-J. Shao, W. Zhang, C. Zhang, X. Zheng, H. Du and Q-H. Yang, J. Phys. Chem. C, 2014, 118, 25918-25923.
- 38 S. Sun, G. Zhang, D. Geng, Y. Chen, M. N. Banis, R. Li, M. Cai and X. Sun, *Chem.-Eur. J.*, 2010, 16, 829-835.
- 39 R. Chetty, S. Kundu, W. Xia, M. Bron, W. Schuhmann, V. Chirila, W. Brandl, T. Reinecke and M. Muhler, *Electrochim. Acta*, 2009, 54, 4208-4215.

Scheme and Figures and Figure Captions

View Article Online DOI: 10.1039/C5RA24709H

RSC Advances Accepted Manuscript



Scheme 1 Schematic illustration of the synthetic procedure of hollow AuPt nanospheres.



Fig. 1 (A) Typical SEM image and (B) TEM image of AuPt-HNSs.

View Article Online

DOI: 10.1039/C5RA24709H



Fig. 2 (A) Highly magnified TEM image of an individual hollow AuPt nanoparticle. (B) HRTEM image of the selected region in panel A.



Fig. 3 (A) HAADF-STEM image and (B, C, D) corresponding elemental mapping of AuPt-HNSs.



Fig. 4 (A) Au 4f and (B) Pt 4f XPS spectra of AuPt-HNSs.



Fig. 5 (A, C) Cyclic voltammograms (CVs) and (B, D) chronoamperometric curves of AuPt-HNSs and Pt/C in 0.5 M NaOH solution containing 0.5 M EG. The chronoamperometric curves were obtained at -0.1 V.

RSC Advances Accepted Manuscript

Graphical Abstract

Hollow AuPt spherical nanoelectrocatalysts for ethylene glycol oxidation was synthesized by a

facile and effective method.



1