View Article Online View Journal

# ChemComm

### Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: W. Li, Y. Xu, Y. Dong, Y. Wu, C. Zhang, M. Zhou, Q. Fu, M. Wu and Y. Lei, *Chem. Commun.*, 2019, DOI: 10.1039/C9CC01937E.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the **author guidelines**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the ethical guidelines, outlined in our <u>author and reviewer resource centre</u>, still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/chemcomm

BiOCl is demonstrated as the first bismuth oxyhalide compound serving as a metricle Online anode material for potassium ion batteries.



View Article Online DOI: 10.1039/C9CC01937E

## Bismuth oxychloride nanoflake assemblies as a new anode for potassium ion batteries

Received 00th January 20xx, Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

Published on 07 May 2019. Downloaded on 5/8/2019 1:51:14 AM

Wei Li,<sup>a</sup> Yang Xu,<sup>\*b,c</sup> Yulian Dong,<sup>a</sup> Yuhan Wu,<sup>b</sup> Chenglin Zhang,<sup>b</sup> Min Zhou,<sup>b</sup> Qun Fu,<sup>a</sup> Minghong Wu,<sup>\*a</sup> and Yong Lei <sup>\*b</sup>

This work reports the first demonstration of bismuth oxyhalides as anode materials in potassium-ion batteries. BiOCl nanoflake assemblies deliver high capacities of 367 mAh g<sup>-1</sup> at 50 mA g<sup>-1</sup> and 175 mAh g<sup>-1</sup> at 1 A g<sup>-1</sup>. The formation of K-Bi alloys at an early stage of potassiation is observed.

Investigation of the feasibility of K-ion batteries (KIBs) has been greatly prompted during the past few years.<sup>1-5</sup> There are two important advantages of KIBs that encourage researchers to proceed from Li-ion batteries (LIBs) to KIBs. First, K has a lower standard redox potential than Li in nonaqueous electrolytes, which can be translated to a higher cell voltage of KIBs.<sup>1</sup> Second, nonaqueous K electrolytes have a higher ionic conductivity than Li electrolytes and lower interfacial reaction resistance deriving from the lower desolvation activation energy.<sup>2,3</sup> Study of KIB cathodes is mainly focused on intercalation-type materials,<sup>6,7</sup> but there is a great variety of KIB anodes because of the various electrochemical mechanisms to store K-ions.<sup>1,4,8</sup> It can be anticipated that the mechanisms in KIBs might be beyond our expectations and different from those in LIBs even given the same material. Despite the diverse mechanisms, two criteria are important to obtain satisfactory KIB performance: (i) suitable ion diffusion pathways exist in the anode's structure to ensure fast ionic transport and (ii) high electronic conductivity is achievable to ensure fast electronic transport.

As a group of V-VI-VII ternary compounds, bismuth oxyhalides BiOX (X = Cl, Br and I) are a classic type of layerstructured materials. They crystallize into a tetragonal matlockite (PbFCl-type) structure (space group P4/nmm) that consists of [X-Bi-O-Bi-O-X] slices stacking by the van der Waals interaction through the halogen atoms along the *c* axis.<sup>9,10</sup> The layered structure is featured by strong intralayer covalent bonding and weak interlayer van der Waals interaction, which results in highly anisotropic electrical, mechanical and optical properties, endowing BiOX with potential applications in various fields.<sup>11-15</sup> However, there has been very little study of BiOX in the application of rechargeable alkali-metal ion batteries (LIBs<sup>16,17</sup> and Na-ion batteries (NIBs)<sup>18</sup>). It is surprising because BiOX meets the two criteria. On the one hand, the van der Waals gaps in BiOX naturally serve as two-dimensional (2D) ion diffusion pathways. On the other hand, metallic Bi can be formed by the conversion reaction to enhance the electronic conductivity of electrode matrix. Thus, it is urgent yet rational to exploit the potential of BiOX in the emerging field of KIBs.

In this work, we report the first application of BiOX compounds in KIBs by taking BiOCl as a demonstrator. BiOCl nanoflake assemblies (NFAs) are prepared and characterized by a submicron hierarchical structure that consists of square-shaped flake nanounits. The electrochemical mechanism study reveals the formation of K-Bi alloys at the initial stage of potassiation, which has not been observed in lithiation and sodiation of BiOX. BiOCl NFAs deliver a high capacity of 367 mAh g<sup>-1</sup> and retain 58% capacity after 50 cycles at 50 mA g<sup>-1</sup>. They also show great rate capability by delivering a capacity of 175 mAh g<sup>-1</sup> at 1 A g<sup>-1</sup>. To the best of our knowledge, the NFAs exhibit the best electrochemical performance among all the BiOX compounds tested in alkali-metal ion batteries.

BiOCl NFAs are fabricated by a solvothermal reaction, where NH<sub>4</sub>Cl not only serves as the Cl precursor, but also lowers the pH value of the reaction solution to reduce the hydrolysis rate of  $Bi(NO_3)_3 \cdot 5H_2O$ .<sup>19</sup> The lowered hydrolysis rate and the viscosity of ethylene glycol (EG) as the reaction solvent can affect the growth of the nanoflakes and lead to the formation of assemblies.<sup>20</sup> The X-ray diffraction (XRD) pattern (Fig. 1a) can be well indexed to tetragonal phase BiOCl (JCPDS No. 06-0249) with a space group of P4/nmm. Good crystallinity can be verified by the sharpness of the peaks.<sup>21,22</sup> (001), (002) and (003)

<sup>&</sup>lt;sup>a</sup>. Institute of Nanochemistry and Nanobiology, School of Environmental and Chemical Engineering, Shanghai University, Shanghai 200444, China. E-mail: mhwu@shu.edu.cn

<sup>&</sup>lt;sup>b.</sup> Fachgebiet Angewandte Nanophysik, Institut für Physik & ZMN MacroNano (ZIK), Technische Universität Ilmenau, Ilmenau 98693, Germany. E-mail: yong.lei@tuilmenau.de

<sup>&</sup>lt;sup>c</sup> Department of Chemistry, University College London, London WC1H 0AJ, UK. Email: y.xu.1@ucl.ac.uk

<sup>&</sup>lt;sup>+</sup> Electronic Supplementary Information (ESI) available: experimental details, TEM, SEM after ultrasonic and cycling, survey XPS, O 1s and Cl 2p XPS after the first cycle, schematic of reaction pathways. See DOI: 10.1039/x0xx00000x

Published on 07 May 2019. Downloaded on 5/8/2019 1:51:14 AM

#### COMMUNICATION

peaks are broader than (110) and (200) peaks, indicating that the crystallite size along the c-axis, which is regarded as the thickness of the flakes, is smaller than that of the *a*-*b* plane, as will be seen in Fig. 2. The relatively strong (110) peak suggests that the flakes favour the growth along the (110) orientations which are perpendicular to the *c*-axis, forming thin slabs.<sup>23</sup> BiOCl has a typical layered structure (Fig. 1b) where  $[Bi_2O_2]^{2+}$  stabs stack along the c axis while being sandwiched by two stabs of Cl<sup>-</sup>, forming [Cl-Bi-O-Bi-Cl] units along the same axis. This enables the expose of (001) facets and the 2D K-ion diffusion pathways between the [Bi<sub>2</sub>O<sub>2</sub>]<sup>2+</sup> stabs. X-ray photoelectron spectroscopy (XPS) survey spectrum (Fig. S1, ESI<sup>+</sup>) shows the presence of only Bi, O, Cl and C. Bi 4f spectrum (Fig. 1c) shows two peaks located at 159.0 and 164.3 eV that can be assigned to Bi 4f5/2 and 4f7/2 spin-orbital components of Bi<sup>3+</sup>. Cl 2p spectrum (Fig. 1d) consists of Cl 2p3/2 and 2p1/2 peaks located at 197.1 and 198.7 eV, respectively. The peaks agree well with previous reports.24,25



**Fig. 1** (a) XRD pattern, (b) crystal structure, (c) Bi 4f, and (d) Cl 2p XPS spectra of BiOCl NFAs.

Fig. 2a shows the panoramic-view scanning electron microscope (SEM) image of the NFAs. It reveals a high yield of hierarchical assemblies with an erythrocyte-like shape and a typical diameter of 800 nm-1 µm. Zoom-in SEM image (Fig. 2b) transmission electron microscope (TEM) image (Fig. S2, ESI<sup>+</sup>) show the assemblies consist of nanoflakes with the thickness of 35-40 nm. The nanoflakes are square shaped with clearly corners and smooth surface. The hierarchical structure is still intact after a lengthy (1 h) ultrasonic treatment (Fig. S3, ESI<sup>+</sup>), indicating the good structural stability. The high-resolution TEM (HRTEM) image of a single nanoflake (Fig. 2c) displays two sets of continuous lattice fringes with the spacing of 0.2 and 0.28 nm that correspond to the (200) and (110) planes of tetragonal BiOCl, respectively. The selected-area electron diffraction (SAED) pattern (Fig. 2c, inset) reveals that the electron beam can be indexed to the [001] zone, suggesting the exposed surface to be the (001) plane. HRTEM image at the corner of the nanoflake (Fig. S4, ESI+) shows that the four lateral surfaces can

be assigned to {110} facets. A schematic diagram (Fig. 2d) provides a direct visualization of the Patomik<sup>0</sup> arrangement characterized in HRTEM. One can see that the minimum unit in the (001) plane is in a square shape (white lines). This microscopic feature at atomic level agrees with the macroscopic morphology of the square-shaped nanoflakes (Fig. 2b).



**Fig. 2** (a and b) SEM images, (c) HRTEM image (inset is SAED pattern) of BiOCI NFAs, and (d) schematic diagram of the crystal structure along the *c* axis.

The potassium storage mechanism of BiOCI NFAs is studied by using half cells at the current density of 50 mA g<sup>-1</sup> in a voltage window of 0.01-2.0 V. The cyclic voltammetry (CV) curves of Cycle1 (Fig. 3a) show four cathodic peaks. The strong peak at 1.5 V is attributed to the conversion of BiOCl to Bi.<sup>16,17</sup> The two small peaks (0.72 and 0.54 V) and another strong peak at 0.1 V correspond to the multi-phase K-Bi alloying reactions, while the two anodic peaks at 0.65 and 1.25 V correspond to the dealloying reactions.<sup>26,27</sup> In Cycle2 and Cycle3, the cathodic peak at 1.5 V disappears, indicating the irreversibility of the conversion reaction in Cycle1, as will be discussed later. Other peaks remain almost unchanged except for the slight shift of the anodic peak (0.71 V) and the occurrence of two shoulder peaks (0.2 and 0.83 V). Thus, the two redox pairs of 0.1(0.2)/0.71(0.83) V and 0.72/1.25 V are established, indicating the stabilization of the alloying/de-alloying reactions. The Cycle1 charge/discharge profiles (Fig. 3b) agree well with the observations in the CV curves. There are two discharge plateaus at 1.6 and 0.2 V as well as a slope in between, while two charge plateaus at 0.6 V and 1.2 V can be observed. The cell delivers initial discharge and charge capacities of 781 and 340 mAh g<sup>-1</sup>, respectively, resulting in an initial columbic efficiency (CE) of 43.5%. Six dischargecharge states (as indicated in Fig. 3b) are selected for the ex-situ XRD measurement (Fig. 3c). When discharging to 1.1 V, the strong Bi peak demonstrates a conversion reaction (BiOCl $\rightarrow$ Bi) has occurred at the initial stage of potassiation, which is correlated to the cathodic peak at 1.5 V in CV curves and the plateau at 1.6 V in the discharge profile. Surprisingly, not only is Bi formed but K-Bi alloys also appear at this stage in the compositions of KBi and K<sub>3</sub>Bi<sub>2</sub>.<sup>26,28</sup> Early formation of alkalimetal-Bi alloys has not been observed in the lithiation and

COMMUNICATION

#### Journal Name

Published on 07 May 2019. Downloaded on 5/8/2019 1:51:14 AM

sodiation of BiOCl.<sup>16-18</sup> Thus, it is likely that reduction of BiOCl and alloying between K and Bi occur concurrently, producing Bi and K-Bi alloys. When discharging to 0.4 V, the amount of KBi and  $K_3Bi_2$  decreases while another alloy  $K_3Bi$  appears.<sup>26,29</sup> At the end of discharge (0.01 V), only Bi and  $K_3Bi$  can be observed. During the charge process, de-alloying reactions occur. It leads to the gradually decreased amount of  $K_3Bi$  and  $K_3Bi_2$  and the final composition of KBi and Bi at 2.0 V. Thus, the BiOCl structure is not restored, which explains the relatively low initial CE and the disappearance of the peak at 1.5 V in the CV curves (Fig. 3a).

Ex-situ XPS results can provide additional support to the electrochemical mechanism. In Fig. 3d, both Bi 4f peaks shift to lower bonding energies after discharge, suggesting the reduction of BiOCl to Bi upon inserting K-ions.<sup>17</sup> The peak positions remain unchanged after charge, indicating the BiOCI structure is not restored when K-ions are extracted. The decomposition of BiOCI can also be evidenced by the evolution of the O 1s peaks (Fig. S5, ESI<sup>+</sup>). The major component of the O bonding changes from Bi-O at the pristine state to K-O after cycle, implying that the decomposition process is accompanied by the formation of potassium oxides.<sup>17,30</sup> The absence of their XRD peaks may be due to their highly amorphous nature. In addition, the Cl 2p peak intensity (Fig. S6, ESI+) dramatically decreases after discharge and charge, suggeting the formation of soluble KCl accompanies the decomposition of BiOCl, which can be seen from the KCl peak in all the ex-situ patterns (Fig. 3c). Based on the above analysis, the overall reaction pathways are schematically summarized in Fig. S7, ESI<sup>+</sup>.



**Fig. 3** (a) CV curves of Cycle1-3, (b) discharge/charge profiles of Cycle1, (c) XRD patterns at discharge/charge states, (d) Bi 4f XPS spectra at pristine state, after discharge and charge states.

The electrochemical performance of BiOCl NFAs is fully demonstrated in Fig. 4. The discharge/charge profiles of Cycle2 and Cycle3 at the current density of 50 mA  $g^{-1}$  (Fig. 4a) well overlap with each other. A pair of plateaus at 0.2 V (discharge)/0.6 V (charge) can be clearly identified. Compared to Cycle1 (Fig. 3b), the discharge plateau at 1.6 V disappears, which can be ascribed to the irreversible conversion from BiOCl

to Bi. The profiles of Cycle2 and 3 exhibit the mixed features of those of the reported Bi anodes in KABS10.5030009ting19the previously discussed electrochemical mechanism. During discharge, the slope between 1.5 and 0.4 V could be mainly ascribed to the formation of KBi and K<sub>3</sub>Bi<sub>2</sub>,<sup>26,28</sup> and the subsequent plateau is characteristic for the formation of K<sub>3</sub>Bi.<sup>26,28,29</sup> The charge profile agrees with those of the Bi anodes, suggesting a reversible dealloying process. It is interesting to note that the intermediate phases are different from one report to another (KBi<sub>2</sub>,<sup>26</sup> K<sub>5</sub>Bi<sub>4</sub>,<sup>27</sup> KBi,<sup>28</sup> and K<sub>3</sub>Bi<sub>2</sub><sup>29</sup>), possibly due to the different size and morphology of the Bi anodes; thus, it is not surprise that the NFAs exhibit mixed features of the phase transition process. BiOCI NFAs deliver most of the discharge capacity below 0.4 V in a voltage window up to only 2 V, which makes BiOCI favourable in assembling fullcells compared to oxides,<sup>31</sup> dichalcogenide KIB anodes<sup>32-34</sup> and even carbons.<sup>35,36</sup> The NFAs delivered Cycle2 capacity of 367 mAh g<sup>-1</sup> and retained 213 mAh g<sup>-1</sup> after 50 cycles (Fig. 4b). It is worth pointing out that the obtained cyclability is far beyond the reported limitation of 15 cycles in LIBs and NIBs.<sup>16-18</sup> The electrode was characterized by SEM after 50 cycles. The yellow dashed squares (Fig. S8, ESI<sup>+</sup>) highlight that the hierarchical structure is maintained after repetitive cycles, and the flakes can be identified, which contributes to the observed cyclability. Unlike Bi anodes that need the incorporation of carbon to maintain the structural integrity,27-29 the NFAs exhibit good structural stability without any carbon incorporation. It also can be seen that the diameter of the NFAs increases due to the volume expansion of the K-Bi alloying reaction, which might be responsible for the slow decay of the capacity over cycles. Strikingly, BiOCI NFAs exhibit better rate performance than in LIBs and NIBs,<sup>16-18</sup> and even some Bi anodes (Bi/rGO<sup>27</sup> and Bi/C composites<sup>28</sup>). They delivered capacities of 346, 314, 272 and 223 mAh g<sup>-1</sup> at the current densities of 50, 100, 200 and 500 mA g<sup>-1</sup>, respectively (Fig. 4c). Half of the capacity (175 mAh g<sup>-1</sup>) was retained when the current density increased to 1 A g<sup>-1</sup>. Moreover, the low discharge plateau is well maintained when the current density increases by 20 times (Fig. 4d). To the best of our knowledge, this is the first demonstration of bismuth oxyhalides that can sustain at a high rate of 1 A g<sup>-1</sup> in alkali-metal ion batteries. The obtained performance of BiOCI NFAs can be ascribed to three factors. First, the interlayer space in the microstructure of BiOCI serves as 2D K-ion diffusion pathways that could reduce the diffusion resistance.<sup>37</sup> Second, the formation of Bi and the alloying reaction naturally enhance the electronic conductivity of the electrode matrix, and this has an even more significant role in determining the rate capability of the NFAs. Third, the macroscopic rigidity keeps the hierarchical structure of the NFAs intact despite the volume change during the alloying reaction. The combination of microstructural, mechanism and macrostructural merits results in the obtained electrochemical performance of BiOCI NFAs. Moreover, unlike the reported Bi anodes, 26-29 the presented performance is obtained without carbon incorporation and ether-based

electrolytes, thereby holding the advantages of the ease of

synthesis and low-cost.



**Fig. 4** (a) discharge/charge profiles of Cycle2 and 3, (b) cycling performance at 50 mA g<sup>-1</sup>, (c) rate performance, and (d) discharge/charge profiles at various current densities from 50 mA g<sup>-1</sup> to  $1 \text{ A g}^{-1}$ .

In summary, we have shown the promise of BiOCI as a potential KIB anode material by studying its electrochemical mechanism to store K-ions and evaluating its electrochemical performance. The mechanism study revealed potassiation of BiOCI proceeds through a conversion reaction of transforming BiOCI to Bi and the alloying reactions of forming KBi, K<sub>3</sub>Bi<sub>2</sub> and K<sub>3</sub>Bi. We observed that K-Bi alloying processes proceed concurrently with the conversion process at the initial stage of potassiation, which is different from the previously reported lithiation and sodiation of bismuth oxyhalides. The electrochemical evaluation showed great cyclability and rate capability of BiOCl, exhibiting the best performance among all the reported bismuth oxyhalides in the battery research. This is the first demonstration of bismuth oxyhalides used as KIB electrode materials, and the demonstration is expected to promote future work of these compounds in this exciting field.

This work was supported by the German Research Foundation (DFG: LE2249/4-1 and LE2249/5-1), and National Natural Science Foundation of China (21577086).

#### **Conflicts of interest**

There are no conflicts to declare.

#### References

- 1 H. Kim, J.C. Kim, M. Bianchini, D.H. Seo, J. Rodriguez-Garcia and G. Ceder, *Adv. Energy Mater.*, 2018, **8**, 1702384.
- 2 M. Okoshi, Y. Yamada, S. Komaba, A. Yamada and H. Nakai, *J. Electrochem. Soc.*, 2017, **164**, A54-A60.
- 3 M. Zhou, Y. Xu, C. Wang, Q. Li, J. Xiang, L. Liang, H. Zhao, M. Wu and Y. Lei, *Nano Energy*, 2017, **31**, 514-524.
- 4 J.C. Pramudita, D. Sehrawat, D. Goonetilleke and N. Sharma, *Adv. Energy Mater.*, 2017, **7**, 1602911.
- 5 S. Komaba, T. Hasegawa, M. Dahbi and K. Kubota, *Electrochem. Commun.*, 2015, **60**, 172-175.

- X. Wu, D.P. Leonard and X. Ji, Chem. Mater., 2017, 29, 5031-View Article Online 5042.
  DOI: 10.1039/C9CC01937E
- 7 C. Zhang, Y. Xu, M. Zhou, L. Liang, H. Dong, M. Wu, Y. Yang and Y. Lei, *Adv. Funct. Mater.*, 2017, **27**, 1604307.
- 8 Y. Xu, C. Zhang, M. Zhou, Q. Fu, C. Zhao, M. Wu and Y. Lei, *Nature Commun.*, 2018, 9, 1720.
- 9 D.S. Bhachu, S.J. Moniz, S. Sathasivam, D.O. Scanlon, A. Walsh, S.M. Bawaked, M. Mokhtar, A.Y. Obaid, I.P. Parkin, J. Tang and C.J. Carmalt, *Chem. Sci.*, 2016, 7, 4832-4841.
- 10 J. Li, Y. Yu and L. Zhang, Nanoscale, 2014, 6, 8473-8488.
- 11 R. Yuan, S. Fan, H. Zhou, Z. Ding, S. Lin, Z. Li, Z. Zhang, C. Xu, L. Wu and X. Wang, Angew. Chem. Int. Ed., 2013, 52, 1035-1039.
- 12 J. Zhang, F. Shi, J. Lin, D. Chen, J. Gao, Z. Huang, X. Ding and C. Tang, *Chem. Mater.*, 2008, **20**, 2937-2941.
- 13 M. Guan, C. Xiao, J. Zhang, S. Fan, R. An, Q. Cheng, J. Xie, M. Zhou, B. Ye and Y. Xie, *J. Am. Chem. Soc.*, 2013, **135**, 10411-10417.
- 14 L. Zhang, W. Wang, S. Sun, Y. Sun, E. Gao and J. Xu, Appl. Catal. B, 2013, 132, 315-320.
- 15 Y. Mi, L. Wen, Z. Wang, D. Cao, Y. Fang and Y. Lei, *Appl. Catal. B*, 2015, **176-177**, 331-337.
- 16 L. Ye, L. Wang, H. Xie, Y. Su, X. Jin and C. Zhang, *Energy Technol.*, 2015, 3, 1115-1120.
- 17 C. Chen, P. Hu, X. Hu, Y. Mei and Y. Huang, Chem. Commun., 2015, 51, 2798-2801.
- 18 Y. Zhang, S. Lu, M.-Q. Wang, Y. Niu, S. Liu, Y. Li, X. Wu, S.-J. Bao and M. Xu, *Mater. Lett.*, 2016, **178**, 44-47.
- 19 K. Zhang, J. Liang, S. Wang, J. Liu, K. Ren, X. Zheng, H. Luo, Y. Peng, X. Zou and X. Bo, *Cryst. Growth Des.*, 2012, **12**, 793-803.
- 20 M. Li, J. Zhang, H. Gao, F. Li, S.-E. Lindquist, N. Wu and R. Wang, ACS Appl. Mater. Interfaces, 2016, 8, 6662-6668.
- 21 W. Chen, W. Cai, Y. Lei and L. Zhang, *Mater. Lett.*, 2001, 50, 53-56.
- 22 S. Wang, M. Wang, Y. Lei and L. Zhang, J. Mater. Sci. Lett., 1999, 18, 2009-2012.
- 23 J. Yuan, J. Wang, Y. She, J. Hu, P. Tao, F. Lv, Z. Lu and Y. Gu, J. *Power Sources*, 2014, **263**, 37-45.
- 24 G. Cheng, J. Xiong and F.J. Stadler, New J. Chem., 2013, 37, 3207-3213.
- 25 S. Peng, L. Li, P. Zhu, Y. Wu, M. Srinivasan, S.G. Mhaisalkar, S. Ramakrishna and Q. Yan, *Chem. Asian J.*, 2013, **8**, 258-268.
- 26 K. Lei, C. Wang, L. Liu, Y. Luo, C. Mu, F. Li and J. Chen, Angew. Chem. Int. Ed., 2018, 57, 4687-4691.
- 27 Q. Zhang, J. Mao, W. Pang, T. Zheng, V. Sencadas, Y. Chen, Y. Liu and Z. Guo, *Adv. Energy Mater.*, 2018, **8**, 1703288.
- 28 R. Zhang, J. Bao, Y. Wang and C.-F. Sun, Chem. Sci., 2018, 9, 6193-6198.
- 29 J. Huang, X. Lin, H. Tan and B. Zhang, Adv. Energy Mater., 2018, 8, 1703496.
- 30 X. Yide, Y. Li and G. Xiexian, Appl. Catal., 1997, A 164, 47-57.
- 31 I. Sultana, M.M. Rahman, S. Mateti, V.G. Ahmadabadi, A.M. Glushenkov and Y. Chen, *Nanoscale*, 2017, **9**, 3646-3654.
- 32 Y. Xu, F. Bahmani, M. Zhou, Y. Li, C. Zhang, F. Liang, S.H. Kazemi, U. Kaiser, G. Meng and Y. Lei, *Nanoscale Horiz.*, 2019, 4, 202-207.
- 33 V. Lakshmi, Y. Chen, A.A. Mikhaylov, A.G. Medvedev, I. Sultana, M.M. Rahman, O. Lev, P.V. Prikhodchenko and A.M. Glushenkov, *Chem. Commun.*, 2017, **53**, 8272-8275.
- 34 J. Zhou, L. Wang, M. Yang, J. Wu, F. Chen, W. Huang, N. Han, H. Ye, F. Zhao and Y. Li, *Adv. Mater.*, 2017, **29**, 1702061.
- 35 Z. Jian, W. Luo and X. Ji, J. Am. Chem. Soc., 2015, 137, 11566-11569.
- 36 J. Zhao, X. Zou, Y. Zhu, Y. Xu and C. Wang, Adv. Funct. Mater., 2016, 26, 8103-8110.
- 37 H. Zhu, C. Xiao, H. Cheng, F. Grote, X. Zhang, T. Yao, Z. Li, C. Wang, S. Wei, Y. Lei and Y. Xie, *Nature Commun.*, 2014, 5, 3960.