www.rsc.org/chemcomm

ChemComm

Fe–Ce–ZSM-5 a new catalyst of outstanding properties in the selective catalytic reduction of NO with NH₃

G. Carja, G. Delahay,* C. Signorile and B. Coq

Laboratoire de Matériaux Catalytiques et Catalyse en Chimie Organique, UMR 5618, CNRS-ENSCM, 8 rue Ecole Normale, 34296 Montpellier, France. E-mail: delahay@cit.enscm.fr; Fax: 33(0)467163470; Tel: 33(0)467163480

Received (in Cambridge, UK) 20th February 2004, Accepted 21st April 2004 First published as an Advance Article on the web 17th May 2004

A Fe–Ce–ZSM-5 catalyst elaborated from a new synthesis route exhibits very high NO conversion (75–100%) in the selective catalytic reduction of NO by NH_3 in a wide temperature window (523–823 K), even in the presence of H_2O and SO_2 .

Nitrogen oxides emitted from mobile and stationary sources have been a major source of air pollution. Up to now the most efficient control technology to remove NO from stationary sources is the selective catalytic reduction (SCR) of NO by ammonia (4NO + $4NH_3 + O_2 \rightarrow 4N_2 + 6H_2O$).¹ Recently, there has been high interest in adapting this technology to mobile diesel engines in order to achieve impending emission standards. The most efficient SCR catalysts show optimum performance in a narrow temperature window while the automotive application of this process calls for a high NO_x removal over a temperature range of 423-823 K. In this context there are continuing efforts to develop new highly active and selective catalysts for the reduction of NO to N2 over a broader temperature window that are stable in the presence of SO₂ and water. Fe-overexchanged zeolite catalysts have been found to be attractive candidates for SCR reactions.2-4 Ma and Grünert2 and Sun et al.3 reported the preparation of an overexchanged Fe-ZSM-5 catalyst by sublimation of FeCl3 into H-ZSM-5; the catalyst showed NO conversions close to 80% (GHSV $\approx 300\ 000\ h^{-1}$ -360 000 h⁻¹) in the temperature range 623-823 K and was stable in the presence of water vapor and SO2. Long and Yang4 reported a Fe-ZSM-5 catalyst prepared by the ion exchange method showing nearly 100% NO conversion within the range 673-773 K; the addition of small amount of cerium increased the catalyst activity for temperatures above 773 K. Zeolites containing cerium were also found to be active catalysts for this process.⁵ Unfortunately, for all these catalysts the NO conversion was very low below 600 K. We want to report here outstanding catalytic performances for the SCR of NO with ammonia over a new Fe-Ce-ZSM-5 catalyst; high NO conversion values (\geq 75%) were obtained within a much broader temperature window (523-823 K) under a high gas hourly space velocity (GHSV) of 332 000 h⁻¹. Its catalytic activity remains stable when SO₂ and H₂O were introduced in the feed. With an NO conversion value close to 90% at 563 K (N_2 selectivity > 99%) the new catalyst is more active than overexchanged Fe-ZSM-5 catalyst prepared by FeCl₃ sublimation method.^{2,3}

This new Fe-Ce-ZSM-5 catalyst was prepared in the organic phase by improving a previously reported method;⁶ the parent zeolite material NH₄-ZSM-5 (Si/Al = 16.4) supplied by Zeolyst International Company was used in its H+ form. Iron and cerium were introduced into zeolite by using a solution of iron acetylacetonate and cerium nitrate dissolved in acetonitrile. Characterised by a higher dipole moment than water and a high dielectric constant, CH₃CN is able to provide a tuned interaction medium inside the small pores of H-ZSM-5. 150 mL of an organic solution of iron and cerium (in the desired molar ratio) was added slowly during an 8 hour period over 3 g of zeolite dispersed in 40 mL of acetonitrile, at 443 K, with strong stirring in a refluxing flask. The triphasic reaction medium and the high temperature value were chosen in order to facilitate specific interactions between the cations and the zeolite framework inside the pores. The resulting product was aged for 48 hours at 393 K, the solvent evaporated and the material dried at 383 K overnight. Before the catalytic tests the samples were calcined at 723 K for 3 hours under a stream of helium and oxygen. Temperature programmed reduction (TPR) by H₂/Ar (3/97) was carried out by using a Micromeritics AutoChem 2910 apparatus with TCD detection. Details about the conditions used during TPR experiment are given elsewhere.⁷ The catalytic experiments are performed at atmospheric pressure with a conventional fixed-bed flow reactor. The typical reaction conditions are as follows: 20 mg of sample (0.025 mL), 2000 ppm NO, 2000 ppm NH₃ and 3% O₂ in helium, balance He, 138.3 mL·min⁻¹ total flow rate and a GHSV = 332 000 h⁻¹. The effluent composition was monitored continuously by sampling on line to a quadrupole mass spectrometer (Pfeiffer vacuum Omnistar equipped with channel-tron and Faraday detectors 0–200 amu). Nine masses characteristic of NO (30), NO₂ (30,46), N₂O (28,30,44), NH₃ (16,17), H₂O (17,18), O₂ (16,32) were followed.

The compositions of the catalysts as determined by ICP analysis are given in Table 1. The conversion of NO as a function of temperature is reported in Fig. 1 for the different samples. For comparison, the catalytic behavior of an overexchanged Fe–ZSM-5 catalyst (CVD-Z), prepared according to the FeCl₃ sublimation procedure,⁸ is also reported. The CVD-Z and Fe(3.9)-Z which contain the same Fe amount, exhibit similar trends for NO conversion with light-off temperature (50% NO conversion) at *ca*. 570 K. However, Fe(3.9)-Z demonstrates better performances with

Table 1 Chemical composition of the samples

Sample	Composition (wt%)		Fe, Ce loading	
	Fe	Ce	Al	(mmol·gcat ⁻¹)
Fe(1.9)–Z	1.9	_	1.9	0.35
Fe(3.9)–Z	3.9		1.7	0.70
CVD-Z	3.9		2.1	0.8
Fe(1.6)Ce(2.5)–Z	1.6	2.5	1.9	0.5
Ce(3.9)–Z	—	3.9	1.9	0.3



Fig. 1 NO conversion as a function of temperature, (-O-) Fe(1.6)Ce(2.5)-Z, $(-\Box-)$ CVD-Z, $(-\Delta-)$ Fe(3.9)-Z, $(-\diamondsuit-)$ Ce(3.9)-Z and $(-\bigtriangledown-)$ Fe(1.6)-Z.

View Article Online

full NO conversion above 623 K. It is noteworthy that only trace amounts of N₂O were detected below 673 K. At lower Fe content, Fe(1.9)-Z, the NO conversion profile is shifted to higher temperatures with light-off at about 623 K. For Ce(3.9)-Z the light-off occurs at 640 K. The presence of both Ce and Fe species in Fe(1.6)Ce(2.5)-Z sample has a strong positive influence on the catalyst activity with light-off at ca. 500 K and NO conversions over 90% above 563 K. These results demonstrate that the joint action of cerium and iron gives rise to a highly active catalyst for the process of SCR of NO by ammonia. It should be underlined that the NO selectivity to N₂ is only slightly below 100% above 723 K. The TPR tool may provide useful information regarding the nature of Fe and/or Ce active species. In Fig. 2, large H₂ consumption peaks between 473-1073 K are observed for the TPR profiles of Fe(1.9)-Z, Ce(3.9)-Z and Fe(1.6)Ce(2.5)-Z. For Fe(1.9)-Z the peak maximum occurs at 633 K and the hydrogen consumption (H_2/Fe , mol/mol) is 0.44: From similar TPR patterns and H₂ consumption at $T \le 770$ K, it was proposed that Fe species in Fe-ZSM-5 and Febeta zeolite are composed of "Fe-oxo" cations of low nuclearity, with Fe-O-Fe bridges, which reduce from FeIII to FeII upon TPR treatment.7-10 The TPR profile of Ce-ZSM-5 presents a broad peak with a maximum at ca. 763 K pointing out that Ce species in zeolite are more difficult to reduce than Fe; the H₂/Ce ratio of ca. 0.5 corresponds to the reduction of Ce^{IV} to Ce^{III} . The TPR profile of the Fe(1.6)Ce(2.5)-Z shows that Fe and Ce species are in close interaction because they are simultaneously reduced and thus Fe makes the reduction of Ce much faster. The TPR trace presents a maximum at 663 K and a $H_2/(Fe + Ce)$ ratio of 0.55 agrees quite well with the reduction of Fe^{III} to Fe^{II} and of Ce^{IV} to Ce^{III}. These observations (TPR trace and $H_2/(Fe + Ce)$ value) are strong indications that Fe and Ce could be together in the same "Fe,Ceoxo" cations with possibly Fe-O-Ce bridges. We further studied the effect of H₂O and SO₂ on the SCR activity of Fe(1.6)Ce(2.5)-Z (Fig. 3). Before adding SO₂ and water the SCR reaction had been



Fig. 2 TPR profiles of Fe(1.9)-Z (a), Ce(3.9)-Z (b), Fe(1.6)Ce(2.5)-Z (c).



Fig. 3 NO conversion as a function of time at 573 K on Fe(1.6)Ce(2.5)-Z catalyst.

stabilized for 100 minute at 573 K. Upon switching to a H₂O, SO₂containing feed (2.0% H₂O and 25 ppm SO₂), the NO conversion remains stable (\approx 90%) for 8 h. After removing the water vapor and SO₂ a barely detectable increase of the conversion is observed.

In conclusion the new Fe-Ce-ZSM-5 catalyst exhibits outstanding performance for the selective catalytic reduction of NO when ammonia is used as a reductant. NO conversions maintains above 75% in a wide temperature window (523–823 K) with a GHSV of 332 000 h⁻¹; the catalytic activity is stable in the presence of water vapor and SO₂. It is assumed that the special preparation method is able to promote specific iron–cerium interactions within the zeolite framework. The facility of the catalyst preparation makes it attractive for industrial application. Optimization of the catalyst formulation (*i.e.* the ratio Fe/Ce) is under way in our laboratory.

We acknowledge financial support from the "Agence De L'Environment de la Maitrise de L'Energie (ADEME)".

Notes and references

- H. Bosch and F. Janssen, *Catal. Today*, 1988, **2**, 369; G. Delahay and B. Coq, *Zeolites for cleaner technologies*, in *Catalytic Sciences Series*, ed. M. Guisnet and J.-P. Gilson, Imperial College Press, London, 2002, **vol. 3**, p. 347.
- 2 A. Z. Ma and W. Grünert, Chem .Commun., 1999, 71.
- 3 Q. Sun, Z.-X. Gao, H.-Y. Chen and W. M. H. Sachtler, J. Catal., 2001, 201, 89.
- 4 R. Q. Long and R. T. Yang, J. Am. Chem. Soc., 1999, 121, 5595.
- 5 W. E. J. van Kooten, B. Liang, H. C. Krijnsen, O. L. Oudshoorn, H. P. A. Calis and C. M. van den Bleek, *Appl. Catal. B*, 1999, **21**, 203.
- 6 G. Delahay, A. Guzmán-Vargas, D. Valade and B. Coq, Proceeding, 14th International Zeolite Conference, ed. E. W. J. van Steen, L. H. Callanan, M. Claeys and C. T. O'Connor, 2004, Cape Town (South Africa), *Stud. Surf. Sci. Catal.*, p. 2501.
- 7 A. Guzman-Vargas, G. Delahay and B. Coq, *Appl. Catal. B*, 2003, 42, 369.
- 8 H. Y. Chen and W. M. H. Sachtler, Catal. Today, 1998, 48, 73.
- 9 M. Mauvezin, G. Delahay, B. Coq, S. Kieger, J. C. Jumas and J. Olivier-Fourcade, J. Phys. Chem. B, 2001, **105**, 928.
- 10 F. Heinrich, C. Schmidt, E. Löffler, M. Menzel and W. Grünert, J. Catal., 2002, 212, 157.