

## Article

# A General Protocol for the Polycondensation of Thienyl-MIDA Boronate Esters to Form High Molecular Weight Copolymers.

Josue Ayuso Carrillo, Michael L Turner, and Michael J. Ingleson

J. Am. Chem. Soc., Just Accepted Manuscript • DOI: 10.1021/jacs.6b07666 • Publication Date (Web): 16 Sep 2016 Downloaded from http://pubs.acs.org on September 18, 2016

## Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.



Journal of the American Chemical Society is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036

Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

10

11 12 13

14 15

16

17 18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59

60

# A General Protocol for the Polycondensation of Thienyl MIDA-Boronate Esters to Form High Molecular Weight Copolymers.

Josue Ayuso Carrillo, Michael L. Turner,\* Michael J. Ingleson\*

School of Chemistry, University of Manchester, Manchester, UK, M13 9PL

Supporting Information Placeholder

ABSTRACT: Thienyl di-MIDA boronate esters are readily synthesized by electrophilic C-H borylation producing bench stable crystalline solids in good yield and excellent purity. Optimal conditions for the slow release of the boronic acid using KOH as the base in biphasic THF/water mixtures enables the thienyl MIDA boronate esters to be extremely effective homo-bifunctionalized (AA-type) monomers in Suzuki-Miyaura co-polymerizations with dibromoheteroarenes (BB-type monomers). A single polymerization protocol is applicable for the formation of five alternating thienvl copolymers that are (or are close analogues of) state of the art materials used in organic electronics. The five polymers were produced in excellent yields and with high molecular weights comparable to those produced using Stille co-polymerization protocols. Therefore thienyl di-MIDA boronate esters represent bench stable / low toxicity alternatives to highly toxic di-trimethylstannyl AA-type monomers that are currently ubiquitous in the synthesis of these important alternating copolymers.

#### Introduction

Thiophene moieties, including annulated derivatives, are key constituents of many polymers used in organic electronic devices.<sup>1</sup> Whilst early studies were dominated by polythiophenes generated from a heterobifunctional (AB-type) monomer (e.g., P3HT, Figure 1),<sup>1,2</sup> state of the art materials are based on alternating co-polymers produced from two homo-bifunctional monomers (AA-/BB-type).<sup>2</sup> This approach allows access to more complex polythiophenes (e.g., PQT12, PBTTT, Figure 1) and to donor-acceptor (D-A) polymers. D-A polymers are ubiquitous active materials in organic electronic devices and thienyl units, e.g., 4,4'-bis(alkyl)-4H-cyclopenta-[2,1b:3,4-b']-dithiophene (CPDT), are privileged donor moieties in these materials.<sup>3</sup>



FIGURE 1. Selected thiophene containing polymers

Homo-bifunctional CPDT monomers are co-polymerized with bifunctional acceptors such as benzothiadiazole (BT) to form important D-A polymers (e.g. pCPDT-BT, pCPDT-TBTT) that have desirable properties (e.g., high charge mobility).<sup>3</sup> Indeed, thienyl

containing alternating D-A polymers are among the state of the art active components in organic photovoltaic devices (enabling power conversion efficiencies (PCEs) of over 10 %).<sup>2, 3</sup>

Whilst parameters such as charge mobility and PCE are crucial markers of polymer performance in devices another important but often overlooked criteria is the efficiency of monomer and polymer synthesis.<sup>4</sup> Low toxicity monomers that are available in good yield and excellent purity via simple synthetic routes and that undergo highly effective polymerization are crucial for the large scale development of printed electronics.<sup>4</sup> However, the copolymerization of an AA-type thienyl monomer with a BB-type acceptor monomer is dominated by the Stille cross coupling reaction which generally uses di-stannylated thienyl monomers.<sup>4d, 5</sup> This has drawbacks, including obtaining the di-stannylated thienyl monomer in sufficient purity (due to facile cleavage of thienyl-Sn bonds) making the precise control of stoichiometry in co-polymerizations challenging.<sup>6</sup> Furthermore, stoichiometric toxic tin waste is produced which is particularly problematic with the Me<sub>3</sub>Sn-thienyl derivatives (which generate volatile tin by-products but are still widely used due to the crystalline nature of many Me<sub>3</sub>Sn-monomers).<sup>1, 4d, 5</sup> Significant advances have been recently reported using direct (hetero)arylation polymerization (DHAP) which is a more efficient methodology (in terms of synthetic steps to produce the monomers and the quantity of waste by-products).<sup>5, 7</sup> However, for producing D-A polymers such as pCPDT-BT DHAP routes currently have a number of unsolved challenges (including low to moderate yields and / or homocoupling / branching defects) resulting in Stille cross coupling polycondensation protocols still being the dominant method to access a range of important thienyl containing co-polymers.<sup>4c,4d</sup>

The Suzuki-Miyaura cross coupling reaction utilizes organoboranes that have significantly lower toxicity than organostannanes. However, the utility of Suzuki-Miyaura polycondensation protocols in forming thienyl based co-polymers is extremely challenging due to the propensity of thienyl boronic acids (and derivatives) to undergo protodeboronation.8 This generally leads to low yields of pure borylated thienyl monomer or significant impurities in the crude monomer. The latter when combined with premature chain termination events caused by protodeboronation during the polymerization often leads to a reduction in polymer yield and lower than required molecular weights.9 Using pCPDT-BT as a representative example all the Suzuki-Miyaura polycondensation protocols reported to date have, to the best of our knowledge, drawbacks including: moderate monomer yields, complex monomer purifications (multiple flash chromatography cycles or recycling GPC), low to moderate polymer yields and significantly lower molecular weights relative to pCPDT-BT generated by Stille cross coupling polycondensation routes.<sup>10</sup> Therefore a general methodology for the Suzuki-Miyaura polycondensation of AA-/BB- type monomers to produce important thienyl containing alternating copolymers remains an outstanding goal. Key criteria for an ideal protocol are that high molecular weight polymers are formed in good yield from readily accessible, bench stable, crystalline thienyl boronate esters.



FIGURE 2: A comparison of previous routes to alternating thienyl copolymers and that reported herein using MIDA-boronate esters.

N-Methyliminodiacetic acid (MIDA) boronate esters are bench stable, crystalline solids that can be produced on scale from inexpensive commodity chemicals.<sup>11</sup> The use of MIDA boronate esters was pioneered by Burke and co-workers who showed that under optimal hydrolytic cross coupling conditions MIDA boronate esters slowly release the active boronic acid thus enabling high yielding Suzuki-Miyaura cross coupling reactions even with challenging substrates such as 2-pyridyl MIDA boronate esters.8c Furthermore, MIDA is biodegradable making the waste stream from cross coupling using these boronate esters relatively easy to handle.<sup>11h</sup> Since these seminal studies, MIDA boronate esters have become a wellestablished commercially available class of compounds that have enabled notable breakthroughs including: automated iterative synthesis; access to >75% of polyene natural product frameworks by Suzuki-Miyaura cross coupling reactions; stereoselective coupling of sp<sup>3</sup> moieties and the formal homologation of aryl boronate esters.<sup>11</sup> Whilst these are all impressive advances a modular copolymerization protocol using thienyl di-MIDA boronate esters to form important conjugated co-polymers is currently absent. An iterative coupling approach to oligothiophenes requires sequential deprotection, cross coupling and purification cycles and is thus not readily applicable to the formation of polymers, although a quaterthiophene has been made via this strategy.<sup>11b</sup> Herein we report the facile synthesis of highly pure and crystalline AA-type thienyl di-MIDA boronate ester monomers and show that using these monomers a single polycondensation protocol is viable for the formation of a wide range of important alternating copolymers that are produced in excellent yield and with high molecular weights that are comparable to those afforded by Stille cross coupling polymerization reactions.

## **Results and Discussion**

Due to the importance of fused thiophene building blocks in materials for organic electronic applications studies commenced with the extremely electron rich donor moiety CPDT. Previously, we reported the synthesis of 5-bromo-4-hexylthien-2-yl-MIDA boronate ester, 1 (Figure 3 inset bottom left), by electrophilic C-H borylation of 2-bromo-3-hexylthiophene.<sup>12,13</sup> A related procedure enabled the double electrophilic borylation of CPDT (Figure 3) with subsequent MIDA protection leading to crude monomer 3 in high conversion (by *in-situ* NMR spectroscopy). The isolation of this monomer in high yield required purification under anhydrous conditions, with standard purification by silica gel column chromatography using non-purified "wet" solvents leading to protodeboronation and the formation of significant quantities of mono-borylated product 4. The crystalline nature of 3 facilitated isolation under anhydrous conditions in 81 % yield on a multigram scale with single crystals obtained from MeCN / Et<sub>2</sub>O (a partial connectivity map from X-ray diffraction studies for 3 is shown in Figure 3, multiple attempts with a number of crystals only produced low quality data). It is noteworthy that the formation of 3 proceeds at ambient temperature using electrophilic borylation and does not require column chromatography during purification, thus is readily amenable to large scale synthesis. Compound 3 is stable as a solid for at least 12 months under an inert atmosphere and in the solid state 3 can be handled on the bench for several hours without any special precautions. While the di-MIDA thienyl monomers reported herein can be stored under ambient atmosphere as a solid for at least one week with no observable decomposition (by NMR spectroscopy) prolonged storage leads to slow protodeboronation (e.g., after 18 months pristine 3 had converted to a mixture of 86 % 3 / 14 %2).



FIGURE 3. Synthesis (and partial solid state structure) of 3.

Hydrolysis Studies. The protodeboronation of 3 during silica gel chromatography with "wet solvents" warranted investigation as it is essential to prevent this process during step growth polymerization reactions if high molecular weight polymers are to be obtained. Heteroaryl MIDA boronate esters are generally compatible with column chromatography and even stable towards strong Brønsted acids (e.g., triflic acid), with the stability attributed to the rigid tridentate chelation of boron by the MIDA dianion.<sup>11f</sup> NMR studies on 3 confirmed the rigid tridentate chelation of  $MIDA^2$  to boron persists to at least 100°C with the CH<sub>2</sub> groups of MIDA remaining diastereotopic over this temperature range. Furthermore, compound 3 proved stable towards protodeboronation by DCl (in Et<sub>2</sub>O) in anhydrous THF (for at least 1 h) indicating it is not 3, but a different compound derived from 3, that is undergoing protodeboronation under standard workup conditions using "wet" (nonpurified) solvents and silica gel chromatography. This suggests that BMIDA hydrolysis in 3 must be occurring in the absence of base (as workup conditions are base free) and it is a hydrolyzed boron species derived from 3 that is undergoing protodeboronation. This was confirmed by dissolution of 3 in  $d_8$ -THF containing  $D_2O$  (60 equiv. relative to 3) resulting in the slow hydrolysis of 3 at 23°C and formation of the boronic acid 5 (15 % of 3 is consumed after 24 h with the rate of hydrolysis accelerated at 55°C, with 86 % consumed after 24 h at 55°C).

1



SCHEME 1. Hydrolysis of 3 in THF/water to form 5.

Probing the hydrolysis of **3** in THF containing <sup>17</sup>O labelled water revealed that 5 contained labelled oxygen but the isolated diacid of MIDA produced from 3 did not (by <sup>17</sup>O NMR spectroscopy). Whilst isotopic scrambling of boronic acids in the presence of  $H_2^{17}O$  has been previously reported (thus incorporation of  $^{17}O$  into 5 is mechanistically inconclusive)<sup>14</sup> the absence of any <sup>17</sup>O in the MIDA diacid indicates that water is hydrolysing the B-O bonds in 3 and not the C-O bonds of the ester moiety. This observation is consistent with the recent detailed mechanistic study into the hydrolysis of MIDA boronate esters which also observed only B-O heterolysis under neutral conditions.<sup>15</sup> Thus during the work up water is hydrolysing the B-O bonds in 3 and a compound containing a partially dechelated MIDA (e.g., A, Scheme 1, although only 3 and 5 are observed by multinuclear NMR spectroscopy) or the boronic acid 5 is formed and then undergoes protodeboronation. It is notable that 5 ( $\delta_{11B}$  +26.4 ppm which is characteristic for a thienyl boronic acid) is stable in  $d_8$ -THF/D<sub>2</sub>O solutions for days (by <sup>1</sup>H NMR spectroscopy), this is consistent with the enhanced stability of 2-thienyl boronic acids at neutral pH.8e However, electron rich 5 undergoes rapid protodeboronation when exposed to Brønsted acids such as DCl (and presumably silica gel or H<sub>2</sub>MIDA).

The hydrolysis of 3 under conditions more relevant to cross coupling was also examined. It is essential for high fidelity cross coupling that the formation of the active boron transmetallating reagent derived from 3 (5 or [thienylB(OH)<sub>3</sub>]<sup>-</sup>) proceeds under optimal slow release conditions.8c Previously, optimal rates of hydrolysis of MIDA boronate esters were achieved using K<sub>3</sub>PO<sub>4</sub> as base, with complete BMIDA hydrolysis generally requiring 3-6 hours at 60°C in etherate/H<sub>2</sub>O mixtures.<sup>8c, 11</sup> However, monomer 3 undergoes slow hydrolysis at 55°C in d<sub>8</sub>-THF containing 60 equiv. of  $D_2O$  and 6 equivalents of  $K_3PO_4$  to produce 5, with only 50 % consumption of 3 observed after 24 h at 55°C. This is notably slower than the hydrolysis of 3 in the absence of  $K_3PO_4$  (under otherwise identical conditions). These basic THF/water solutions are biphasic, with a minor base rich aqueous phase.<sup>11d,e, 16</sup> The presence of a basic aqueous biphase will lower the concentration of water in the organic phase leading to a slower hydrolysis of the BMIDA moieties by water.<sup>15</sup> These in-situ hydrolysis studies were performed in NMR tubes fitted with J. Young valves that were not effectively stirred (either rotated at a frequency of 10 revolutions / min for 23°C reactions or not agitated for studies at 55°C). The low interfacial area between the two phases and poor mixing limit mass transport between the phases<sup>17</sup> slowing the BMIDA hydrolysis. Repeating the hydrolysis of 3 at  $55^\circ\text{C}$  in  $d_{8}\text{-}\text{THF/water}$  (60 equiv. of D<sub>2</sub>O, 6 equiv of K<sub>3</sub>PO<sub>4</sub>) in a Schlenk tube with stirring (900 rpm) to increase the interfacial area between phases led to more rapid BMIDA hydrolysis, consistent with improved mass transport between the two phases. However, even with stirring ca. 5 % of 3 remained after 24 hours at 55°C under these conditions. Incomplete hydrolysis of 3 during polymerization is highly undesirable as in step-growth polymerizations this would prevent the formation of high molecular weight polymers.



**FIGURE 4.** Hydrolysis of a 2 : 1 mixture of 1/3 in d<sub>8</sub>-THF/ D<sub>2</sub>O (30 equiv. relative to BMIDA) / 3 equiv of K<sub>3</sub>PO<sub>4</sub> (relative to BMIDA) at 55°C. Top, <sup>1</sup>H NMR spectra at various times, bottom, pseudo first order BMIDA hydrolysis kinetics. Compound **6** is the boronic acid derived from **1**. The resonance at 7.33 ppm is 2-Br-3-hexylthiophene produced from protodeboronation of **6**.<sup>18</sup>

The hydrolysis of the BMIDA groups in extremely electron rich 3 is slower than BMIDA hydrolysis in  $1.^{12}$  For a direct comparison under identical conditions 1 and 3 (in a 2 : 1 ratio to obtain a 1 : 1 ratio of the respective thienyl-BMIDA moieties) were combined with 3 equiv. of K<sub>3</sub>PO<sub>4</sub> (per BMIDA moiety) in d<sub>8</sub>-THF/water (30 equiv. of D<sub>2</sub>O per BMIDA moiety) and the hydrolysis monitored by NMR spectroscopy at 55°C. This confirmed that the BMIDA groups in 1 are hydrolyzed approximately twice as fast as those in 3 under pseudo-first order kinetics (Figure 4). The slower hydrolysis of the BMIDA groups in the more electron rich heteroaromatic 3 relative to 1 suggests a build-up of negative charge at boron during the hydrolysis process<sup>15</sup> and is consistent with studies on the rate of ester hydrolysis where more electron rich aromatic esters undergo slower ester hydrolysis.<sup>19</sup> It should be noted that the rate of hydrolysis of 1 is not changed by the presence (or absence) of 3 under otherwise identical conditions indicating that 3 does not significantly affect the phase separation or concentration of H<sub>2</sub>O (or base) in the THF phase.

Effective Suzuki-Miyaura polymerization reactions require faster hydrolysis of the BMIDA groups in 3 than that possible with K<sub>3</sub>PO<sub>4</sub> as the base under these conditions. Metal hydroxide salts

have been previously reported to give extremely rapid hydrolysis of BMIDA groups in aryl and heteroaryl MIDA boronate esters.<sup>8</sup>c Replacing  $K_3PO_4$  with KOH produced a biphasic system, and importantly led to faster hydrolysis of the BMIDA groups in 3 under identical reaction conditions. Boronic acid 5 was cleanly produced from 3 (e.g., 84 % conversion after 3 h at 55°C) with no protode-boronation products observed (2 is not observed after 3 h). This indicates that KOH is a more appropriate base than  $K_3PO_4$  for enabling release of the boronic acid from 3 at a suitable rate for polymerization under these specific biphasic conditions.

pCPDT-BT Polymerization Studies. The synthesis of pCPDT-BT from 3 and 4,7-dibromo-benzo[c]-1,2,5-thiadiazole, 7, was initially attempted utilizing K<sub>3</sub>PO<sub>4</sub> as base. This resulted in no significant polymer formation after 24 h at 55°C (table 1, entry 1) consistent with the aforementioned BMIDA hydrolysis studies. The absence of significant polymer was not due to pervasive chain termination by protodeboronation as CPDT-BMIDA groups were still present after 24 h of reaction (by NMR spectroscopy). Based on the BMIDA hydrolysis studies two equivalents of KOH were added to this reaction mixture to accelerate the hydrolysis of the BMIDA groups and subsequent heating for an additional 24 h now led to more effective polymerization (pCPDT-BT formed with  $M_p / M_w$  = 10.2 / 21.4 kDa). In contrast, no significant pCPDT-BT is produced in the absence of KOH even on further heating (72 h). This indicates that under these conditions: (i) active thienyl boronic species derived from 3 are still present even after prolonged heating at 55°C (with stirring at 900 rpm) in the presence of  $K_3PO_4/H_2O$ , (ii)  $K_3PO_4$  is not an effective base for the polymerization of 3 to form high molecular weight polymer due to the slow hydrolysis of the BMIDA moieties in 3.

Replacing K<sub>3</sub>PO<sub>4</sub> with KOH under otherwise identical polymerization conditions leads to highly effective polymerization and formation of high molecular weight pCPDT-BT (entry 2), with the polymerization complete within 24 h. Investigations into the effect of KOH stoichiometry confirms that 6 equiv. of KOH (relative to 3) is optimal. Notably, changing the hydroxide salt to nBu<sub>4</sub>NOH, which contains a cation that facilitates the phase transfer of salts into the organic phase,<sup>17</sup> leads to significantly lower molecular weight polymer being formed in lower yield (entry 3) than that with KOH as base. Analysis of the polymerization reaction mixture containing nBu<sub>4</sub>NOH indicated more rapid hydrolysis of BMIDA groups in 3 (relative to that with K<sub>3</sub>PO<sub>4</sub> and KOH) with no BMIDA moieties remaining after 4 h of reaction, with protodeboronation products also observed at this point (by multinuclear NMR spectroscopy). This disparity is presumably due to a greater concentration of base being present in THF when using nBu<sub>4</sub>NOH, with hydroxide documented to lead to rapid BMIDA hydrolysis.<sup>15</sup> Thus, in the polymerization of 3 under these conditions hydrolysis of the BMIDA groups with K<sub>3</sub>PO<sub>4</sub> as base is too slow (and incomplete even after 24 hours), whilst with nBu<sub>4</sub>NOH hydrolysis is too rapid leading to competitive protodeboronation and chain termination. In contrast, the use of KOH and biphasic mixtures provides an appropriate BMIDA hydrolysis rate leading to high molecular weight pCPDT-BT in high yield.

 TABLE 1. Polymerization of CPDT monomers and 7.

 $M \xrightarrow{S} M \xrightarrow{N} M \xrightarrow{N}$ 

				рСРОТ-ВТ		
	Method / Monomer	Yield	M <sub>n</sub>	M <sub>w</sub>	rof	
	(Base)	(%) <sup>b</sup>	(kDa)	(kDa)	iei	
1ª	Suzuki / M= BMIDA (K2PO4)	12	1.5°	2.7°	this work	
2ª	Suzuki / M= BMIDA (KOH)	98	42.5 <sup>d</sup> (21.5) <sup>c</sup>	130.0 <sup>d</sup> (40.4) <sup>c</sup>	this work	
3ª	Suzuki ∕ M= BMIDA (nBu₄NOH)	75	3.0°	5.7°	this work	
4	Stille / M = Me <sub>3</sub> Sn <sup>e</sup>	80	34.0	58.0	6	
5	DHAP / M = C-H <sup>f</sup>	40	38.2	80.0	7c	
6	Suzuki / M = BPin	56	14.1	47.2	10	
7	Suzuki / M = BPin	72	15.0	22.0	10	
8	Suzuki / M = BPin	63	11.7	31.0	10	

<sup>a</sup> T: 55°C, [3] = 3.5 × 10<sup>2</sup> M, Base: 6 equiv, H<sub>2</sub>O: 60 equiv, Pd<sub>2</sub>(dba)<sub>3</sub>: 2.5 mol%, SPhos: 5 mol%, solvent: THF, t: 24 h, 900 rpm stirring. <sup>b</sup> Isolated. <sup>c</sup>Determined by GPC (THF at 35 °C, PS calibration). <sup>d</sup> Determined by GPC (1,2,4-trichlorobenzene at 160°C, PS calibration). <sup>e</sup> This is a representative high  $M_{\rm w}$  polymer from a Stille coupling polymerization procedure. <sup>f</sup> Polymer with the minimum level of homocoupling / other defects chosen.

Using 6 equiv. of KOH (relative to 3) as base the formation of high molecular weight pCPDT-BT is essentially quantitative (entry 2) and does not require an excess of 3, with a 1 : 1 ratio of monomers effective (in contrast to Stille protocols).<sup>6</sup> The C<sub>6</sub>H<sub>5</sub>Cl Soxhlet fraction was isolated in 98 % yield as a dark green solid that was not fully soluble in THF even at raised temperatures (hence  $M_n / M_w$ determined by GPC in THF at 35 °C are not representative of the actual molecular weight distribution of this polymer, whereas pCPDT-BT produced using K<sub>3</sub>PO<sub>4</sub> or nBu<sub>4</sub>NOH, entries 1 and 3, are fully soluble in THF at 35 °C). Subsequent analysis in 1,2,4trichlorobenzene at 160°C revealed that extremely high molecular weight pCPDT-BT is formed using this methodology (entry 2). Extremely high molecular weight pCPDT-BT was obtained from several separate polymerizations run under identical conditions, confirming the reproducibility of this process. This is significant as high molecular weight pCPDT-BT ( $M_n > 20$  kDa) is essential for good hole mobility.<sup>20</sup> The <sup>1</sup>H NMR spectrum (70°C, C<sub>6</sub>D<sub>5</sub>Br) of this pCPDT-BT does not display any observable resonances corresponding to homo-coupling linkages indicating that the polymer has extremely low defect levels. Further analysis of this polymer (and the other thienyl polymers discussed below) by MALDI-TOF spectroscopy revealed only H/H, H/Br or Br/Br end groups, with no residual BMIDA groups observed, presumably these undergo hydrolysis and protodeboronation during quenching of the polymerization (using acidified MeOH). The UV-vis spectrum of this high molecular weight pCPDT-BT in chlorobenzene at room temperature ( $\lambda_{\text{max}}$  of absorption at 416 and 730 nm) was closely comparable to that reported for pCPDT-BT produced via other protocols,6 indicating comparable electronic properties (the other

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

polymers discussed below also have UV-vis absorption spectra comparable to that reported for the analogous polymer produced by other synthetic methods). The formation of high molecular weight pCPDT-BT from **3** is higher yielding than that reported for producing pCPDT-BT Stille polycondensation which also required super-stoichiometric quantities of the Me<sub>3</sub>Sn stannylated monomer due to protodestannylation (entry **4**).<sup>6</sup> Furthermore, the yield of pCPDT-BT produced via **3** is higher than that of low defect pCPDT-BT made via DHAP (entry **5**)<sup>7c</sup> and higher than pCPDT-BT made via other Suzuki-Miyaura cross coupling protocols from diborylated CPDT monomers (entries 6 to 8).<sup>10</sup> Therefore the copolymerization of **3** is an extremely effective methodology for producing pCPDT-BT of useful molecular weight, which combined with the high yielding formation of crystalline monomer **3** make this an attractive alternative to the established Stille protocols.

## Extension to form other CPDT co-polymers.

To be truly modular a new polymerization methodology needs to be effective for a range of nucleophilic and electrophilic coupling partners using a single set of polymerization conditions. If the rate of hydrolysis of the BMIDA moieties in 3 is the key factor in enabling effective polymerization then the same polymerization conditions should be viable for co-polymerizing 3 with different comonomers. To demonstrate this monomer 8 was co-polymerized with 3, as the resulting pCPDT-FBT polymers give excellent performance as the active component in bulk hetero-junction solar cells.<sup>21</sup> Analogous to the formation of pCPDT-BT, monomer 8 is polymerized effectively quantitatively to form pCPDT-FBT (table 2, entry 1) using identical polymerization conditions to that used for pCPDT-BT. The molecular weight of the resultant pCPDT-FBT polymer is lower than that achieved for pCPDT-BT derived from 3 possibly due to the lower solubility of pCPDT-FBT which may lead to premature polymer precipitation during the reaction.<sup>22</sup> Nevertheless, the molecular weight pCPDT-FBT formed from 3 is still sufficiently high for applications and it is formed in superior yield to that produced by Stille cross coupling polymerization protocols (95% using 3 Vs. 40-67% by Stille, e.g., entry 2 is a representative example).21,22

Polymerization of monomer 9 was examined as it is a dibromoheteroarene electronically distinct to 7 and 8 (an electron rich thienyl-bromide versus electron poor dibromo-benzothiadiazoles) whilst still being relevant for the production of high performing D-A polymers.<sup>2</sup> Furthermore, pCPDT-TBTT is a highly soluble polymer precluding any premature polymer precipitation that may have limited the molecular weight of pCPDT-FBT derived from 3. Using identical conditions to that successful for forming high molecular weight pCPDT-BT from 3 pCPDT-TBTT was produced in excellent yield and high molecular weight (entry 3) with both being greater than that reported for polymers produced by Stille cross coupling reactions (entry 4 is a representative example).<sup>23</sup> Therefore this polymerization protocol using monomer 3 is applicable to copolymerization reactions with a range of electronically distinct dibromo co-monomers. The importance of KOH as base in achieving appropriate slow release of the boronic acid again was confirmed using K<sub>3</sub>PO<sub>4</sub> as base instead of KOH under otherwise identical polymerization conditions. This produced pCPDT-TBTT in low yield (10%) and with low  $M_n / M_w$  (4.3 / 5.6 kDa) after 24 h. In situ NMR spectroscopy at this point revealed that thienyl BMIDA moieties remained, thus slow BMIDA hydrolysis was again limiting polymerization when using K<sub>3</sub>PO<sub>4</sub> under these conditions.



<sup>*a*</sup> T: 55°C, [3] =  $3.5 \times 10^2$  M, KOH: 6 equiv, H<sub>2</sub>O: 60 equiv, Pd<sub>2</sub>(dba)<sub>3</sub>: 2.5 mol %, SPhos: 5 mol %, solvent: THF, t: 24 h, 900 rpm stirring. <sup>*b*</sup> C<sub>6</sub>H<sub>5</sub>Cl fraction. <sup>*c*</sup>Isolated. <sup>*d*</sup>Determined by GPC (1,2,4-trichlorobenzene at 160°C, PS calibration). <sup>*c*</sup>Determined by GPC (THF at 35 °C, PS calibration).

#### Extension to other thienyl di-MIDA boronate esters.

For the formation of high molecular weight polymers derived from other thienyl MIDA boronate esters conditions enabling an appropriate rate of BMIDA hydrolysis have to be identified. For example, the hydrolysis of BMIDA in 1 is more rapid than that in 3 and thus optimal hydrolysis conditions for 1 required K<sub>3</sub>PO<sub>4</sub> and not KOH (in basic THF/water mixtures). This is exemplified by the Suzuki-Miyaura polymerization of 1 using KOH as base (under otherwise identical conditions) giving significantly poorer outcomes due to BMIDA hydrolysis being too fast and protodeboronation of the thienylboronic acid becoming a significant factor (P3HT produced from 1 with  $K_3PO_4$  as base yield = 90%,  $M_n/M_w = 13.8/24.1$  kDa;<sup>12</sup> with KOH as base yield = 47 %  $M_p/M_w$  = 10.0/14.1 kDa). Nevertheless, excluding the change in base the polymerization of 1 and 3 both proceed under otherwise identical conditions. Therefore, the identification of highly effective polymerization conditions for any new thienyl-MIDA boronate ester monomer should only require the identification of conditions that result in appropriate BMIDA hydrolysis rates using either  $K_3PO_4$  or KOH (at 55°C in THF / water).

To validate this hypothesis the synthesis of PQT12 from a thienyl di-MIDA boronate ester was investigated. PQT12 is a well-studied polymer with a number of synthetic routes previously reported; however, these generally proceed from the preformed quaterthiophene (often made via Stille cross couplings) or from copolymerization of Me<sub>3</sub>Sn-functionalised bithiophenes.<sup>7a, 2427</sup> The required di-MIDA boronate ester monomer **10** can be synthesized and isolated as a crystalline solid (a partial connectivity map from X-ray diffraction studies for **10** is shown in figure 5) on a multigram scale using an analogous electrophilic borylation methodology to that successful for **3**. Anhydrous work up conditions are again essential due to the hydrolysis and protodeboronation of **10** using standard isolation procedures and "wet" (non-purified) solvents.

## **TABLE 2.** The copolymerisation of 3 and Acceptor-(Br)2.



**FIGURE 5.** Left, compound 10 (including partial solid state structure) and right the formation of PQT12 and PBTTT from 10. a = determined by GPC at 70°C in  $C_6H_5Cl$ , PS calibration.

Prior to commencing polymerization studies the hydrolysis of the BMIDA moieties in 10 was explored in  $d_8$ -THF/D<sub>2</sub>O (60 equiv. relative to 10) using both  $K_3PO_4$  and KOH as the base (6 equiv. relative to 10). As expected both bases led to faster hydrolysis of the BMIDA moieties in 10 relative to those in the more electron rich 3. Again, K<sub>3</sub>PO<sub>4</sub> led to undesirably slow hydrolysis of the BMIDA moieties with a significant amount of 10 still remaining after 18 h at 55°C. Using KOH as base led to a more desirable BMIDA hydrolysis rate for subsequent slow release polymerization applications. The co-polymerization of 10 with 5,5'dibromobithiophene (in a 1 : 1 monomer ratio) was explored using identical polymerization conditions as previously utilized. This resulted in a higher yield and a higher molecular weight PQT12 using KOH as the base (Figure 5) relative to PQT12 formed using K<sub>3</sub>PO<sub>4</sub> as the base, fully consistent with the studies into the hydrolysis of BMIDA groups in 10. The molecular weight of POT12 formed from 10 using KOH as base is good for POT12 produced by the co-polymerization of two homo-bifunctionalized AA/BB-type monomers. Importantly, the PQT12 produced from 10 contains significantly more thiophene units than required to exhibit key desirable properties, with the effective conjugation length for PQT12 determined to be in the range of 22 thiophene units.28 Furthermore, we reiterate that the UV-vis spectra of the thienyl polymers produced using di-MIDA boronate ester monomers are effectively identical to that reported for the analogous polymer produced by other methodologies confirming comparable electronic properties of the polymers (e.g., for PQT12 made from 10  $\lambda_{\text{max}}$  = 470 nm, for PQT12 made via Stille coupling protocols  $\lambda_{max}$  =470 nm, both in CHCl<sub>3</sub>).<sup>28</sup>

Finally, with the standard polymerization conditions demonstrated to be viable for PQT12 formation from monomer 10 the synthesis of PBTTT was investigated. PBTTT exhibits desirable properties for organic electronic applications, e.g., good charge mobilities, but is generally synthesized by Stille co-polymerization protocols using Me<sub>3</sub>Sn-substituted bithiophenes.<sup>29</sup> The co-polymerization of 10 with 2,5-dibromo-thieno[3,2-b]thiophene under identical polymerization conditions used with monomer **3** and for forming PQT12 from **10** was effective for producing PBTTT in excellent yield and good molecular weight (Figure 5).<sup>30</sup> The PBTTT produced from **10** is comparable to that produced from Stille protocols,<sup>29</sup> this further confirms the generality of this Suzuki-Miyaura polycondensation procedure.

#### Conclusions

In conclusion, a scalable synthesis of thienyl-di MIDA boronate esters that can be isolated as highly pure crystalline solids in good to excellent yields is reported. Reaction conditions that enable desirable BMIDA hydrolysis rates have been identified and these have been applied for the synthesis of a range of important and electronically distinct thienyl containing alternating co-polymers. The co-polymers are all produced in excellent yield, have low defect levels and high molecular weights that are comparable to the analogous copolymers produced by Stille cross coupling protocols. Thus thienyl di-MIDA boronate esters represent a general, environmentally benign class of monomers useful for forming a range of important alternating co-polymers widely utilized in state of the art plastic electronic applications that are currently made using highly toxic trimethylstannyl functionalized monomers.

## ASSOCIATED CONTENT

#### Supporting Information

Full experimental, characterization and crystallographic details are available for all compounds. This material is available free of charge via the Internet at http://pubs.acs.org.

### **Corresponding Author**

Michael.ingleson@manchester.ac.uk Michael.turner@manchester.ac.uk

## ACKNOWLEDGMENT

This research has received funding from Conacyt (scholarship No. 311311), the EPSRC (EP/K03099X/1), the ERC (Grant No. 305868) and the Royal Society (the award of a URF to MJI). MLT thanks InnovateUK for financial support of the KCMC and the EPSRC Centre for Innovative Manufacturing in Large Area Electronics. Additional research data supporting this publication are available as supplementary information accompanying this publication. Dr Inigo Vitorica-Yrezabal, Dr James Raftery and Dr Jay Dunsford are thanked for crystallographic analysis of **3** and **10**, Dr Ralph Adams is thanked for useful discussions.

## REFERENCES

(1) (a) Handbook of thiophene based materials: Applications in organic electronics and photonics. Eds. Perepichka, I. F.; Perepichka, D. F., Wiley, **2009**. (b) McCullough, R. D. *Adv. Mater.* **1998**, *10*, 93.

(2) Lu. L.; Zheng, T.; Wu, Q.; Schneider, A. M.; Zhao, D.; Yu, L. Chem. Rev. 2015, 115, 12666.

(3) Guo, X.; Baumgarten, M.; Müllen, K. Prog. Polym. Sci. 2013, 38, 1832.
(4) (a) Osedach, T. P.; Andrew, T. L.; Bulovic, V. Energy Environ. Sci. 2013, 6, 711.
(b) Marrocchi, A.; Facchetti, A.; Lanari, D.; Petrucci, C.; Vaccaro, L. Energy Environ. Sci. 2016, 9, 763.
(c) Po, R.; Bianchi, G.; Carbonera, C.; Pellegrino, A.; Macromolecules 2015, 48, 453.
(d) Burke, D. J.; Lipomi, D. J., Energy Environ. Sci. 2013, 6, 2053.

(5) Morin, P.-O.; Bura, T.; Leclerc, M.; Mater. Horiz. 2016, 3, 11.

(6) Coffin, R. C.; Peet, J.; Rogers, J.; Bazan, G. C. Nat. Chem. 2009, 1, 657.

(7) For polythiophenes by DHAP: (a) Bura, T.; Morin, P.-O.; Leclerc, M.; Macromolecules 2015, 48, 5614. (b) Iizuka, E.; Wakioka, M.; Ozawa, F.; Macromolecules 2016, 49, 3310. (c) Kowalski, S.; Allard, S.; Scherf, U. Macromol. Rapid Commun. 2015, 36, 1061. For a recent perspective on DHAP: (d) Bura, T.; Blaskovits, J. T.; Leclerc, M. J. Am. Chem. Soc. 2016, 138, 10056.

(8) For a review of Suzuki-Miyaura polycondensation see: (a) Sakamoto, S.; Rehahn, M.; Schlüter, A. D. in *Design and synthesis of conjugated polymers*, eds. Leclerc, M.; Morin, J.-F. Wiley-VCH Verlag GmbH & Co. KGaA, Weinheim, **2010**, pp. 45–90. For a selection of articles discussion the protodeboronation of heteraryl borane species see: (b) Tyrrell, E.; Brookes, P. Synthesis **2003**, 469. (c) Knapp, D. M.; Gillis, E. P.; Burke, M. D. J. Am.

1

Chem. Soc. 2009, 131, 6961 (d) Kinzel, T.; Zhang, Y.; Buchwald, S. L. J. Am. Chem. Soc. 2010, 132, 14073. (e) Cox, P. A.; Leach, A. G.; Campbell, A. D.; Lloyd-Jones, G. C. J. Am. Chem. Soc. 2016, 138, 9145.

(9) This is particularly prevalent with more electron rich thienyl substitusubstituents, for a recent example see: Ji, L.; Edkins, R. M.; Sewell, L. J.; Beeby, A.; Batsanov, A. S.; Fucke, K.; Drafz, M.; Howard, J. A. K.; Moutounet, O.; Ibersiene, F.; Boucekkine, A.; Furet, E.; Liu, Z.; Halet, J.-F.; Katan, C.; Marder, T. B. *Chem. Eur. J.* **2014**, 20, 13618.

(10) To the best of our knowledge only three synthetic protocols have been previously reported to form pCPDT-BT from di-boronate esters of CPDT. (a) Bijleveld, J. C.; Shahid, M.; Gilot, J.; Wienk, M. M.; Janssen, R. A. J. Adv. Funct. Mater. 2009, 19, 3262. (b) Gibson, G. L.; McCormick, T. M.; Seferos, D. S. J. Am. Chem. Soc. 2012, 134, 539. (c) Lange, A.; Krueger, H.; Ecker, B.; Tunc, A. V.; von Hauff, E.; Morana, M. J. Polym. Sci., Part A. Polym. Chem. 2012, 50, 1622.

(11) For notable recent uses of MIDA boronates: (a) Li, J.; Burke, M. D.
J. Am. Chem. Soc. 2011, 133, 13774. (b) Li, J.; Ballmer, S. G.; Gillis, E. P.;
Fujii, S.; Schmidt, M. J.; Palazzolo, A. M. E.; Lehmann, J. W.; Morehouse,
G. F.; Burke, M. D. Science 2015, 347, 1221. (c) Woerly, E. M.; Roy, J.;
Burke, M. D. Nat. Chem. 2014, 6, 484. (d) Fyfe, J. W. B.; Seath, C. P.;
Watson, A. J. B. Angew. Chem. Int. Ed. 2014, 53, 12077. (e) Searth, C. P.;
Fyfe, J. W. B.; Molloy, J. J.; Watson, A. J. B. Angew. Chem. Int. Ed. 2015, 54, 9976. For reviews on MIDA boronate esters see (f) Gillis, E. P.; Burke, M. D. Aldrichimica Acta 2009, 42, 17. (g) Li, J.; Grillo, A. S.; Burke, M. D. Acc. Chem. Res. 2015, 48, 2297. For biodegradability of MIDA see: (h) Warren,
C. B.; Malec, E. J. Science 1972, 176, 277.

(12) Ayuso Carrillo, J.; Ingleson, M. J.; Turner, M. L. Macromolecules 2015, 48, 979.

(13) Bagutski, V.; Del Grosso, A.; Ayuso Carrillo, J.; Cade, I. A.; Helm, M. D.; Lawson, J. R.; Singleton, P. J.; Solomon, S. A.; Marcelli, T.; Ingleson, M. J. J. Am. Chem. Soc. 2013, 135, 474.

(14) Gierczyk, B.; Kazmierczak, M.; Schroeder, G.; Sporzynski, A. New J. Chem. 2013, 37, 1056.

(15) During the preparation of this manuscript we became aware of a detailed mechanistic study into the hydrolysis of BMIDA moieties. Gonzalez, J. A.; Ogba, O. M.; Morehouse, G. F.; Rosson, N.; Houk, K. N.; Leach, A. G.; Cheong, P. H. Y.; Burke, M. D.; Lloyd-Jones, G. C. *Nat. Chem.* **2016**, DOI: 10.1038/NCHEM.2571. Our independent findings are fully consistent with this work and the reader is directed to this more extensive study for further information.

(16) Lennox, A. J. J.; Lloyd-Jones, G. C. J. Am. Chem. Soc. 2012, 134, 7431.

(17) For phase transfer catalysis see: Ooi, T.; Marouka, K. Angew. Chem. Int. Ed. 2007, 46, 4222 (and references therein).

(18) The quantity of **5** present is lower than expected due to the formation of the borate dianion formed by addition of two equivalents of hydroxide to **5** which then transfers to the aqueous base biphase (and this dianion is observed by mass spectroscopy of this phase).

(19) Hammett, L. P. Chem. Rev. 1935, 17, 125.

(20) Morana, M.; Wegscheider, M.; Bonanni, A.; Kopidakis, N.; Shaheen, S.; Scharber, M.; Zhu, Z.; Waller, D.; Gaudiana, R.; Brabec, C. *Adv. Func. Mat.* **2008**, *18*, 1757

(21) For a recent report using pCPDT-FBT in devices see: Albrecht, S.; Janietz, S.; Schindler, W.; Frisch, J.; Kurpiers, J.; Kniepert, J.; Inal, S.; Pingel, P.; Fostiropoulos, K.; Koch, N.; Neher, D. J. Am. Chem. Soc. 2012, 134, 14932.

(22) Li, Y.; Zou, J.; Yip, H.-L; Li, C.-Z.; Zhang, Y.; Chueh, C.-C.; Intemann, J.; Xu, Y.; Liang, P.-W.; Chen, Y.; Jen, A. K.-Y. *Macromolecules* 2013, 46, 5497.

(23) Lee, S. K.; Cho, S.; Tong, M.; Hwa Seo, J.; Heeger, A. J. J. Polym. Sci. Part A Polym. Chem. 2011, 49, 1821.

(24) Thompson, B. C.; Kim, B. J.; Kavulak, D. F.; Sivula, K.; Mauldin, C.; Frechet, J. M. J. Macromolecules, 2007, 40, 7425.

(25) Ong, B. S.; Wu, Y.; Liu, P.; Gardner, S. J. Am. Chem. Soc. 2004, 126, 3378.

(26) Kokubo, H.; Yamamoto, T. Macromol. Chem. Phys. 2001, 202, 1031. (27) For a recent example of quaterthiophenes made via Stille couplings see: Brouwer, F.; Alma, J.; Valkenier, H.; Voortman, T. P.; Hillebrand, J.; Chiechi, R. C.; Hummelen, J. C. J. Mater. Chem. 2011, 21, 1582.

(28) Zhang, L.; Colella, N. S.; Liu, F.; Trahan, S.; Baral, J. K.; Winter, H.

H.; Mannsfeld, S. C. B.; Briseno, A. L. J. Am. Chem. Soc. 2013, 135, 844.

(29) McCulloch, I.; Heeney, M.; Bailey, C.; Genevicius, K.; Macdonald, I.; Shkunov, M.; Sparrowe, D.; Tierney, S.; Wagner, R.; Zhang, W.; Chabinyc, M. L.; Kline, R. J.; McGehee, M. D.; Toney, M. F. Nat. Mater. 2006, *5*, 328.

(30) GPCs on PBTTT were performed in PhCl at 70°C conditions in which not all PBTTT produced from 10 is soluble, therefore the actual molecular weight of PBTTT produced via this route will be higher.

