



Article

Subscriber access provided by UB + Fachbibliothek Chemie | (FU-Bibliothekssystem)

Highly Emissive Divalent Ion Doped Colloidal CsPb1– xMxBr3 Perovskite Nanocrystals through Cation Exchange

Ward van der Stam, Jaco J. Geuchies, Thomas Altantzis, Karel H.W. van den Bos, Johannes D. Meeldijk, Sandra Van Aert, Sara Bals, Daniël Vanmaekelbergh, and Celso de Mello Donegá *J. Am. Chem. Soc.*, **Just Accepted Manuscript •** DOI: 10.1021/jacs.6b13079 • Publication Date (Web): 04 Mar 2017 Downloaded from http://pubs.acs.org on March 5, 2017

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.



Journal of the American Chemical Society is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036 Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

Highly Emissive Divalent Ion Doped Colloidal $CsPb_{1-x}M_xBr_3$ Perovskite Nanocrystals through Cation Exchange

Ward van der Stam, $\dagger \| \Delta$ Jaco J. Geuchies, $\dagger \|$ Thomas Altantzis, \ddagger Karel H. W. van den Bos, \ddagger Johannes D. Meeldijk, Sandra Van Aert, \ddagger Sara Bals, \ddagger Daniel Vanmaekelbergh, \dagger and Celso de Mello Donega \dagger^*

AUTHOR ADDRESS

- Condensed Matter and Interfaces, Debye Institute for Nanomaterials Science, Utrecht University, P.O. Box 80000, 3508 TA Utrecht, The Netherlands
- EMAT, University of Antwerp, Groenenborgerlaan 171, B-2020 Antwerp, Belgium
- § Electron Microscopy Utrecht, Utrecht University, 3584 CH Utrecht, The Netherlands

|| These authors contributed equally to this work

ABSTRACT

Colloidal CsPbX₃ (X = Br, Cl, I) perovskite nanocrystals (NCs) have emerged as promising phosphors and solar cell materials due to their remarkable optoelectronic properties. These properties can be tailored not only by controlling the size and shape of the NCs, but also by postsynthetic composition tuning through topotactic anion exchange. In contrast, property control by cation exchange is still underdeveloped for colloidal CsPbX₃ NCs. Here, we present a method that allows partial cation exchange in colloidal CsPbBr₃ NCs, whereby Pb²⁺ is exchanged for several isovalent cations, resulting in doped CsPb_{1-x}M_xBr₃ NCs (M= Sn²⁺, Cd²⁺, Zn²⁺, $0 \le x \le 0.1$), with preservation of the original NC shape. The size of the parent NCs is also preserved in the product NCs, apart from a small (a few %) contraction of the unit cells upon incorporation of the guest cations. The partial Pb^{2+} for M^{2+} exchange leads to a blue-shift of the optical spectra, while maintaining the high photoluminescence quantum yields (>50%), sharp absorption features and narrow emission of the parent CsPbBr₃ NCs. The blue-shift in the optical spectra is attributed to the lattice contraction that accompanies the Pb^{2+} for M^{2+} cation exchange, and is observed to scale linearly with the lattice contraction. This work opens up new possibilities to engineer the properties of halide perovskite NCs, which are demonstrated to be the only known system up to date where cation and anion exchange reactions can be sequentially combined while preserving the original NC shape, resulting in compositionally diverse perovskite NCs.

KEYWORDS: Perovskite nanocrystals, cation exchange, CsPbBr₃, doped nanocrystals

INTRODUCTION

The recent development of colloidal CsPbX₃ (X = Cl, Br, I) perovskite nanocrystals (NCs) has resulted in a burst of scientific interest, owing to their outstanding optical properties.¹⁻³ Due to their high photoluminescence quantum yields (PLQY's up to 90%) without any additional surface passivation, and tunable optical properties throughout the entire visible spectrum, CsPbX₃ NCs are promising new materials for various optoelectronic applications, such as low threshold one- and two-photon pumped^{4,5} gain materials for lasing and highly efficient LEDs.⁶ Moreover, recently, colloidal CsPbI₃ NCs were used in solution processed photovoltaic cells with device efficiencies exceeding 10%.⁷

Currently, synthetic protocols for colloidal CsPbX₃ NCs with a variety of shapes are available, such as cubes,^{1,8} nanowires^{9,10} and nanoplatelets.^{2,11,12} Besides all-inorganic CsPbX₃ perovskite NCs, colloidal organic-inorganic perovskite NCs have also been recently prepared.^{2,13} Furthermore, the composition of colloidal halide perovskite NCs can easily be post-synthetically tailored through topotactic halide-exchange reactions with preservation of the size and shape of the parent NCs (despite a small lattice expansion or contraction, depending on the size of the guest halide).^{14,15} This is in striking contrast to what has been commonly observed for anion exchange reactions in colloidal II-VI semiconductor NCs, which typically result in severe size and shape transformations, often leading to hollow NCs.^{16,17}

Topotactic cation exchange reactions are commonplace in colloidal semiconductor II-VI and III-V NCs, allowing access to a variety of compositions and shapes that are not attainable through direct synthesis protocols.¹⁸⁻²² In contrast, post-synthetic cation exchange in colloidal CsPbX₃ perovskite NCs remains elusive, and has only been addressed in two recent works, which

 reported conflicting observations.^{14,15} While Akkerman *et al.* report the observation of CH₃NH₃⁺ (MA⁺) for Cs⁺ exchange in CsPbBr₃ NCs as an undesired complication in anion exchange protocols using MA-X salts,¹⁵ Nedelcu *et al.* state that attempts to exchange either Cs⁺ or Pb²⁺ for other cations (Rb⁺, Ag⁺, Cu⁺, Ba²⁺, Sn²⁺, Ge²⁺, or Bi³⁺) in CsPbBr₃ NCs were invariably unsuccessful and lead only to the decomposition of the parent NCs.¹⁴ The resistance of CsPbBr₃ NCs to cation exchange was rationalized by Nedelcu *et al.* as a consequence of the fact that the perovskite crystal structure is stabilized primarily by the rigid cationic sublattice.¹⁴

The introduction of impurity ions in colloidal II-VI and III-V semiconductor NCs provides another synthetic tool to control the optoelectronic properties and to bestow the parent NCs with novel functionalities, such as magnetism due to unpaired electrons in the dopant,²³ or increased effective Stokes shift due to exciton recombination on the impurity ions.^{24,25} Furthermore, impurity doping of perovskite thin films has been shown to improve their performance in solar cells.²⁶⁻²⁸ Recently, Mn²⁺ doping in colloidal CsPbCl₃ perovskite NCs has been achieved by a direct synthesis method, in which PbCl₂ and MnCl₂ precursors were mixed in the desired ratio, leading to NCs with the characteristic Mn²⁺ emission.²⁹ However, post-synthetic control over the perovskite composition by introducing different impurity ions has yet to be achieved.

In this work, we present a novel method to perform post-synthetic cation exchange reactions in CsPbBr₃ NCs, through which Pb^{2+} cations are partially replaced by divalent cations (M = Sn²⁺, Cd²⁺ and Zn²⁺), yielding doped CsPb_{1-x}M_xBr₃ NCs. The Pb²⁺ for M²⁺ cation exchange results in a blue-shift of the absorption and emission spectra, while preserving the high PLQY's (>50%) and narrow PL linewidth (80 meV) of the parent NCs. We attribute the blue-shift in the optical spectra to the contraction of the perovskite cubic unit cell, which results in shorter Pb-Br bonds and hence, a stronger ligand field within the Pb-halide octahedra. Interestingly, the blue-shift

scales linearly with the lattice contraction. A blue-shift of the PL maximum is also observed upon anion exchange reactions from iodide to chloride.^{14,15} However, blue-emitting CsPbCl₃ NCs obtained by anion exchange methods or direct synthesis protocols have low PLQY's (<15%) and broad PL linewidths (>120 meV),^{1,2,14,15} in contrast to the blue-emitting NCs synthesized with our approach (PLQY >50%, PL linewidth ~80 meV). Our work opens up many new possibilities to engineer the properties of halide perovskite NCs, which are demonstrated to be the only known system where topotactic cation and anion exchange can be sequentially combined, resulting in compositionally diverse colloidal CsPb_{1-x}M_xBr₃ perovskite NCs (M = Sn²⁺, Zn²⁺, Cd²⁺ and $x \le 0.1$) with size and shape preservation and high PL quantum yields.

RESULTS AND DISCUSSION

Optical properties. Colloidal CsPbBr₃ NCs (PL maximum at 512 nm) were reacted inside a nitrogen purged glovebox at room temperature with metal bromide salts (SnBr₂, CdBr₂, ZnBr₂) and oleylamine dissolved in toluene, which lead to a blue-shift of the absorption and PL spectra (Figure 1). The use of metal bromide salts as precursors for the guest cation ensures that solely the cation can be exchanged, since both the parent NCs and the precursor contain the same halide. The spectral position of the PL band blue-shifted over a wide range, depending on the divalent metal cation used and the precursor concentration (Figure 1a-c). Interestingly, although the blue-shift of the absorption and PL spectra is observed in all cases (*i.e.*, for all divalent cations and precursor concentrations), it is more pronounced for specific concentrations and cations. For example, the blue-shift is small (*i.e.*, 30 meV) for both low and high concentrations of SnBr₂ (0.25 mM SnBr₂, PL maximum at 506 nm; 1.7 mM SnBr₂, PL maximum at 504 nm; Figure 1d), but is much larger (170 meV) for a SnBr₂ concentration of 0.5 mM, resulting in

efficient PL in the blue region of the visible spectrum (PL maximum at 479 nm, PLQY 62%, see Supporting Information, Figure S1a). By varying the concentration of SnBr₂ in toluene, while keeping all other reaction parameters constant, the position of the PL maximum can be tuned between 479 nm and 512 nm. The increase in the SnBr₂ concentration also results in the appearance of a weak and broad absorption feature at ~580 nm. The possible nature of this transition and of the observed spectral blue-shift will be discussed later in this paper.

Reaction of the CsPbBr₃ NCs with other divalent ions (*i.e.* Cd^{2+} and Zn^{2+}) leads to more pronounced blue-shifts than reaction with SnBr₂, resulting in efficient PL between 452 nm and 512 nm for CsPbBr₃ NCs reacted with CdBr₂ and between 462 nm and 512 nm for CsPbBr₃ NCs reacted with ZnBr₂ (Figure 1e). The key spectral features of the parent CsPbBr₃ NCs, such as the sharp optical absorption edge, well-defined absorption peaks, and the narrow PL linewidth (FWHM ~80 meV), are maintained after reaction with metal bromide salts. High PLQY's over 60% are observed after reaction with divalent cations for all samples (see Supporting Information, Figure S1a). We note that the PL peak shifts further over time (100-200 meV over 4 weeks), due to the presence of metal bromide precursor in the stored colloidal dispersions, since the samples could not be purified due to difficulties with precipitation of the NCs. However, the NCs do not deteriorate, and maintain their size, shape, high PLQY's and colloidal stability in toluene over the course of (at least) several months. Furthermore, we find that the absorption increases with 2% over the first 90 min of reaction (see Figure S1b, Supporting Information). The increase in absorption on longer time scales is hard to quantify, since the absorption spectrum also shifts to higher energies. It has also been observed in other reports that colloidal perovskite NCs require very high centrifugation speeds to be destabilized from colloidal suspension and precipitated.³⁰ In the present case, such high centrifugation speeds also lead to

precipitation of the unreacted metal-bromide precursor, while using stronger anti-solvents (*e.g.*, methanol) deteriorates the NCs. A recent study by Luther and co-workers reported a novel purification procedure for perovskite NCs, involving methyl acetate as anti-solvent, which does not lead to degradation of the NCs, although still requiring high centrifugation speeds.⁷ We also used this purification method, but were able to recover only a very small amount of NCs from the reaction mixtures (see Experimental Section below for details).

The PL lifetimes of the parent CsPbBr₃ NCs and the product perovskite NCs after reaction with metal bromide salts were measured, displaying multi-exponential decay for all samples, both before and after the cation exchange reactions (Supporting Information, Figure S2). Therefore, the average lifetime (τ_{avg}) was calculated,³¹ which reveals that τ_{avg} is of the same order of magnitude (~10 ns) in all cases. Furthermore, we note that the higher the PL energy, the shorter τ_{avg} is, as expected based on Fermi's golden rule.³² For the CsPbBr₃ NCs reacted with SnBr₂, the average exciton lifetime (τ_{avg}) decreases from 16.8 ns for the parent CsPbBr₃ NCs to 6.8 ns for the product NCs obtained upon reaction with 1.7 mM SnBr₂. A decrease in τ_{avg} is also observed for the product NCs obtained upon reaction with CdBr₂ and ZnBr₂, to 6.4 ns and 7.2 ns, respectively.



Figure 1. Tunable photoluminescence of CsPbBr₃ nanocrystals upon reaction with divalent cation bromide salts. Photographs of colloidal suspensions under UV illumination of (**a**) perovskite NCs after reaction of CsPbBr₃ NCs with different concentrations of SnBr₂ (0.5 mM, 1.25 mM, 1.7 mM) (**b**) parent CsPbBr₃ NCs (right vial) and product NCs after reaction of CsPbBr₃ NCs with different concentrations of CdBr₂ (0.5 mM, 1.0 mM) and (**c**) parent CsPbBr₃ NCs (right vial) and product NCs after reaction of CsPbBr₃ NCs with different concentrations of CdBr₂ (0.5 mM, 1.0 mM) and (**c**) parent CsPbBr₃ NCs (right vial) and product NCs after reaction of CsPbBr₃ NCs with different concentrations of ZnBr₂ (0.5 mM, 1.0 mM). Photoluminescence (full lines) and absorption (dashed lines) spectra of (**d**) parent CsPbBr₃ NCs (green lines) and product NCs obtained after reaction with different concentrations of CdBr₂ (orange lines) and product NCs obtained after reaction with different concentrations of CdBr₂ (blue lines). In all cases, a blue-shift of both the absorption and the photoluminescence spectra is observed after reacting CsPbBr₃ NCs with divalent cation bromides, while the well-defined absorption features and the narrow PL FWHM (~80 meV) are preserved.

Lattice contraction after reaction with MBr₂ salts. Transmission Electron Microscopy (TEM) measurements reveal that the shape and size of the NCs are preserved after reaction with metal-bromide salts (Figure 2 and Supporting Information, Figure S3 and S4), since cubes of ~9 nm are observed in all cases. Electron Diffraction (ED) analysis shows that the atomic reflections are shifted to larger scattering vectors after the reaction with divalent ions. This indicates that the atomic CsPbBr₃ lattice contracts due to the incorporation of the smaller $Sn^{2+}/Cd^{2+}/Zn^{2+}$ guest cations (Figure 2d,h). The 1D Powder ED (PED) patterns (Figure 2d,h) were obtained by azimuthally integrating the 2D ED patterns, displayed as insets in the TEM images (Figure 2ac.e-g).³³ As displayed in Figure 2, the lattice contraction after reaction with Cd^{2+} and Zn^{2+} bromide salts is larger than after reaction with SnBr₂. This is expected based on the ionic radii of the divalent cations, in the case that Pb^{2+} ($r(Pb^{2+}) = 119$ pm, coordination number (CN) = 6) is replaced by the guest divalent cation ($r(Cd^{2+}) = 95 \text{ pm}$, $r(Zn^{2+}) = 74 \text{ pm}$, $r(Sn^{2+}) = 118 \text{ pm}$, CN = 6 in all cases).³⁴ Quantification of the $\{100\}$ d-spacing is displayed in Figure 2, panels d and h. The diffraction patterns were calibrated with both TlCl and Au reference samples (see Supporting Information, Supplementary Method 1 and Figure S5 and S6 for details).



Figure 2. Size and shape preservation and lattice contraction of CsPbBr₃ nanocrystals (NCs) after reaction with MBr₂ (reaction time: ~ 16 h). Transmission Electron Microscopy (TEM) images of (a) parent CsPbBr₃ NCs and (b,c) product NCs obtained after reaction of CsPbBr₃ NCs with different concentrations of SnBr₂ precursor (0.5 and 1.7 mM, respectively). The insets in (a-c) display the 2D Electron Diffraction (ED) patterns, which result in (d) 1D Powder ED (PED) patterns after azimuthal integration (concentration of SnBr₂: 0.25, 0.50, 1.0, 1.25, and 1.7 mM, from top to bottom, respectively). The colors of panels a-c correspond to the colors of the 1D PED patterns in panel d. TEM images of (e) parent CsPbBr₃ NCs and (f) product NCs obtained after reaction of CsPbBr₃ NCs with ZnBr₂ and (g) with CdBr₂. The insets in (e-g) display the 2D ED patterns, which result in (h) 1D PED patterns after azimuthal integration. The colors of panels e-g correspond to the colors of the 1D PED patterns in panel h. A large lattice contraction is observed upon reaction of CsPbBr₃ NCs with Cd^{2+} and Zn^{2+} (**h**), whereas a minor lattice contraction is observed upon reaction with Sn^{2+} (d). Quantification of the {100} d-spacing is given in panels d and h. Enlarged versions of the TEM images displayed in panels a-c and e-g, as well as the TEM images and ED patterns of the other samples, can be found in the Supporting Information (Figures S3 and S4).

The lattice contraction of CsPbBr₃ NCs after reaction with MBr₂ salts is also observed in the high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM)

images (Figure 3). Here, statistical parameter estimation theory is used to extract structure parameters from the images.^{35,36} One of the structure parameters corresponds to the atomic column positions, which have been used to estimate the absolute distance between neighboring Pb/halide columns in order to quantify the lattice parameter (Figure 3). By fitting a normal distribution to these distance estimates, the mean lattice parameter has been determined. The lattice parameter of the parent CsPbBr₃ NCs was calibrated to the value reported in the literature for the cubic perovskite structure of CsPbBr₃. A lattice contraction from $|a| = 5.849 \pm 0.003$ Å to $|a| = 5.839 \pm 0.005$ Å is observed upon reaction of CsPbBr₃ NCs with 0.5 mM SnBr₂. The obtained CsPbBr₃ unit vector corresponds well to recent X-ray diffraction experiments for the cubic perovskite crystal structure, but does not exclude the presence of a small portion of orthorhombic distortions of the octahedra in the atomic lattice.³⁷ Similar analysis on CsPbBr₃ NCs reacted with 0.5 mM CdBr₂ and 1.0 mM ZnBr₂ shows a lattice contraction from |a| = 5.849 ± 0.003 Å to $|a| = 5.819 \pm 0.008$ Å (Cd²⁺) and $|a| = 5.808 \pm 0.014$ Å (Zn²⁺), respectively. We do not observe clustered areas with larger/smaller lattice vectors in the images showing the deviations from the mean lattice vector (Figure 3, middle row, red: larger than mean distances, blue: smaller than mean distances). From this we deduce that the incorporated guest cations are homogeneously distributed throughout the NCs. Thickness profiles obtained from the total scattered intensities of the atomic columns confirm this observation (Figure S7).

As can be seen, the lattice contraction for Cd- and Zn-dopants (0.5 % and 0.7 %, respectively) is larger than for the Sn-doped NCs (0.2%), which is in full agreement with the electron diffraction data presented in Figure 2. The statistical student's t-test with unequal variances has been used to verify that the found differences are significant.³⁸ Here, the distribution of the measured lattice parameters of the parent CsPbBr₃ NCs have been compared to a distribution of

the measurements on the doped $CsPb_{1-x}M_xBr_3$ NCs at a significance level of 10%, indicating that the distributions have different means. Based on these results, we conclude that guest divalent cations are indeed present in the perovskite NCs and are distributed homogeneously across the perovskite lattice.



Figure 3. Quantitative High-Angle Annular Dark-Field STEM measurements reveal a lattice contraction of (a) parent CsPbBr₃ NCs ($|a| = 5.849 \pm 0.003$ Å) upon reaction with (b) 0.5 mM SnBr₂ ($|a| = 5.839 \pm 0.005$ Å), (c) 0.5 mM CdBr₂ ($|a| = 5.819 \pm 0.008$ Å) and (d) 1.0 mM ZnBr₂ ($|a| = 5.808 \pm 0.014$ Å) (reaction time: 16 h). In the HAADF-STEM images, the mixed Pb/halide (bright contrast), Cs (intermediate contrast) and halide (low contrast) atomic columns can be easily assigned (top panels). After detecting the positions of the Pb/halide columns from the HAADF-STEM images, we calculate the interatomic distances (*i.e.* the lattice spacing, middle panels). Red bars indicate a larger distance than the mean |a| and blue bars a smaller distance than the mean |a|. The histogram of distances together with the estimated normal distribution

reveal a contraction of the cubic perovskite CsPbBr₃ atomic lattice upon reaction with SnBr₂, CdBr₂ and ZnBr₂ NCs (bottom panels).

Elemental analysis. The results presented above suggest that Pb²⁺ cations in CsPbBr₃ NCs are replaced by other divalent cations, *i.e.* $\text{Sn}^{2+}/\text{Cd}^{2+}/\text{Zn}^{2+}$, resulting in a lattice contraction due to the smaller ionic radius of the incorporated cations. To verify the incorporation and the distribution of the guest cations, Energy Dispersive X-ray Spectroscopy (EDS) chemical mapping was performed. We note that the EDS measurements were performed on areas containing a large amount of NCs, in order to obtain a statistically relevant result. The EDS measurements show that Cd (Figure 4a-e) and Zn (Figure 4f-j) are incorporated in the CsPbBr₃ NCs in low concentrations. Moreover, no indication for surface preference or phase segregation is observed, which leads us to conclude that the distribution of the guest cations within the $CsPb_{1-x}M_xBr_3$ NCs is homogeneous, consistent with the observations presented above. Quantification of the EDS measurements reveals a Cd:Pb ratio of 0.16 for the product CsPb_{1-x}Cd_xBr₃ NCs obtained after 16 h reaction with 0.5 mM CdBr₂ (Supporting Information, Figure S8-S10) and a Zn:Pb ratio of 0.05 for the product $CsPb_{1-x}Zn_xBr_3$ NCs obtained after 16 h reaction with 1.0 mM ZnBr₂ (Supporting Information, Figure S11). The CsPbBr₃ NCs reacted with 0.5 mM SnBr₂ for 16 h were also analyzed with bulk EDS measurements, which reveal a Sn:Pb ratio of 0.1 (Supporting Information, Figure S12). We also performed an EDS quantification of the product $CsPb_{1}$ $_{x}Cd_{y}Br_{3}$ perovskite NCs, and of portions of the TEM grid surrounding clusters of NCs (*i.e.* the background). This analysis clearly shows a Cd peak at 3.1 keV for the area containing NCs, whereas Cd-peaks are below the noise level in the background (see Supporting Information, Figure S13). The EDS analysis thus clearly demonstrates that divalent guest cations are

successfully incorporated in CsPbBr₃ NCs upon reaction with MBr₂ salts. It should be noted that the elemental concentrations are upper limit estimates, since the samples were not washed prior to the EDS measurements (see experimental section for details). A few selected samples were thoroughly purified by precipitating with methyl acetate, which yielded only very small amounts of NCs (see experimental section for details). The purified NCs showed reduced carbon contamination upon prolonged exposure to the e-beam (see Supporting Information, Figure S14). Furthermore, the Sn:Pb ratio for purified NCs (0.085, see Supporting Information Figure S15) was similar to the Sn:Pb ratio for the unpurified samples (0.1, see Supporting Information Figure S12). This lead us to conclude that the above presented cation:Pb ratios are valid upper limit estimates for the incorporated divalent cations. A possible mechanism for the post-synthetic incorporation of divalent cations into CsPbBr₃ NCs will be discussed below.

It must be noted that we observe bright spots on the CsPbBr₃ NCs upon exposure to the electron beam (see *e.g.* Figure 4). High resolution HAADF-STEM analysis shows that these spots correspond to metallic Pb nanoparticles (Supporting Information, Figure S16). This implies that, upon imaging the NCs with an electron beam, part of the Pb²⁺ ions are reduced to metallic Pb. Furthermore, the measured atomic ratios indicate that the parent CsPbBr₃ NCs are halide deficient (Cs:Pb:Br = 1:1:2; ratio cation charge/anion charge= 1.5, Supporting Information, Figure S8), and that the halide deficiency is preserved after reaction with MBr₂ salts (ratio cation charge/anion charge= 1.5, Supporting Information ratios significantly larger than unity are commonly observed for NCs of II-VI (*e.g.*, CdSe) and IV-VI (*e.g.*, PbSe) semiconductors synthesized in the presence of X-type ligands (*e.g.*, oleate), and have been rationalized by considering that the stoichiometric NC is coated by a layer of M-X units.³⁹

d

from Cs-oleate and Pb-oleate. Nevertheless, halide deficiency is commonly observed in bulk perovskites, due to the very low activation energies for the creation of anion vacancies in these materials,⁴⁰⁻⁴² and is likely also present in perovskite NCs. Density Functional Theory calculations show that anion vacancies do not result in mid-gap trap states in halide perovskites, since their energy levels lie within the conduction band.⁴³ Therefore, despite the presence of halide vacancies, the exciting optoelectronic properties of the parent CsPbBr₃ NCs, such as high PLQY and sharp excitonic features, are preserved in the product CsPb_{1-x}M_xBr₃ NCs.

Figure 4. Energy Dispersive X-ray Spectroscopy mapping of $CsPb_{1-x}Cd_xBr_3$ and $CsPb_1_xZn_xBr_3$ nanocrystals. (a) HAADF-STEM image of $CsPb_{1-x}Cd_xBr_3$ NCs and the corresponding (b) Cs map, (c) Pb map, (d) Br map and (e) Cd map, demonstrating the presence of Cd in the perovskite NCs. The inset in panel (a) shows a photograph of a colloidal suspension of the NCs under UV illumination. (f) HAADF-STEM image of $CsPb_{1-x}Zn_xBr_3$ NCs and the corresponding (g) Cs map, (h) Pb map, (i) Br map and (j) Zn map, indicating the presence of Zn in the perovskite NCs. The inset in panel (f) shows a photograph of a colloidal suspension of the NCs under UV illumination. The bright spots observed in the HAADF-STEM images are metallic Pb

nanoparticles, formed upon prolonged exposure to the electron beam (see Supporting Information, Figure S16).

Cation exchange mechanism in CsPbBr₃ NCs. The results presented above clearly show that divalent guest cations $(Sn^{2+}, Cd^{2+}, Zn^{2+})$ can be incorporated into CsPbBr₃ NCs by post-synthetic cation exchange reactions. Considering that aliovalent exchange of Cs⁺ (radius: 1.88 Å) for M²⁺ would strongly destabilize the perovskite structure, since it would result in smaller M²⁺ cations in sites with coordination number 12 and would require charge compensation, we will assume below that only isovalent exchange of Pb²⁺ for M²⁺ has taken place, leading to partial substitutional replacement of PbBr₆ octahedra by MBr₆ octahedra (Figure 5).



Figure 5. Schematic overview of partial cation exchange in CsPbBr₃ nanocrystals. Pb^{2+} cations are partially replaced by other divalent cations (Sn²⁺, Cd²⁺, Zn²⁺) by post-synthetic cation exchange reactions, resulting in divalent cation doped CsPb_{1-x}M_xBr₃ NCs (the MBr₆ octahedra are schematically depicted by the blue metal-halide octahedra). Incorporation of smaller divalent cations results in contraction of the atomic lattice, which induces a blue-shift of the optical transitions (absorption and PL). The halide anions are depicted smaller for clarity.

Cation exchange reactions have been extensively investigated in NCs of II-VI, IV-VI, III-V, and I-VI semiconductors,^{18-22,44,45} and shown to consist of several inherently linked elementary kinetic steps, which must proceed in a concerted way. The first step is the extraction of the native cation from the parent NCs, which may occur by a direct place exchange reaction (*i.e.*, extraction of the native cation and incorporation of the guest cation occur in a direct reaction mediated by a ligand in solution, e.g. Zn^{2+} for Cd^{2+} exchange in ZnSe mediated by oleate ligands⁴⁴), or by an independent chemical pathway that is only kinetically coupled to the incorporation of the guest cation (*e.g.*, cation exchange in $Cu_{2-x}S$ NCs in the presence of excess phosphines).⁴⁶ The rates of extraction of the native cation and incorporation of the guest cation must be balanced, otherwise the accumulation of cation vacancies eventually leads to the collapse of the NC.^{20,21} There are several factors involved in the cation extraction process, such as breaking of the cation-anion bonds within the NC and formation of cation-ligand bonds, while the incorporation of the guest cation requires breaking the cation-ligand bonds and formation of the cation-anion bonds in the NC.^{18,20} The thermodynamic driving force for the cation exchange is determined by the energy balance of the overall reaction. It should also be noted that the cation exchange process is essentially a surface reaction, which, in the absence of cation diffusion in the NC, would stop as soon as all surface cations had been exchanged by the guest cations.⁴⁴ Therefore, the cation exchange rates are often limited by the diffusion rates of the outgoing and incoming cations.^{18,20,44} Cation diffusion in semiconductor NCs is often attributed to vacancy-mediated migration,^{18,20,44,45} and its rate is therefore limited by the activation energies for vacancy formation.

Cation exchange reactions have not vet been studied in detail in perovskite NCs, but topotactic

anion exchange has been shown to be very efficient and fast in CsPbX₃ (X= Cl, Br, I) halide perovskite NCs.^{14,15} due to the low activation energy for the formation and diffusion of halide vacancies in these materials.^{14,15} In contrast, cation diffusion in perovskites is a very slow process, owing to the high activation energies for the formation of cation vacancies and the lack of interstitial sites for interstitial diffusion. A recent study on bulk CH₃NH₃PbI₃ has concluded that vacancy-assisted iodide diffusion in this perovskite material has an activation energy of only 0.58 eV, leading to fast diffusion even at room temperature (diffusion coefficient: 10^{-12} cm².s⁻¹), while cation diffusion has much higher activation energies (0.84 eV and 2.31 eV for $CH_3NH_3^+$ and Pb^{2+} , respectively).⁴⁷ As a result, $CH_3NH_3^+$ diffusion is four orders of magnitude slower than Iodide diffusion, and the Pb²⁺ sublattice is essentially immobile.⁴⁷ This implies that cation exchange processes involving Pb^{2+} in CsPbX₃ perovskites would be limited by very slow diffusion fluxes for both the outgoing Pb^{2+} and the incoming M^{2+} guest cations. Our results show that this is indeed the case, since the Pb^{2+} for M^{2+} exchange reaction is very slow and only occurs partially, despite the large excess of M²⁺ cations with respect to the parent CsPbBr₃ NCs (from 8×10^3 to 3×10^5 , see Experimental Methods). The number of Pb²⁺ cations in a 9 nm CsPbBr₃ NC is ~3600 (unit cell volume: 0.2 nm³, NC volume: 729 nm³). This means that even in the low precursor concentration regime, there is a two-fold excess of guest M^{2+} cations with respect to Pb^{2+} , implying that full exchange would be possible, if a sufficiently strong driving force would be present. As it will be discussed below, the fact that the cation exchange does not reach completion despite the large M/Pb ratios used, shows that the driving force is small and that the reaction may in fact be self-limited.

Page 19 of 39

The use of metal bromide precursors has multiple benefits in our cation exchange protocol, leading to successful partial exchange of Pb²⁺ for M²⁺ cations in CsPbBr₃ NCs, resulting in doped CsPb_{1-x}M_xBr₃ NCs. The presence of Br in the guest cation precursor allows us to take advantage of the ease of formation of halide vacancies in CsPbX₃ NCs and to explore the fact that CsPbX₃ NCs quickly establish an equilibrium with solvated halides in the solution phase, especially in the presence of amines, allowing fast cross-exchange between NCs with different halides.^{14,15} Given that MBr₂ does not dissociate in toluene, it binds to the surface Br vacancies as a molecular unit, thereby incorporating MBr_2 in the NC. This releases energy due to the formation of bonds between the incoming Br and the NC, but does not consume energy because the M-Br bonds do not need to be broken. The energy released can then be used to break the bonds between a PbBr₂ unit and the NC. Because the bonds formed and broken are similar, the energy balance is close to zero, and therefore the surface Pb²⁺ cations can be quickly exchanged into guest M^{2+} cations, despite the low temperatures (*i.e.* room temperature) used in our cation exchange protocol. To allow the cation exchange process to continue, two diffusion fluxes have to be established: inward diffusion of guest M^{2+} cations and outward diffusion of Pb^{2+} cations. As discussed above, these fluxes will be slow, since they have high activation energies, and will be primarily driven by the increase in entropy that results from the formation of $C_{s}Pb_{1-x}M_{x}Br_{3}$ solid solutions. However, the exchange of Pb^{2+} by smaller M^{2+} cations leads to a progressive contraction of the lattice, which leads to strain within the NC. This increasing strain field counteracts the entropic gain, eventually becoming sufficiently strong to halt the cation exchange process. This could be a reason for a self-limited cation exchange, as we have observed here for several isovalent ions. A schematic representation of the cation exchange mechanism proposed above is given in the Supporting Information (Figure S17).

The fact that the lattice contraction (and therefore the extent of Pb^{2+} for M^{2+} exchange) does not directly scale with the concentration of MBr_2 precursors, but instead reaches a maximum at intermediate concentrations, can be rationalized by considering that the cation exchange is actually driven by the concentration of halide vacancies in the template CsPbBr₃ NCs, as discussed above. The formation of halide vacancies is promoted by the OLAM molecules present in solution,^{14,15} which nevertheless can form OLAM-Br complexes with halides from both NCs and MBr₂ precursors. As a result, the increase in the concentration of MBr₂ in the reaction medium will eventually decrease the cation exchange rates by outcompeting the NCs for the limited supply of OLAM, thereby decreasing the formation rate of halide vacancies.

We have also performed a series of experiments at fixed SnBr₂/NC concentration and total volume, but different OLAM concentrations (Supporting Information, Figures S18 and S19). We find that the position of the PL peak after the reaction depends on the amount of OLAM present in solution, but the exact trend depends on the reaction time: for short reaction times (48 h, Figure S18) the blue-shift is larger for lower OLAM concentrations, while for longer reaction times (84 h, Figure S19) the opposite trend is observed. These observations are consistent with the mechanism proposed above and can be rationalized by considering that the cation exchange is driven by the formation of anion vacancies in the NCs, but is rate-limited by inward diffusion of the guest cations (*i.e.*, surface sites have to be made available to allow the process to proceed). Therefore, increasing the concentration of surface halide vacancies does not directly increase the extent of the cation-exchange at shorter reaction times because the cation diffusion rates remain constant. Under these conditions, OLAM will extract from the NC surface not only Br but also SnBr₂. Therefore, higher OLAM concentrations decrease the relative extent of the cation exchange in the short reaction time regime by shifting the equilibrium towards solvated SnBr₂.

The inward diffusion of SnBr₂ competes with its removal from the surface by OLAM, and, albeit slowly, gradually moves Sn^{2+} away from the surface, thereby incorporating it into the NC lattice. As a result, after sufficiently long reaction times (*e.g.*, 84 h, Figure S19) the concentration of guest cations incorporated in the NCs will reflect the equilibrium concentration of halide vacancies, and will thus be larger for higher OLAM concentrations. It should be noted that higher OLAM concentrations induce shape distortions and structural changes after long reaction times (Supporting Information, Figure S19), indicating that large excesses of OLAM lead to partial deterioration of halide vacancies and the cation exchange rates. We have also observed that the PL intensity of the product CsPb_{1-x}Sn_xBr₃ NCs is higher for reactions carried out under higher OLAM concentrations (see Supporting Information, Figure S18), which can be attributed to a better surface passivation, either by OLAM molecules or by oleylammonium bromide formed in-situ.³⁰

Lattice contraction and blue-shift of the optical transitions. Interestingly, the PL energy of doped $CsPb_{1-x}M_xBr_3$ perovskite NCs scales linearly with the lattice vector (Figure 6) independently of the type of cation that has been incorporated. This is most evident for the Sn-doped NCs, for which more data points are available (Figure 6a), but is also clear when the other two cations are taken into account (Figure 6b).



Figure 6. Photoluminescence (PL) energy and lattice vector correlation in CsPb_{1-x}M_xBr₃ perovskite NCs. (a) PL energy as a function of the lattice vector in doped CsPb_{1-x}Sn_xBr₃ NCs obtained by post-synthetic Pb²⁺ for Sn²⁺ cation exchange in parent CsPbBr₃ NCs. (b) PL energy as a function of the lattice vector in doped CsPb_{1-x}M_xBr₃ (M= Sn, Cd, Zn) NCs obtained by post-synthetic Pb²⁺ for M²⁺ cation exchange in parent CsPbBr₃ NCs. The different colors of the symbols in panels (a) and (b) correspond to the colors used to identify the different samples in Figures 1 and 2.

The bandgaps of ABX₃ perovskites are known to increase with the increase of the electronegativity of both B and X atoms and with the decrease of the unit cell volume.⁴⁸ It is thus quite remarkable that the trends for the three cations are very similar despite their different radii, electronic configurations and properties (Pb²⁺ [5d¹⁰6s²6p⁰]: r= 119 pm, electronegativity χ = 1.6;

 Sn^{2+} [4d¹⁰5s²5p⁰]: r= 118 pm, χ = 1.7; Cd²⁺ [4d¹⁰5s⁰]: r= 95 pm, χ = 1.5; Zn²⁺ [3d¹⁰4s⁰]: r= 74 pm, χ = 1.7; polarizability and Lewis hardness decrease from Pb²⁺ to Zn²⁺). This implies that the observed blue-shift of the optical transitions is primarily due to the lattice contraction, and that the MBr₆ guest octahedra are electronically decoupled from the PbBr₆ framework. This is particularly clear for the Sn-doped NCs, since it is reported in literature that the band gap of CsSnBr₃ and CsPb_{1-x}Sn_xBr₃ are red-shifted with respect to that of CsPbBr₃.^{49,50} This shows that the band-edge absorption and the PL transition of the CsPb_{1-x}Sn_xBr₃ NCs prepared in this work are solely determined by the PbBr₆ octahedra, despite the presence of SnBr₆ groups in the NC. The additional feature observed at lower energies (540-600 nm) in the absorption spectra of the CsPb_{1-x}Sn_xBr₃ NCs (Figure 1d) can thus be ascribed to these electronically isolated SnBr₆ octahedra.

The PL transition of ABX₃ halide perovskites has also been reported to blue-shift upon proceeding along the I, Br, Cl series, as clearly illustrated by the PL tunability achieved by synthetic and post-synthetic compositional control in both bulk and nanocrystalline ABX₃.^{14,15,51,52} Although this is accompanied by a contraction of the unit cell, the PL shift does not depend linearly on the lattice contraction, since the widening of the band gap is largely due to the increase in electronegativity along the halide series, which effectively increases the ionic character of the B-X bond.^{48,51,52}

In fact, our work provides the first clear observation of a linear relationship between lattice vector and PL energy in perovskites. A recent work reported a blue-shift of the PL peak of bulk CsSnBr₃ upon warming (lattice expansion),⁵³ in striking contrast with our results. Similar observations (*i.e.*, PL blue-shift with increasing temperature) have also been reported for CsPbBr₃ NCs⁵⁴ and bulk CsSnI₃.⁵⁵ However, it should be noted that this behavior (linear increase

of the bandgap with increasing temperature) is anomalous, since most semiconductors show the opposite temperature-dependence (*i.e.*, linear increase of the bandgap with decreasing temperature).⁵⁵⁻⁵⁸ This anomalous temperature-dependence is also observed for copper halides (CuBr, CuCl), lead chalcogenides, and black phosphorus, and has been attributed to a dominance of the lattice thermal expansion contribution over the electron-phonon interaction contribution.^{55,57} In the specific case of CsSnBr₃ and CsPbBr₃ the widening of the bandgap upon lattice expansion is ascribed to simultaneous narrowing and stabilization of both the valence and conduction bands, as a result of the antibonding character of their maximum and minimum, respectively.⁵³

PL shifts have also been recently reported for MAPbX₃ bulk films and single crystals subjected to high-pressures.^{59,60} Interestingly, small red-shifts (\leq 50 meV) were observed in the lowpressure regime (below 0.35-1 GPa), while strongly non-linear blue-shifts (up to 200 meV) were observed in the high-pressure regime (above 1-2.5 GPa), and were ascribed to amorphization of the MAPbX₃ lattice.^{59,60} This explanation is however inadequate for the PL blue-shifts reported in our work, since we do not observe any signs of loss of crystallinity, disorder or phase transitions in the doped CsPb_{1-x}M_xBr₃ NCs obtained by post-synthetic Pb²⁺ for M²⁺ cation exchange, despite very clear lattice contractions. It should be pointed out that also from this perspective the behavior of bulk ABX₃ halide perovskites seems to be anomalous, since the PL of most common semiconductors (*e.g.* GaN, CdTe) blue-shifts linearly with increasing pressure.^{61,62}

The behavior observed for the $CsPb_{1-x}M_xBr_3$ NCs prepared in the present work by postsynthetic Pb^{2+} for M^{2+} cation exchange in 9 nm $CsPbBr_3$ NCs is thus in line with the normal pressure-dependence of the bandgap energies of bulk semiconductors, but is opposite to what is

observed for bulk ABX₃ halide perovskites.^{59,60} This is striking, and is likely due to nanoscale effects. The contribution of quantum confinement effects to the blue-shift observed in the optical spectra of the CsPbBr₃ NCs after the cation exchange reaction is however negligible, since the NCs under study here are larger than the estimated exciton Bohr diameter for CsPbBr₃ (*viz.*, 7 nm),¹ and are therefore in the weak confinement regime. Although the reduction in the NC size should result in an increase in quantum confinement, the effect would be too small to account for the magnitude of the spectral shifts observed after the cation exchange reactions (up to 300 meV, which would require a size reduction from 9 nm to ~5 nm, according to the theoretical size dependence of the band gap reported in ref. 1). Furthermore, Protesescu *et al.* have shown that blue-emitting CsPbBr₃ NCs are in the sub-4 nm size regime,¹ whereas the CsPb_{1-x}M_xBr₃ NCs obtained in this work have a diameter of 9 nm and yet display efficient PL in the blue region of the electromagnetic spectrum.

We thus propose that the remarkable behavior observed here for doped CsPb_{1-x}M_xBr₃ NCs indicates that they can accommodate larger isotropic compressive strains than bulk ABX₃ halide perovskites, and, as a result, all PbBr₆ octahedra within a NC contract without significant (additional) distortion, so that the compressive strain is homogenously distributed throughout the NC (as indicated by Figure 3 above). Distortion and tilting of the BX₆ octahedra is known to induce bandgap reduction.⁴⁸ These distortions are however always accompanied by lattice constant changes that act in the opposite direction, thereby decreasing the extent of the red-shift.⁴⁸ Recent X-Ray diffraction analysis of CsPbBr₃ NCs suggests that orthorhombic distortions are an important feature of these materials.³⁷ Although the linear relationship observed in the present work between the degree of lattice contraction and the blue-shift of the PL of CsPb₁. _xM_xBr₃ NCs (Figure 6) does not rule out the possibility of orthorhombic distortions in the NCs, it

implies that their contribution does not significantly change with the nature of M or the extent of the replacement, and therefore that the lattice contraction is the dominant effect. The contraction of the PbBr₆ octahedra leads to shorter Pb-Br bonds and therefore stronger interactions between the Pb and Br orbitals. This widens the bandgap because the conduction band minimum (CBM) is composed of the antibonding combinations between Pb(6p) and Br(4p) orbitals,⁴³ and therefore should shift to higher energies with stronger interactions. Although the valence band maximum is also antibonding,⁴³ we expect it to shift less than the CBM because it emerges from the relatively weaker interaction between the Br(4p⁶) orbitals and the Pb(6s²) orbitals, which are stabilized by lone pair and relativistic effects.⁵³ In contrast, the Pb(6p)-Br(4p) interaction is largely responsible for the chemical bonding in APbX₃ perovskites as it leads to charge transfer from the Pb(6p) to the X(np) orbitals.⁴³

CONCLUSIONS

We present a post-synthetic cation exchange method, which allows us to partially exchange Pb^{2+} ions in CsPbBr₃ NCs for several other divalent cations (Sn²⁺, Cd²⁺, Zn²⁺). This isovalent cation exchange results in a blue-shift of the PL bands, without loss of the high PLQYs (>60%), narrow emission bandwidth, and sharp excitonic absorption transitions. The blue-shift is attributed to contraction of the perovskite lattice due to the incorporation of smaller divalent guest cations (Sn²⁺/Cd²⁺/Zn²⁺), resulting in shorter Pb-halide bonds and hence an increased interaction between Pb and Br orbitals. We show that the blue-shifted PL energy scales linearly with the lattice vector of the doped CsPb_{1-x}M_xBr₃ NCs, in striking contrast to what has been reported for bulk perovskite materials. This is the first example of post-synthetic cation exchange

in CsPbBr₃ perovskite NCs, demonstrating that halide perovskite NCs are the only known system in which the complete composition can be post-synthetically tailored with size and shape preservation, by sequentially combining topotactic anion and cation exchanges. This opens up a library of possible compositions attainable for colloidal CsPbX₃ NCs, which might possess unprecedented and unparalleled optoelectronic properties and may prove beneficial for a number of applications.

EXPERIMENTAL METHODS

Materials. Cesium carbonate (Cs₂CO₃, Sigma Aldrich, 99.9%), 1-octadecene (ODE, Sigma Aldrich, 90%), oleic acid (OA, Sigma Aldrich, 90%), Lead bromide (PbBr₂, Sigma Aldrich, 99.999%), oleylamine (OLAM, Sigma Aldrich, 70%), Tin(II) bromide (SnBr₂, Sigma Aldrich), Cadmium bromide tetrahydrate (CdBr₂.4H₂O, Sigma Aldrich, 98%), Zinc bromide (ZnBr₂, Sigma Aldrich, 99.999%), anhydrous toluene (Sigma Aldrich, 99.8%), anhydrous hexane (Sigma Aldrich, 95%), anhydrous methyl acetate (Sigma Aldrich, 99.5%). OLAM and OA were degassed at 120 °C for 1 h prior to use. All others chemicals were used as received.

CsPbBr₃ nanocrystal synthesis. The CsPbBr₃ NCs were prepared according to the method described by Protesescu *et al.*¹ First, Cs-oleate precursor stock solution was prepared. Cs₂CO₃ (0.814g), 2.5 mL OA and 40 mL ODE were loaded into a 100 mL round-bottom flask. The mixture was dried under vacuum for approximately 1 h at 120 °C, and then heated under N₂ to 150 °C until all Cs₂CO₃ had reacted with OA. ODE (5 mL) and PbBr₂ (0.069g) were loaded into a separate 25 mL flask and dried under vacuum for 1 h at 120 °C. OLAM (0.5 mL) and OA (0.5 mL) were injected at 120 °C under N₂ atmosphere. After PbBr₂ had dissolved, the temperature

was raised to 180 °C and a 0.4 mL portion of the Cs-oleate stock solution was quickly injected. We note that the Cs-oleate stock solution had to be preheated to ~100 °C before injection. After five to ten seconds the reaction mixture was cooled by an ice-water bath in order to quench the reaction.

Purification of the nanocrystals. The CsPbBr₃ NCs were purified following the method described by De Roo *et al.*³⁰ (for a synthesis based on 69 mg of PbBr₂). The crude synthesis solution was centrifuged for 3 min at 10000 rpm and the colored supernatant was discarded. Then, 300 μ L of hexane was added and the NCs were dispersed using a vortex mixer. Subsequently, the suspension was again centrifuged for 3 min at 10 000 rpm, after which the precipitate, containing larger NCs and agglomerates, was discarded. Another 300 μ L of hexane was added to the supernatant, resulting in a colloidal dispersion of CsPbBr₃ NCs.

A second purification procedure, based on recent work by Luther and co-workers,⁷ was also used for a few selected samples of colloidal perovskite NCs after Pb²⁺ for Sn²⁺ cation exchange (see below). The additional purification of the colloidal CsPb_{1-x}Sn_xBr₃ perovskite NCs was performed by adding 1 mL of methyl acetate to the crude NC solution, followed by centrifugation at 13000 rpm for 1 hour. The amount of precipitate was extremely small. After removing the supernatant, the precipitate was redispersed in 300 μ L hexane. Subsequently, 300 μ L methyl acetate was added and the NCs were again centrifuged at 13000 rpm. The supernatant was discarded and the even smaller amount of precipitate was redispersed in 50 μ L of hexane before being dropcast on a Copper TEM grid for further analysis.

Cation exchange. Cation exchange precursor stock solutions were prepared by dissolving 1 mmol metalbromide salt (MBr₂, with $M = Sn^{2+}$, Zn^{2+} , Cd^{2+}) in 10 mL toluene (0.1 M MBr₂), in the presence of 100 µL OLAM. In a typical cation exchange experiment, 1.5 mL diluted NCs in

toluene (concentration: ~0.01 μ M, using an extinction coefficient of 37.9 cm⁻¹ μ M⁻¹ at 335 nm, for cubes of roughly 9 nm)³⁰ and 0.5 mL cation-precursor (different concentrations, ranging between 0.125 mM and 1.67 mM, [M²⁺]/[NC] ratio varied between ~8000 and ~300 000) were mixed and stirred at room temperature for ~16 h. In the majority of the cases, the NCs were not purified after the cation exchange reactions, due to difficulties with precipitation of the NCs. The second purification procedure described above, in which methyl acetate is used as anti-solvent, was applied to a few selected samples after reaction witth SnBr₂, but yielded only very small amounts of NCs, which were only enough to get sub-monolayer coverage on a TEM grid.

The influence of the amount of OLAM was investigated by replacing a volume of toluene (5, 10, or 30 μ L) by OLAM, while keeping all other variables (*i.e.*, total volume, concentration of NCs and SnBr₂, ratio SnBr₂/NCs) unchanged. The products of the reaction were analyzed after 48 hours and 84 hours.

Transmission Electron Microscopy (TEM) and Energy Dispersive X-Ray Spectroscopy (**EDS).** TEM measurements were performed using a Tecnai20F (FEI) microscope equipped with a Field Emission Gun and a Gatan 694 CCD camera. The microscope was operated at 200 kV. EDS measurements were performed on FEI Talos F200X and an aberration corrected 'cubed' FEI Titan 60-300 electron microscope equipped with a ChemiSTEM system⁶³ operated at 200 kV and 300 kV, respectively. Acquisition time for EDS measurements was ~300 s. Samples for TEM imaging were prepared by dripping a diluted nanocrystal solution in toluene on a carbon coated polymer film copper grid (300 mesh). The solvent (toluene) was allowed to evaporate prior to imaging.

HAADF-STEM. High-resolution High Angle Annular Dark Field Scanning Transmission Electron Microscopy (HAADF-STEM) measurements were performed using an aberration corrected cubed FEI Titan 60-300 electron microscope operated at 300 kV.

1D Powder Electron Diffraction (PED). PED patterns were obtained by azimuthally integrating the 2D ED patterns (with the freely available software package CrysTBox)³³ acquired on a Tecnai-12 transmission electron microscope using a selected-area aperture. 2D ED patterns were acquired on areas containing a large number of nanocrystals to make the 1D PED patterns statistically valid (see Supporting Information, Supplementary Method 1 and Figure S5 and S6 for details).

Optical spectroscopy. Samples for optical measurements were prepared by diluting the colloidal dispersion of NCs with anhydrous toluene under nitrogen and stored in sealed quartz cuvettes. Absorption spectra were measured on a double beam Perkin-Elmer Lambda 16 UV/Vis spectrometer. Photoluminescence (PL) spectra were recorded on an Edinburgh Instruments FLS920 Spectrofluorimeter equipped with a 450 W Xenon lamp as excitation source and double grating monochromators. PL decay curves were obtained by time-correlated single-photon counting on a Hamamatsu H7422-02 photomultiplier tube with low dark count rate (< 10 cts/s). A pulsed diode laser (EPL-445 Edinburgh Instruments, 375 nm, 55 ps pulse width, 0.2 MHz repetition rate) was used as the excitation source.

Photoluminescence quantum yields (PLQY). The PLQYs of the perovskite NCs were determined with respect to the fluorophore Lumogen red 350 (PLQY= 95%).⁶⁴ Samples for PLQY measurements were prepared by diluting the colloidal dispersion of NCs with anhydrous toluene under nitrogen in sealed quartz cuvettes, keeping the optical density of both the Lumogen Red and the perovskite NCs below 0.1 at 442 nm in order to minimize reabsorption.

The absorption and PL emission spectra were measured using the instruments mentioned above. The PLQYs were calculated using the following equation:

$$PLQY = \frac{1 - \text{Tref}}{1 - \text{T}} * \frac{\Phi}{\Phi \text{ref}} * QY \text{ref}$$

in which T is the transmission at 442 nm of the sample, T_{ref} is the transmission at 442 nm of Lumogen Red, Φ is the integrated PL photon flux of the sample, Φ_{ref} is the integrated PL photon flux of Lumogen Red and QY_{ref} is the QY of Lumogen Red (95%) (See Supporting Information, Supplementary Method 2 and Figure S20 for more details).

ASSOCIATED CONTENT

Supporting Information. PLQY measurements, in-situ absorption measurements, PL lifetime measurements, additional TEM images and ED patterns for CsPb_{1-x}Sn_xBr₃ NCs and CsPb_{1-x}Zn_xBr₃ NCs, EDS spectra of CsPbBr₃ NCs, CsPb_{1-x}Sn_xBr₃ NCs, CsPb_{1-x}Zn_xBr₃ NCs and CsPb_{1-x}Cd_xBr₃ NCs, HRTEM images of CsPbBr₃ NCs, PL spectra of CsPb_{1-x}Sn_xBr₃ NCs after reaction with higher concentration of OLAM, Supplementary Methods. This material is available free of charge via the Internet at http://pubs.acs.org.

AUTHOR INFORMATION

Corresponding Author: <u>*c.demello-donega@uu.nl;</u>

Present Address

 Δ Opto-electronic Materials Section, Department of Chemical Engineering, Delft University of Technology, van der Maasweg 9, 2629 HZ Delft, The Netherlands.

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript. || These authors contributed equally to this work.

ACKNOWLEDGMENTS

W.v.d.S. and C.d.M.D. acknowledge financial support from the division of Chemical Sciences (CW) of the Netherlands Organization for Scientific Research (NWO) under grant number ECHO.712.012.001. J.J.G. and D.V. acknowledge financial support from the Debye Graduate program. S.B. acknowledges financial support from the European Research Council (ERC Starting Grant # 335078-COLOURATOMS). K.H.W.v.d.B., S.B., S.V.A. and T.A. acknowledge financial support from the Research Foundation Flanders (FWO, Belgium) through project fundings (G.0374.13N, G.0368.15N, G.0369.15N), a Ph.D. grant to K.H.W.v.d.B, and a postdoctoral research grant to T.A.

REFERENCES

Protesescu, L.; Yakunin, S.; Bodnarchuk, M. I.; Krieg, F.; Caputo, R.; Hendon, C. H.;
 Yang, R. X.; Walsh, A.; Kovalenko, M. V. *Nano Lett.*, **2015**, *15*, 3692.

(2) Weidman, M. C.; Seitz, M.; Stranks, S. D.; Tisdale, W. A. ACS Nano, 2016, 10, 7830.

(3) Sun, S.; Yuan, D.; Xu, Y.; Wang, A.; Deng, Z. ACS Nano, 2016, 10, 3648.

(4) Yakunin, S.; Protesescu, L.; Krieg, F.; Bodnarchuk, M. I.; Nedelcu, G.; Humer, M.; De Luca, G.; Fiebig, M.; Heiss, W.; Kovalenko, M. V. *Nat. Commun.*, **2015**, *6*, 8056.

(5) Xu, Y.; Chen, Q.; Zhang, C.; Wang, R.; Wu, H.; Zhang, X.; Xing, G.; Yu, W. W.; Wang, X.; Zhang, Y.; Xiao, M. J. Am. Chem. Soc., 2016, 138, 3761.

(6) Zhang, X.; Lin, H.; Huang, H.; Reckmeier, C.; Zhang, Y.; Choy, W. C. H.; Rogach, A. L. *Nano Lett.*, **2016**, *16*, 1415.

(7) Swarnkar, A.; Marshall, A. R.; Sanehira, E. M.; Chernomordik, B. D.; Moore, D. T.; Christians, J. A.; Chakrabarti, T.; Luther, J. M. *Science*, **2016**, *354*, 6308.

(8) Lignos, I.; Stavrakis, S.; Nedelcu, G.; Protesescu, L.; de Mello, A. J.; Kovalenko, M. V. *Nano Lett.*, **2016**, *16*, 1869.

(9) Zhang, D.; Eaton, S. W.; Yu, Y.; Dou, L.; Yang, P. J. Am. Chem. Soc., 2015, 137, 9230.

(10) Imran, M.; Di Stasio, F.; Dang, Z.; Canale, C.; Khan, A. H.; Shamsi, J.; Brescia, R.;Prato, M.; Manna, L., *Chem. Mater.* 2016, *28*, 6450.

(11) Akkerman, Q. A.; Motti, S. G.; Srimath Kandada, A. R.; Mosconi, E.; D'Innocenzo, V.;
Bertoni, G.; Marras, S.; Kamino, B. A.; Miranda, L.; De Angelis, F.; Petrozza, A.; Prato, M.;
Manna, L. J. Am. Chem. Soc., 2016, 138, 1010.

(12) Sichert, J. A.; Tong, Y.; Mutz, N.; Vollmer, M.; Fischer, S.; Milowska, K. Z.; García Cortadella, R.; Nickel, B.; Cardenas-Daw, C.; Stolarczyk, J. K.; Urban, A. S.; Feldmann, J. *Nano Lett.*, **2015**, *15*, 6521.

(13) Protesescu, L.; Bakunin, S.; Bodnarchuk, M. I.; Bertolotti, F.; Masciocchi, N.; Guagliardi, A.; Kovalenko, M. V. J. Am. Chem. Soc., 2016, 138, 14202.

(14) Nedelcu, G.; Protesescu, L.; Yakunin, S.; Bodnarchuk, M. I.; Grotevent, M. J.; Kovalenko, M. V. *Nano Lett.*, **2015**, *15*, 5635.

(15) Akkerman, Q. A.; D'Innocenzo, V.; Accornero, S.; Scarpellini, A.; Petrozza, A.; Prato, M.; Manna, L. J. Am. Chem. Soc., 2015, 137, 10276.

(16) Hodges, J. M.; Kletetschka, K.; Fenton, J. L.; Read, C. G.; Schaak, R. E. Angew. Chem. Int. Ed., 2015, 54, 8567.

(17) Wu, H.; Sato, R.; Yamaguchi, A.; Kimura, M.; Haruta, M.; Kurata, H.; Teranishi, T. *Science*, **2016**, *351*, 1306.

(18) Beberwyck, B. J.; Surendranath, Y.; Alivisatos, A. P. J. Phys. Chem. C, 2013, 117, 19759.

(19) Gupta, S.; Kershaw, S. V.; Rogach, A. L. Adv. Mater., 2013, 25, 6923.

(20) De Trizio, L.; Manna, L. Chem. Rev., 2016, 116, 10852.

(21) van der Stam, W.; Bladt, E.; Rabouw, F. T.; Bals, S.; de Mello Donega, C. *ACS Nano*, **2015**, *9*, 11430.

(22) Li, H.; Brescia, R.; Krahne, R.; Bertoni, G.; Alcocer, M. J. P.; D'Andrea, C.; Scotognella,
F.; Tassone, F.; Zanella, M.; De Giorgi, M.; Manna, L. *ACS Nano*, **2012**, *6*, 1637.

(23) Schwartz, D. A.; Norberg, N. S.; Nguyen, Q. P.; Parker, J. M.; Gamelin, D. R. J. Am. Chem. Soc., 2003, 125, 13205.

2	
3	
4	
5	
5	
0	
7	
8	
9	
10	
10	
11	
12	
13	
14	
15	
10	
16	
17	
18	
19	
20	
21	
Z I	
22	
23	
24	
25	
20	
20	
27	
28	
29	
20	
30	
31	
32	
33	
34	
35	
30	
36	
37	
38	
39	
10	
40	
41	
42	
43	
44	
15	
40	
46	
47	
48	
49	
50	
50	
51	
52	
53	
54	
54	
22	
56	
57	
58	

59 60 (24) Knowles, K. E.; Nelson, H. D.; Kilburn, T. B.; Gamelin, D. R. J. Am. Chem. Soc., 2015, 137, 13138.

(25) Meinardi, F.; Colombo, A.; Velizhanin, K. A.; Simonutti, R.; Lorenzon, M.; Beverina, L.;Viswanatha, R.; Klimov, V. I.; Brovelli, S. *Nat. Photonics*, **2014**, *8*, 392.

(26) Pérez-del-Rey, D.; Forgács, D.; Hutter, E. M.; Savenije, T. J.; Nordlund, D.; Schulz,P.; Berry, J. J.; Sessolo, M.; Bolink, H. J. *Adv. Mater.*, **2016**, *28*, 9839.

(27) Frolova, L. A.; Anokhin, D. V.; Gerasimov, K. L.; Dremova, N. N.; Troshin, P. A, J. Phys. Chem. Lett., 2016, 7, 4353.

(28) Abdelhady, A. L.; Saidaminov, M. I.; Murali, B.; Adinolfi, V.; Voznyy, O.; Katsiev, K.; Alarousu, E.; Comin, R.; Dursun, I.; Sinatra,, L.; Sargent, E. H.; Mohammed, O. F.; Bakr, O. M. *J. Phys. Chem. Lett.*, **2016**, *7*, 295.

(29) Liu, W.; Lin, Q.; Li, H.; Wu, K.; Robel, I.; Pietryga, J. M.; Klimov, V. I. J. Am. Chem. Soc., 2016, 138, 14954.

(30) De Roo, J.; Ibáñez, M.; Geiregat, P.; Nedelcu, G.; Walravens, W.; Maes, J.; Martins, J.C.; Van Driessche, I.; Kovalenko, M. V.; Hens, Z. ACS Nano, 2016, 10, 2071.

(31) Driel, A. F. Van; Nikolaev, I. S.; Vergeer, P.; Lodahl, P.; Vanmaekelbergh, D.; Vos, W.
L. *Phys Rev B*, **2007**, *75*, 035329.

(32) Delerue, C.; Lannoo, M. Nanostructures - Theory and Modeling; Springer: Berlin, 2004.

(33) Klinger, M.; Jäger, A. J. Appl. Crystallogr., 2015, 48, 2012.

(34) Atkins, P. W.; Overton, T.; Rourke, J.; Weller, M.; Armstrong, F. Shriver and Atkins' Inorganic Chemistry; 5th Ed., Oxford University Press: Oxford, 2010.

(35) van Aert, S.; Verbeeck, J.; Erni, R.; Bals, S.; Luysberg, M.; van Dyck, D.; van Tendeloo,G. *Ultramicroscopy*, **2009**, *109*, 1236.

(36) de Backer, A.; van den Bos, K. H. W.; van den Broek, W.; Sijbers, J.; van Aert, S. *Ultramicroscopy*, **2016**, *171*, 104.

(37) Cottingham, P.; Brutchey, R. L. Chem. Commun., 2016, 52, 5246.

(38) Student, *Biometrika*, **1908**, *6*, 1.

(39) Boles, M. A.; Ling, D.; Hyeon, T.; Talapin, D. V. Nat. Mater. 2016, 15, 141.

(40) Walsh, A.; Scanlon, D. O.; Chen, S.; Gong, X. G.; Wei, S.-H. Angew. Chem. Int. Ed., 2015, 54, 1791.

(41) Yang, T.-Y.; Gregori, G.; Pellet, N.; Gratzel, M.; Maier, J. Angew. Chem. Int. Ed., 2015, 54, 7905.

(42) Buin, A.; Pietsch, P.; Xu, J.; Voznyy, O.; Ip, A. H.; Comin, R.; Sargent, E. H. *Nano Lett.*,**2014**, *14*, 6281.

(43) Brandt, R. E.; Stevanović, V.; Ginley, D. S.; Buonassisi, T. MRS Commun., 2015, 5, 265.

(44) Groeneveld, E.; Witteman, L.; Lefferts, M.; Ke, X.; Bals, S.; van Tendeloo, G.; de Mello Donega, C. *ACS Nano* **2013**, *7*, 7913.

(45) Lesnyak, V.; Brescia, R.; Messina, G. C.; Manna, L. J. Am. Chem. Soc. 2015, 137, 9315.

(46) van der Stam, W.; Berends, A. C.; Rabouw, F. T.; Willhammar, T.; Ke, X.; Meeldijk, J. D.; Bals, S.; Donega, C. d. M. *Chem. Mater.* 2015, *27*, 621.

(47) Eames, C.; Frost, J. M.; Barnes, P. R. F.; O'Regan, B. C.; Walsh, A.; Saiful Islam, M. *Nature Commun.* **2015**, *6*, 7497.

(48) Castelli, I. E.; Garcia-Lastra, J. M.; Thygesen, K. S.; Jacobsen, K. W. APL Mater. 2014, 2, 081514.

(49) Jellicoe, T. C.; Richter, J. M.; Glass, H. F. J.; Tabachnyk, M.; Brady, R.; Dutton, S. E.;
Rao, A.; Friend, R. H.; Credgington, D.; Greenham, N. C.; Böhm, M. L. J. Am. Chem. Soc.,
2016, 138, 2941.

(50) Hao, F.; Stoumpos, C. C.; Chang, R. P. H.; Kanatzidis, M. G. J. Am. Chem. Soc., 2014, 136, 8094.

(51) Chen, Q.; De Marco, N.; Yang, Y.; Song, T.-Z.; Chen, C.-C.; Zhao, H.; Hong, Z.; Zhou,
H.; Yang, Y. *Nano Today* 2015, *10*, 355.

(52) Li, C.; Wei, J.; Sato, M.; Koike, H.; Xie, Z.-Z.; Li, Y.-Q.; Kanai, K.; Kera, S.; Ueno, N.;
Tang, J.-X. ACS Appl. Mater. Interfaces 2016, 8, 11526.

(53) Fabini, D. H.; Laurita, G.; Bechtel, J. S.; Stoumpos, C. C.; Evans, H. A.; Kontos, A. G.;
Raptis, Y. S.; Falaras, P.; Van der Ven, A.; Kanatzidis, M. G.; Seshadri, R. J. Am. Chem. Soc.,
2016, 138, 11820.

(54) Wei, K.; Xu, Z.; Chen, R.; Zheng, X.; Cheng, X.; Jiang, T. Opt. Lett. 2016, 41, 3821.

(55) Yu, C.; Chen, Z.; Wang, J. J.; Pfenninger, W.; Cockic, N.; Kenney, J. T.; Shum, K. J. *Appl. Phys.* **2011**, *110*, 063526.

(56) Cardona, M.; Thewalt, M. L. W. Rev. Mod. Phys. 2005, 77, 1173.

(57) Villegas, C. E. P.; Rocha, A. R.; Marini, A. Nano Lett. 2016, 16, 5095.

(58) Osherov, A.; Hutter, E. M.; Galkowski, K.; Brenes, R.; Maude, D. K.; Nicholas, R. J.; Plochocka, P.; Bulovic, V.; Savenije, T. J.; Stranks, S. D. *Adv. Mater.* **2016**, *28*, 10757.

(59) Wang, Y.; Lu, X.; Tang, W.; Wen, T.; Yang, L.; Ren, X.; Wang, L.; Lin, Z.; Zhao, Y. J.
Am. Chem. Soc. 2015, 137, 11144.

(60) Szafranski, M.; Katrusiak, A. J. Phys. Chem. Lett. 2016, 7, 3458.

(61) Teisseyre, H.; Perlin, P.; Suski, T.; Grzegory, I.; Jun, J.; Porowski, S. J. Phys. Chem. Solids 1995, 56, 353.

(62) Gilliland, S.; Gonzalez, J.; Guder, H. S.; Segura, A.; Mora, I.; Munoz, V. *Phys. Status Solidi B* **2003**, *235*, 441.

(63) Schlossmacher, P.; Klenov, D. O.; Freitag, B.; Von Harrach, H. S. *Microsc. Today*, **2010**, *18*, 14.

(64) Donega, C. D. M.; Hickey, S. G.; Wuister, S. F.; Vanmaekelbergh, D; Meijerink, A. J. Phys. Chem. B, 2003, 107, 489.

Insert Table of Contents Graphic and Synopsis Here

