

Table I

molality of solutes × 10 <sup>2</sup>		initial atomic ratio of Hf/Zr	atomic ratio of Hf/Zr in product
Zr(IV)	Hf(IV)		
6	6	1	0.005
0.98	0.94	0.96	0.003
1.18	0.48	0.41	Hf not detectable

For a determination of the nature of the reduction product, the black precipitate observed at the electrode after electrolysis at <0 V vs. the Al(III)/Al reference electrode was treated with molten Al<sub>2</sub>Cl<sub>6</sub> (to remove remaining NaCl) and filtered. The residual Al<sub>2</sub>Cl<sub>6</sub> was removed by sublimation under vacuum; the shiny black precipitate was examined by powder X-ray diffraction. The powder pattern showed that the precipitate was either Al<sub>3</sub>Hf<sup>10</sup> or a mixture of Al<sub>3</sub>Hf and aluminum. Thus a simultaneous reduction of Hf(IV) and Al(III) is observed; depending on the ratio of Hf(IV) to Al<sub>2</sub>Cl<sub>7</sub><sup>-</sup> and the potential of the electrode, the product is either Al<sub>3</sub>Hf or a mixture of that compound with aluminum.

## 2. Electrochemical Separation of Zirconium from Hafnium.

Since the difference between the reduction of Zr(IV) and Al<sub>2</sub>Cl<sub>7</sub><sup>-</sup> increases slightly when the chloroaluminate melts become less acidic, melts containing ~50.5 mol % AlCl<sub>3</sub> were used for the separation experiments. The solubility of HfCl<sub>4</sub> in these melts at 175 °C is ~8 × 10<sup>-2</sup> m. In a typical controlled-potential electrolysis experiment 50 g of an AlCl<sub>3</sub>-NaCl (50.5 mol % AlCl<sub>3</sub>) melt containing ~10<sup>-2</sup> m each of ZrCl<sub>4</sub> and HfCl<sub>4</sub> was used. The potential of a tungsten spiral cathode (area 3.5 cm<sup>2</sup>) was controlled at 0.09 V vs. the Al(III)/Al reference electrode in the melt of the same composition. A reticulated vitreous carbon cylinder (4 cm long, 0.5 cm in diameter) was used as an anode; it was separated from the main compartment by a Pyrex frit of medium porosity. After 14 h of electrolysis at 175 °C voltammograms obtained at a tungsten microelectrode indicated that most of the Zr(IV) was reduced. The product was scraped from the electrode; residual ZrCl<sub>4</sub>, HfCl<sub>4</sub>, and Al<sub>2</sub>Cl<sub>6</sub> were removed by sublimation at 205 °C. The product after sublimation was examined by X-ray fluorescence. This analysis showed that the atomic ratio of Hf/Zr decreased from 0.96 before the electrolysis to 0.003 in the product of the electrolysis. The Raman spectrum of the product showed a sharp line at 212 cm<sup>-1</sup>, characteristic of ZrCl<sub>3</sub>.<sup>4</sup> Results of three experiments are given in Table I. An excess of charge was involved in the reduction step; for example, in the experiment described above 164 coulombs were consumed compared to the expected value of 47 coulombs. It is likely that some of the chlorine produced at the anode reached the cathode to oxidize the ZrCl<sub>3</sub> product.

In preliminary experiments using platinum as the anode, the black cathodic deposit contained significant amounts of platinum. Clearly the use of platinum as an anodic counterelectrode in molten chloroaluminates should be avoided. In summary, we have demonstrated that hafnium-free zirconium can be produced by controlled-potential electrolysis using slightly acidic chloroaluminate melts. The separation factors achieved electrochemically are better than those achieved previously by chemical reduction.<sup>6</sup>

**Acknowledgment.** This research was supported by National Science Foundation Grant CHE-77-21370. M. Katabua acknowledges support by the Fulbright Foundation.

**Registry No.** Zr, 7440-67-7; Hf, 7440-58-6.

Contribution from the Department of Chemistry,  
The University, Southampton SO9 5NH, United Kingdom

## Synthesis of Substituted Octahedral Anions of Chromium(III), [R<sub>4</sub>N][*cis*-Cr(L-L)X<sub>4</sub>], and the Nature of Cr(L-L)<sub>1.5</sub>X<sub>3</sub> (L-L = Diphosphine or Diarsine; X = Cl, Br)

Annette L. Hale, William Levason,\*  
and Francis P. McCullough<sup>1</sup>

Received February 1, 1982

Octahedral halo anions MX<sub>6</sub><sup>n-</sup> are known for most transition metals, but substituted analogues containing neutral mono- (L) or bidentate (L-L) ligands are rare, especially in the 3d series.<sup>2</sup> The green [Ph<sub>4</sub>P][*trans*-CrL<sub>2</sub>Cl<sub>4</sub>] (L = PEt<sub>3</sub>, P-*n*-Bu<sub>3</sub>) were obtained from [CrL<sub>2</sub>Cl<sub>3</sub>]<sub>2</sub> and Ph<sub>4</sub>PCl in CH<sub>2</sub>Cl<sub>2</sub>.<sup>3</sup> During a study of chromium(III) complexes with soft donor ligands, as a prelude to examining small-molecule (O<sub>2</sub>, NO, etc.) binding by chromium complexes, we isolated the *cis*-[Cr(L-L)X<sub>4</sub>]<sup>-</sup> (X = Cl, Br) ions as R<sub>4</sub>N<sup>+</sup> salts. Nyholm<sup>4</sup> obtained materials of empirical formula Cr(das)<sub>1.5</sub>X<sub>3</sub> (das = *o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>) from chromium(III) halides and the ligand in moist acetone or alcohol, for which the three most likely formulations are [Cr(das)<sub>2</sub>X<sub>2</sub>][Cr(das)X<sub>4</sub>], [Cr(das)<sub>3</sub>][CrX<sub>6</sub>], and (das)X<sub>3</sub>Cr(das)CrX<sub>3</sub>(das). Since treatment with HClO<sub>4</sub> converted Cr(das)<sub>1.5</sub>X<sub>3</sub> into [Cr(das)<sub>2</sub>X<sub>2</sub>]ClO<sub>4</sub>, and attempts to prepare [Cr(das)<sub>3</sub>]<sup>3+</sup> failed, Nyholm favored the first formulation. It should be noted however that a ligand-bridged dimeric structure was proposed for Cr(Ph<sub>2</sub>PCH<sub>2</sub>-CH<sub>2</sub>PPh<sub>2</sub>)<sub>1.5</sub>X<sub>3</sub>·*n*H<sub>2</sub>O.<sup>5</sup> Our synthesis of [Cr(L-L)X<sub>4</sub>]<sup>-</sup> led us to reinvestigate the Cr(das)<sub>1.5</sub>X<sub>3</sub> complexes.

## Results and Discussion

The reaction of CrCl<sub>3</sub>(THF)<sub>3</sub>, *n*-Pr<sub>4</sub>NCl, and the appropriate bidentate ligand (L-L) in dry CH<sub>2</sub>Cl<sub>2</sub> produced the tetrapropylammonium *cis*-tetrachloro(ligand)chromate(III), [Pr<sub>4</sub>N][*cis*-CrCl<sub>4</sub>(L-L)] (L-L = *o*-C<sub>6</sub>H<sub>4</sub>(PMe<sub>2</sub>)<sub>2</sub>, *o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>, Ph<sub>2</sub>PCH<sub>2</sub>CH<sub>2</sub>PPh<sub>2</sub>, *cis*-Ph<sub>2</sub>PCH=CHPPh<sub>2</sub>, *cis*-Ph<sub>2</sub>AsCH=CHAsPh<sub>2</sub>), as blue powders. The [Ph<sub>3</sub>PCH<sub>2</sub>Ph][Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)Br<sub>4</sub>] was obtained similarly (Table I). Attempts to isolate these anions using smaller cations were unsuccessful. It should be noted that reaction of CrBr<sub>3</sub>(THF)<sub>3</sub> with R<sub>4</sub>NBr in a 1:1 ratio in CH<sub>2</sub>Cl<sub>2</sub> produces deep green solutions that may contain [R<sub>4</sub>N][Cr(THF)<sub>2</sub>Br<sub>4</sub>], although we have been unable to isolate these. The complexes are 1:1 electrolytes in 10<sup>-3</sup> M nitromethane solutions and have magnetic moments ca. 3.88 μ<sub>B</sub> as expected for d<sup>3</sup> Cr(III). The [*n*-Pr<sub>4</sub>N][Cr(*o*-C<sub>6</sub>H<sub>4</sub>(PMe<sub>2</sub>)<sub>2</sub>)Cl<sub>4</sub>] complex is deliquescent, but the others are stable to moist air for short periods of time but are fairly readily decomposed by water or alcohols in solution. In spite of this, attempts to displace one halide from [Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)Cl<sub>4</sub>]<sup>-</sup> by stirring or heating CH<sub>2</sub>Cl<sub>2</sub> or toluene solutions with monodentate ligands such as PhMe<sub>2</sub>P, PPh<sub>3</sub>, AsMe<sub>2</sub>Ph, or MePhS (L), failed to give [Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)LCl<sub>3</sub>], most of the starting complex being recovered unchanged.

The far-IR spectra of a *cis*-[CrCl<sub>4</sub>(L-L)]<sup>-</sup> ion should show four chromium-chlorine stretching vibrations (2A<sub>1</sub> + B<sub>1</sub> + B<sub>2</sub>), and despite the complications produced by absorptions of L-L in the same region, three or four bands were generally

(1) Present address: Dow Chemical Co., Freeport, TX.

(2) R. Colton and J. H. Canterford, "Halides of the First Row Transition Metals", Wiley, New York, 1968.

(3) M. A. Bennett, R. Clark, and A. Goodwin, *J. Chem. Soc. A*, 541 (1970).

(4) R. S. Nyholm and G. Sutton, *J. Chem. Soc.*, 560 (1958).

(5) W. Baker and P. Lutz, *Inorg. Chim. Acta*, 16, 5 (1976).

(10) A. E. Dwight, J. W. Downey, and R. A. Conner, *Acta Crystallogr.*, 14, 75 (1961).

Table I. Chromium(III) Physical and Spectroscopic Data

complex	% C <sup>a</sup>	% H	% X	% N	% Cr	color	$\nu(\text{Cr-X}), \text{cm}^{-1}$ <sup>b</sup>
[NPr <sub>4</sub> ][Cr( <i>o</i> -C <sub>6</sub> H <sub>4</sub> (PMe <sub>2</sub> ) <sub>2</sub> )Cl <sub>4</sub> ]	45.3 (45.6)	7.9 (7.6)	24.3 (24.6)	2.2 (2.4)	...	purple	375 sh, 355 m, 330 s, 305 sh
[NPr <sub>4</sub> ][Cr( <i>o</i> -C <sub>6</sub> H <sub>4</sub> (AsMe <sub>2</sub> ) <sub>2</sub> )Cl <sub>4</sub> ]	39.4 (39.6)	6.1 (6.6)	21.8 (21.3)	2.0 (2.1)	7.2 (7.8)	blue	358 sh, 333 m, 325 s, 312 sh
[NPr <sub>4</sub> ][Cr(Ph <sub>2</sub> PCH <sub>2</sub> CH <sub>2</sub> PPh <sub>2</sub> )Cl <sub>4</sub> ]	58.5 (58.6)	6.1 (6.7)	17.0 (18.2)	1.9 (1.8)	5.9 (6.7)	purple	366 sh, 340 m, 315 sh, 300 s
[NPr <sub>4</sub> ][Cr(Ph <sub>2</sub> PCH=CHPPh <sub>2</sub> )Cl <sub>4</sub> ]	58.4 (58.7)	6.7 (6.4)	17.9 (18.3)	1.9 (1.8)	6.3 (6.7)	purple	340 s, 315 s
[NPr <sub>4</sub> ][Cr(Ph <sub>2</sub> AsCH=CHAsPh <sub>2</sub> )Cl <sub>4</sub> ]	52.2 (52.8)	5.4 (5.6)	16.2 (16.8)	1.7 (1.6)	6.0 (6.0)	purple	346 m, 335 s, 302 s
[PPh <sub>3</sub> CH <sub>2</sub> Ph][Cr( <i>o</i> -C <sub>6</sub> H <sub>4</sub> (AsMe <sub>2</sub> ) <sub>2</sub> )Br <sub>4</sub> ]	41.8 (41.5)	3.6 (3.8)	30.9 (31.7)	...	...	blue	312 m, 285 s, 258 s
Cr( <i>o</i> -C <sub>6</sub> H <sub>4</sub> (AsMe <sub>2</sub> ) <sub>2</sub> ) <sub>1.5</sub> Cl <sub>3</sub>	30.5 (30.7)	4.0 (4.1)	18.0 (18.1)	...	9.3 (8.8)	green	380 m, 333 sh, 321 s, 307 sh
Cr( <i>o</i> -C <sub>6</sub> H <sub>4</sub> (AsMe <sub>2</sub> ) <sub>2</sub> ) <sub>1.5</sub> Br <sub>3</sub>	25.4 (25.0)	3.8 (3.3)	32.6 (33.3)	...	...	green	320, 285, 258 sh
[Cr( <i>o</i> -C <sub>6</sub> H <sub>4</sub> (AsMe <sub>2</sub> ) <sub>2</sub> )Cl <sub>2</sub> ] <sub>2</sub> ClO <sub>4</sub>	30.3 (30.2)	4.3 (4.0)	...	...	...	bright green	380 m
[Cr( <i>o</i> -C <sub>6</sub> H <sub>4</sub> (AsMe <sub>2</sub> ) <sub>2</sub> )Br <sub>2</sub> ] <sub>2</sub> ClO <sub>4</sub>	27.2 (27.2)	3.6 (3.6)	...	...	...	bright green	320 m

<sup>a</sup> Found values are given, with calculated values in parentheses. <sup>b</sup> Nujol mulls. All complexes have magnetic moments close to  $\mu_{\text{eff}} = 3.88 \mu_{\text{B}}/\text{Cr}$  as expected for Cr(III).

identified (Table I). The characterization of these [CrX<sub>4</sub>(das)]<sup>-</sup> complexes enabled us to definitely identify the structure present in Cr(das)<sub>1.5</sub>X<sub>3</sub> (X = Cl, Br), by far-IR spectroscopy. (Attempts to grow crystals of Cr(das)<sub>1.5</sub>X<sub>3</sub> for X-ray crystallographic examination were frustrated by the poor solubility, and only powders were produced from in situ syntheses.) The [Cr(das)<sub>2</sub>X<sub>2</sub>]<sub>2</sub>ClO<sub>4</sub> were readily obtained by treatment of Cr(das)<sub>1.5</sub>X<sub>3</sub> with HClO<sub>4</sub>, and as can be seen from Table I, the bands in the IR spectrum of Cr(das)<sub>1.5</sub>Cl<sub>3</sub> in the range 400–200 cm<sup>-1</sup> are all accounted for by superimposition of the spectra of [Cr(das)Cl<sub>4</sub>]<sup>-</sup> and [Cr(das)<sub>2</sub>Cl<sub>2</sub>]<sup>+</sup>. Similar conclusions are drawn for Cr(das)<sub>1.5</sub>Br<sub>3</sub>, although here the overlapping of Cr–Br and ligand bands makes the spectral assignments more difficult. Thus the far-IR spectra demonstrate that the Cr(das)<sub>1.5</sub>X<sub>3</sub> complexes are indeed [*trans*-Cr(das)<sub>2</sub>X<sub>2</sub>]<sup>+</sup> [*cis*-Cr(das)X<sub>4</sub>]<sup>-</sup>.

## Experimental Section

All reactions were carried out under dry dinitrogen by using standard Schlenk tube and dry box techniques. CrCl<sub>3</sub>(THF)<sub>3</sub> was prepared from anhydrous CrCl<sub>3</sub>, zinc dust, and dry tetrahydrofuran,<sup>6</sup> and CrBr<sub>3</sub>(THF)<sub>3</sub> analogously from anhydrous CrBr<sub>3</sub>. Physical measurements were made as described previously.<sup>7</sup>

Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)<sub>1.5</sub>X<sub>3</sub> (X = Cl, Br). CrX<sub>3</sub>(THF)<sub>3</sub> (1 mmol) was dissolved in dry dichloromethane (20 cm<sup>3</sup>), the solution filtered, and *o*-phenylenebis(dimethylarsine) (0.57 g, 2 mmol) added. When the mixture was stirred at room temperature, green solids separated, which were filtered off, rinsed thoroughly with diethyl ether, and dried in vacuo; yield ca. 70%.

[Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)X<sub>2</sub>]<sub>2</sub>ClO<sub>4</sub>. Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)<sub>1.5</sub>X<sub>3</sub> (1 mmol) was added to 40% aqueous perchloric acid and the mixture stirred for 4–5 h. The bright green solids were separated by filtration and washed with distilled water, until the washings were colorless. The solids were rinsed with diethyl ether and dried; yield ca. 65%.

[*n*-Pr<sub>4</sub>][Cr(L-L)Cl<sub>4</sub>] (L-L = *o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>, Ph<sub>2</sub>PCH<sub>2</sub>-CH<sub>2</sub>PPh<sub>2</sub>, *cis*-Ph<sub>2</sub>PCH=CHPPh<sub>2</sub>, Ph<sub>2</sub>AsCH=CHAsPh<sub>2</sub>, *n*-Pr<sub>4</sub>NCl was dried by heating at 80–90 °C in vacuo for 2 days. The appropriate ligand (2 mmol), CrCl<sub>3</sub>(THF)<sub>3</sub> (2 mmol), and *n*-Pr<sub>4</sub>NCl (2 mmol) were dissolved in CH<sub>2</sub>Cl<sub>2</sub> and the solutions combined and stirred for several hours. The solutions were filtered and concentrated in vacuo. The oils produced were stirred with petroleum ether until they were converted to fine powders, which were filtered off and dried in vacuo. [N-*n*-Pr<sub>4</sub>][Cr(*o*-C<sub>6</sub>H<sub>4</sub>(PMe<sub>2</sub>)<sub>2</sub>)Cl<sub>4</sub>] was prepared similarly in acetone

and [Ph<sub>3</sub>PCH<sub>2</sub>Ph][Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)Br<sub>4</sub>] from the ligand, CrBr<sub>3</sub>(THF)<sub>3</sub>, and Ph<sub>3</sub>PCH<sub>2</sub>PhBr.

**Acknowledgment.** We thank the SRC and BOC (Techsep) for support.

**Registry No.** [NPr<sub>4</sub>][Cr(*o*-C<sub>6</sub>H<sub>4</sub>(PMe<sub>2</sub>)<sub>2</sub>)Cl<sub>4</sub>], 82456-75-5; [NPr<sub>4</sub>][Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)Cl<sub>4</sub>], 82456-77-7; [NPr<sub>4</sub>][Cr(Ph<sub>2</sub>PCH<sub>2</sub>CH<sub>2</sub>PPh<sub>2</sub>)Cl<sub>4</sub>], 82456-79-9; [NPr<sub>4</sub>][Cr(Ph<sub>2</sub>PCH=CHPPh<sub>2</sub>)Cl<sub>4</sub>], 82469-03-2; [NPr<sub>4</sub>][Cr(Ph<sub>2</sub>AsCH=CHAsPh<sub>2</sub>)Cl<sub>4</sub>], 82456-81-3; [PPh<sub>3</sub>CH<sub>2</sub>Ph][Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)Br<sub>4</sub>], 82456-83-5; Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)<sub>1.5</sub>Cl<sub>3</sub>, 82456-84-6; Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)<sub>1.5</sub>Br<sub>3</sub>, 82456-85-7; [Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)Cl<sub>2</sub>]<sub>2</sub>ClO<sub>4</sub>, 14127-30-1; [Cr(*o*-C<sub>6</sub>H<sub>4</sub>(AsMe<sub>2</sub>)<sub>2</sub>)Br<sub>2</sub>]<sub>2</sub>ClO<sub>4</sub>, 60536-77-8; CrCl<sub>3</sub>(THF)<sub>3</sub>, 10170-68-0; CrBr<sub>3</sub>(THF)<sub>3</sub>, 82456-86-8.

Contribution from the Department of Chemistry, University of Cincinnati, Cincinnati, Ohio 45221

## Electrochemical Oxidation and Reduction of Methylcobalamin and Coenzyme B<sub>12</sub>

Kenneth A. Robinson,\* Eiki Itabashi, and Harry B. Mark, Jr.

Received March 10, 1982

Although the electrochemical reduction of alkylcobalamins has been reported, the number of electrons involved and the reaction products were in doubt.<sup>1–3</sup> The oxidation of these compounds has not previously been studied. We report here the spectroelectrochemical and product analysis of both the electrochemical oxidation and reduction of methylcobalamin and coenzyme B<sub>12</sub>. The electrochemical reactions of the alkylcobalamins are completely different from those of vitamin B<sub>12</sub>, cyano[Co(III)]cobalamin, and other cobalamins.<sup>1,4,5</sup>

## Experimental Section

The cyclic voltammetric and coulometric studies of coenzyme B<sub>12</sub> and methylcobalamin were carried out in 0.5 M Na<sub>2</sub>SO<sub>4</sub>. In both cases, Britton–Robinson buffer was used.

- (6) W. Herwig and H. H. Zeiss, *J. Org. Chem.*, **23**, 1404 (1958).
- (7) D. J. Gulliver, W. Levason, K. G. Smith, M. J. Selwood, and S. G. Murray, *J. Chem. Soc., Dalton Trans.*, 1872 (1980).

- (1) Mark, H. B., Jr.; Kenyhercz, T. M.; Kissinger, P. T. In "Electrochemical Studies of Biological Systems"; Sawyer, D. T., Ed.; American Chemical Society: Washington, D.C., 1977; ACS Symp. Ser. No. 38, pp 1–25.
- (2) Lexa, D.; Saveant, J. M. *J. Am. Chem. Soc.* **1978**, *100*, 3220–3222.
- (3) Hogenkamp, H. P. C.; Holmes, S. *Biochemistry* **1970**, *9*, 1886–1892.
- (4) Kenyhercz, T. M.; DeAngelis, T. P.; Norris, B. J.; Heineman, W. R.; Mark, H. B., Jr. *J. Am. Chem. Soc.* **1976**, *98*, 2469–2477.
- (5) Lexa, D.; Saveant, J. M.; Zickler, J. *J. Am. Chem. Soc.* **1977**, *99*, 2786–2790.