

Synthesis and Properties of Dithieno-Fused 1,4-Azaborine Derivatives

Koichi Mitsudo,*,[†][®] Keisuke Shigemori,[†] Hiroki Mandai,[†][®] Atsushi Wakamiya,[‡][®] and Seiji Suga^{*,†}[®]

[†]Division of Applied Chemistry, Graduate School of Natural Science and Technology, Okayama University, 3-1-1 Tsushima-naka, Kita-ku, Okayama 700-8530, Japan

[‡]Institute for Chemical Research, Kyoto University, Uji, Kyoto 611-0011, Japan

Supporting Information



ABSTRACT: The first synthesis of dithieno[3,2-b:2',3'-e][1,4]azaborinine (DTAB) derivatives has been achieved by Buchwald-Hartwig coupling and subsequent Friedel-Crafts-type C-H borylation. A facile method for further π -extension of DTAB was also developed via stannylation and subsequent Kosugi-Migita-Stille cross-coupling reaction. The fundamental properties of DTAB derivatives were also investigated.

zaborines, which are benzene ring alternatives that Ainclude boron and nitrogen atoms, have received considerable attention since the pioneering work reported by Dewar,^{1,2} and several new azaborine derivatives have been studied extensively over the past decade due to their unique properties.³ Meanwhile, thienoacenes, acene derivatives that contain thiophene moieties, have also been the focus of research as promising compounds for the synthesis of organic materials.⁴ The incorporation of main-group atoms into thienoacenes is also a hot topic these days, and several heterothienoacenes have been reported.⁵ Thienoazaborines, thiophene-fused azaborines, have also been studied.⁶ For instance, Perepichka and co-workers reported integrated compounds that contained thiophene and 1,2-azaborine units. They synthesized terthiophenes fused by two 1,2azaborine rings and found that these compounds exhibited fluorescence (Figure 1a).^{6d} In 2013, Wang, Yuan, and Pei reported the synthesis of BN-substituted tetrathienonaphthalene derivatives and their properties as semiconductors.^{6g} In contrast to thienoacenes, including 1,2-azaborines, there has been no report on the synthesis of thienoacenes including 1,4azaborines as far as we can tell, although they should be potential candidates for the synthesis of interesting organic materials. We have been interested in the synthesis and properties of heterothienoacenes,⁷ and focus here has been on dithieno[3,2-b:2',3'-e][1,4]azaborinine (DTAB) (Figure 1 b). The syntheses of dibenzo [b,e] [1,4] azaborine (DBAB)⁸ and dithieno[3,2-b:2',3'-e][1,4]thiaborine (DTTB), analogues of DTAB, have already been reported by Clark^{8a} and Liu.⁹ At the beginning of our study, we calculated the NICS(1) values of DBAB, DTTB, and DTAB, which have a methyl group on the nitrogen atom and a phenyl group on the boron atom (Figure



Figure 1. (a) Representative examples of previously reported thiophene-fused 1,2-azaborines. (b) Structure of dibenzo-1,4azaborine (DBAB), dithieno-1.4-thiaborine (DTTB), and dithieno-1,4-azaborine (DTAB) with NICS(1) calculated at the GIAO-B3LYP/6-311+G(2d,p)//B3LYP/6-31G(d) level. NICS values were calculated for the structures with R = Me, Ar = Ph.

1(b)). The NICS(1) value of DTAB (-6.3) was the most negative among them, suggesting that it is highly aromatic. Clark and Liu reported that the boron-containing rings of DBAB and DTTB were almost planar, indicating their aromaticity, and the introduction of a bulky substituent such as a mesityl group conferred stability upon them. We assumed

Received: October 16, 2018

that DTAB would be stable on account of its high aromaticity even without a bulky substituent on the boron atom. Based on this hypothesis, we started to synthesize DTAB derivatives that had a phenyl group on the boron atom.

Our synthetic strategy is illustrated in Scheme 1. We considered that DTAB (1) could be synthesized by a Friedel-





Crafts-type C–H borylation¹⁰ of 3,3'-dithienylamine **2** derived from 3-thienylamine **3** and 3-bromothiophene via a Buchwald–Hartwig cross-coupling reaction. Furthermore, the thusobtained **1** could be transformed to more π -extended derivatives by cross-coupling reactions.

While 3,3'-dithienylamines have been known to be useful precursors for dithienopyrroles, there has been only one report on the synthesis of more π -extended 3,3'-dithienylamine derivatives.¹¹ Therefore, we first developed a synthetic method for the construction of **2** by a Buchwald–Hartwig cross-coupling reaction (eqs 1–5). *N*-Methyl- and *N*-phenyl-3,3'-



dithienylamine (2a and 2b) could be synthesized by a similar method reported by Rasmussen and co-workers.¹¹ $P(t-Bu)_3$ was an effective ligand, and 2a and 2b were obtained in respective yields of 75% and 72%. For the synthesis of Nmethyl-3-benzo b thiophenyl-3-thienylamine (2c), the use of $P(t-Bu)_3$ was not effective. Optimization of the reaction conditions revealed that RuPhos, a commonly used ligand for Buchwald-Hartwig coupling reactions, was effective. With RuPhos, the reaction of 3a with 3-bromobenzo b thiophene afforded the desired product 2c in 78% yield. A tandem coupling reaction using 3,6-dibromothieno [3,2-b] thiophene was also carried out; the use of $Pd[P(t-Bu)_3]_2$ gave both the dehalogenated monocoupling product 2d and the doublecoupled diamine 2e in respective yields of 21% and 13%. When RuPhos was used as a ligand, the yield of 2e increased to 58%.¹¹

Next, we chose 2a as a model compound, and C-H borylation was carried out (Table 1). In chlorobenzene,



S	Me PhBCl ₂ N E PhCl S PhCl 13	(1.5 equiv) Et ₃ N (0.29 M) 35 °C	
	2a		1a
entry	Et ₃ N (equiv)	time (h)	yield ^b (%)
1	0	48	40
2	1.0	48	61
3	2.0	24	88
4	2.0	48	>99 (96) ^c
5	2.0	48	82 ^{<i>c</i>,<i>d</i>}

^{*a*}Reaction conditions: **2a** (0.20 mmol), PhBCl₂ (1.5 equiv), Et₃N (0–2 equiv), PhCl (0.29 M), 135 °C. ^{*b*}Determined by ¹H NMR with 1,1,2,2-tetrachloroethane as an internal standard. ^{*c*}Isolated yield. ^{*d*}Performed with 1.0 mmol of **2a**.

treatment of **2a** with PhBCl₂ (1.5 equiv) at 135 °C for 48 h gave the desired azaborine **1a** regioselectively in 40% yield (entry 1). Further optimization revealed that the addition of Et₃N increased the yield of **1a**. With 1 equiv of Et₃N, the NMR yield of **1a** increased to 61% (entry 2). The reaction proceeded quite efficiently with 2 equiv of Et₃N. Compound **1a** was obtained in 88% yield even within 24 h (entry 3), and the reaction proceeded quantitatively within 48 h (entry 4, > 99% NMR yield, 96% isolated yield). When the reaction was performed on a 1 mmol scale, **1a** was also obtained in good yield (entry 5).

The structure of **1a** was confirmed by X-ray analysis (Figure 2). The sum of the bond angles around the nitrogen, boron, and carbon atoms that comprised the azaborine ring was 360° , and the sum of the interior angles of the azaborine ring was 720° , indicating that the azaborine ring is completely planar. The packed structure of **1a** is illustrated in Figure 2b. Intermolecular N–B interaction was not observed, and the packed structure was mainly effected by $\pi-\pi$ interaction.

Next, we performed C-H borylation of 2b-d under the optimized conditions (Scheme 2). Phenyl(di-3-thienyl)amine (2b) could also be used for this reaction, and the corresponding DTAB 1b was obtained in 66% yield with 3 equiv of PhBCl₂. Precursors bearing 3-benzo[b]thienyl and 3-



Figure 2. (a) ORTEP drawing of 1a with 50% thermal ellipsoids. (b) Packed structure of 1a.

Scheme 2. Synthesis of Several Dithienoazaborines via C–H Borylation"



^{*a*}Reaction conditions: **2** (0.20 mmol), PhBCl₂ (1.5 equiv), Et₃N (2 equiv), PhCl (0.29 M). Isolated yield. ^{*b*}Performed with 3 equiv of PhBCl₂. ^{*c*}Performed with **2e** (0.32 mmol), PhBCl₂ (3 equiv), Et₃N (4 equiv) in PhCl (0.07 M).

thieno[3,2-*b*]thienyl groups were efficient for this reaction, and the π -expanded DTAB derivatives 1c and 1d were obtained in respective yields of 86% and 84%. Notably, a more π -expanded ladder-type DTAB 1e was readily obtained from precursors 2e, which have two reaction sites (61% yield). As expected, 1a–e were all stable, could be easily handled in air under ambient conditions, and could be purified by simple column chromatography on silica gel. This is likely due to their high aromaticity.

For further derivatization of the thus-obtained DTABs, a stannyl group was introduced to 1c. When 1c was treated with *t*-BuLi (2.2 equiv) and TMEDA (2.6 equiv) at -78 °C, lithiation proceeded smoothly, and a subsequent reaction with Me₃SnCl gave the stannylated DTAB 4 in 84% yield (Scheme 3).¹³

Thus-obtained 4 was a good precursor of π -extended DTAB derivatives, and several DTAB derivatives were obtained by Kosugi-Migita-Stille cross-coupling (Table 2). In the presence of Pd[P(*t*-Bu)₃]₂ (5 mol %), treatment of 4 with iodobenzene (2 equiv) at 80 °C gave phenyl-substituted DTAB 5a in 85% yield (entry 1). Aryl halides bearing electron-donating or -withdrawing groups could be used in the reaction

Scheme 3. Stannylation of 1c







^{*a*}Reaction conditions: **4** (0.20 mmol), aryl halide (2 equiv), $Pd[P(t-Bu)_{3}]_{2}$ (5 mol %), toluene (0.1 M). ^{*b*}Isolated yield. ^{*c*}Performed on a 1 mmol scale.

to give the corresponding π -extended DTABs in good to excellent yields (entries 2–7).

Next, the fundamental physical properties of DTABs were investigated. UV–vis absorption spectra of 1a-e are illustrated in Figure 3. The onset of absorbance (λ_{onset}) of 1a was 369 nm,



Figure 3. UV-vis spectra of 1a-e measured in $o-C_6H_4Cl_2$ (1.0 × 10^{-5} M).

which is similar to that of **1b** (367 nm). The value of λ_{onset} increased with π -extension, and that of **1e** was 418 nm, which is the longest among them. These results suggest that the HOMO–LUMO gaps of DTABs become smaller by π -extension and that of **1e** is the smallest among them (2.96 eV). A similar tendency was observed in the UV–vis absorption spectra of **5a**–**g**.¹⁴ We also measured fluorescence spectra of DTABs and found that DTAB **1a**–**e** exhibited weak fluorescence ($\Phi < 0.1$). The fluorescence emission (λ_{em}) of **1a**–**e** was observed around 377–417 nm, and the value was increased with their π -extension. Among **5a**–**g**, the fluorescence fluorescence fluorescence fluorescence fluorescence fluorescence with their π -extension.

rescence of 5d was the strongest ($\Phi = 0.27$) probably because the diphenylamino moiety would work as an efficient donor unit.¹⁵

Cyclic voltammetry (CV) was then carried out for 1a-e and 5a-g.¹⁴ In all of the cyclic voltammograms, irreversible oxidation peaks were observed. In contrast, no clear reduction peak was observed in the range of the electron window. The onset values of oxidation (E_{onset}) were in the range of 0.55–0.77 V for $1a-e^{16}$ and 0.33–0.59 V for 5a-g (vs Fc/Fc⁺). The combined electrochemical and optical data led to estimated HOMO–LUMO levels for 1a-e and 5a-g (Table 3 and

Table 3. 1	Electrochemical	and O	ntical Data	for DTAB	la-e
I UDIC DI J	Licculounchicun	und O	puicui Duiu	IOI D IIID	IL C

1	$\lambda_{\max}\left(nm ight)$	$\log \varepsilon$	$rac{\lambda_{ m onset}/E_{ m g}^{ m opt}}{ m (nm/eV)}$	E _{HOMO} (eV)	$E_{ m LUMO}$ (eV)
1a	351	4.24	369, 3.36	-5.52	-2.16
1b	350	4.37	367, 3.38	-5.57	-2.19
1c	305	4.41	395, 3.14	-5.35	-2.21
1d	293	4.40	382, 3.24	-5.44	-2.20
1e	303	4.71	418, 2.96	-5.37	-2.19

 ${}^{a}E_{\text{onset}}$ values were determined by the onset of CV in CH₂Cl₂. All potentials were calibrated with reference to Fc/Fc⁺. E_{HOMO} values were determined with reference to ferrocene (4.8 eV vs vacuum).¹⁸ Optical band gap: $E_{\text{g}}^{\text{opt}} = 1240/\lambda_{\text{onset}}$. $E_{\text{LUMO}} = E_{\text{HOMO}} + E_{\text{g}}^{\text{opt}}$.

Supporting Information). All of the DTABs have HOMO levels lower than -5.1 eV and deep LUMO levels,¹⁷ suggesting that they would be stable in air and would act as electron-acceptors. Their energy levels are consistent with the results of DFT calculations.

In conclusion, we have achieved the first syntheses of DTAB 1a-e by Buchwald–Hartwig coupling and subsequent C–H borylation. Further π -extension of 1c to afford 5a-g was also achieved. The fundamental physical properties of the DTAB derivatives were also studied. Further investigations of these derivatives are in progress in our laboratory.

ASSOCIATED CONTENT

Supporting Information

The Supporting Information is available free of charge on the ACS Publications website at DOI: 10.1021/acs.or-glett.8b03316.

Experimental details, photophysical and electrochemical properties of 1a-e and 5a-g, spectral data for all new compounds, and data for theoretical calculations (PDF)

Accession Codes

CCDC 1858599, 1858601–1858602, and 1858671 contain the supplementary crystallographic data for this paper. These data can be obtained free of charge via www.ccdc.cam.ac.uk/data_request/cif, or by emailing data_request@ccdc.cam.ac.uk, or by contacting The Cambridge Crystallographic Data Centre, 12 Union Road, Cambridge CB2 1EZ, UK; fax: +44 1223 336033.

AUTHOR INFORMATION

Corresponding Authors

*E-mail: mitsudo@cc.okayama-u.ac.jp. *E-mail: suga@cc.okayama-u.ac.jp.

ORCID ®

Koichi Mitsudo: 0000-0002-6744-7136

Hiroki Mandai: 0000-0001-9121-3850 Atsushi Wakamiya: 0000-0003-1430-0947 Seiji Suga: 0000-0003-0635-2077

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

This work was supported in part by a Grant-in-Aid for Scientific Research (C) (Nos. 25410042, 16K05695) from JSPS, Japan, by the Collaborative Research Program of Institute for Chemical Research, Kyoto University (Grant No. 2018-42), Okayama Foundation for Science and Technology, and by JST, ACT-C, Japan. The authors thank Prof. Yasujiro Murata (Kyoto University) for fruitful discussions.

REFERENCES

(1) For reviews of azaborines, see: (a) Giustra, Z. X.; Liu, S.-Y. J. Am. Chem. Soc. **2018**, 140, 1184. (b) Campbell, P. G.; Marwitz, A. J. V.; Liu, S.-Y. Angew. Chem., Int. Ed. **2012**, 51, 6074.

(2) For representative works, see: (a) Dewar, M. J. S. J. Am. Chem.
Soc. 1961, 83, 1754. (b) Dewar, M. J. S.; Kubba, V. P. J. Am. Chem.
Soc. 1961, 83, 1757. (c) Dewar, M. J. S.; Lepley, A. R. J. Am. Chem.
Soc. 1961, 83, 4560. (d) Dewar, M. J. S.; Kaneko, C.; Bhattacharjee,
M. K. J. Am. Chem. Soc. 1962, 84, 4884. (e) Dewar, M. J. S.; Rogers,
H. J. Am. Chem. Soc. 1962, 84, 395.

(3) For recent representative examples, see: (a) Yang, Y.; Jiang, J.; Yu, H.; Shi, J. Chem. - Eur. J. 2018, 24, 178. (b) Liu, Z.; Ishibashi, J. S. A.; Darrigan, C.; Dargelos, A.; Chrostowska, A.; Li, B.; Vasiliu, M.; Dixon, D. A.; Liu, S.-Y. J. Am. Chem. Soc. 2017, 139, 6082. (c) Baggett, A. W.; Liu, S.-Y. J. Am. Chem. Soc. 2017, 139, 15259. (d) Arrowsmith, M.; Boehnke, J.; Braunschweig, H.; Celik, M. A. Angew. Chem., Int. Ed. 2017, 56, 14287. (e) Abengozar, A.; Garcia-Garcia, P.; Sucunza, D.; Frutos, L. M.; Castano, O.; Sampedro, D.; Perez-Redondo, A.; Vaquero, J. Org. Lett. 2017, 19, 3458. (f) Xu, S.; Zhang, Y.; Li, B.; Liu, S.-Y. J. Am. Chem. Soc. 2016, 138, 14566. (g) Schaefer, M.; Beattie, N. A.; Geetharani, K.; Schaefer, J.; Ewing, W. C.; Krahfuss, M.; Hoerl, C.; Dewhurst, R. D.; Macgregor, S. A.; Lambert, C.; Braunschweig, H. J. Am. Chem. Soc. 2016, 138, 8212. (h) Mazzanti, A.; Mercanti, E.; Mancinelli, M. Org. Lett. 2016, 18, 2692. (i) Liu, X.; Zhang, Y.; Li, B.; Zakharov, L. N.; Vasiliu, M.; Dixon, D. A.; Liu, S.-Y. Angew. Chem., Int. Ed. 2016, 55, 8333. (j) Lee, H.; Fischer, M.; Shoichet, B. K.; Liu, S.-Y. J. Am. Chem. Soc. 2016, 138, 12021. (k) Jouffroy, M.; Davies, G. H. M.; Molander, G. A. Org. Lett. 2016, 18, 1606. (1) Edel, K.; Brough, S. A.; Lamm, A. N.; Liu, S.-Y.; Bettinger, H. F. Angew. Chem., Int. Ed. 2015, 54, 7819. (m) Burford, R. J.; Li, B.; Vasiliu, M.; Dixon, D. A.; Liu, S.-Y. Angew. Chem., Int. Ed. 2015, 54, 7823. (n) Brown, A. N.; Li, B.; Liu, S.-Y. J. Am. Chem. Soc. 2015, 137, 8932. (o) Braunschweig, H.; Celik, M. A.; Hupp, F.; Krummenacher, I.; Mailaender, L. Angew. Chem., Int. Ed. 2015, 54, 6347. (p) Baggett, A. W.; Vasiliu, M.; Li, B.; Dixon, D. A.; Liu, S.-Y. J. Am. Chem. Soc. 2015, 137, 5536. (q) Baggett, A. W.; Guo, F.; Li, B.; Liu, S.-Y.; Jaekle, F. Angew. Chem., Int. Ed. 2015, 54, 11191. (r) Amani, J.; Molander, G. A. Org. Lett. 2015, 17, 3624. (s) Wu, D.; Kong, L.; Li, Y.; Ganguly, R.; Kinjo, R. Nat. Commun. 2015, 6, 7340.

(4) For reviews, see: (a) Li, L.; Zhao, C.; Wang, H. Chem. Rec. 2016, 16, 797. (b) Cinar, M. E.; Ozturk, T. Chem. Rev. (Washington, DC, U. S.) 2015, 115, 3036. (c) Takimiya, K.; Osaka, I.; Mori, T.; Nakano, M. Acc. Chem. Res. 2014, 47, 1493. (d) Takimiya, K.; Nakano, M.; Kang, M. J.; Miyazaki, E.; Osaka, I. Eur. J. Org. Chem. 2013, 2013, 217. (e) Takimiya, K.; Shinamura, S.; Osaka, I.; Miyazaki, E. Adv. Mater. 2011, 23, 4347.

(5) For representative reviews see: (a) Rasmussen, S. C.; Evenson, S. J. Prog. Polym. Sci. 2013, 38, 1773. (b) Ohshita, J. Macromol. Chem.

Organic Letters

Phys. 2009, 210, 1360. (c) Romero-Nieto, C.; Baumgartner, T. Synlett 2013, 24, 920.

(6) (a) Dewar, M. J. S.; Marr, P. A. J. Am. Chem. Soc. 1962, 84, 3782. (b) Gronowitz, S.; Ander, I.; Zanirato, P. Chem. Scr. 1983, 22, 55. (c) Zanirato, P. J. Organomet. Chem. 1985, 293, 285. (d) Lepeltier, M.; Lukoyanova, O.; Jacobson, A.; Jeeva, S.; Perepichka, D. F. Chem. Commun. 2010, 46, 7007. (e) Lukoyanova, O.; Lepeltier, M.; Laferriere, M.; Perepichka, D. F. Macromolecules 2011, 44, 4729. (f) Wang, X.; Zhang, F.; Liu, J.; Tang, R.; Fu, Y.; Wu, D.; Xu, Q.; Zhuang, X.; He, G.; Feng, X. Org. Lett. 2013, 15, 5714. (g) Wang, X.-Y.; Lin, H.-R.; Lei, T.; Yang, D.-C.; Zhuang, F.-D.; Wang, J.-Y.; Yuan, S.-C.; Pei, J. Angew. Chem., Int. Ed. 2013, 52, 3117. (h) Wang, X.-Y.; Zhuang, F.-D.; Wang, R.-B.; Wang, X.-C.; Cao, X.-Y.; Wang, J.-Y.; Pei, J. J. Am. Chem. Soc. 2014, 136, 3764. (i) Wang, X.-Y.; Zhuang, F.-D.; Zhou, X.; Yang, D.-C.; Wang, J.-Y.; Pei, J. J. Mater. Chem. C 2014, 2, 8152. (j) Crossley, D. L.; Cade, I. A.; Clark, E. R.; Escande, A.; Humphries, M. J.; King, S. M.; Vitorica-Yrezabal, I.; Ingleson, M. J.; Turner, M. L. Chem. Sci. 2015, 6, 5144. (k) Wang, X.; Zhang, F.; Gao, J.; Fu, Y.; Zhao, W.; Tang, R.; Zhang, W.; Zhuang, X.; Feng, X. J. Org. Chem. 2015, 80, 10127. (1) Wang, X.-Y.; Yang, D.-C.; Zhuang, F.-D.; Liu, J.-J.; Wang, J.-Y.; Pei, J. Chem. - Eur. J. 2015, 21, 8867. (m) Wang, X.-Y.; Zhuang, F.-D.; Wang, J.-Y.; Pei, J. Chem. Commun. 2015, 51, 17532. (n) Zhang, W.; Zhang, F.; Tang, R.; Fu, Y.; Wang, X.; Zhuang, X.; He, G.; Feng, X. Org. Lett. 2016, 18, 3618. (o) Zhou, J.; Tang, R.; Wang, X.; Zhang, W.; Zhuang, X.; Zhang, F. J. Mater. Chem. C 2016, 4, 1159. (p) Zhang, W.; Fu, Y.; Qiang, P.; Hunger, J.; Bi, S.; Zhang, W.; Zhang, F. Org. Biomol. Chem. 2017, 15, 7106. (q) Li, G.; Chen, Y.; Qiao, Y.; Lu, Y.; Zhou, G. J. Org. Chem. 2018, 83, 5577.

(7) Kurimoto, Y.; Mitsudo, K.; Mandai, H.; Wakamiya, A.; Murata, Y.; Mori, H.; Nishihara, Y.; Suga, S. Asian J. Org. Chem. 2018, 7, 1635. (b) Mitsudo, K.; Tanaka, S.; Isobuchi, R.; Inada, T.; Mandai, H.; Korenaga, T.; Wakamiya, A.; Murata, Y.; Suga, S. Org. Lett. 2017, 19, 2564. (c) Mitsudo, K.; Kurimoto, Y.; Mandai, H.; Suga, S. Org. Lett. 2017, 19, 2821. (d) Mitsudo, K.; Murakami, T.; Shibasaki, T.; Inada, T.; Mandai, H.; Suga, S. Synlett 2016, 27, 2327. (e) Mitsudo, K.; Sato, H.; Yamasaki, A.; Kamimoto, N.; Goto, J.; Mandai, H.; Suga, S. Org. Lett. 2015, 17, 4858. (f) Mitsudo, K.; Shimohara, S.; Mizoguchi, J.; Mandai, H.; Suga, S. Org. Lett. 2012, 14, 2702.

(8) (a) Kranz, M.; Hampel, F.; Clark, T. J. Chem. Soc., Chem. Commun. 1992, 1247. (b) Agou, T.; Kobayashi, J.; Kawashima, T. Inorg. Chem. 2006, 45, 9137. (c) Agou, T.; Kojima, T.; Kobayashi, J.; Kawashima, T. Org. Lett. 2009, 11, 3534. (d) Agou, T.; Sekine, M.; Kobayashi, J.; Kawashima, T. J. Organomet. Chem. 2009, 694, 3833. (e) Agou, T.; Arai, H.; Kawashima, T. Chem. Lett. 2010, 39, 612.

(9) Yan, Y.; Sun, Z.; Li, C.; Zhang, J.; Lv, L.; Liu, X.; Liu, X. Asian J. Org. Chem. **2017**, *6*, 496.

(10) Quite recently, Hatakeyama reported a synthesis of nanographene by Friedel–Crafts-type C–H borylation; see: Matsui, K.; Oda, S.; Yoshiura, K.; Nakajima, K.; Yasuda, N.; Hatakeyama, T. J. Am. Chem. Soc. **2018**, 140, 1195.

(11) Ogawa, K.; Radke, K. R.; Rothstein, S. D.; Rasmussen, S. C. J. Org. Chem. 2001, 66, 9067.

(12) For details of the Buchwald–Hartwig coupling, see the Supporting Information.

(13) Prior to the stannylation, optimization of the lithiation conditions was carried out by a deuteration reaction. For details, see the Supporting Information.

(14) For the details of physical properties of DTABs, see the Supporting Information.

(15) Ito, M.; Ito, E.; Hirai, M.; Yamaguchi, S. J. Org. Chem. 2018, 83, 8449.

(16) The low oxidation potential of 5d would be derived from the highly electron-rich triphenylamine moiety. DFT calculations suggest that the HOMO of 5d would be delocalized on the triphenylamine.

(17) The LUMO level (-2.16 eV) of DTAB 1a was lower than that of DTTB (-1.43 eV), see ref 9), suggesting higher electron-accepting ability of DTABs.

(18) Pommerehne, J.; Vestweber, H.; Guss, W.; Mahrt, R. F.; Bässler, H.; Porsch, M.; Daub, J. Adv. Mater. **1995**, 7, 551.