This article was downloaded by: [Syracuse University Library] On: 06 June 2014, At: 01:07 Publisher: Taylor & Francis Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



# Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information: http://www.tandfonline.com/loi/gmcl20

# New Photoalignment Materials in LCD's Development: Liquid Crystal Pretilt Angle Variations By Using Fluoroalkylmethacrylates

L. Vretik<sup>a</sup>, L. Paskal'<sup>a</sup>, V. Syromyatnikov<sup>a</sup>, V. Zagniy<sup>a</sup>, O. Savchuk<sup>a</sup>, L. Dolgov<sup>b</sup>, O. Yaroshchuk <sup>b</sup> & C.-D. Lee<sup>c</sup>

<sup>a</sup> Macromolecular Chemistry Department , Taras
Shevchenko Kyiv National University , Kyiv, Ukraine
<sup>b</sup> Institute of Physics, National Academy of Science of Ukraine , Kyiv, Ukraine

<sup>c</sup> Industrial Technology Research Institute, Chutung, Hsinchu, Taiwan, Republic of China Published online: 22 Sep 2010.

To cite this article: L. Vretik , L. Paskal' , V. Syromyatnikov , V. Zagniy , O. Savchuk , L. Dolgov , O. Yaroshchuk & C.-D. Lee (2007) New Photoalignment Materials in LCD's Development: Liquid Crystal Pretilt Angle Variations By Using Fluoroalkylmethacrylates, Molecular Crystals and Liquid Crystals, 468:1, 173/ [525]-179/[531], DOI: <u>10.1080/15421400701229909</u>

To link to this article: <u>http://dx.doi.org/10.1080/15421400701229909</u>

# PLEASE SCROLL DOWN FOR ARTICLE

Taylor & Francis makes every effort to ensure the accuracy of all the information (the "Content") contained in the publications on our platform.

However, Taylor & Francis, our agents, and our licensors make no representations or warranties whatsoever as to the accuracy, completeness, or suitability for any purpose of the Content. Any opinions and views expressed in this publication are the opinions and views of the authors, and are not the views of or endorsed by Taylor & Francis. The accuracy of the Content should not be relied upon and should be independently verified with primary sources of information. Taylor and Francis shall not be liable for any losses, actions, claims, proceedings, demands, costs, expenses, damages, and other liabilities whatsoever or howsoever caused arising directly or indirectly in connection with, in relation to or arising out of the use of the Content.

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden. Terms & Conditions of access and use can be found at http://www.tandfonline.com/page/terms-and-conditions



## New Photoalignment Materials in LCD's Development: Liquid Crystal Pretilt Angle Variations By Using Fluoroalkylmethacrylates

- L. Vretik
- L. Paskal'
- V. Syromyatnikov
- V. Zagniy
- **O. Savchuk**

Macromolecular Chemistry Department, Taras Shevchenko Kyiv National University, Kyiv, Ukraine

#### L. Dolgov

#### **O. Yaroshchuk**

Institute of Physics, National Academy of Science of Ukraine, Kyiv, Ukraine

#### C.-D. Lee

Industrial Technology Research Institute, Chutung, Hsinchu, Taiwan, Republic of China

Fluorinated copolymers based on 4-(N-methacryloylamino)phenyl methacrylate are proposed as materials for the liquid crystal (LC) photoalignment with a wide range of variations of a pretilt angle. As fluorinated chains, 2,2,3,3-tetrafluoropropylmethacrylate and 2,2,3,3,4,4,5,5-octafluoropenthylmethacrylate are used. The growth of a pretilt angle with the concentration of fluorinated chains, more pronounced in a series with longer fluorinated chain, is observed. The pretilt angle of TN LC ZLI 2293 is smoothly varied in the range 0°–20°. Additionally, the uniform high pretilt angle (89°–90°) alignment is realized for VA LC MJ961180.

**Keywords:** fluorinated copolymer; liquid crystal photoalignment; methacrylate; pretilt angle

Address correspondence to L. Vretik, Macromolecular Chemistry Department, Taras Shevchenko Kyiv National University, 64 Volodymyrs' ka Str., Kyiv, 01033, Ukraine. E-mail: svg@mail.univ.kiev.ua

### 1. INTRODUCTION

Over the last decade, a big amount of works has been directed towards the photo-induced liquid crystal (LC) alignment [1–4] as an alternative route of the rubbing method. The photoalignment effect is due to the ordering of polymer fragments under the action of polarized ultraviolet (UV) light. The photoalignment method allows one to induce an anisotropy on the alignment layer preventing contact, pollution, electrical charging and mechanical destruction of the surface. It has been reported that the LC alignment occurs with films having the cis-trans-isomerization of azo-chromophore or cinnamate chromophore [5-10]; photo-crosslinking of cinnamate, coumarin [11], chalconyl [12] chromophore by the (2+2) cycloaddition reaction or photocrosslinking of anthracenyl chromophore by a (4+4) cycloaddition reaction [13] on the illumination with UV light; cationic photopolymerization involving the ring opening of epoxide groups for the alignment fixation [14–16]. But the existing photoaligning materials have a number of drawbacks, such as low anchoring energy, low thermal stability and photostability, and hard control of an LC pretilt angle. So many efforts are directed to the searching for new photoaligning materials with improved characteristics.

In our previous work [17], we proposed bis-methacrylics (particularly 4-(N-methacryloylamino)phenyl methacrylate) as a new class of photoaligning materials. Such materials have two methacrylic groups with different reactivities. One group is thermally polymerized in the process of synthesis of the polymer, while the other one anisotropically crosslinks polymer chains under the photoalignment treatment. These materials demonstrate the improved stability of LC alignment, but, however, impact to an LC small pretilt angle.

In order to control the pretilt angle, we propose to vary the hydrophobic properties of methacrylates by means of using their fluorinated copolymers. 4-(N-methacryloylamino)phenyl methacrylate copolymerized with 2,2,3,3-tetrafluoropropylmethacrylate and 2,2,3,3,4,4,5,5octafluoropenthylmethacrylate are considered. Controlling the type and content of fluorinated chains, we expect to control the LC pretilt angle.

## 2. EXPERIMENTAL SECTION

### 2.1. Synthesis and Characterization of Alignment Materials

All solvents of p.a. quality (Aldrich) were stored over molecular sieves of 3 or 4 Å. All chemicals were purchased from Aldrich and used without further purification. Monomer synthesis was done by the usual acylation of aminophenole (Fig. 1). Particularly, 4-(N-methacryloylamino)phenyl methacrylate was synthesized via acylation of 4-aminophenole (1) in dry tetrahydrofuran with methacryloyl chloride (2) at  $15-20^{\circ}$ C [17].

Copolymers were synthesized by the following method: 4-(N-methacryloylamino)phenyl methacrylate (MAPhM) and 2,2,3,3-tetrafluoropropylmethacrylate or 2,2,3,3,4,4,5,5-octafluoropenthylmethacrylate in a corresponding molar ratio with 1 wt.% of AIBN in dry dimethylformamide were heated to 80°C, and polymer product was isolated by precipitation into diethyl ether.

By this way, two series of copolymers were synthesized with two different fluorinated agents (Fig. 2 a, b). Copolymers inside the series differ from each other by the x:y ratio, i.e. by the mole fraction  $c_f$  of fluorinated tails in the main chain. In the series of copolymers based on 2,2,3,3-tetrafluoropropylmethacrylate, homologues with  $c_f$  equal to 41.2, 57, and 70 mole % were obtained. In turn, in the series with 2,2,3,3,4,4,5,5-octafluoropenthylmethacrylate, the  $c_f$  values were 10, 41.2, 50, and 70 mole %.

The characterization of polymers was performed by different methods. Thin layer chromatography was performed with Merck Kieselgel plates 60F254. NMR spectra were recorded with a Bruker NMR-spectrometer (500 MHz) with TMS as internal standard. IR spectra were run on a Nicolet 5SXB FTIR-spectrophotometer. GPC-measurements were performed using PSS-SDV columns and a DMF eluent containing LiBr at a flow rate of 1.0 L/min. The calibration curves for GPC analysis were obtained using PSS polystyrene standards (1000 – 400 000 D). Differential scanning calorimetry was carried out with a Perkin-Elmer DSC 7.



FIGURE 1 Scheme of synthesis of 4-(N-methacryloylamino)phenyl methacrylate.



**FIGURE 2** Groups of copolymers of MAPhM: (a) with 2,2,3,3-tetrafluoropropylmethacrylate; (b) with 2,2,3,3,4,4,5,5-octafluoropenthylmethacrylate.

## 2.2. Testing of LC Alignment

The quality of LC photoalignment was investigated in the following way. A 2-wt.% solution of the investigated polymer in dimethylformamide was spincoated (3000 rpm, 1 min) on the glass substrate. The obtained film was pre-backed during 10 min at 100°C, then backed at 180°C during 1 h. After that, the polymer film was normally irradiated by polarized UV light ( $I = 28 \text{ mW/cm}^2$ , t = 15 min) and then obliquely irradiated by unpolarized UV ( $I = 100 \text{ mW/cm}^2$ , t = 1 min). At last, a symmetric optical cell (the cell thickness is  $20 \,\mu\text{m}$ ) with antiparallel LC alignment was made from the irradiated substrates. The cell was filled by liquid crystal ZLI 2293 ( $\Delta \varepsilon > 0$ ) or MJ 961180 ( $\Delta \varepsilon < 0$ ). The quality of liquid crystal alignment was estimated by the observation of a sample in polarized light (a light box and a polarizing microscope). The pretilt angle of a liquid crystal in the cell was measured by the commonly used crystal rotation method [18].

### 3. RESULTS AND DISCUSSION

It was revealed that both MAPhM homopolymer and its fluorinated copolymers provide the LC alignment of excellent quality (Fig. 3).

Using copolymers with different fluorinated chains allows us to control the liquid crystal pretilt angle. Figures 4 and 5 demonstrate



**FIGURE 3** Photoalignment of liquid crystal MJ961180 ( $\Delta \varepsilon < 0$ ) in the cell based on: (a) poly-MAPhM, planar alignment; (b) MAPhM copolymer with 2,2,3,3-tetrafluoropropylmethacrylate ( $c_f = 57$ ), tilted alignment; (c) MAPhM copolymer with 2,2,3,3,4,4,5,5-octafluoropenthylmethacrylate ( $c_f = 70$ ), vertical alignment. Symmetrical cells are in crossed polarizers.

the monotonous increase of the pretilt angle with concentration of fluorinated chains. One can see also that, for TN LC ZLI2293, the longer fluorinated tail promotes a higher value of the pretilt angle than the shorter one at the same mole concentration in the polymer. This difference is less pronounced for VA LC MJ961180 having negative dielectric anisotropy. The pretilt angle of LC ZLI2293 is varied in the range  $0^{\circ}-20^{\circ}$ . In turn, the pretilt angle of MJ961180 runs the whole range of pretilt angles, i.e., it changes from  $0^{\circ}$  to  $90^{\circ}$ . The values close to  $90^{\circ}$  are easily achieved, which makes these materials promising for the VA mode.

Noteworthy, even if the concentration of non-photosensitive fluorinated monomers is 50–70 mole%, the alignment quality is good. Thus, the LC pretilt angle changes with the concentration of fluorinated tails without noticeable changes in the alignment quality. In addition, in contrast to copolymers with cinnamate units [19], LC photoalignment in copolymers with methacrylic reactive groups is much more stable. These results make such method of pretilt angle variation extremely promising for applications.

L. Vretik et al.



**FIGURE 4** Dependence of LC pretilt angle vs. mole concentration  $c_f$  of fluorinated fragments in 2,2,3,3-tetrafluoropropylmethacrylate. (1) ZLI2293  $(\Delta \varepsilon > 0)$ ; (2) MJ961180 ( $\Delta \varepsilon < 0$ ).



**FIGURE 5** Dependence of LC pretilt angle vs. mole concentration  $c_f$  of fluorinated fragments in 2,2,3,3,4,4,5,5-octafluoropenthylmethacrylate. (1) ZLI2293 ( $\Delta \varepsilon > 0$ ); (2) MJ961180 ( $\Delta \varepsilon < 0$ ).

179/[531]

### CONCLUSIONS

We have proposed an effective method to control the LC pretilt angle on the methacrylate copolymer surface. Copolymerization of methacrylic monomers with fluorinated fragments of different lengths and different concentrations in copolymer is considered. It is revealed that both the lengthening of a fluorine chain and the increase of the mole concentration of a fluorine fragment leads to the growth of the liquid crystal pretilt angle. Fluorinated chains increase the polymer hydrophobic properties and promote a gradual change of the LC alignment from a planar to tilted and then to vertical alignment. The increase of the pretilt angle with the concentration of hydrophobic chains is not accompanied with the worsening of the LC alignment and alignment stability. This fact makes the method extremely promising for industrial applications.

#### REFERENCES

- [1] Ichimura, K., Suzuki, Y., Seki, T., Hosoki, A., & Aoki, K. (1988). Langmuir, 4, 1214.
- [2] Gibbons, W. M., Shannon, P. J., Sun, S. T., & Swetlin, B. J. (1991). Nature, 351, 49.
- [3] Dyadyusha, A., Marusii, T., Reznikov, Y., Khizhnyak, A., & Reshetnyak, V. (1992). JETP Lett., 56, 17.
- [4] Schadt, M., Schmitt, K., Kozenkov, V., & Chigrinov, V. (1992). Jpn. J. Appl. Phys., 31(1), 2155.
- [5] Ichimura, K., Furumi, S., Morino, Sh., Kidowaki, M., Nakagawa, M., Ogawa, M., & Nishiura, Y. (2000). Adv. Mater., 12(13), 951.
- [6] Kim, H.-T., Lee, J.-W., Sung, Sh.-J., & Park, J.-K. (2000). Liq. Cryst., 27(10), 1343.
- [7] Perny, S., Barny, P., Sung, Sh.-J., Delaire, J., Buffeteau, T., & Sourisseau, C. (2000). Liq. Cryst., 27(3), 341.
- [8] Seo, D.-Sh. & Hwang, L.-Y. (2000). Jpn. J Appl. Phys., 39, L1239.
- [9] Kawatsuki, N., Takatsuka, H., & Yamamoto, T. (2001). Jpn. J Appl. Phys., 40, L209.
- [10] Sapich, B., Stumpe, J., Gerus, I., & Yaroshchuk, O. (2000). Mol. Cryst. Lyq. Cryst., 352, 443.
- [11] Jackson, P. R. & O'Neill, M. (2001). Chem. Mater., 13, 694.
- [12] Hwang, J.-Y., Seo, D.-Sh., Jong, H. S., & Suh, D. H. (2000). Jpn. J. Appl. Phys., 39, L1108.
- [13] Kawatsuki, N., Tadahiro, A., Kawakami, Y., & Yamamoto, T. (2000). Jpn. J. Appl. Phys., 39, L5943.
- [14] Sonpatki, M. M., Sergan, T., Kelly, J., & Chein, L. C. (2000). Macromol. Symp., 154, 83.
- [15] Li, Z. (1995). Liq. Cryst., 19(3), 307.
- [16] Ichimura, K., Kidowaki, M., Akiyama, H., & Kazuaki, K. (1996). Macromol. Rapid. Commun., 17, 545.
- [17] Vretik, L., Yaroshchuk, O., Syromyatnikov, V., Zagniy, V., Paskal, L., Dolgov, L., Kyrychenko, V., & Lee, C.-D. (2007) Mol. Cryst. Liq. Cryst., Accepted for publication.
- [18] Cuminal, M.-P. & Brunet, M. (1997). Liq. Cryst., 22(2), 185.
- [19] Dyadyusha, A., Marusii, T., Reznikov, Yu., & Yaroshchuk, O. (1996). SPIE Proceedings, 2731, 151.