CHEMISTRY LETTERS, pp. 195-198, 1987.

Photochromic Solid Films Prepared by Doping with Donor-Acceptor Norbornadienes

Sadao MIKI, Yoshinobu ASAKO, and Zen-ichi YOSHIDA^{*} Department of Synthetic Chemistry, Kyoto University, Yoshida, Kyoto 606

Thin solid films of PMMA doped with donor-acceptor norbornadienes were prepared, and their photochromic properties were examined. The photochromic solid films have absorption at a visible region, and their photochemical decolorization due to valence isomerization proceeded in high quantum yields. They show resistivity for the repeated cycle of the interconversions and no loss in the extinction was observed even after 10^3 times of cycle of reactions.

Compounds having photochromic properties are currently attracting a great interest, inter alia , in the fields of the solar energy storage and the photoimage storage.¹⁾ Since the formation of cage compounds by intramolecular photocycloaddition is known to bring about the large change in the refractive index,²⁾ this type of reaction might offer us a photochromic system potentially applicable for data storage. The pair of compounds norbornadiene/quadricyclane is a photochromic system, but this system does not have absorption in the region above 300nm and the quantum yield (0.05) of the photo-process is very low. In the course of our study on molecular energy storage for solar energy,³⁾ we have found out that the DA-type substitutional modification of norbornadiene (Eq. 1) provides the molecule having a new absorption in a visible region. Here, the DA-norbornadienes were incorporated in poly(methyl methacrylate) (PMMA) matrix, and the photochromic properties of the resulting solid film based on 1/2 interconversion were examined. The photochromic solid films have some ideal character, i.e., high quantum yields for the photo-process and remarkable resistivity for the repeated cycle of reactions.





Fig. 1. Absorption spectra of la-i in acetonitrile.

Norbornadienes $(\underline{1a}-\underline{h})$ were synthesized by Diels-Alder reaction of appropriate cyclopentadiene derivatives⁴) with dicarbomethoxy- and dicyano-acetylenes. Analytical and spectroscopic data for $\underline{1a}-\underline{h}$ are shown in Table 1.

Fig. 1 shows the CT-absorption bands of $\underline{1a}-\underline{h}$ in a visible region. Especially the absorption cut-off of $\underline{1f}$ reaches to 550 nm. Even in the case of 2,3-dicyano-4,5,6-trimethylnorbornadiene ($\underline{1i}$),⁵) in which methyl groups were employed as a donor group, the absorption edge comes up to 430 nm.

In a typical run of preparation of the solid film of PMMA incorporating with $\underline{1}$, to a solution of 5 g of PMMA (Wako Pure Chemical LTD., mean value of n = 1200 for $(C_5H_8O_2)_n$) in 25 ml CHCl₃ was added a 10 ml solution of $\underline{1}$ of 0.05 M. The resulting solution was sonificated for 1 h to give a homogeneous viscous liquid. The liquid was casted on an optical quartz plate so that a homogeneous thin film

			Calcd (Found)/%				¹ H-NMR(CDC1 ₃)	
Compd	Mp/°C	Formula	С	H	N	0	δ	
la	140	с ₂₅ н ₂₄ 0 ₄	77.30	6.23		16.47	1.29(s,3H), 1.39(s,3H), 3.79(s,8H),	
			(77.26)	(6.13)		(16.18)	7.26(s,10H)	
<u>1b</u>	102.5	с ₂₇ н ₂₈ 04	77.85	6.78		15.37	1.26(s,3H), 1.35(s,3H), 2.31(s,6H),	
		27 20 4	(77.70)	(6.73)		(15.29)	3.75(s,2H), 3.78(s,6H), 7.11(m,8H)	
<u>1d</u>	149	C23H18N2	85.68	5.63	8.69		1.21(s,3H), 1.40(s,3H), 3.78(s,2H),	
		20 10 2	(85.38)	(5.61)	(8.69)		7.19(s,10H)	
le	132	C ₂₅ H ₂₂ N ₂	85.68	6.33	7.99		1.25(s,3H), 1.43(s,3H), 2.33(s,6H),	
		23 22 2	(85.93)	(6.37)	(7.87)		3.80(s,2H), 7.08(s,8H)	
<u>lf</u>	127	C ₂₅ H ₂₂ N ₂ O ₂	78.51	5.80	7.32	8.37	1.24(s,3H), 1.41(s,3H), 3.77(s,2H),	
			(78.71)	(5.73)	(7.41)	(8.31)	3.80(s,6H), 6.97(m,8H)	
<u>1h</u>	208.5	C23H18N2	85.68	5.63	8.69		1.43(s,6H), 2.41(dd,2H),	
		23 10 2	(85.82)	(5.47)	(8.68)		6.98(m,10H)	

Table 1. Analytical Data of 2,3-Dicarbomethoxy and 2,3-Dicyano-5,6-diarylnorbornadienes

		bl	Thermal reversion of $2 + 1$		
System	AE of $1 / nm^{\alpha}$	$\Phi \text{ for } \underline{1} \neq \underline{2} $	$k \ge 10^2 / \min^{-1}$	Temp / °C	
<u>a</u>	456	0.76	0.608	35	
b	469	0.76	1.08	35	
c	494	0.55	1.45	35	
d	494		5.68	25	
e	518		8.83	25	
f	551		14.7	25	
a	403	0.79	0.116	80	
h	454	0.73	0.118	45	
i	430	0.79	0.103	81	

Table 2. Photochromic Properties of PMMA films doped with la-i

a) AE is the wavelength of $\log \epsilon = 0$ in acetonitrile.

b) Excitation wavelength is 334 nm with band path of 10 nm.

was obtained and was dried at ambient temperature in the dark until the constant weight was obtained.

Electronic absorption spectrum of each solid film on quartz plate showed the almost same shape as that of the solution of the respective norbornadiene derivative. Upon irradiation with a xenon lamp complete decolorization of the films was observed. The extinctions were completely recovered by heating the decolorized films. This back process was found to obey the first order kinetics. The rate constants are shown in Table 2. In the case of 1g/2g and 1i/2i systems, no substantial recovery of 1 was observed at room temperature.

Quantum yields for the photochemical conversion of $\underline{1}$ to $\underline{2}$ in the solid films were determined by the modification of the method reported by Saito⁶) according to the equation⁷

$$\log[(I_n/I_0-1)/(I_n/I_t-1)] = e \phi (1-r/2) I_{ir} t$$
 (2)

where t is irradiation time, I_0 and I_t are the transmitted light intensities at t=0 and t=t, I_n is the transmitted light intensity through the film without <u>1</u>, I_{ir} is the intensity of the incident light, r is the refractance of a sample film and ε is the molar extinction coefficient of <u>1</u> at the wavelength of the monochromatic light used. For the determination of the quantum yield according to this principle, a spectrofluorometer (Shimazu RF 502A) was used. The monochromatic excitation light beam was used as incident light for photoreaction. The value I_{ir} was determined by potassium ferioxalate actinometry. Samples were casted on the outer surface of 1 cm x 1 cm quartz cell, which was filled with 10^{-7} M aqueous solution of quinine sulfate. The cell was set in the cell holder so that the excitation light passes through the film, and the transmitted light intensities were determined by monitoring the intensity of fluorescence of the

quinine sulfate.⁸⁾ Transmitted light intensity was monitored as a function of irradiation time t. The value I_{∞} was used as I_n . Using the values thus obtained, plots of the logarithmic value in Eq. 2 vs. irradiation time t gave

straight lines through origin, and quantum yields were evaluated from the slope of the plots. As shown in Table 2, the photochemical process in each films proceeded in high quantum yields ranging 0.55-0.8.

Noteworthy is the remarkably high repetitionality of the reactions, photochemical $\underline{1} + \underline{2}$ and thermal $\underline{2} + \underline{1}$. For example, Fig. 2 shows that the chemical oscillations of $\underline{1f} \neq \underline{2f}$ of 10^3 times in solid film proceed without any loss, whereas 20% loss in extinction was observed after the 10^3 cycles of reactions in solution.





References

- 1) A. E. J. Wilson, Phys. Technol., 15, 232(1984).
- 2) S. Tazuke and H. Watanabe, Tetratedron Lett., 23, 197(1982).
- 3) Z. Yoshida, J. Photochem., 29, 27(1985).
- 4) Preliminary presentation of la and ld was at the 40th National Meeting of Chemical Society of Japan: Z. Yoshida, T. Hijiya, Y. Umehara, and S. Miki, 40th National Meeting of Chemical Society of Jpn. (Fukuoka, 1979), preprint, p558. 2,3-Diphenyl-5,5-dimethylcyclopenta-1,3-diene was prepared according to the literature: H. E. Zimmerman and J. A. Pincock, J. Am. Chem. Soc., 95, 3246(1973). 2,3-Diphenyl-1,4-dimethylcyclopenta-1,3-diene was prepared by dehydration of 3,4-diphenyl-2,5-dimethylcyclopent-2-en-1-ol, which was obtained by the reduction of 3,4-diphenyl-2,5-dimethylcyclopent-2-en-1-one with NaBH₄. 2,3-Di-p-toly1-5,5-dimethylcyclopenta-1,3-diene was synthesized by dehydration of 1,2-di-p-tolyl-4,4-dimethylcyclopentane-1,2-diol, which was obtained from 3,3-dimethyl-1,5-di-p-tolylpentane-1,5-dione by the intramolecular ketone coupling according to the method reported by Mukaiyama: T. Mukaiyama, T. Saito, and J. Hanna, Chem. Lett., 1973, 1041. 2,3-Di-p-anisyl derivative was prepared in an analogous manner. Syntheses of 1c and 1g were reported by Yonemitsu: T. Toda, A. Ando, T. Honda, and O. Yonemitsu, J. Chem. Soc., Chem. Commun., 1982, 1551.
- 5) Z. Yoshida, Jpn. Kokai Tokkyo Koho, JP57 149,251/1982 (Chem. Abstr., <u>98</u>, 53253q(1983)).
- S. Murakami, T. Tsutsui, R. Tanaka, and S. Saito, Nippon Kagaku Kaishi, <u>1985</u>, 1598.
- 7) W. J. Tomlinson, Appl. Opt., <u>11</u>, 533(1972).
- 8) The linear correlation between the intensities of incident light into the cell and the intensities of the fluorescence of quinine sulfate has been established experimentally.
 (Received October 23, 1986)

198