


Molecular Formula 分子式	C ₂₃ H ₃₀ N ₂ O ₂
Molecular Weight 分子量	366.50
Appearance 外观	Slightly Yellow Powder 微淡黄色粉末
Assay 含量	99.0%min(HPLC)
Melting Point 熔点	110-115°C
Volatile 挥发份	0.25%max
Ash 灰分	0.10%max
Package 包装	20kg/carton
Application 应用	PI-369 can be used as a photoinitiator in Etch Resists for PCB,Solder Masks,Offset Inks,Screen Inks,Flexo Inks or Inkjet Inks,Xi-and Xn-free Applications,Low Volatility and Low Odor. 用途：6699可应用于PCB抗蚀剂，阻焊油墨，胶版油墨，丝印油墨、柔印油墨，喷墨油墨，无卤素应用，低挥发性和低气味性等领域。
Structural Formula 分子结构式	
Transmittance 透光率	(1g / 10ml Toluene):450nm≥85.0%;500nm≥90.0%.
Storage Conditions 贮存条件	Store in a cool dry place and prevent from light. 阴凉，干燥，避光条件下贮存。