

FCC Additives



When using shape-selective zeolite-based active ingredient propylene prolific production of highly active additives, curing and FCC FCC primary catalyst in combination, can increase the yield of LPG and propylene. The catalytic additives have a higher selective catalytic activity. It has good abrasion resistance and particle size distributi

Item	Unite	Spec
Appearance	/	white flowing microspheres
BET	M2/g	135
Attrition Index	%h-1	1.5
Bulk Density	g/ml	0.72
Pore Volume	ml/g	0.35
Na2O	wt%	0.10
Al2O3	wt%	28
LOI	wt%	5
D50	um	83
0-20	um	4
0-40	um	13
0-149	um	92